



Sliding friction between an elastomer network and a grafted polymer layer: the role of cooperative effects

Thomas Vilmin, Elie Raphael

► To cite this version:

Thomas Vilmin, Elie Raphael. Sliding friction between an elastomer network and a grafted polymer layer: the role of cooperative effects. 2004. hal-00003070

HAL Id: hal-00003070

<https://hal.science/hal-00003070>

Preprint submitted on 14 Oct 2004

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Sliding friction between an elastomer network and a grafted polymer layer: the role of cooperative effects

T. Vilmin and E. Raphaël

Laboratoire de Physique de la Matière Condensée
UMR 7125 CNRS and FR 2438 "Matière et Systèmes Complexes"
Collège de France
11, Place Marcelin Berthelot, 75231 Paris Cedex 05, France

October 14, 2004

Abstract

We study the friction between a flat solid surface where polymer chains have been end-grafted and a cross-linked elastomer at low sliding velocity. The contribution of isolated grafted chains' penetration in the sliding elastomer has been early identified as a weakly velocity dependent pull-out force. Recent experiments have shown that the interactions between the grafted chains at high grafting density modify the friction force by grafted chain. We develop here a simple model that takes into account those interactions and gives a limit grafting density σ_l beyond which the friction no longer increases with the grafting density, in good agreement with the experimental data.

1 Introduction

In recent years, polymer chains grafted to a surface or an interface have been the subject of many theoretical and experimental studies because of their practical importance[1]. In particular, the interface between a solid surface and a crosslinked elastomer network can be strengthened by the addition of chains that are tethered by one end to the solid surface. As a crack grows along the interface, these coupling chains are progressively pulled-out from the elastomer leading to significant energy dissipation[2][3]. The presence of end-tethered chains plays also an important role in friction[4,




Figure 1: Grafted chain that has partially entered the elastomer (λ_0 is the distance between cross-links, λ the slab width, and d is the stretching length of the n_{eq} confined monomers).

2, 5, 3]. Very recently, Bureau and Léger [9] studied the friction of a poly(dimethylsiloxane) (PDMS) elastomer network sliding, at low velocity, on a substrate on which PDMS chains are end-tethered and clearly evidenced the contribution to friction of the pull-out mechanism of chain-ends that penetrate into the network. This study, while confirming semi-quantitatively the picture of arm retraction relaxation of the grafted chains proposed by Rubinstein *et al.* [4][5], also reveals the unexpected feature that the friction stress, after increasing with the grafting density of tethered chains, reaches a plateau. In this letter we proposed a simple model, based on the role of cooperative effects, that is able to explain this result. In the whole paper we will consider a cross-linked elastomer of reticulation number P (the mesh-size is $\lambda_0 = aP^{\frac{1}{2}}$, where a is the monomer size), in contact with a flat neutral surface with N -mer grafted chains ($N > P$) of the same chemical constitution. The starting point of our study is the description of the penetration of a single grafted chain in a static rubber, made by O'Connor and McLeish [6]. They assume that the chains can be confined in a slab between the elastomer and the flat surface without entangling with the elastomer (see fig. 1). This slab should correspond to the first mesh of the elastomer and its width λ be on the order of λ_0 . They considered the case where the end of a grafted chain penetrates the elastomer at a distance d from the grafting point. This leads to a partial penetration on only m monomers, while the n remaining monomers ($n = N - m$) are confined in the slab.

As the swelling energy of the elastomer can easily be shown to be negligible for a single chain (and even for higher grafting densities [7], see last section), the m monomers 'feel' like in a melt of longer chains, and the free energy of the chain only contains the stretching and the confinement energies

of the n monomers [8] :

$$\frac{F(n)}{kT} \simeq \frac{3}{2} \frac{d^2}{a^2 n} + \frac{3}{2} \frac{a^2 n}{\lambda^2} \quad (1)$$

when $d > \lambda$. Minimizing this expression with respect to n , we get the equilibrium value of n : $n_{eq} = \lambda d/a^2$ if d is inferior to $d_{max} = a^2 N/\lambda$, and the minimum free energy $F_{in}/kT = 3d/\lambda$. The n_{eq} monomers constitute a stretched string of blobs of size λ (see fig. 1 and 2a), which exerts a strong horizontal force $f_0 = 3kT/\lambda$ on the elastomer. If $d < \lambda$, the stretching force is not horizontal, and its projection on the horizontal axis is $f \simeq 3kTd/\lambda^2$. This partial penetration state is metastable as long as $d \geq 0$, but its life time is very long, for the chain has to go through a high energy state in order to reach another state of smaller d . In this high energy state the whole chain is confined in the slab, it forms a string of flat blobs of size $l = a^2 N/d$ if $d > aN^{\frac{1}{2}}$, and a blob of size $aN^{\frac{1}{2}}$ otherwise (see fig. 2b), and the free energy is $F_{out} = F(N)$. Then, the time it takes for the chains to relax to another state is proportional to $\exp[(F_{out} - F_{in})/kT]$.

When the elastomer slides on the grafted surface, the chain can not relax to the state where $d = 0$. The competition between the relaxation and the pull-out due to the elastomer sliding is thus key to the understanding of how a grafted chain can enhance friction. In the next section we will calculate the relaxation time for a given d . Then, we will see how a sliding velocity $\mathbf{v}$ imposes a mean extension d and a pull-out friction force $\mathbf{f}$. In another sections we will consider interactions between several grafted chains, and show how it can modify the average friction force by grafted chain. Lastly, we will compare our results with recent experiments proceeded by Bureau and Léger [9].

2 Relaxation time

When the chain partially penetrates the elastomer and has n monomers in the slab, the difference between its free energy and the minimum free energy is $(F(n) - F_{in})/kT = 3a^2(n - n_{eq})^2/(2n\lambda^2)$. Then, setting $l = a^2 n/\lambda$, we can consider the chain free end as a random walker diffusing in the potential $U(l) = 3(l - d)^2/(2l\lambda)$ ($0 < l < d_{max}$) with a diffusion coefficient $D_{eff}(l)$. The relaxation time we are looking for is the mean first passage time at $l = d_{max}$ (that is when the chain retracts entirely in the slab, $n = N$), from the initial position $l = d_{max} - \lambda_0$ (that is the chain just penetrates the elastomer on a mesh size, $n = N - P$). This mean first passage time τ_{in} can

be shown [10][11] to be:

$$\tau_{in}(d) = \int_{d_{max}-\lambda_0}^{d_{max}} dx \exp[U(x)] \int_0^x dx' \frac{e^{-U(x')}}{D_{eff}(x')} \quad (2)$$

The inner integral is dominated by the region near $x' = d$ and can be approximated by $(D_{eff}(d)(2U''(d)/\pi)^{\frac{1}{2}})^{-1}$, where $U''(d) = 3/\lambda d$, and $D_{eff}(d) = 2a^2/\tau_0 N$ if $\lambda = \lambda_0/2$, which we will assume here-after (τ_0 is the monomer relaxation time). The outer integral can be approximated by $\lambda_0 \exp[U(d_{max})]$, as $(U'(d_{max}))^{-1} > \lambda_0$. Then, the mean relaxation time at a given d is:

$$\tau_{in}(d) \simeq \begin{cases} \tau_0 N \frac{\lambda^2}{a^2} \sqrt{\frac{\pi}{6}} \exp\left[\frac{3}{2} \frac{(d_{max}-\lambda)^2}{a^2 N}\right] & , \text{ if } d < \lambda \\ \tau_0 N \frac{\lambda^2}{a^2} \sqrt{\frac{\pi d}{6\lambda}} \exp\left[\frac{3}{2} \frac{(d_{max}-d)^2}{a^2 N}\right] & , \text{ if } \lambda < d < d_{max} - \frac{1}{2} \sqrt{\frac{\pi}{6}} a N^{\frac{1}{2}} \\ \tau_0 N \frac{\lambda}{a^2} \left(\frac{1}{2} \sqrt{\frac{\pi}{6}} a N^{\frac{1}{2}} + d_{max} - d\right) & , \text{ if } d_{max} - \frac{1}{2} \sqrt{\frac{\pi}{6}} a N^{\frac{1}{2}} < d < d_{max} \end{cases} \quad (3)$$

Notice that τ_{in} does not vanish at $d = d_{max}$, as the chain end can still explore the inside of the elastomer on the curvilinear distance $\sqrt{\pi/6}(aN^{\frac{1}{2}}/2)$. This calculation of the relaxation time notably differs from the one of Rubinstein *et al.* [4][5], and the result is smaller by a factor $(P/N)^{\frac{1}{2}}$ to P/N when $d < d_{max} - \sqrt{\pi/6}(aN^{\frac{1}{2}}/2)$. Another interesting time is the mean first passage time at $n = N - P$ from the initial position $n = N$, which is the time τ_{out} the chain spends entirely in the slab before to hop inside the elastomer. It corresponds to the diffusion time of the chain free end through the first mesh of the elastomer: $\tau_{out} = \tau_0 P^2$. During this short time, the free end is driven back toward the grafting point as a result of the elastic shrink of the chain on the mean distance $6d\tau_{out}/\tau_0 N^2$, but it also diffuses horizontally on the distance λ_0 which is much bigger than $6d\tau_{out}/\tau_0 N^2$. Therefore, diffusion dominates.

3 Sliding friction

If the elastomer slides on the grafted surface at the velocity $\mathbf{v}$, a fully penetrating chain would be pulled-out of the elastomer and stretched in the sliding direction. But if $v\tau_{in} < d_{max}$, the chain will spontaneously relax and hop out of the elastomer before its complete stretching. Then, a permanent regime will settle, corresponding to cycles of hopping in and out, fixing an average value for d . Every hopping out, the free end of the




Figure 2: a) Top view of a grafted chain that has partially entered the elastomer. b) The same chain confined in the slab when relaxing from the stretched conformation a).

chain diffuses in the slab on the distance λ_0 , and every hopping in this free end is shifted of $v\tau_{in}(d)$ in the sliding direction. Then, the smallest possible value d_{min} for d is given by the relation $v\tau_{in}(d_{min}) = \lambda_0$. All the values between d_{min} and d_{max} can be explored by diffusion, but as $\tau_{in}(d)$ is a strongly decreasing function of d , the time averaged value of d is approximately $d_{min} - \lambda_0(v\tau'_{in}(d_{min}))^{-1}$, with the standard deviation $\delta d = -\lambda_0(v\tau'_{in}(d_{min}))^{-1}$. The value of $\delta d \simeq a^2 N/3(d_{max} - d_{min})$ varies from $\lambda_0/6$ when $d_{min} = \lambda_0$, to $aN^{1/2}/\sqrt{3}$ when $d_{min} = d_{max} - aN^{1/2}/\sqrt{3}$, and is thus always much smaller than d_{min} . Then, we can approximate the average value of d by d_{min} , which gives :

$$v\tau_{in}(d) \simeq \lambda_0 \quad (4)$$

Equation 4 has been already proposed by Rubinstein *et al.* [4], but the prediction for $\tau_{in}(d)$ differs from ours (see eq. 3). Now that we get d as a function of v , we can express the force f applied by a grafted chain on the elastomer for different velocities. Four velocity regimes can be brought out of this result :

If $v < v_1 \simeq \lambda_0 e^{-\frac{3}{2} \frac{a^2 N}{\lambda^2}} / (\tau_0 N P)$, then $d < \lambda$, the chain is almost fully relaxed, and $f \simeq f_0 \frac{v}{v_1}$. For we consider cases where $a^2 N \gg \lambda^2$, v_1 is extremely small.

If $v_1 < v < v_2 \simeq a/(\tau_0 N^{\frac{3}{2}})$, then the chain is partially stretched, and as $\lambda < d < d_{max}$, $f \simeq f_0$. In addition to this stretching force we shall take into account the Rouse friction of the elastomer on the whole chain ¹,

¹Even if the the part of the chain that is in the elastomer is relaxed, it is pulled-out at

which is approximately $kT\tau_0 Nv/a^2$, much smaller than f_0 in this regime and the latter one. We note $v'_1 \simeq v_2 \sqrt{aN^{\frac{1}{2}}/\lambda} \exp[-3(d_{max} - aN^{\frac{1}{2}})^2/2a^2N]$ the velocity for which $d = aN^{\frac{1}{2}}$. Below v'_1 the chain relaxes forming a flat blob of size $aN^{\frac{1}{2}}$. The velocities v_1 and v'_1 are extremely small. When $v < v_2/2$, as $d < d_{max} - \frac{1}{2}\sqrt{\frac{\pi}{6}}aN^{\frac{1}{2}}$, d is given by the relation

$$\frac{v}{v_2} \simeq \frac{1}{2} \sqrt{\frac{d_{max}}{d}} e^{-\frac{3}{2} \frac{a^2 N}{\lambda^2} \left(1 - \frac{d}{d_{max}}\right)^2} \quad (5)$$

If $v_2 < v < v_3 = a/(\tau_0 P^{\frac{3}{2}})$, then the chain is pulled-out faster than it can relax, $d = d_{max}$, and the friction force on the chain is $f_0 + kT\tau_0 Nv/a^2$, where $kT\tau_0 Nv/a^2$ is no longer much smaller than f_0 .

At last, if $v_3 < v$, the Rouse friction dominates, and $d > d_{max}$.

These regimes have been depicted by Rubinstein *et al.*, but the expressions of v_1 and v_2 differs, mainly because their estimation of τ_{in} differs from ours. Notice that the friction of the elastomer on the substrate is to be added to the friction of the chains, and that it could be partially screened out by the grafted layer [2].

At this point it is important to notice that nothing prevents the chain orientation to fluctuate around the sliding direction². If the angle between the chain orientation and $\mathbf{v}$ is θ , one should replace v by $v\cos\theta$ in equation 4, which really changes d only for angles close to $\pi/2$ or $-\pi/2$. These fluctuations lower the effective pull-out friction force by grafted chains of a factor $2/\pi$. Considering more than one grafted chain, one can foresee that a more important consequence of these fluctuations is that it allows the chains to entangle one with the other.

4 Cooperative effects at higher grafting densities

If two chains are grafted at a distance D smaller than d , they can cross, and possibly entangle one with the other. Two situations can be distinguished. First, if the distance $D_{\perp}$ between the two grafting points perpendicularly to $\mathbf{v}$ (see fig. 3a) is bigger than the size l of the flat blobs, the entanglement can only form at the end of one of the chains, and will untie within approximately $(l/\lambda_0)^4$ hopping in and out cycles (the time for the end of the chain to diffuse on the size l), whereas it took $(D_{\perp}/\lambda_0)^4$ cycles to form. Thus, that kind

the velocity $v\lambda/\lambda_0$ in average.

²This was not possible in the situation Rubinstein *et al.* studied, as the chain was dragged inside the elastomer.




Figure 3: Entanglement process between two grafted chains: a) The free end of the relaxed chain B passes over and underneath the stretched part of the chain A . b) The chain B recovers its plume conformation.

of entanglement is fleeting and irrelevant. If $D_{\perp}$ is smaller than l , then an entanglement can form relatively quickly and let the chains recover the same orientation as $\mathbf{v}$. Then, the stretching forces of the two chains equilibrate, and the entanglement slides toward the middle of the chains (see fig. 3b). The effective friction force applied on the elastomer by those two chains is then $f_A + f_B = f_0(\cos\theta_A + \cos\theta_B) < 2f_0$. This entanglement can untie only if one of the chains free end reaches it. But as d can not be smaller than d_{min} , this kind of entanglement has a quasi-infinite life time if the distance $D_{\parallel}$ between the two grafting points parallel to $\mathbf{v}$ is smaller than d_{min} . Therefore, we can assume that a chain entangle with all the chains that are grafted within the area $2l \times d_{min} \simeq 2ld = 2a^2N$ if $v'_1 < v < v_2$. Then, if σ is the grafting density scaled by a^2 , we can roughly evaluate the average value of $\cos\theta$ as

$$\langle \cos\theta \rangle \simeq \frac{\frac{d}{2\sigma N}}{\sqrt{\left(\frac{d}{2\sigma N}\right)^2 + \left(\frac{l}{2}\right)^2}} = \frac{1}{\sqrt{1 + \sigma^2 \left(\frac{aN}{d}\right)^4}} \quad (6)$$

This gives the pull-out friction by surface unit as a function of σ :

$$\Sigma \simeq \frac{\sigma f_0}{a^2 \sqrt{1 + \sigma^2 \left(\frac{aN}{d}\right)^4}} \simeq \begin{cases} f_0 \frac{\sigma}{a^2} & , \text{ if } \sigma < \left(\frac{d}{aN}\right)^2 \\ f_0 \frac{d^2}{a^4 N^2} & , \text{ if } \sigma > \left(\frac{d}{aN}\right)^2 \end{cases} \quad (7)$$

So, this rough model exhibit an interesting feature of elastomer-grafted surface friction: at low grafting densities ($\sigma < \sigma_l \simeq (d/aN)^2$) the friction force by surface unit increases linearly with σ , there is no interaction between grafted chains. At higher grafting densities ($\sigma > \sigma_l$) the friction force by surface unit saturates at the value $\Sigma_l = f_0 d/aN$ (we don't consider here the

friction of the elastomer on the substrate). The roughness of our evaluation of $\langle \cos\theta \rangle$ actually only allows us to give an evaluation of σ_l , give or take a multiplicative constant. Nevertheless, $\sigma_l \simeq (d/aN)^2 = a^2/l^2$ is the grafting density beyond which the mean distance between grafted chains is smaller than l , and we can understand that entanglements produce an important orientation disorder beyond this limit.

The general tendencies for σ_l correspond to the four velocity regimes we developed in the previous section. If $v < v'_1$, then $l = aN^{\frac{1}{2}}$ and $\sigma_l = \sigma_{min} \simeq 1/N$, whereas if $v_2 < v < v_3$, then $l = \lambda$ and $\sigma_l = \sigma_{max} \simeq 4/P$. When $v > v_3$, the Rouse friction dominates and should not be sensitive to entanglements. Using equation 5 we can establish the relation between v and σ_l between v'_1 and $v_2/2$:

$$\frac{v}{v_2} \simeq \frac{1}{2} \left(\frac{\sigma_{max}}{\sigma_l} \right)^{\frac{1}{4}} e^{-\frac{3}{2} \frac{a^2 N}{\lambda^2} \left(1 - \left(\frac{\sigma_l}{\sigma_{max}} \right)^{\frac{1}{2}} \right)^2} \quad (8)$$

The ratio $X^2 = a^2 N / \lambda^2 \sim N/P$ is an important parameter characterizing the system; it gives the range of saturation grafting densities $\sigma_{max}/\sigma_{min} = X^2$. The parameter X also drives the way σ_l evolves within $(\sigma_{min}, \sigma_{max})$ while v varies from v'_1 to v_2 (see fig. 4). Indeed, the range of velocities for which σ_l is bigger than $\sigma_{max}/2$ is given by $v(1/2)/v_2 \simeq \exp[-X^2/8]$, which represents several decades when $X \gg 1$ (see fig. 4a). Another way to see the role played here by X is to write the saturation grafting density corresponding to $v = v_2/10$: $\sigma_l(1/10)/\sigma_{max} \simeq (1 - 1/X)^2$ (all logarithmic factor being ignored, see fig. 4b), which correspond to $d \simeq d_{max} - N^{\frac{1}{2}}$.

It is interesting to note that σ_{max} and Σ_{max} are independent of the chains length N ; Σ_{max} being the maximum friction enhancement one can obtain grafting polymer chains on the flat surface, and σ_{max} the minimum grafting density one should use in order to reach Σ_{max} . The grafted chains length is though an important parameter as it fixes the velocity range over which $\sigma_l \sim \sigma_{max}$. One should use long chains ($a^2 N \gg \lambda^2$) in order to have Σ_l close to Σ_{max} at very low velocities. Nevertheless, the maximum grafting density one can experimentally reach is $1/N^{\frac{1}{2}}$, and one can show that beyond $\sigma^* \simeq P^{\frac{1}{10}} N^{-\frac{3}{5}}$ the grafted layer no longer interdigitates with the elastomer [7]; thus the maximum chain length one should use is $N \simeq P^{\frac{1}{6}}$.




Figure 4: Characteristic plots of the evolution of σ_l/σ_{max} with v/v_2 ($X^2 = a^2N/\lambda^2$).

5 Results and experiment comparison

Comparison with experiments is made harder by the fact that λ is an unknown parameter assumed to be approximately $\lambda_0/2$. However, it can give insights into the validity of the model. Using a PDMS elastomer with reticulation number $P = 100$ and a grafted surface of $N = 1540$ [9] and 380(unpublished studies) PDMS chains, Bureau *et al.* systematically studied $\Sigma = f(\sigma)$ for sliding velocities from 0.3 to $250\mu m.s^{-1}$, each time observing a friction force by grafted chain on the order of kT/λ_0 at low grafting densities, and a saturation of the friction at high grafting densities [9].

For $N = 1540$, they studied saturation at $v = 0.3, 10$, and $100\mu m.s^{-1}$, while $v_2 \simeq 300\mu m.s^{-1}$. At $v = 0.3\mu m.s^{-1}$, $\sigma_l \simeq 0.025nm^{-2}$, at $v = 10\mu m.s^{-1}$, $\sigma_l \simeq 0.035nm^{-2}$, and at $100\mu m.s^{-1}$ the friction seems to saturate around $0.04nm^{-2}$. For $N = 380$, they studied saturation at $v = 10, 100$, and $250\mu m.s^{-1}$, while $v_2 \simeq 2000\mu m.s^{-1}$. At $v = 10\mu m.s^{-1}$, $\sigma_l \simeq 0.015nm^{-2}$, at $v = 100\mu m.s^{-1}$, $\sigma_l \simeq 0.025nm^{-2}$, and at $250\mu m.s^{-1}$, the friction seems to saturate at $\sigma_l \simeq 0.035nm^{-2}$.

As $1/a^2P = 0.04nm^{-2}$, $\sigma_{max} \simeq 0.08nm^{-2}$ would fit with $\lambda \simeq 0.7\lambda_0$. Then, for $N = 1540$, $X^2 = a^2N/\lambda^2 \simeq 30$. For the three velocities studied experimentally, expression 8 gives $\sigma_l(0.3) \simeq 0.03nm^{-2}$, $\sigma_l(10) \simeq 0.04nm^{-2}$, and $\sigma_l(100) \simeq 0.055nm^{-2}$. For $N = 380$, $X^2 \simeq 8$, then, expression 8 gives $\sigma_l(10) \simeq 0.01nm^{-2}$, $\sigma_l(100) \simeq 0.02nm^{-2}$, and $\sigma_l(250) \simeq 0.03nm^{-2}$. Thus, the model reasonably captures those experimental data, even if a slight misevaluation of λ would induce consequent errors on X^2 and $\sigma_l(v)$.

Although more data are needed to confirm the model, we think that it is the best candidate explaining the saturation of the friction : The first other possibility comes from the fact that increasing the grafting density can induce an increase of λ , and a decrease of $f_0 \simeq kT/\lambda$. Indeed, we can

estimate that $\lambda \simeq \lambda_0/2 + \sigma n_{eq}a$. Then, $\sigma f_0 \simeq \sigma kT/(\lambda_0/2 + \sigma n_{eq}a)$, which would give a saturation grafting density equal to $P^{\frac{1}{2}}/n_{eq}$. This overestimates σ_l , and would give σ_l as an decreasing function of v and N , which is not the case experimentally. The second possibility comes from the fact that when $\sigma > \sigma^* \simeq P^{\frac{1}{10}}N^{-\frac{3}{5}}$, the grafted chains no longer penetrate the elastomer because the swelling of the elastomer would not be negligible any more. But, again, this over estimate σ_l , and would give σ_l as an decreasing function of N .

6 Conclusion

We have described here a model for the sliding friction of an elastomer on a flat grafted surface that allows us to understand the participation of grafted chains on friction at low and high grafting densities. This model describes the pull out process of the grafted chains and the formation of entanglements between grafted chains at high grafting densities. The general feature that follows from this is a linear relation between the pull out friction force by surface unit and the surface grafting density when σ is low, and a saturation of the pull out friction force by surface unit beyond a limit grafting density σ_l , which is an increasing function of v and N . The predictions for σ_l are in good agreement with experimental results of Bureau *et al.* which have been mainly conducted in the range $v < v_2$. For $v_2 < v < v_3$, our model predicts that σ_l simply varies like $1/P$; it would be very interesting to experimentally check this prediction in the future.

We thanks Lionel Bureau and Liliane Léger for very interesting discussions and for letting to our knowledge unpublished results.

References

- [1] R. A. L. Jones, R. W. Richards, Polymers at Surfaces and Interfaces, Cambridge University Press (1999).
- [2] H. R. Brown, Science, 263, 1411 (1994).
- [3] L. Léger , E. Raphael , H. Hervet, Advances in Poly. Sci.138, 185 (1999).
- [4] M. Rubinstein, A. Ajdari, L. Leibler, F. Brochard-Wyart and P. G. de Gennes, C. R. Acad. Sci., 316 II, 317 (1993).
- [5] A. Ajdari, F. Brochard-Wyart , P. G. de Gennes, L. Leibler, J. L. Viovy and M. Rubinstein, Physica A, 204, 17, (1994).

- [6] K. P. O'Connor and T. C. B. McLeish, *Macromol.*, 26, 7322 (1993).
- [7] T. Vilmin and E. Raphael, to be published (2004).
- [8] J. M. Deutsch and H. Yoon, *Macromol.*, 27, 5720 (1994).
- [9] L. Bureau and L. Léger *Langmuir*, 20, 4523, 2004.
- [10] C. W. Gardiner, *Handbook of Stochastic Methods*, 3rd ed. (2004), Springer.
- [11] S. T. Milner and T. C. B. McLeish *Macromol.*, 30, 2159, 1997.