



**HAL**  
open science

# High pressure and chemical bonding in materials chemistry

G rard Demazeau

► **To cite this version:**

G rard Demazeau. High pressure and chemical bonding in materials chemistry. *Zeitschrift fur Naturforschung B*, 2006, 61 (7), pp.799-807. 10.1515/znb-2006-0705 . hal-00090712

**HAL Id: hal-00090712**

**<https://hal.science/hal-00090712v1>**

Submitted on 2 Nov 2023

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destin e au d p t et   la diffusion de documents scientifiques de niveau recherche, publi s ou non,  manant des  tablissements d'enseignement et de recherche fran ais ou  trangers, des laboratoires publics ou priv s.



Distributed under a Creative Commons Attribution - NonCommercial - NoDerivatives 4.0 International License

# High Pressure and Chemical Bonding in Materials Chemistry

G rard Demazeau

Universit  Bordeaux 1, Sciences and Technologies, 351 cours de la Lib ration,  
F-33405 Talence Cedex, France  
ICMCB- (UPR CNRS 9048), 87 Avenue du Dr A. Schweitzer, F-33608 Pessac Cedex, France

Reprint requests to Prof. G. Demazeau. E-mail: demazeau@icmcb-bordeaux.cnrs.fr

Z. Naturforsch. **61b**, 799 – 807 (2006); received February 9, 2006

*Dedicated to Professor Wolfgang Jeitschko on the occasion of his 70<sup>th</sup> birthday*

Materials chemistry under high pressures is an important research area opening new routes for stabilizing novel materials or original structures with different compositions (oxides, oxoborates, nitrides, nitridophosphates, sulfides, ...).

Due to the varieties of chemical compositions and structures involved, high pressure technology is also an important tool for improving the investigations on chemical bonding and consequently the induced physico-chemical properties.

Two different approaches can be described: (i) the chemical bond is pre-existing and in such a case, high pressures lead to structural transformations, (ii) the chemical bond does not exist and high pressures are able to help the synthesis of novel materials. In both cases the condensation effect ( $\Delta V < 0$  between precursors and the final product) is the general rule. In addition, through the improvement of the reactivity, high pressures can lead to materials that are not reachable through other chemical routes.

*Key words:* Materials Chemistry, High Pressure Synthesis, Structural Transformations, Novel Materials, Chemical Bonding

## Introduction

A chemical bond can be characterized by different factors:

(i) The involved atoms, *versus* their position in the Periodic Table, inducing some specific atomic properties: electronegativity, ionization potential... and consequently the distribution of bonding electrons (leading to ionic, covalent, metallic character).

(ii) Its strength induced by the overlap of the corresponding orbitals and directly dependent on the interatomic distance, such a distance being correlated, in particular: with (a) the size of the corresponding atoms, (b) the structure of the material (inducing the coordination number), (c) the formal oxidation state of the involved cation...

The energy of the resulting chemical bond is dependent on both factors. If we compare this energy to that conveyed by high pressures, it appears that pressure is a soft thermodynamical parameter, in particular when the liquid or solid phases are concerned (Table 1).

Two different approaches can be analyzed:

Table 1. Energy added by compression *versus* the nature of the medium compared to the average energy of a chemical reaction [R. H. Wentorf, Jr. Chemical Engineering, Oct. 16, p. 177 – 186 (1961)].

Pressure (bar)	Medium	Energy cal/mol
1000	gas	3000
1000	solid	1
10 000	solid	5
100 000	iron	20
100 000	H <sub>2</sub> O	1000
1	chemical reaction	20 000

(i) the chemical bond exists in the involved material-keeping the same chemical composition – and consequently high pressures can, through a structural transformation, modify such a bond,

(ii) the chemical bond does not exist and, in such a case, high pressure can be developed for bonding atoms, leading to the synthesis of novel materials.

## Structural Transformations under High Pressures

The general factor characterizing a structural transformation (from two different structural forms: F<sub>1</sub> to




Fig. 1. Structural evolution vs. pressure for some  $ABO_3$  polytypes [3].

$F_2$ ) under high pressures for a material with a constant composition ( $F$ : corresponding to a specific structural form) is the densification effect (negative  $\Delta V$  value), if

$$\Delta V = \left( \frac{V_1}{Z_1} \right)_{F_1} - \left( \frac{V_2}{Z_2} \right)_{F_2}$$

Such a structural transformation ( $F_1 \rightarrow F_2$ ) can be initiated by different factors: electrostatic and/or steric interactions induced through the compression of the chemical bond.

A structural transformation ( $F_1 \rightarrow F_2$ ) can lead to different structural phenomena:

- the removal of the charged atoms (cations or sometime anions),
- the increase of the coordination number for the most charged atoms.

#### Structural transformations associated with electrostatic interactions

The most illustrative example is the sequence of structural forms for the hexagonal perovskites  $ABX_3$  from the 2H structure to the cubic 3C ones (Fig. 1) [1–3].

In such a case, the coordination number of the  $B^{n+}$  most charged cations remains constant (VI), the electrostatic repulsions  $B^{n+} \cdots B^{n+}$  inducing the transition from face sharing octahedra ( $BX_6$ ) to corner sharing ones. Consequently the  $B^{n+} \cdots B^{n+}$  distance is increased from a  $d$  value to approximately  $d\sqrt{2}$  reducing electrostatic repulsions. With the increase of the pressure the number of corner sharing ( $BX_6$ ) octahedra increases.

For the  $Li_2M^{4+}F_6$  fluorides ( $M^{4+} = Ge, Ti, Zr$ ), structural transformations are induced by both steric and electrostatic interactions. The  $M^{4+} \cdots M^{4+}$  distance remains approximately constant but the number of




Fig. 2. Variation of the volume for a unit  $Li_2MF_6$  versus  $r^3(M^{4+})$  ( $r$  being the ionic radius) [4].

common edges between ( $M^{4+}F_6$ ) and ( $Li^+F_6$ ) octahedra decreases with the  $M^{4+}$  size or under high pressures for a constant  $M^{4+}$  cation (Fig. 2) [4].

Binary oxides  $MO_2$  at normal pressure, involving highly electropositive transition metals, are ionic and adopt 3D structures such as the rutile structure in order to minimize the electrostatic repulsion between  $O^{2-}$  anions. For example,  $TiO_2$  adopts only the 3D rutile structure due to the large electronegativity difference between Ti and O (1.54 and 3.44, respectively). On the contrary  $PtO_2$  – due to the smaller electronegativity difference between Pt and O (2.28 and 3.44, respectively) – can adopt at ambient pressure the layered  $CdI_2$ -type structure ( $\alpha$ - $PtO_2$ ) [5]. Under high pressure conditions – due to the enhancement of the electrostatic repulsion – the  $\alpha$ - $PtO_2$  ( $CdI_2$ -type) is transformed to the rutile form ( $\beta$ - $PtO_2$ ) [6]. First principles electronic calculations have recently confirmed the relative stabilities of the rutile and  $CdI_2$  structural types versus the metal-oxygen and oxygen-oxygen orbital interactions [7].

For the binary oxides characterized at normal pressure by the rutile structure, under high pressures a competition is observed between the fluorite structure (CaF<sub>2</sub>-type, space group  $Fm\bar{3}m$ ) and the pyrite structure (FeS<sub>2</sub>-type, space group  $Pa\bar{3}$ ). The transition rutile → fluorite is observed for TiO<sub>2</sub> [8], ZrO<sub>2</sub> [9] or HfO<sub>2</sub> [10]. On the other hand, the transition rutile → pyrite is induced for GeO<sub>2</sub> [11], SnO<sub>2</sub> [12], PbO<sub>2</sub> [13] and RuO<sub>2</sub> [13].

The main difference between both structural types being the positions of the oxygen atoms, consequently electrostatic interactions induced under high pressures appear to play a key role.

Another interesting high pressure transformation under high pressures is the transition observed for the K<sub>2</sub>MO<sub>3</sub> oxides ( $M = \text{Zr, Hf, Sn, Pb}$ ) from the prismatic K<sup>+</sup> coordination to a pseudo-octahedral one in order to reduce the O<sup>-δ</sup>-O<sup>-δ</sup> electrostatic interactions [14].

Structural transformations are particularly interesting when different chemical bonds are involved. As an example, binary alkaline earth subnitrides (AE)<sub>2</sub>N ( $M = \text{Ca, Sr, Ba}$ ) can be characterized by a unique combination of ionic and metallic bonding within the same crystal structure. Due to the formal description resulting of the charge neutrality, such a structure can be described by the formula (AE)<sub>2</sub><sup>2+</sup> · N<sup>3-</sup> · e<sup>-</sup>. The anti-CdCl<sub>2</sub> structure type is built from two-dimensional hexagonal double layers of AE<sup>2+</sup> atoms with nitrogen atoms centering M<sub>6</sub> octahedra within the layers [15]. Ionic bonding between (AE)<sup>2+</sup> and N<sup>3-</sup> holds the (AE)<sub>2</sub>N layers together, metallic inter-layer bonding results from nearly-free remaining electrons. Under high pressures – up to 40 GPa – different phase-transitions are observed that allow to study the behaviour of this combination of chemical bonding [15].

#### *Structural transformations induced by different bond compressibilities*

The bond compressibilities allow to induce high-pressure structural transformations [16]. The development of high T<sub>c</sub> superconductivity has improved the synthesis of a large variety of compositions and structures for complex copper oxides with different linkages of square planar CuO<sub>4</sub> units (1D, 2D, 3D) versus the involved counter-cation [17].

Due to the difference of compressibility between the Cu-O bond and the (counter-cation) – O bond, the structure of cuprates can be modified *versus* temperature and pressure [18]. For example the quasi-1D

structure of SrCuO<sub>2</sub> (characterized by double Cu-O chains) can be transformed to a 2D-structure (with CuO<sub>2</sub> sheets) at 3 GPa and 900 °C [19].

The high-pressure behaviour of the GdFeO<sub>3</sub>-type orthorhombic perovskites (ABO<sub>3</sub>) – in particular the tilting of the (BO<sub>6</sub>) octahedra – has recently been explained in terms of relative compressibilities of the (BO<sub>6</sub>) and (AO<sub>12</sub>) polyhedra. If the (BO<sub>6</sub>) octahedra are less compressible than the (AO<sub>12</sub>) dodecahedra the structural distortion is increased under high pressures. In the opposite case, if the (BO<sub>6</sub>) octahedra are more compressible than the (AO<sub>12</sub>) polyhedra; the structural distortion is decreased. A bond-valence concept has recently been developed for explaining the relative compressibilities of the cationic sites in oxide perovskites [20].

#### **Synthesis of Novel Materials Induced by High Pressures**

The syntheses helped by high pressures are also governed by a so-called “densification effect”. In such a case, the negative value  $\Delta V$  characterizes the difference between the volume of the precursors and that of the resulting materials [if  $A + B \rightarrow AB$ ,  $\Delta V = (V_A/Z_A + V_B/Z_B) - (V_{AB}/Z_{AB})$ ].

Densification effects can play an important role in phase diagrams; the formation of specific compositions different than that observed at normal pressure can be induced.

For example, in the Al<sub>2</sub>O<sub>3</sub>-B<sub>2</sub>O<sub>3</sub> diagram, at normal pressure two compositions are observed: 9Al<sub>2</sub>O<sub>3</sub>-2B<sub>2</sub>O<sub>3</sub> and 2Al<sub>2</sub>O<sub>3</sub>-B<sub>2</sub>O<sub>3</sub>; on the contrary at 4 GPa and the same temperature domain, the previous compositions do not exist but two new ones are stabilized (Al<sub>3</sub>BO<sub>6</sub> and AlBO<sub>3</sub>) [21].

In addition, different factors can induce synthesis under high pressures:

- thermodynamical factors,
- improvement of the reactivity and/or the decrease of the inter-atomic distances,
- structural factors involving the “*in-situ*” compressibility of the corresponding atoms.

#### *Modification of the thermodynamic properties and the high pressure applications in metallurgy*

Melt-quenching under high pressures has been developed in metallurgy. Through the induced thermo-

dynamical effects, high pressure processes have been mainly investigated in three domains:

- the synthesis of new alloy compositions,
- the stabilization of amorphous alloys,
- the preparation of nanostructured alloys.

#### Synthesis of new alloys and intermetallic compounds

The variation of melting point with pressure has been applied to improve the rapid solidification of melted alloys [22, 23].

The liquid  $\rightarrow$  solid transformation is usually accompanied by a volume change. Consequently high pressures favour only the denser phases characterized by a negative  $\Delta V$  value [24].

Pressure is able to have also a strong influence on the thermodynamic driving force and nucleation rate for each phase [25]. In addition, the long range atomic rearrangement will be depressed at high pressures leading to a change of the microstructure and phase composition for solidification products [26, 27].

As an illustration, high pressure has a strong influence on the solidification of Al-Mn alloys leading to a new orthorhombic  $\text{Al}_{3.4}\text{Mn}$  phase as well as nanocrystalline Al obtained by quenching the Al(20 wt%) Mn alloy melt at 6 GPa [28].

In the system Ca-Au at ambient pressure, the formation of two intermetallic phases  $\text{CaAu}_3$  [29] and  $\text{Ca}_2\text{Au}_7$  [30] has been observed. Using  $\text{Ca}_3\text{N}_2$  and metallic Au as precursors at 850 °C and a mild pressure (7.5 MPa), a new composition  $\text{Ca}_3\text{Au}_4$  was stabilized [31].

More recently a novel intermetallic compound  $\text{MgCu}$  with a CsCl-type structure has been obtained under high pressures (6 GPa, 800 °C, 8 h.). This compound decomposes at 520 K in normal pressure conditions into  $\text{Mg}_2\text{Cu}$  and  $\text{MgCu}_2$  [32].

#### Synthesis of amorphous alloys

Using high pressures – suppressing the diffusion processes and lowering the critical cooling rate of the amorphous formation – metallic glasses can be induced at a relatively lower cooling rate [33].

The  $\text{Cu}_{85}\text{Sn}_{15}$  amorphous alloy has been prepared by melting the alloy under high pressure and cooling to r. t. at a cooling rate close to  $10^3$  K/s [34].

During the last twenty years the synthesis of amorphous alloys has been investigated [35, 36].

Table 2. Some illustrations of the high-pressure synthesis of novel materials from thermally unstable precursors.

Thermally unstable Precursors	Resulting materials	References
$\text{PbO}_2$	$\text{PbSnO}_3$	[40]
$\text{CrO}_2$	$\text{PbCrO}_3$	[41]
	$\text{CaCrO}_3$	[42]
$\text{HgO}$	$\text{Hg}_x\text{WO}_3$	[43]
	$\text{Hg}_2\text{M}_2\text{O}_7$	[44]

#### Preparation of nanocrystalline alloys

The preparation of nanocrystalline materials is strongly correlated to the control of nucleation and growth of grains. In order to prepare nanometer scaled crystals the nucleation must be strongly improved and the growth rate reduced. Due to the high pressure effects on the activation energy of viscous flow, melting rate increases and growth rate decreases.

If the pressure is high enough the grain size can be controlled by adjusting the pressure value. Nanocrystalline Zn with a grain size close to 20 nm has been prepared by high pressure melt quenching [37].

The effect of high pressures on the preparation of bulk nanocrystalline materials has also been, observed for the ternary system Pd-Si-Cu [38] and the binary system Ti-Cu [39].

#### *Thermodynamic effects and the stabilization of thermally unstable precursors*

In a chemical system, at the temperature required for the reaction between the precursors, high vapour pressure can be induced due to different thermal phenomena involving the precursors (decomposition, sublimation. . .). High pressures being able to suppress or to push to higher temperatures such effects, this technique is efficient for synthesizing novel materials with an appropriate stoichiometry. High pressure has been used for improving Materials Chemistry not only for preparing new oxides (Table 2) [40–44], but also for developing new research domains.

As an example, due to the reduced thermal stability of  $\text{P}_3\text{N}_5$ , leading to the irreversible elimination of  $\text{N}_2$ , high pressures increased the decomposition temperature leading to the synthesis of new materials from this precursor. Consequently original high pressures-high temperatures routes (4 GPa, 1300 °C) have been developed for preparing alkali and alkaline-earth nitridophosphates:  $M^1\text{P}_4\text{N}_7$  ( $M = \text{Na}, \text{K}, \text{Rb}, \text{Cs}$ ) or  $M^1_3\text{P}_6\text{N}_{11}$  ( $M = \text{Rb}, \text{Cs}$ ) using phosphorus nitride  $\text{P}_3\text{N}_5$  and metal azides as precursors [45, 46].

In order to improve Materials Chemistry involving nitridophosphate, the same chemical route ( $2\text{P}_3\text{N}_5 + 3\text{Ba}(\text{N}_3)_2 \rightarrow 3\text{BaP}_2\text{N}_4 + 8\text{N}_2$ ) has been set-up (8 GPa, 1400 °C) [47]. The crystal structure of the resulting material ( $\text{BaP}_2\text{N}_4$ ) is isostructural with that of  $\text{BaGa}_2\text{S}_4$  [48] and the high pressure form of  $\text{CaB}_2\text{O}_4$  [49].

In parallel, the thermal stabilization of  $\text{P}_3\text{N}_5$  has allowed to prepare a new high pressure form  $\gamma\text{P}_2\text{N}_5$  characterized by tetrahedral ( $\text{PN}_4$ ) and square pyramidal ( $\text{PN}_5$ ) units [50] compared to  $\alpha\text{-P}_3\text{N}_5$  characterized only by ( $\text{PN}_4$ ) tetrahedra [51, 52]. Consequently high pressure is also able to increase the phosphorus coordination number ( $\text{IV} \rightarrow \text{V}$ ) and also the density (32%). Such a high pressure transformation is comparable to the stabilization of the cubic  $\gamma\text{-Si}_3\text{N}_4$  phase under high pressure conditions [53, 54].

Another illustration of the development of a new high pressure chemistry is the stabilization of thioborate compounds.  $\text{CaB}_2\text{S}_4$  has been prepared under high pressure conditions (6.2 GPa, 800–1100 °C) under the vapour pressure of sulphur in the required temperature domain for the reaction. In addition to the thermal stabilization of the precursors, the densification effects leads to a structure characterized by a three-dimensional linkage of ( $\text{BS}_4$ ) tetrahedra and icosahedral sulphur coordination for calcium [55].

Consequently it appears that high pressures are a fruitful tool for opening new research areas in Materials Chemistry (as: nitrodophosphates, thioborates, high pressure-forms of borates...) improving the knowledge of the correlations between the chemical bond, the structure and the resulting physical properties.

#### *Synthesis of materials with mixed anions*

The preparation of materials with mixed anions requires, in most cases, the use of precursors characterized by different physico-chemical properties. Consequently the reactivity is different and high pressures can be an important tool.

During the last thirty years several new materials have been stabilized, mainly in the domain of oxyfluorides, as  $\text{MOF}$  with  $M = \text{Ti}, \text{V}, \text{In}$  [56, 57],  $\text{Ti}_2\text{OF}_2$  [58], and  $\text{KTiO}_2\text{F}$  [59].

More recently a strong interest has been devoted to nitride-halides:  $\text{MNX}$  with  $M = \text{Zr}, \text{Hf}$  and  $X = \text{Cl}, \text{Br}$  [60] or  $\text{ZrNF}$  [61].

Two different routes can be developed for preparing such materials:

- the reaction between two different precursors as:  $\text{KF} + \text{TiO}_2 \rightarrow \text{KTiO}_2\text{F}$  [59],
- the use of a reactive pressure, as for the preparation of  $\text{Ti}_2\text{OF}_2$  resulting from the treatment of  $\text{TlF}$  under oxygen pressure [58] or  $\text{ZrNF}$  obtained through a high pressure reaction of  $\text{ZrN}$  with  $\text{NH}_4\text{F}$  as source of fluorine [61].

#### *Stabilization of strong covalent bonds under high pressure conditions*

The covalency of a chemical bond is strongly correlated to the overlap of the atomic orbitals and consequently to the interatomic distance between the involved atoms.

High pressures are able to play an important role in the formation of covalent bonds through two different routes:

- (i) the improvement of reactivity for the synthesis of materials with light elements (in particular the elements involving 2p orbitals: B, C, N, ...),
- (ii) the stabilization of the highest oxidation states of transition metals.

#### *Stabilization of materials with light elements*

The corresponding materials involve mainly the 2p elements (B, C, N). Due to the small reactivity of such elements and the three dimensional structure of the materials characterized by a large panel of physico-chemical properties (diamond, c-BN), high pressures are required for preparing novel materials with light elements [62–64]. More recently the high pressure polymerisation of fullerenes has been investigated [65–66].

During the last ten years a strong interest for such materials has been developed with the attempts to synthesize carbonitrides – in particular 3D forms of  $\text{C}_3\text{N}_4$  – with properties comparable with that of diamond [67–68]. This area can be considered as an example where computational chemistry and high pressure synthesis are associated for developing Materials Chemistry [69].

Concerning 3p elements, high pressures have recently opened new developments in silicon clathrate physical chemistry [70–71].

The development of novel materials with light elements will be of a great interest in the near future either for improving basic science (how chemical bonding with these elements can develop correlations be-

Table 3. Evolution of the  $\text{Fe}^{n+}\text{-O}$  distances versus the formal  $n_+$  value [ $r(\text{Fe}^{n+})$  is defined on the basis of  $r(\text{O}^{2-}) = 1.40 \text{ \AA}$ ] [72].

	Fe(III)-O ( $\text{LiFeO}_2$ )	Fe(IV)-O ( $\text{Sr}_{0.50}\text{La}_{1.50}\text{Li}_{0.50}\text{Fe}_{0.50}\text{O}_4$ )	Fe(V)-O ( $\text{La}_2\text{LiFeO}_6$ )
$\text{Fe}^{n+}\text{-O}$ ( $\text{\AA}$ )	2.03	1.95 <sub>6</sub>	1.86
$r(\text{Fe}^{n+})$ ( $\text{\AA}$ )	0.63	0.55 <sub>6</sub>	0.46

tween Materials Chemistry and Physics) or industrial applications involving large band-gap materials, high mechanical properties, high thermal conductivity, ...

#### *Preparation of materials with high oxidation states of transition metals*

When the formal oxidation state of a metal is increased, the interatomic distance  $\text{M}^{n+}\text{-X}$  is strongly reduced compared to the compressibility effect. Table 3 gives an illustration for the evolution of  $\text{Fe}^{n+}\text{-O}$  distances (octahedral  $\text{Fe}^{n+}$  coordination) *versus* the improvement of the formal  $n_+$  oxidation state [72].

Due to the corresponding enhancement of the  $\text{M}^{n+}\text{-O}$  bond strength, different electronic phenomena can be induced:

- intra-atomic phenomena, as the change of electronic configurations correlated to the local ( $\text{Dq/B}$ ) value [73],
- inter-atomic phenomena as insulator  $\rightarrow$  metal transitions [74] or – in the case of anisotropic electronic configuration [as high-spin  $\text{Fe}^{4+}(t_{2g}^3 e_g^1)$  or low-spin  $\text{Ni}^{3+}(t_{2g}^6 e_g^1)$ ] – disproportionation ( $2\text{M}^{n+} \rightleftharpoons \text{M}^{(n-\epsilon)+} + \text{M}^{(n+\epsilon)+}$ ) [75, 76].

The development of such a research area appears important for improving the knowledge of correlations between the strongest chemical bonds and the induced physical phenomena.

Recently Mössbauer spectroscopy, as a local physical characterization, has allowed to follow such electronic phenomena in  $\text{RENiO}_3$  ( $\text{RE} = \text{rare-earth}$ ) slightly doped with  $^{57}\text{Fe}$  (1–2%) [77, 78].

#### *High pressures and reactivity*

The improvement of the reactivity plays an important role on the formation of chemical bonds and consequently on the synthesis of novel materials. In a general case, under high pressure conditions, the reaction time is considerably reduced and the reaction temperature also. Consequently such effects are able to help

the development of high pressures and soft chemistry in materials synthesis.

Two approaches can be involved versus the physical state of the precursors.

(i) At the beginning of the development of Materials Chemistry under high pressures using solid precursors, the strong effect on the kinetics of materials preparation was underlined [79]. The inducing effects are not so well-known and it would be important to improve this knowledge.

(ii) The reaction between a solid phase and a liquid phase is able to improve strongly the reactivity. Different hypotheses have been postulated for explaining such an effect: dissolution-recrystallisation phenomena, improvement of the dissociation of the solvent, physico-chemical phenomena at the interface between solid/liquid phases *etc.* This domain involves both: hydrothermal synthesis with aqueous solutions [80, 81] or solvothermal reactions with non-aqueous solvents [82–84].

The first approach has led to the synthesis of novel materials. Two different families have recently been investigated under very high pressure ( $P \geq 10 \text{ GPa}$ ) and high temperature ( $1100 \leq T \leq 1700 \text{ }^\circ\text{C}$ ) conditions: (i) the rare earth silicates  $\text{RE}_2\text{Si}_2\text{O}_7$  [85] and (ii) the rare earth borates  $\text{RE}_3\text{B}_5\text{O}_{12}$  with a crystal structure isostructural with the beryllio-silicate-mineral: semenorite [86]. In such a domain, high pressures help for the synthesis of these new oxides and stabilize novel interesting structures.

Hydrothermal and solvothermal reactions appear to be very fruitful. The overlap of different parameters: (i) chemical composition of the solvent adapted to that of the expected materials, (ii) use (simultaneously) of the two thermodynamical parameters: (pressure and temperature), are able to develop the synthesis of novel materials (in particular metal-organic frameworks with unusual units and mixed ligands) [87–88]. During the last ten years this domain has been developed either for preparing nanoparticles [89–90] or large single crystals [91–93] and for setting up new processes for the preparation of ceramics under mild conditions [94].

#### *Modification of the reactivity through the atomic compressibility under high pressures*

The compressibility of atoms, under very high pressure conditions, is able to modify the energy of the orbitals and consequently to change their electronic

structure. Such a compressibility depends on the position of such atoms in the Periodic Table [95].

On the basis of the compressibility of potassium and the associated modifications of the electronic configuration ( $d^0s^1 \rightarrow s^0d^1$ ), Badding et al. have explained the synthesis of new materials  $K_xM$  ( $M = Ag, Ni, Pd$ ) [96–98].

### Conclusions and Perspectives for Developing High Pressure Materials Chemistry

Through the different aspects of high pressure contributions (thermodynamical and structural effects, improvement of the reactivity, ...) Materials Chemistry under High Pressures seems able to help the formation of specific chemical bonds and consequently to improve basic knowledge of correlations between composition/chemical bond/structure and the resulting physico-chemical properties. All the areas of the Materials Chemistry can be involved (intermetallic compounds, oxides fluorides, borides, carbides, nitrides, ...) but also materials with mixed anions (carbonitrides, fluoronitrides, ...) where two different chemical bonds are present in the same structure.

In particular, the research domain involving intermetallic compounds could be important either for basic research (as for example the high pressure structural transformations of lanthanoid platinum germanides [99] or ternary lanthanoid pnictides  $Li(AE)Pn$  ( $AE = Eu, Pn = P, As, Sb, Bi$ ) [100]) or for preparing new materials for specific applications.

During the last five years, due to the progress in the diamond anvil cell and laser heating techniques [101], a new synthesis route in Materials Chemistry was initiated under very high pressure conditions (several ten GPa). This process was developed for the preparation of different novel materials: PtN [102], PtC [103], and  $Co_2N$  [104].

Such a route for preparing specific materials appears fruitful for the future but, due to the small energy conveyed by high pressures and taking into account that – in most cases – such synthesis involves the elements (metal+nitrogen or carbon) more or less non-reactive, a particular effort for improving the reactivity of the involved precursors – through a chemical analysis – could be important, in particular for reducing the preparation conditions.

- 
- [1] J. M. Longo, J. A. Kafalas, *J. Solid State Chem.* **1**, 103 (1969).
- [2] J. M. Longo, J. A. Kafalas, *Mater. Res. Bull.* **3**, 687 (1968).
- [3] J. B. Goodenough, J. A. Kafalas, J. M. Longo, in P. Hagenmuller (ed.): *High Pressure Synthesis*, Chapter I p. 2–65, Preparative Methods in Solid State Chemistry, Academic Press, New York, London (1972).
- [4] G. Demazeau, F. Menil, J. Portier, P. Hagenmuller, *C.R. Acad. Sci.* **273**, 1093 (1971).
- [5] H. R. Hoekstra, S. Siegel, F. X. Gallacher, *Adv. Chem. Ser.* **98**, 39 (1971).
- [6] K. J. Range, F. Rau, U. Klement, A. M. Heyns, *Mater. Res. Bull.* **22**, 1541 (1987).
- [7] C. Souillard, X. Rocquefelte, S. Jobic, D. Dai, H. J. Koo, M. H. Whangbo, *J. Solid State Chem.* **175**, 353 (2003).
- [8] M. Mattesini, J. S. de Almeida, L. Dubrovinsky, N. Dubrovinskaia, B. Johansson, R. Ahuja, *Phys. Rev. B* **70**, 212101 (2004).
- [9] P. Bouvier, V. Dmitriev, G. Lucazeau, *Eur. Phys. J.* **B35**, 301 (2003).
- [10] T. Mori, M. Fujiwara, R. R. Manory, I. Shimizu, T. Tanaka, S. Miyake, *Surf. Coat. Technol.* **169-170**, 528 (2003).
- [11] S. Ono, K. Hirose, T. Tsuchiya, Y. Ohishi, *Phys. Rev. B* **68**, 014103 (2003).
- [12] J. Haines, J. M. Leger, *Phys. Rev. B* **55**, 11144 (1997).
- [13] J. Haines, J. M. Leger, O. Schulte, *Science* **271**, 629 (1996).
- [14] C. Delmas, G. Demazeau, M. Devalette, C. Fouassier, P. Hagenmuller, *J. Solid State Chem.* **18**, 87 (1976).
- [15] G. V. Vajenine, A. Grzechnik, K. Syassen, I. Loa, M. Hanfland, A. Simon, *C. R. Chimie* **8**, 1897 (2005).
- [16] I. D. Brown, P. Klages, A. Skowron, *Acta Crystallogr. B* **59**, 439 (2003).
- [17] H. Müller-Buschbaum, *Angew. Chem. Int. Ed. Engl.* **16**, 674 (1977).
- [18] H. G. Drickamer, R. W. Lynch, R. L. Clendenen, E. A. Perz-Albuerne, *Solid State Physics Vol. 19*, p. 135–228, Ed: F. Seitz and D. Turnbull, Academic Press, New York (1996).
- [19] M. Takano, Y. Takeda, H. Okada, M. Miyamoto, K. Kusaka, *Physica C* **159**, 375 (1989).
- [20] J. Zhao, N. L. Ross, R. J. Angel, *Acta Crystallogr. B* **60**, 263 (2004).
- [21] J. J. Capponi, J. Chenavas, J. C. Joubert, *Bull. Soc. Mineral. Cristallogr.* **95**, 412 (1972).
- [22] J. A. Sekhar, M. Mohan, C. Divakar, A. K. Singh, *Scripta Metall.* **18**, 1327 (1984).
- [23] D. W. He, F. X. Zhang, M. Zhang, R. P. Liu, Z. Q. Qin, Y. F. Xu, N. K. Wang, *Appl. Phys. Lett.* **71**, 3811 (1997).
- [24] D. W. He, F. X. Zhang, M. Zhang, R. P. Liu, W. K. Wang, *Cryst. Res. Technol.* **33**, 43 (1998).



- [25] C. P. Lee, T. G. Wang, *J. Appl. Phys.* **71**, 5721 (1992).
- [26] W. K. Wang, I. Iwasaki, C. Suryanarayana, I. Masumoto, *J. Mater. Sci.* **18**, 3765 (1983).
- [27] Y. Xu, X. Huang, W. Wang, *Appl. Phys. Lett.* **56**, 1957 (1990).
- [28] D. He, M. He, C. S. Kiminami, F. X. Zhang, Y. F. Xu, W. K. Wang, K. H. Kuo, *J. Mater. Res.* **16**, 910 (2001).
- [29] M. Notin, J. Hertz, *Comput. Coupling Phase Diag. Thermochem.* **6**, 49 (1982).
- [30] J. J. Egan, *High Temp. Sci.* **19**, 111 (1985).
- [31] P. F. Henry, M. T. Weller, *J. Alloys Comp.* **292**, 152 (1999).
- [32] H. Takamura, H. Kakuta, Y. Goto, H. Watanabe, A. Kamegawa, M. Okada, *J. Alloys Comp.* **404–406**, 372 (2005).
- [33] Z. Q. Hu, B. Z. Ding, H. F. Zhang, D. J. Li, B. Yao, H. Z. Liu, A. M. Wang, *Science and Technology of Advanced Materials* **2**, 41 (2001).
- [34] V. V. Brazhkin, S. V. Popova, *Met. Phys.* **7**, 103 (1985).
- [35] D. J. Li, J. T. Wang, B. Z. Ding, S. L. Li, *Chin. J. High Press. Phys.* **8**, 74 (1994).
- [36] D. J. Li, J. T. Wang, B. Z. Ding, *Scr. Metall. Mater.* **28**, 1083 (1993).
- [37] H. Z. Liu, A. M. Wang, L. H. Wang, B. Z. Ding, Z. Q. Hu, *Proceedings of the 3<sup>rd</sup> Pacific Rim International Conference on Modeling and Solidification Processes*, p. 422, B. C. Liu, T. Jing (eds.), Academic Publishers, New York (1996).
- [38] B. Yao, B. Z. Ding, G. L. Sui, A. M. Wang, Z. Q. Hu, *J. Mater. Res.* **11**, 912 (1996).
- [39] D. J. Li, A. M. Wang, B. Yao, B. Z. Ding, Z. Q. Hu, *J. Mater. Res.* **11**, 2685 (1996).
- [40] F. Sugawara, Y. Syono, S. Akimoto, *Mater. Res. Bull.* **3**, 529 (1968).
- [41] W. L. Roth, R. C. de Vries, *J. Applied Phys.* **38**, 951 (1967).
- [42] J. H. Weiher, B. L. Chamberland, J. L. Gillson, *J. Solid State Chem.* **3**, 529 (1971).
- [43] Ph. Plante, G. Demazeau, M. Pouchard, P. Hagenmuller, *Bull. Soc. Chim. Fr.* **12**, 3301 (1973).
- [44] A. W. Sleight, *Inorg. Chem.* **7**, 1704 (1968).
- [45] K. Landskron, E. Irran, W. Schnick, *Chem. Eur. J.* **5**, 2548 (1999).
- [46] K. Landskron, W. Schnick, *J. Solid State Chem.* **156**, 390 (2001).
- [47] F. W. Karau, W. Schnick, *J. Solid State Chem.* **178**, 135 (2005).
- [48] B. Eisenmann, M. Jakowski, H. Schäfer, *Mater. Res. Bull.* **17**, 1169 (1982).
- [49] M. Marezio, J. P. Remeika, D. D. Dernier, *Acta Crystallogr.* **B25**, 965 (1969).
- [50] K. Landskron, H. Huppertz, J. Senker, W. Schnick, *Angew. Chem.* **40**, 2643 (2001).
- [51] W. Schnick, *Angew. Chem.* **105**, 846 (1993).
- [52] S. Horstmann, E. Irran, W. Schnick, *Angew. Chem.* **109**, 1938 (1997).
- [53] A. Zerr, G. Miehe, G. Serghiou, M. Schwartz, E. Kroke, R. Riedel, P. Kroll, R. Boehler, *Nature.* **400**, 340 (1999).
- [54] M. Schwartz, G. Miehe, A. Zerr, E. Kroke, B. Poe, H. Fuess, R. Riedel, *Adv. Mater.* **12**, 883 (2000).
- [55] T. Sasaki, H. Takizawa, T. Takeda, T. Endo, *Mater. Res. Bull.* **38**, 33 (2003).
- [56] B. L. Chamberland, A. W. Sleight, *Solid State Commun.* **5**, 765 (1967).
- [57] B. L. Chamberland, K. R. Babcock, *Mater. Res. Bull.* **2**, 481 (1967).
- [58] G. Demazeau, J. Grannec, A. Marbeuf, J. Portier, P. Hagenmuller, *C. R. Acad. Sci. Paris* **269**, 987 (1969).
- [59] B. L. Chamberland, *Mater. Res. Bull.* **6**, 311 (1971).
- [60] I. O. Troyanchuk, N. V. Kasper, O. S. Mantyskaya, E. F. Shapovalova, *Mater. Res. Bull.* **30**, 421 (1995).
- [61] L. Zhu, X. Chen, S. Yamanaka, *Solid State Commun.* **130**, 227 (2004).
- [62] L. Vel, G. Demazeau, J. Etourneau, *Materials Science & Engineering Solid State Materials for Advanced Technology* **B10**, 149 (1991).
- [63] N. V. Novikov, *J. Mater. Processing. Technol.* **161**, 169 (2005).
- [64] V. L. Solozhenko, E. Gregoryanz, *Materials Today* **44** (2005).
- [65] V. D. Blank, G. A. Dubitsky, R. N. Serebryanaya, B. Mavrin, V. N. Denisov, S. G. Buga, L. A. Chernozatonskii, *Physica B* **339**, 39 (2003).
- [66] R. Moret, T. Wagberg, B. Sundquist, *Carbon* **43**, 709 (2005).
- [67] A. Y. Liu, M. L. Cohen, *Science* **245**, 841 (1989).
- [68] D. Teter, R. J. Hemley, *Science* **271**, 53 (1996).
- [69] M. L. Cohen, *Solid State Commun.* **107**, 589 (1998).
- [70] E. Reny, S. Yamanaka, C. Cros, M. Pouchard, *J. Phys. Condens. Matter.* **14**, 11233 (2002).
- [71] N. Jaussaud, P. Toulemonde, M. Pouchard, A. San-Miguel, P. Gravereau, S. Pechev, G. Goglio, C. Cros, *Solid State Sci.* **6**, 401 (2004).
- [72] G. Demazeau, *Materials Science & Engineering R.*, submitted.
- [73] S. H. Byeon, G. Demazeau, L. Fournès, J. M. Dance, J. H. Choy, *Solid State Commun.* **80**, 457 (1991).
- [74] M. Medarde, A. Fontaine, J. L. Garcia-Muñoz, J. Rodriguez-Carjaval, M. De Santis, M. Sacchi, G. Rossi, P. Lacorre, *Phys. Rev. B* **46**, 14975 (1992).
- [75] J. Matsuno, T. Mizokawa, A. Fujimori, Y. Takeda, S. Kawasaki, M. Takano, *Phys. Rev. B* **66**, 193103 (2002).
- [76] J. A. Alonso, J. L. Garcia-Muñoz, M. T. Fernandez-Diaz, M. A. Aranda, M. J. Martinez-Lope, M. T. Casais, *Phys. Rev. Lett.* **82**, 3871 (1999).
- [77] S. J. Kim, I. Presniakov, G. Demazeau, K. Pokholok,

- A. Baranov, A. Sobolev, D. Pankratov, N. Ovanesyan, *J. Solid State Chem.* **168**, 126 (2002).
- [78] I. A. Presniakov, G. Demazeau, A. V. Baranov, A. V. Sobolev, K. V. Pokholok, *Phys. Rev. B* **71**, 054409 (2005).
- [79] P. Hagenmuller, *Preparative Methods in Solid State Chemistry*, Chap. 1, High Pressure Synthesis, p. 2, Academic Press, New York (1972).
- [80] S. Feng, R. Xu, *Acc. Chem. Res.* **34**, 329 (2001).
- [81] K. Byrappa, M. Yoshimura, *Handbook of Hydrothermal Technology Materials Science and Processing Technology Series*, Noyes Publications, Park Ridge, New Jersey, New York (2001).
- [82] G. Demazeau, *J. Mater. Chem.* **9**, 15 (1999).
- [83] P. Reig, G. Demazeau, R. Naslain, *Eur. J. Solid State Inorg. Chem.* **32**, 439 (1995).
- [84] J. Li, Z. Chen, R. J. Wang, D. M. Proserpio, *Coordination Chem. Rev.* **190-192**, 707 (1999).
- [85] M. E. Fleet, X. Liu, *J. Solid State Chem.* **178**, 3275 (2005).
- [86] H. Emme, M. Vallador, R. Pöttgen, H. Huppertz, *Chem. Mater.* **17**, 2707 (2005).
- [87] Y. Yan, C. D. Wu, X. He, Y. Q. Sun, C. Z. Lu, *Crystal Growth & Design.* **5**, 821 (2005).
- [88] S. Sharma, A. Ramanan, M. Jansen, *Solid State Ionics* **170**, 93 (2004).
- [89] Y. Gu, Y. Qian, L. Chen, F. Zhou, *J. Alloys Comp.* **352**, 325 (2003).
- [90] W. Zhang, D. Ma, J. Liu, L. Kong, W. Yu, Y. Qian, *Carbon* **42**, 2341 (2004).
- [91] F. Lafon, G. Demazeau, *Matériaux et Techniques* **3-4**, 11 (1997) and **5-6**, 17 (1997).
- [92] A. Denis, G. Goglio, G. Demazeau, *Mater. Sci. Eng.* (2006), in press.
- [93] U. Ozgur, Y. I. Alivov, C. Liu, A. Teke, M. A. Reshchikov, S. Dogan, V. Avrutin, S. J. Cho, H. Morkoç, *J. Appl. Phys.* **98**, 041301 (2005).
- [94] R. E. Riman, W. L. Suchanek, M. M. Lencka, *Ann. Chim. Sci. Mat.* **27**, 15 (2002).
- [95] S. Woorizadeh, M. Parhizgar, *J. Mol. Struct.: THEOCHEM.* **725**, 23 (2005).
- [96] J. V. Badding, L. J. Parker, D. A. Nesting, *J. Solid State Chem.* **117**, 229 (1995).
- [97] M. Hasegawa, T. Atou, J. V. Badding, *J. Solid State Chem.* **130**, 311 (1997).
- [98] L. J. Parker, M. Hasegawa, T. Atou, J. V. Badding, *Rev. High Pressure Sci. Technol.* **7**, 1049 (1998).
- [99] Y. M. Prots, R. Pöttgen, D. Niepmann, M. W. Wolff, W. Jeitschko, *J. Solid State Chem.* **142**, 400 (1999).
- [100] M. Prill, B. D. Mosel, W. Müller-Warmuth, J. Albering, Th. Ebel, W. Jeitschko, *Solid State Sci.* **4**, 695 (2002).
- [101] R. Boehler, *Materials Today*, Nov. 34 (2005).
- [102] G. E. Gregoryanz, C. Sanloup, M. Somayazulu, J. Badro, G. Fiquet, H. K. Mao, R. J. Hemley, *Nat. Mater.* **3**, 294 (2004).
- [103] S. Ono, T. Kikayawa, Y. Ohishi, *Solid State Commun.* **133**, 55 (2005).
- [104] M. Hasegawa, T. Yagi, *Solid State Commun.* **135**, 294 (2005).