



HAL
open science

Magnetic resonance spectroscopy of perpendicularly magnetized permalloy multilayer disks

G. de Loubens, V. V. Naletov, Michel Viret, Olivier Klein, Hervé Hurdequint, J. Ben Youssef, F. Boust, N. Vukadinovic

► **To cite this version:**

G. de Loubens, V. V. Naletov, Michel Viret, Olivier Klein, Hervé Hurdequint, et al.. Magnetic resonance spectroscopy of perpendicularly magnetized permalloy multilayer disks. *Journal of Applied Physics*, 2007, 101 (9), pp.09F514. 10.1063/1.2711699 . hal-00113175v3

HAL Id: hal-00113175

<https://hal.science/hal-00113175v3>

Submitted on 12 Dec 2006

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Magnetic resonance spectroscopy of perpendicularly magnetized permalloy multilayer disks

G. de Loubens, V. V. Naletov,* M. Viret, and O. Klein

Service de Physique de l'État Condensé,

CEA Orme des Merisiers, F-91191 Gif-Sur-Yvette

H. Hurdequint

Laboratoire de Physique des Solides,

Université Paris-Sud, F-91405 Orsay

J. Ben Youssef

Laboratoire de Magnétisme de Bretagne, 6 Av. Le Gorgeu, F-29285 Brest

F. Boust

ONERA, 29 avenue de la Division Leclerc, F-92322 Châtillon

N. Vukadinovic

Dassault Aviation, DGT/DTIAE, 78 quai Marcel Dassault, F-92552 Saint-Cloud

(Dated: December 13, 2006)

Abstract

Using a Magnetic Resonance Force Microscope, we compare the ferromagnetic resonance spectra of individual micron-size disks with identical diameter, $1 \mu\text{m}$, but different layer structures. For a disk composed of a single 43.3 nm thick permalloy (Py) layer, the lowest energy mode in the perpendicular configuration is the uniform precession. The higher energy modes are standing spin-waves confined along the diameter of the disk. For a Cu(30)/Py(100)/Cu(30) nm multilayer structure, it has been interpreted that the lowest energy mode becomes a precession localized at the Cu/Py interfaces. When the multilayer is changed to Py(100)/Cu(10)/Py(10) nm, this localized mode of the thick layer becomes coupled to the precession of the thin layer.

The dynamical properties of micron sized ferromagnetic structures provides new challenges and opportunities for novel magnetoelectronics devices¹. A recent focus is on the study of the exact nature of the normal modes in these small structures². Experimental works in the quasi-saturated^{3,4} and closure domain structures states^{5,6} have been recently reported. As for numerical simulations, the interplay between the short-distance exchange and long-range dipolar interactions makes calculations^{7,8} challenging. Moreover, the recently discovered spin diffusion mechanism^{9,10} makes the dynamical properties of such small structures still unsorted.

Ferromagnetic resonance (FMR) has been for a long time the basic tool to study the microwave susceptibility of magnetic samples¹¹. FMR uses a well-defined selection rule, where the excitation field preferentially couples to the most uniform mode in the sample. However, the limited sensitivity of standard FMR implies that it can only be performed on arrays of micron size disks, which statistically averages the spectra of many disks and makes it insensitive to individual differences. In this paper, using a mechanical-FMR we report on a study of *individual* micron size disks. It is shown that different multilayer structures yield different characteristics for the lowest energy mode.

To detect the FMR response of an individual microstructure, we exploit the high sensitivity of mechanical-FMR^{12,13}, a technique inspired by scanning probe techniques. As shown schematically in Fig. 1, the static part of the sample magnetization is coupled through the dipolar interaction to a magnetic sphere attached to the end of a very soft cantilever (spring constant 5 mN/m). Exciting the sample at a fixed frequency, the signal from the sample is detected by measuring the cantilever motion as a function of the perpendicular dc applied field, H_{ext} . A force on the cantilever, proportional to the variation of longitudinal magnetization (component along the precession axis), is associated with the resonance¹⁴. In the experiment reported here, the sphere is an alloy whose principle constituents are (80 wt%) Co and (10 wt%) Fe. It has a diameter of 4 μm and its magnetic moment is $(5 \pm 0.5)10^{-9}$ emu. The center of the sphere is positioned above the center of the disk (2.5 ± 0.1) μm away from the sample surface. In this geometry, the perturbation induced by the stray field of the sphere on the FMR spectrum solely corresponds to a perturbation shift of -300 Oe of the whole spectrum¹³. To enhance the sensitivity by the quality factor of the mechanical resonator ($Q = 4500$), we measure with a lock-in the response of the cantilever to a source (amplitude) modulation. The modulation frequency is then set at the resonance frequency

of the cantilever, which lies well below all the relaxation rates in the spin system.

The excitation antenna, which generates the microwave field, is a $50\ \Omega$ microstrip circuit shorted at its extremity, a design allowing studies in a broad frequency range. The microstrip is a Ti/Au(150 nm) line deposited on a sapphire substrate. The disks studied in the present work have all the same diameter, $1\ \mu\text{m}$. They are patterned by electron-beam lithography and ion-milling techniques out of different multilayer thin films and are positioned at a magnetic field anti-node of the microstrip.

Fig. 2 shows the 5.6 GHz mechanical-FMR spectrum of an individual $\phi = 1\ \mu\text{m}$ disk composed of a single $t = 43.3\ \text{nm}$ thick permalloy (Py) layer sandwiched by two insulating layers of Al_2O_3 (16 nm). The spectrum displayed on Fig. 2, as well as the ones of Fig. 3 and 4, has been recorded at a stabilized temperature $T = 280\ \text{K}$ and in the linear regime, where the peak amplitude remains proportional to the excitation power (*i.e.* precession angles limited to 1°). The most intense peak located at the highest field (lowest energy), $H_u \approx 10.5\ \text{kOe}$, is the uniform mode. Smaller amplitude modes at lower field (higher energy) correspond to standing spin-wave (or magnetostatic modes) with an increasing order m along the radial direction¹⁵. Note that the linewidth (31 Oe) of the peaks is among the smallest reported at this frequency for Py. Such a regular spectrum has been also measured by mechanical-FMR on an individual ferrite microdisk¹³. It has also been observed using a cavity-FMR technique by Kakazei *et al.*¹⁵ on an *array* of Py disks of same diameter and similar thickness. The position of the magnetostatic modes can be calculated analytically¹⁵. Using the physical parameters characterizing our Py film deduced from X-band cavity-FMR performed on the extended film¹⁷ from which the disk was patterned out, we find that we have to introduce a small misalignment (5°) with respect to the perpendicular direction to fit our data, without any other fitting parameter.

Fig.3 shows the 5.6 GHz mechanical-FMR spectrum obtained for a thicker Py layer ($t = 100\text{nm}$) sandwiched by two Cu layers of 30nm. There are several important differences with the previous spectrum:

- i-* The peaks of largest amplitude occur around $H_u \approx 9.8\ \text{kOe}$ (red square symbol). They should be associated to the largest volume of precession (uniform mode). Lower value of the resonance field H_u is consistent with our previous measurement, since H_u decreases with increasing thickness. This is the consequence of the decrease of the dipolar field as the aspect ratio (t/ϕ) increases. The expected shift, $\approx -800\ \text{Oe}$, is close to the experimental one. The

uniform mode is followed by small peaks at lower fields, whose amplitudes are consistent with their magnetostatic nature.

ii- While there is a single mode at the resonance field of the uniform precession in the single layer (Fig.2), the main mode (red square) is split into at least two narrow peaks of 39 Oe linewidth for the (Py/Cu) layers. Such an observed spectrum points to the presence of significant magnetic inhomogeneities in the film of this disk sample. We indicate that this (Py/Cu) layers have been deposited on the microstrip Au layer. As reported in ref¹⁸, a detailed study of the FMR spectrum of the control film (deposited on a Si substrate) has clearly revealed the presence of such inhomogeneities: gradient of magnetization along the thickness and roughness at the Cu/Py interfaces.

iii- The other striking feature is the appearance of a new mode at $H_l \approx 10.3$ kOe (green triangle) below the energy of the uniform mode. This new peak is interpreted¹⁸ as a precession localized at the top and bottom Cu/Py interface near the disk center, in the region of minimum internal field. Indeed, spins excited in the minima region lead to a mode lower in energy than the core precession because the gain in demagnetizing energy exceeds the cost in exchange energy¹⁹. This explanation is consistent with the absence of the localized mode in the spectrum of Fig.2.

A cartography of the transverse component, obtained with a micromagnetic code⁷ in which the magnetic properties of our Py have been used and where the two Cu layers have been neglected, is displayed using a color code for the first three main modes. The largest peak corresponds to the so-called “uniform” mode where all the spins precess in phase in the bulk of the sample. The mode at lower field (pink square) is the magnetostatic mode $m = 2$ identified in Fig.2 with a nodal circle in the disk (a locus where the magnetization stays still along the equilibrium axis) and a cylindrical regions precessing in opposition of phase with the core. The same visualization of the lowest energy mode shows a precession localized at the minima of the internal field.

Fig. 4 shows the 5.9 GHz mechanical-FMR spectrum for a double layer structure which consists of Py(100)/Cu(10)/Py(10) nm. It is directly deposited on the microstrip gold layer, and is capped by a 10 nm gold layer. This spectrum bears some strong resemblance with the one observed in Fig.3. This is expected since the main features should be dominated by the dynamics of the thick layer. In particular, we recognize the same group of large peaks at $H_u = 9.8$ kOe (red square), suggesting that this mode also corresponds to the uniform

precession of the thick layer. However, the largest peak is now the lowest energy mode at $H_l = 10.4$ kOe instead of the uniform mode, and a new group of peaks appears between those two modes. These two new features are likely related to the presence of the thin Py layer. Numerical simulations where the Cu spacer has been replaced by a vacuum layer have been performed on this structure. The simulated spectrum (not shown) gives the uniform mode of the thick layer as well as a higher field and higher amplitude mode. The latter corresponds to a localized precession of the thick layer coupled here through the dipolar interaction to the magnetization dynamics of the thin layer, shown in the inset of Fig. 4. One can understand that this mode may have a larger amplitude than the uniform precession since the top and bottom interfaces of the thick layer *and* the thin layer are now precessing at H_l . Physical process mediated by the normal metal layer, which are neglected in the simulation (e.g. spin diffusion), should enhance this coupling mechanism. We emphasize that the simulation does not explain the new group of peaks observed between the coupled localized and the uniform modes. However, this high field feature should be related to the dynamics inside the thin layer (probably coupled to the dynamics of the thick layer), where the internal field inhomogeneity and the quantization of the spin-wave modes can give rise to several localized modes²⁰.

In conclusion, we have shown that different types of multilayer patterned into the same microstructure yield different FMR spectra. Importantly, the nature of the lowest energy mode depends on the thickness of the Py layer. It shifts from the uniform mode to a localized mode at the surfaces as the thickness increases. The influence of a thinner layer separated by a normal metal spacer has also been measured. We emphasize that the multiplicity of peaks for the two thicker disks reported above have been attributed to extrinsic effects¹⁸ and does not alter the main conclusions of this work. For a finer interpretation of the reported spectra, such effects should be taken into account, as well as the intrinsic effects associated to the diffusion of the microwave magnetization⁹ inside the whole metallic layered structure.

We are greatly indebted to A.N. Slavin, X. Waintal, and A.-L. Adenot for their help and support. This research was partially supported by the ANR grant PNANO06-0235.

* Also at Physics Department, Kazan State University, Kazan 420008 Russia

¹ G. A. Prinz, J. Magn. Magn. Mater. **200**, 57 (1999).

- ² B. Hillebrands and K. E. Ounadjela, *Spin Dynamics in Confined Magnetic Structures*, vol. 2 (Springer, Berlin, 1996).
- ³ W. K. Hiebert et al., Phys. Rev. Lett. **79**, 1134 (1997).
- ⁴ M. Bailleul et al., Phys. Rev. B **73**, 104424 (2006).
- ⁵ K. Perzlmaier et al., Phys. Rev. Lett. **94**, 057202 (2005).
- ⁶ J. P. Park et al., Phys. Rev. B **67**, 020403(R) (2003).
- ⁷ F. Boust and N. Vukadinovic, Phys. Rev. B **70**, 172408 (2004).
- ⁸ R. D. McMichael and M. D. Stiles, J. Appl. Phys. **97**, 10J901 (pages 3) (2005).
- ⁹ H. Hurdequint, to be published in J. Magn. Magn. Mater. 2006.
- ¹⁰ Y. Tserkovnyak et al., Rev. Mod. Phys. **77**, 1375 (2005).
- ¹¹ P. E. Wigen, Thin Solid Films **114**, 135 (1984).
- ¹² Z. Zhang et al., Appl. Phys. Lett. **68**, 2005 (1996).
- ¹³ V. Charbois et al., Appl. Phys. Lett. **80**, 4795 (2002).
- ¹⁴ V. V. Naletov et al., Appl. Phys. Lett. **83**, 3132 (2003).
- ¹⁵ G. N. Kakazei et al., Appl. Phys. Lett. **85**, 443 (2004).
- ¹⁶ B. A. Kalinikos and A. N. Slavin, J. Phys. C **19**, 7013 (1986).
- ¹⁷ H. Hurdequint, J. Magn. Magn. Mater. **242-245**, 521 (2002).
- ¹⁸ G. de Loubens et al., cond-mat/0606245 (2006).
- ¹⁹ J. Jorzick et al., Phys. Rev. Lett. **88**, 47204 (2002).
- ²⁰ C. Bayer et al., Phys. Rev. B **72**, 064427 (2005).

Figures




FIG. 1: Schematic of the mechanical-FMR.




FIG. 2: Mechanical-FMR spectrum of a single $t = 43.3$ nm thick Py layer disk ($\phi = 1 \mu\text{m}$) at 5.6GHz. The lowest energy mode corresponds to the uniform precession. The experimental positions of the magnetostatic modes are shown as squares.




FIG. 3: Mechanical-FMR spectrum of a single $t = 100$ nm thick Py layer disk ($\phi = 1 \mu\text{m}$) at 5.6GHz. The lowest energy mode is interpreted as a mode localized at the surface of the disk, shown as a triangle. Squares denote the uniform and magnetostatic modes. The top shows the transverse dynamics of the main modes represented in a color code, calculated using a micromagnetic simulation.




FIG. 4: Mechanical-FMR spectrum of a double layer Py disk ($\phi = 1 \mu\text{m}$) with thicknesses of 10 nm and 100 nm at 5.9 GHz. The spacer is a 10 nm thick Cu layer. The lowest energy mode is associated to a coupled precession between the localized mode of the thick layer and the dynamics of the thin layer. The inset is a result of a micromagnetic simulation.