



Crystal structure of Li_{0.50}Co_{0.25}TiO(PO₄)

H. Belmal, Abdelaziz El Jazouli, Jean-Pierre Chaminade

► To cite this version:

H. Belmal, Abdelaziz El Jazouli, Jean-Pierre Chaminade. Crystal structure of Li_{0.50}Co_{0.25}TiO(PO₄). Phosphorous Research Bulletin, 2004, 15, pp.131-135. 10.3363/prb1992.15.0_131 . hal-00161627

HAL Id: hal-00161627

<https://hal.science/hal-00161627>

Submitted on 2 Feb 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Crystal Structure of $\text{Li}_{0.50}\text{Co}_{0.25}\text{TiO}(\text{PO}_4)$

H. BELMAL¹, A. EL JAZOULI^{1*} and J.P. CHAMINADE²

¹Laboratoire de Chimie des Matériaux Solides, Faculté des Sciences Ben M'Sik, UH2M, Boulevard Idriss El Harti, B.P. 7955 Casablanca, Maroc.

²Institut de Chimie de la Matière Condensée de Bordeaux, ICMCB CNRS, 87, Av. Dr. Schweitzer, 33608 Pessac, France.

*Corresponding author: a.eljazouli@univh2m.ac.ma

Abstract

$\text{Li}_{0.50}\text{Co}_{0.25}\text{TiO}(\text{PO}_4)$ has been obtained by the conventional solid state reaction technique. Its crystal structure has been refined from X-ray powder diffraction data by the Rietveld method in $P2_1/c$ space group ($R_B=0.08$, $R_F=0.05$, $R_p=0.13$ and $R_{wp}=0.18$). The monoclinic unit cell parameters are: $a_m=6.400\pm0.001\text{\AA}$, $b_m=7.279\pm0.001\text{\AA}$, $c_m=7.385\pm0.001\text{\AA}$, $\beta=90.36\pm0.02^\circ$, $Z=4$. The structure is formed by a three dimensional framework of TiO_6 octahedra and PO_4 tetrahedra. TiO_6 octahedra form - $\text{Ti}-\text{O}-\text{Ti}-\text{O}-$ infinite chains parallel to the c axis. In these chains, very short $\text{Ti}-\text{O}$ bonds ($\sim 1.68\text{\AA}$) and very long ones ($\sim 2.26\text{\AA}$) are alternating. The cobalt and lithium atoms occupy octahedral cavities which form infinite chains of edge-sharing octahedra running parallel to the a axis.

INTRODUCTION

Titanium oxyphosphates $M^1\text{TiO}(\text{PO}_4)$ ($M^1 = \text{Li}, \text{Na}, \text{K}, \text{Rb}, \text{Cs}, \text{Tl}$) have been extensively studied for their nonlinear optical and electrooptical properties^{1, 2, 3, 4, 5, 6, 7}. The substitution of a monovalent ion by a divalent one led us to a new series of titanium oxyphosphates. Recently we determined the structure of $\text{Ni}_{0.50}\text{TiO}(\text{PO}_4)^{8,9}$ and $\text{Li}_{0.5}\text{Ni}_{0.25}\text{TiO}(\text{PO}_4)^{10}$. The present paper reports on the determination of $\text{Li}_{0.50}\text{Co}_{0.25}\text{TiO}(\text{PO}_4)$ crystal structure from X-ray diffraction powder pattern.

EXPERIMENTAL

The powder of $\text{Li}_{0.50}\text{Co}_{0.25}\text{TiO}(\text{PO}_4)$ was obtained from stoichiometric mixture of Li_2CO_3 , CoO , TiO_2 and $(\text{NH}_4)_2\text{HPO}_4$ heated respectively at 300°C , 600°C , 800°C and 1000°C with intermediate regrindings. The final product is pink. Diffraction data were collected at room temperature on a Philips PW 3040 ($\theta-\theta$) diffractometer using a graphite monochromator [$\text{CuK}\alpha$ radiation (40 kV, 40 mA)], the experimental conditions are presented in table 1.

STRUCTURAL DETERMINATION

The structure of $\text{Li}_{0.50}\text{Co}_{0.25}\text{TiO}(\text{PO}_4)$ was refined by the Rietveld method using the Fullprof program¹¹. The initial atomic coordinates used for the refinement were those of the isostructural compound $\text{Li}_{0.50}\text{Ni}_{0.25}\text{TiO}(\text{PO}_4)$. After the refinement of 46 parameters (1 scale factor, 21 atomic parameters, 4 unit cell parameters, 1 zero shift error, 6 background parameters, 4 parameters of line profiles u , v , w and x ; 1 parameter of the Pseudo-Voigt function η : linear combination of the Gaussian and Lorentzian functions, 2 asymmetrical

parameters, 5 isotropic temperature factors and the microabsorption coefficient), the conventional reliability factors were: $R_B=0.08$, $R_F=0.05$, $R_p=0.13$, $R_{wp}=0.18$, $CR_p=0.17$, and $CR_{wp}=0.22$. The cell parameters are: $a_m=6.400\pm0.001\text{\AA}$, $b_m=7.279\pm0.001\text{\AA}$, $c_m=7.385\pm0.001\text{\AA}$, $\beta=90.36\pm0.02^\circ$, $Z=4$. The atomic positions and the principal interatomic distances are given in tables 2 and 3, respectively. Figure 1 shows good agreement between observed and calculated patterns.

Table 1: Structural data and X-ray Rietveld refinement parameters

Diffractometer	Philips PW 3040
Wavelength (\AA)	$\lambda K\alpha 1 = 1.54060 \text{\AA}$, $\lambda K\alpha 2 = 1.54442 \text{\AA}$
Step scan increment ($^{\circ}2\theta$)	0.02
2θ range ($^{\circ}$)	10-120
Zero point ($^{\circ}2\theta$)	-0.0331
Pseudo-voigt function	$PV = \eta L + (1-\eta)G$, $\eta = 0.49(2)$
Caglioti law parameters	$U=0.0326(7)$; $V=0.0027(1)$; $W=0.0030(3)$
No. of reflections	1023
No. of refined parameters	46
System; Space group	Monoclinic; $P2_1/c$
a (\AA); b (\AA); c (\AA); β ($^{\circ}$)	6.400; 7.279; 7.385; 90.36
Volume (\AA^3); Z	344.03; 4
R ; R_B ; R_p ; R_{wp} ; CR_p ; CR_{wp}	0.05; 0.08; 0.13; 0.18; 0.17; 0.22

Table 2: Atomic coordinates and isotropic temperature factors (\AA^2)

Atom	Site	Sym site	x	y	z	Biso(\AA^2)	Occupancy
L	2a	1	0.0000	0.0000	0.0000	0.49(2)	1.00
C	2b	1	0.5000	0.0000	0.0000	0.38(3)	0.50
T	4e	1	0.7580(9)	0.2205(7)	0.3339(8)	0.30(4)	1.00
P	4e	1	0.2512(6)	0.1270(10)	0.3743(12)	0.40(3)	1.00
O(1)	4e	1	0.7538(1)	0.1551(4)	0.1146(3)	0.29(2)	1.00
O(2)	4e	1	0.7362(12)	0.0028(10)	0.7968(9)	0.29(2)	1.00
O(3)	4e	1	0.2491(13)	0.4886(1)	0.0528(5)	0.29(2)	1.00
O(4)	4e	1	0.4514(10)	0.2487(5)	0.8696(2)	0.29(2)	1.00
O(5)	4e	1	0.9548(1)	0.7453(8)	0.1324(15)	0.29(2)	1.00

The structure of $\text{Li}_{0.50}\text{Co}_{0.25}\text{TiO}(\text{PO}_4)$ is similar to that of $\text{Li}_{0.50}\text{Ni}_{0.25}\text{TiO}(\text{PO}_4)^{10}$. It is formed by a three dimensional framework of TiO_6 octahedra and PO_4 tetrahedra. PO_4 groups are isolated each from other and connected to TiO_6 octahedra by corners. Each TiO_6 octahedron shares four corners of its basic plan with four PO_4 tetrahedra and the two other corners with two TiO_6 . TiO_6 octahedra form infinite chains $\text{Ti}-\text{O}-\text{Ti}-\text{O}$ parallel to the c axis (Figure 2). In these chains, a very short $\text{Ti}-\text{O}$ bonds (1.68\AA) and very long one (2.26\AA) are alternating. Lithium atoms fully occupy the site 2a, whereas cobalt atoms occupy statistically half of the site 2b. The cobalt and lithium octahedra form infinite chains of edge-sharing octahedra running parallel to the a axis (Figure 3). Each TiO_6 shares two adjacent faces with LiO_6 and CoO_6 .




Figure 1: Observed (circle), calculated (solid line) and difference X-ray profiles of $\text{Li}_{0.50}\text{Co}_{0.25}\text{TiO}(\text{PO}_4)$




Figure 2: Chain of TiO_6 octahedra running parallel to the c axis and linked by PO_4 tetrahedra

The average P-O distance (1.57 Å) is close to those generally observed for isostructural oxyphosphates. Angles O-P-O vary from 106.3 to 110.6°. The distances of the equatorial Ti-O bonds, implying oxygens of PO_4 groups [$\text{Ti}-\text{O}(\text{PO}_4)$] are fairly uniform with a mean of 1.94 Å. The distances Li-O and Co-O vary respectively from 2.11 to 2.25 Å and 2.07 to 2.14 Å. CoO_6 octahedra are isolated each from others ($d_{\text{Co-Co}} = 5.18 \text{ \AA}$).




Figure 3: Chains of LiO_6 and CoO_6 octahedra running parallel to the a axis

Table 3: Interatomic distances (\AA) and angles ($^\circ$) for $\text{Li}_{0.50}\text{Co}_{0.25}\text{TiO}(\text{PO}_4)$
X–O (X = Li, Co, Ti, P) distances are underlined. O–O distances are given below the diagonal and O–X–O angles are given above

LiO_6	O(1)	O(1')	O(2)	O(2)	O(5)	O(5)
O(1)	<u>2.11(1)</u>	180.0(1)	72.8(3)	107.2(1)	100.2(2)	79.7(3)
O(1')	4.23(2)	<u>2.11(1)</u>	107.2(1)	72.8(3)	79.7(3)	100.2(2)
O(2)	2.59(3)	3.51(2)	<u>2.25(2)</u>	180.0(1)	102.2(1)	77.7(3)
O(2)	3.51(2)	2.59(3)	4.50(1)	<u>2.25(2)</u>	77.7(3)	102.2(1)
O(5)	3.25(1)	2.71(2)	3.40(1)	2.74(2)	<u>2.11(1)</u>	180.0(1)
O(5)	2.71(2)	3.25(1)	2.74(2)	3.40(1)	4.23(1)	<u>2.11(1)</u>
CoO_6	O(1)	O(1')	O(2)	O(2)	O(4)	O(4)
O(1)	<u>2.14(2)</u>	180.0(1)	74.6(2)	105.3(3)	80.4(3)	99.5(1)
O(1')	4.29(1)	<u>2.14(2)</u>	105.3(3)	74.6(2)	99.5(1)	80.4(3)
O(2)	2.59(3)	3.40(1)	<u>2.13(3)</u>	180.0(1)	76.7(2)	103.2(3)
O(2)	3.40(1)	2.59(3)	4.27(1)	<u>2.13(3)</u>	103.2(3)	76.7(2)
O(4)	2.72(2)	3.22(1)	2.61(1)	3.30(2)	<u>2.07(1)</u>	180.0(1)
O(4)	3.22(1)	2.72(2)	3.30(2)	2.61(1)	4.14(1)	<u>2.07(1)</u>
TiO_6	O(1)	O(1')	O(2)	O(3)	O(4)	O(5)
O(1)	<u>1.68(2)</u>	172.6(3)	98.5(1)	99.9(2)	98.5(2)	99.5(1)
O(1')	3.94(1)	<u>2.26(1)</u>	74.1(2)	87.2(2)	79.4(3)	81.7(3)
O(2)	2.83(1)	2.59(3)	<u>2.03(3)</u>	160.6(4)	80.8(1)	89.3(3)
O(3)	2.73(2)	2.87(1)	3.86(3)	<u>1.88(1)</u>	90.8(2)	93.1(2)
O(4)	2.79(2)	2.72(2)	2.61(1)	2.76(2)	<u>1.99(1)</u>	160.5(3)
O(5)	2.71(1)	2.71(3)	2.74(2)	2.72(1)	3.80(1)	<u>1.86(2)</u>
PO_4	O(2)	O(3)	O(4)	O(5)		
O(2)	<u>1.58(1)</u>	110.6(3)	106.3(2)	110.3(2)		
O(3)	2.58(3)	<u>1.56(2)</u>	109.8(3)	108.0(1)		
O(4)	2.52(1)	2.56(2)	<u>1.56(3)</u>	111.5(2)		
O(5)	2.59(1)	2.54(1)	2.60(1)	<u>1.57(2)</u>		

REFERENCES

1. R. Masse and J. C. Grenier. *Bull. Soc. fran\c{c}. Mineral. Cristallogr.* 91, 437-439 (1971).
2. I. Tordjman, R. Masse and J. C. Guitel. *Z. Kristallogr.* 139, 103-115 (1974).
3. Nagornyi, P. G., Kapshuk, A. A., Stus', N. V., Slobodyanik, N. S., and Chernega, A. N., *Russ. J. Inorg. Chem.* 36, 1551-1552(1991).
4. K.W. Godfrey, P.A. Thomas and B.E. Watts. *Materials Science and Engineering. B* 9, 479-483 (1991).
5. A. Robertson, J.G. Fletcher, J. M.S. Skakle and A. R. West. *J. Solid State Chem.* 109, 53-59 (1994).
6. William T. A. Harrison, Thurman E. Gier, Galen D. Stucky and Arthur J. Schultz. *Mater. Res. Bull.* 30, (11), 1341-1349 (1995).
7. M. Kunz, R. Dinnebier, L. K. Cheng, E. M. McCarron, D. E. Cox, J. B. Parise, M. Gehrke, J. Calabrese, P. W. Stephens, T. Vogt and R. Papoula. *J. Solid State Chem.* 120, 299-310 (1995).
8. A. El Jazouli, S. Krimi, B. Manoun, J.P. Chaminade, P. Gravereau and D. de Waal, *Ann. Chim. Sc. Mat.* 23, 1-2 (1998).

- 9.** P. Gravereau, J. P. Chaminade, B. Manoun, S. Krimi and A. El Jazouli, *Powder Diff.* 14, (1), 10-15 (1999).
- 10.** B. Manoun, A. El Jazouli, P. Gravereau, J. P. Chaminade and F. Bourée “Determination and Rietveld refinement of the crystal structure of $\text{Li}_{0.50}\text{Ni}_{0.25}\text{TiO}(\text{PO}_4)$ from powder X-ray and neutron diffraction”, *Powder Diff.*, accepted (2002).
- 11.** J. Rodriguez-Carvajal. “Fullprof: A program for Rietveld refinement and pattern matching analysis”. In *Collected Abstract of Powder Diffraction Meeting*, Toulouse, France, 127, (1990).