



**HAL**  
open science

## **Oxidation modelling of a Si<sub>3</sub>N<sub>4</sub>-TiN ceramic: microstructure and kinetic laws**

Frédéric Deschaux-Beaume, Nicole Fréty, Thierry Cutard, Christophe Colin

### ► **To cite this version:**

Frédéric Deschaux-Beaume, Nicole Fréty, Thierry Cutard, Christophe Colin. Oxidation modelling of a Si<sub>3</sub>N<sub>4</sub>-TiN ceramic: microstructure and kinetic laws. *Ceramics International*, 2007, 33 (7), pp.1331-1339. <10.1016/j.ceramint.2006.04.016>. <hal-00170659>

**HAL Id: hal-00170659**

**<https://hal.science/hal-00170659v1>**

Submitted on 6 Nov 2019

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

# Oxidation modelling of a $\text{Si}_3\text{N}_4$ -TiN ceramic:

## Microstructure and kinetic laws

F. Deschaux-Beaume<sup>a</sup>, N. Fréty<sup>b,\*</sup>, T. Cutard<sup>c</sup>, C. Colin<sup>d</sup>

<sup>a</sup> Université de Montpellier II, LMGC, 34095 Montpellier Cedex 5, France

<sup>b</sup> Université de Montpellier II, LPMC, 34095 Montpellier Cedex 5, France

<sup>c</sup> Ecole des Mines d'Albi-Carmaux, CROMeP, Campus Jarlard, 81013 Albi Cedex 9, France

<sup>d</sup> Ecole Nationale Supérieure des Mines de Paris, Centre des Matériaux P.M. Fourt, 91003 Evry Cedex, France

---

### Abstract

The oxidation of a silicon nitride–titanium nitride ceramic has been studied. Based on microstructural observations, a phenomenological oxidation model is described, and an oxidation kinetic model has been proposed. For temperatures  $<1000$  °C, only the TiN phase is oxidised. The oxidation process is then controlled by oxygen diffusion through  $\text{TiO}_2$ , described by a parabolic oxidation kinetic law. The process is more complex above 1000 °C, because of the simultaneous oxidation of both  $\text{Si}_3\text{N}_4$  and TiN phases. Three oxidation modes, controlled by distinct diffusion mechanisms, take place successively. In a first step,  $\text{Si}_3\text{N}_4$  and TiN phases are independently oxidised, respectively into  $\text{SiO}_2$  and  $\text{TiO}_2$  phases.  $\text{Si}_3\text{N}_4$  oxidation is controlled by oxygen diffusion through  $\text{SiO}_2$ , while TiN oxidation is controlled by titanium diffusion through  $\text{TiO}_2$ . In a second step, the TiN oxidation is controlled by oxygen diffusion through  $\text{TiO}_2$  and through  $\text{SiO}_2$  formed by  $\text{Si}_3\text{N}_4$  oxidation. In the third step, oxidation of the TiN and  $\text{Si}_3\text{N}_4$  phases is controlled by oxygen diffusion through the silica layer. Kinetic laws have been proposed for each of these three oxidation modes.

*Keywords:* B. Microstructure-final; C. Diffusion; D. Nitrides; E. Structural applications

---

### 1. Introduction

Silicon nitride based ceramics are good candidates for high-temperature structural applications. With their low-density, low thermal expansion coefficient, high hardness, high-corrosion resistance and high-mechanical resistance, these materials are more appropriate than metals for such applications. However, the development of engineering ceramic components is impeded by the high cost of fine ceramic parts. Electroconductive ceramics, such as silicon nitride–titanium nitride composites ( $\text{Si}_3\text{N}_4$ -TiN), are of particular interest because they combine the high performance of  $\text{Si}_3\text{N}_4$ -based ceramics with machinability by electro-discharge machining (EDM) [1–3]. In this way, the manufacture cost of ceramic components with complex shapes is limited to the hard metallic material one.

However, the main disadvantage of  $\text{Si}_3\text{N}_4$ -TiN ceramics is the oxidation behaviour at high temperatures, which is strongly influenced by the addition of a titanium nitride phase. The oxidation mechanisms of both TiN and  $\text{Si}_3\text{N}_4$  ceramics have been widely studied and described [4,5]. The oxidation of titanium nitride to rutile ( $\text{TiO}_2$ ) starts between 500 and 600 °C. It is observed that the oxidation is controlled via oxygen diffusion through  $\text{TiO}_2$  especially at temperatures  $<1000$  °C [4,6–8]. At higher temperatures, the rate-controlling mechanism is not clearly identified but a cationic diffusion of titanium may be supposed with the outward growth of rutile crystals and the observed porosity under the rutile layer [9,10]. The oxidation of silicon nitride ceramics is also complex [11–17]. Oxidation of pure silicon nitride leads to the formation of a  $\text{SiO}_2$  amorphous layer on the surface, separated from the core material by a thin layer of a graded sub-oxide ( $\text{SiN}_x\text{O}_y$ ) [18–20] or a crystalline oxynitride ( $\text{Si}_2\text{N}_2\text{O}$ ) [11–17]. Oxidation is then controlled by the diffusion of oxygen through the  $\text{SiO}_2$  and oxynitride layers. Sintered silicon nitride generally oxidises more quickly than pure silicon nitride [21–25]. This is related to

---

\* Corresponding author. Tel.: +33 4 67 14 33 88; fax: +33 4 67 14 42 90.  
E-mail address: nfrety@lpmc.univ-montp2.fr (N. Fréty).

the presence of an intergranular phase originating from sintering additives ( $Y_2O_3$  and  $Al_2O_3$ ). Some species (Y, Al and O) are more mobile in this phase than in  $Si_3N_4$  at high temperature. Oxidation is then the result of the inward diffusion of oxygen through the oxide layer and the outward diffusion of yttrium and aluminium species through the intergranular phase. Oxidation kinetic, therefore, depends on the composition and amount of the intergranular phase [23].

The oxidation behaviour of  $Si_3N_4$ -TiN ceramics is equally complex because the various mechanisms previously presented may act simultaneously. Some studies have been already carried out, but oxidation mechanisms are not yet well understood above  $1000\text{ }^\circ\text{C}$  [6,26–28]. The aim of the present work is to contribute to the study of the oxidation of  $Si_3N_4$ -TiN ceramics, a particular attention being paid to the  $1000$ – $1200\text{ }^\circ\text{C}$  range. Based on microstructural observations, a phenomenological oxidation modelling is presented as well as the associated kinetic laws.

## 2. Experimental procedure

The studied material is a commercial ceramic (KERSIT 601, Norton Desmarquest, FR), prepared by sintering from a mixture of  $Si_3N_4$  and TiN powders in equivalent ponderal proportions. A few percent of high purity  $Y_2O_3$  and  $Al_2O_3$  powders is added to the initial mixture. The size distribution and the proportion of TiN particles (50 wt.%, i.e. 30 vol.%) have been chosen to confer to the material a sufficient electrical conductivity for electro-discharge machining, without significant decrease of mechanical characteristics [2]. In this way, the ceramic microstructure consists of a continuous TiN network, surrounded by a  $Si_3N_4$  based matrix, containing a fine SiYAION intergranular phase (Fig. 1).

Parallelepipedic samples ( $10\text{ mm} \times 4\text{ mm} \times 2\text{ mm}$ ) were machined using electro-discharge machining, then polished with diamond pastes down to the  $1\text{ }\mu\text{m}$  grade. Samples were oxidised at  $1150\text{ }^\circ\text{C}$  in air for 1–200 h. The microstructure of the sound and oxidised materials was characterised by scanning




Fig. 1. Microstructure of the silicon nitride–titanium nitride ceramic.

electron microscopy (SEM) (Zeiss, DSM982 Gemini). Complementary analyses were performed by energy dispersive spectrometry (EDS) (Noran, Voyager IV) and wavelength-dispersive spectrometry (WDS) (Cameca Instruments, SX 50).

## 3. Phenomenological oxidation modelling

### 3.1. Microstructural investigations

Microstructural observations were investigated on the TiN- $Si_3N_4$  material, which was oxidised at  $1150\text{ }^\circ\text{C}$  in air for a duration of 1–200 h. For oxidation duration of 100 h, a  $50\text{ }\mu\text{m}$  thick oxidised area is observed on the polished cross section in which large microstructural modifications have taken place (Fig. 2). The morphology of this oxidised area is similar to that observed by Bellosi et al. [6] and by Gogotsi et al. [26,28] on similar materials. Three layers are distinguishable in this area from the surface to the non-




Fig. 2. SEM image and schematic representation of the  $Si_3N_4$ -TiN ceramic surface after oxidation of 100 h at  $1150\text{ }^\circ\text{C}$ .

oxidised material core. The first layer (layer 1) is composed primarily of large crystals, which were identified as a  $\text{TiO}_2$  phase, according to the WDS analysis. The second layer (layer 2) is composed of isolated  $\text{TiO}_2$  crystals and a continuous glassy phase. This phase, the composition of which being close to the stoichiometric  $\text{SiO}_2$ , results from the  $\text{Si}_3\text{N}_4$  oxidation. Small grains, which are aluminium- and/or yttrium-rich phases are observed in this second layer. This indicates the diffusion of aluminium toward the surface as previously observed in the case of the oxidation of  $\text{Si}_3\text{N}_4$  ceramics with an intergranular glassy phase. Large pores with diameters of 2–20  $\mu\text{m}$  are also observed. The third layer (layer 3) exhibits a more complex microstructure consisting of several phases ( $\text{SiO}_2$ ,  $\text{TiO}_2$ ,  $\text{Si}_3\text{N}_4$ ,  $\text{TiN}$ ) and porosity.


The evolution of the morphology of the oxidised surface was studied according to the oxidation duration [29]. The diffusion of titanium toward the surface occurs very rapidly at 1150 °C, as is shown by the continuous  $\text{TiO}_2$  surface layer and the sub-layer porosity, already formed after 1 h of oxidation. The growth of the surface layer (layer 1) is rapid at the beginning of oxidation. It then slows down to reach a thickness of 5–10  $\mu\text{m}$  after 10 h, which remains constant. For oxidation times >50 h, the  $\text{TiO}_2$  surface layer contains numerous cracks. After about 100 h of oxidation, a continuous layer of  $\text{SiO}_2$  containing large cavities starts forming under and around the surface  $\text{TiO}_2$  crystals.

### 3.2. Oxidation phenomenological modelling


According to the microstructural investigations, and literature data concerning oxidation controlling mechanisms in  $\text{Si}_3\text{N}_4$  and  $\text{TiN}$  materials, a phenomenological model has been developed to describe the oxidation of the studied  $\text{Si}_3\text{N}_4$ – $\text{TiN}$  ceramic, in the 1000–1200 °C temperature range. The proposed model consists in three steps, where the oxidation of both  $\text{TiN}$  and  $\text{Si}_3\text{N}_4$  phases is controlled by one or several diffusion mechanisms (Fig. 2):

#### (i) First step.

In the first step, the oxidation of the  $\text{TiN}$  phase involves the formation of a rutile ( $\text{TiO}_2$ ) layer at the outer surface of the  $\text{TiN}$  particles, according to the reaction (1):



It is generally admitted that  $\text{TiN}$  oxidation is controlled by the diffusion of oxygen through  $\text{TiO}_2$  [16,27]. However the diffusion of Ti can be faster above 1000 °C or within monocrystalline  $\text{TiO}_2$  [16,30]. During this step, the  $\text{TiN}$  oxidation is controlled by the diffusion of Ti through  $\text{TiO}_2$ , leading to the growth of the surface rutile crystals. This outward diffusion creates vacancies in the  $\text{TiN}$  network, which can coalesce to form closed porosity. The  $\text{Si}_3\text{N}_4$  oxidation in mainly vitreous silica ( $\text{SiO}_2$ ) takes place at the same time, and is controlled by oxygen diffusion through  $\text{SiO}_2$  (2):



However, this mechanism is slower than  $\text{TiN}$  oxidation one. The porosity created in the outer  $\text{TiN}$  particles reduces the surface available for Ti diffusion and leads to a slowdown of the titanium diffusion towards the free surface. On the other hand, oxygen can cross this closed porosity in a molecular form.

#### (ii) Second step.

In the second step, oxygen diffuses faster than titanium through the surface  $\text{TiO}_2$  crystals and oxidises inner  $\text{TiN}$  particles. The transformation of  $\text{Si}_3\text{N}_4$  into  $\text{SiO}_2$ , controlled by the same mechanism than in the first step, leads to a great molar volume increase (+96%). The stresses induced by this volume change may be relaxed by creep of  $\text{SiO}_2$  in the sub-layer porosity [31]. This vitreous phase flows into the porosity resulting from the titanium diffusion, and progressively fills in the sub-layer, forming a continuous layer. The diffusion of oxygen through  $\text{SiO}_2$  being slower than through  $\text{TiO}_2$ , the progressive filling of the porosity with  $\text{SiO}_2$  leads to a decrease of the diffusion rate of oxygen towards inner  $\text{TiN}$  phase.

#### (iii) Third step.

In the third step, for longer oxidation duration, the oxidation process is controlled by a single mechanism, which is the diffusion of oxygen through a dense  $\text{SiO}_2$  layer. The  $\text{SiO}_2$  phase forms a continuous layer below the large surface  $\text{TiO}_2$  crystals. Oxygen then diffuses through this layer to oxidise both  $\text{Si}_3\text{N}_4$  and  $\text{TiN}$  phases. The third step is then a stationary oxidation mode, reached after two transient modes.

## 4. Oxidation kinetic laws

### 4.1. Simplifying assumptions

In order to obtain relatively simple kinetic laws, some simplifying assumptions have to be done. First, diffusion is considered to be unidirectional through each material phase, from the surface to the bulk or inversely. Secondly, it is assumed that the  $\text{TiN}$  particles distribution is homogeneous in the sound material. That involves proportions of  $\text{TiN}$  and  $\text{Si}_3\text{N}_4$  phases are constant on each section of the sound material parallel to the surface.

### 4.2. Oxidation kinetic laws below 1000 °C

Silicon nitride oxidation is very slow at temperatures <1000 °C [16]. Up to this temperature, only the  $\text{TiN}$  phase in the material is significantly oxidised in rutile ( $\text{TiO}_2$ ), and the total mass gain measured,  $\Delta m$ , corresponds to the mass gain of the  $\text{TiN}$  phase,  $\Delta m_{\text{TiN}}$  (3):

$$\frac{\Delta m}{S} = \frac{\Delta m_{\text{TiN}}}{S} = \frac{\Delta m_{\text{TiN}}}{S_{\text{TiN}}} \frac{S_{\text{TiN}}}{S} \quad (3)$$

where  $S$  is the total outer surface of the sample, and  $S_{\text{TiN}}$  is the outer surface of the  $\text{TiN}$  phase.




Fig. 3. Oxidation mechanism of the  $\text{Si}_3\text{N}_4\text{-TiN}$  material for temperature  $<1000\text{ }^\circ\text{C}$ .

It is generally admitted that oxidation of Ti and TiN is controlled by oxygen diffusion, which is faster than Ti diffusion in polycrystalline  $\text{TiO}_2$  below  $900\text{ }^\circ\text{C}$  (Fig. 3) [4,7–10,30,32]. Fig. 4 shows the morphology of the surface of the material oxidised for 100 h at  $800\text{ }^\circ\text{C}$ , in which the TiN surface grains are replaced by  $\text{TiO}_2$  ones. Up to  $900\text{ }^\circ\text{C}$ , the isothermal oxidation kinetic is then given by a parabolic law (4):

$$\frac{\Delta m}{S} = \frac{S_{\text{TiN}}}{S} k_{\text{Po/TiO}_2}^{1/2} t^{1/2} + \frac{\Delta m_{0\text{TiN}}}{S} \quad (4)$$

where  $k_{\text{Po/TiO}_2}$  is the parabolic rate constant corresponding to TiN oxidation below  $900\text{ }^\circ\text{C}$  (controlled by O diffusion through  $\text{TiO}_2$ ),  $t$  is the oxidation time, and  $\Delta m_{0\text{TiN}}$  is the mass gain at the beginning of the parabolic oxidation mode.

A transition takes place between  $900$  and  $1000\text{ }^\circ\text{C}$ , due to two phenomena: the beginning of oxidation of the  $\text{Si}_3\text{N}_4$  phase, and the change in mechanism controlling oxidation of the TiN phase in the ceramic. Below  $900\text{ }^\circ\text{C}$ , this mechanism is oxygen diffusion through  $\text{TiO}_2$ , whereas above  $1000\text{ }^\circ\text{C}$ , it is titanium diffusion, as showed by the continuous  $\text{TiO}_2$  layer formed in the ceramic surface (Fig. 5) and the porosity in the sub-layer (Fig. 2). This mechanism change is due to the higher activation energy of titanium diffusion through  $\text{TiO}_2$  or to the growth of

$\text{TiO}_2$  crystals in the ceramic surface, which reduces the number of grain boundaries, and then the short circuit diffusion paths for oxygen. Indeed, it is admitted that oxygen diffusion is faster than titanium diffusion in polycrystalline  $\text{TiO}_2$ , due to grain boundary diffusion paths, whereas the diffusion mechanism is different for monocrystalline  $\text{TiO}_2$  [4,30].

#### 4.3. Oxidation kinetic laws between $1000$ and $1200\text{ }^\circ\text{C}$

Oxidation mechanisms are more complex above  $1000\text{ }^\circ\text{C}$ , because of the simultaneous oxidation of both TiN and  $\text{Si}_3\text{N}_4$  phases as previously described and represented on Fig. 6. The total mass gain per unit area can then be expressed as a function of TiN and  $\text{Si}_3\text{N}_4$  mass gains according to the relation (5):

$$\frac{\Delta m}{S} = \frac{\Delta m_{\text{TiN}} + \Delta m_{\text{Si}_3\text{N}_4}}{S} \quad (5)$$

where  $\Delta m$ ,  $\Delta m_{\text{TiN}}$  and  $\Delta m_{\text{Si}_3\text{N}_4}$ , are respectively, the mass gains of the material, the TiN phase and the  $\text{Si}_3\text{N}_4$  phase, and  $S$  is the outer surface of the sample.

##### (i) Oxidation kinetic law of $\text{Si}_3\text{N}_4$ .

The oxidation of silicon nitride phase is controlled by oxygen diffusion through silica. The incremental mass gain for this phase, resulting from an isothermal oxidation of duration  $dt$  can be expressed according to relation (6):

$$d\left(\frac{\Delta m_{\text{Si}_3\text{N}_4}}{S}\right) = \frac{1}{2} k_{\text{Po/SiO}_2}^{1/2} \frac{S_{\text{Si}_3\text{N}_4}}{S} t^{-1/2} dt \quad (6)$$

where  $k_{\text{Po/SiO}_2}$  is the parabolic rate constant corresponding to the  $\text{Si}_3\text{N}_4$  oxidation, and  $S_{\text{Si}_3\text{N}_4}$  is the outer surface of the silicon nitride phase.

##### (ii) Oxidation kinetic law of TiN.

The oxidation of TiN phase is more complex, and kinetic depends on the oxidation stage.

During the first stage (first transient oxidation mode) above  $1000\text{ }^\circ\text{C}$ , the rate of titanium diffusion through  $\text{TiO}_2$  overlapping the surface of TiN network is greater than the oxygen




Fig. 4. Microstructure of the  $\text{Si}_3\text{N}_4\text{-TiN}$  material surface (a) sound material and (b) material after oxidation at  $800\text{ }^\circ\text{C}$  during 100 h.




Fig. 5. Microstructure of the  $\text{Si}_3\text{N}_4\text{-TiN}$  material surface after oxidation at  $1150\text{ }^\circ\text{C}$  during 100 h.

diffusion one. The TiN oxidation kinetic is thus controlled by the diffusion of titanium towards the free surface, characterised by the parabolic rate constant  $k_{\text{pTi/TiO}_2}$ , and the available surface  $S_{\text{Ti/TiO}_2}$  (surface between  $\text{TiO}_2$  and inner TiN particles). The incremental mass gain for oxidation of TiN phase during  $dt$  is then given by relation (7a):

$$d\left(\frac{\Delta m_{\text{TiN}}}{S}\right) = \frac{1}{2} k_{\text{pTi/TiO}_2}^{1/2} \frac{S_{\text{Ti/TiO}_2}}{S} t^{-1/2} dt \quad (7a)$$

The titanium diffusion towards the free surface creates porosity within the TiN network, close to the  $\text{TiN/TiO}_2$  interface, which leads to a decrease of the surface  $S_{\text{Ti/TiO}_2}$ , and of the average diffusion rate of titanium, expressed by the  $(k_{\text{pTi/TiO}_2}^{1/2} S_{\text{Ti/TiO}_2}/S)$  term.

In a first approximation, the variation of the diffusion surface during  $dt$ ,  $dS_{\text{Ti/TiO}_2}$ , is proportional to  $S_{\text{Ti/TiO}_2}$  and to the quantity of formed  $\text{TiO}_2$ . This quantity can be expressed by the average thickness variation of the  $\text{TiO}_2$  layer,  $dx$  [33]:

$$-dS_{\text{Ti/TiO}_2} = C_1 S_{\text{Ti/TiO}_2} dx \quad (8)$$

where  $C_1$  is a constant.

Integrating relation (8), the following expression is obtained:

$$S_{\text{Ti/TiO}_2} = C_2 \exp(-C_1 x) \quad (9)$$

where  $C_2$  is a constant.

The growth of the  $\text{TiO}_2$  surface layer being controlled by the titanium diffusion through  $\text{TiO}_2$  during the first mode, the  $x$  variation at the time  $t$  can be written according to relation (10):

$$\frac{dx}{dt} = \frac{1}{2} k^{1/2} \frac{S_{\text{Ti/TiO}_2}}{S} t^{-1/2} \quad (10)$$

where  $k$  is deduced from the parabolic rate constant  $k_{\text{pTi/TiO}_2}$  (11):

$$k = k_{\text{pTi/TiO}_2} \left( \frac{1 + M_{\text{Ti}}/2M_{\text{O}}}{1 - M_{\text{N}}/2M_{\text{O}}} \right) \frac{1}{\rho_{\text{TiO}_2}^2} \quad (11)$$

with  $\rho_{\text{TiO}_2}$  the  $\text{TiO}_2$  density, and  $M_{\text{Ti}}$ ,  $M_{\text{O}}$  and  $M_{\text{N}}$  the molar masses of Ti, O and N. Replacing  $S_{\text{Ti/TiO}_2}$  by expression (9) in Eq. (10), the following relations are obtained:

$$x = \frac{1}{C_1} \ln(at^{1/2} + 1) \quad (\text{with the assumption } x = 0 \text{ at } t = 0) \quad (12)$$

and

$$S_{\text{Ti/TiO}_2} = C_2 \left( \frac{1}{at^{1/2} + 1} \right) \quad (13)$$

with  $a = k^{1/2} C_1 C_2 / S$ , constant at a fixed temperature, and  $C_2 = S_{\text{TiN}}$  (initial outer surface of the TiN phase). The  $S_{\text{TiN}}/S$  ratio is equal to the volume proportion of the TiN phase in the material. This quantity was determined by image analysis, and is equal to 0.3 (and  $S_{\text{Si}_3\text{N}_4}/S = 0.7$ ).

The first transient mode acts while the titanium diffusion towards the free surface is faster than the oxygen diffusion towards the inner TiN particles. Oxygen diffuses through the formed porosity in a molecular form, and its rate diffusion is not significantly changed with the  $S_{\text{Ti/TiO}_2}$  evolution if it is assumed that oxygen diffusion in porosity is faster than in  $\text{TiO}_2$ .

During the second stage (second transient oxidation mode), TiN oxidation is controlled by the diffusion of oxygen towards inner TiN particles.  $\text{Si}_3\text{N}_4$  oxidation in mainly  $\text{SiO}_2$  takes place with an important molar volume increase. Silica gradually fills




Fig. 6. The three steps of the oxidation model for temperature  $>1000\text{ }^\circ\text{C}$ .




Fig. 7. Evolution of oxidation mechanisms during the second oxidation mode.

the porous sub-layer. The TiN oxidation kinetic is controlled, during this mode, by two simultaneous mechanisms (Fig. 7): the diffusion of oxygen through TiO<sub>2</sub>, characterised by the rate constant  $k_{\text{Po/TiO}_2}$  (mechanism 1), and the diffusion of oxygen through silica (which is slower than through TiO<sub>2</sub>), characterised by the rate constant  $k_{\text{Po/SiO}_2}$  (mechanism 2). The incremental mass gain during  $dt$  is given by the following Eq. (7b):

$$d\left(\frac{\Delta m_{\text{TiN}}}{S}\right) = \frac{1}{2} \left( k_{\text{Po/TiO}_2}^{1/2} \frac{S_{\text{O/TiO}_2}}{S} + k_{\text{Po/SiO}_2}^{1/2} \frac{S_{\text{SiO}_2/\text{TiO}_2}}{S} \right) t^{-1/2} dt \quad (7b)$$

where  $S_{\text{O/TiO}_2}$  and  $S_{\text{SiO}_2/\text{TiO}_2}$  are the available surfaces for oxygen diffusion towards inner TiN particles related to each mechanism.

The transition time,  $t_1$ , between the first and second transient modes then corresponds to the equality:

$$k_{\text{Po/TiO}_2}^{1/2} S_{\text{Ti/TiO}_2}(t_1) = k_{\text{Po/TiO}_2}^{1/2} S_{\text{O/TiO}_2}(t_1) + k_{\text{Po/SiO}_2}^{1/2} S_{\text{SiO}_2/\text{TiO}_2}(t_1) \quad (14)$$

During oxidation above 1000 °C, the  $S_{\text{SiO}_2/\text{TiO}_2}$  contact surface between SiO<sub>2</sub> and inner TiO<sub>2</sub> phases increases up to  $S_{\text{TiN}}$ , while the  $S_{\text{O/TiO}_2}$  contact surface between oxygen from outer porosity and inner TiO<sub>2</sub> phase decreases down to zero (Fig. 7), with respect to the equality (15):

$$S_{\text{SiO}_2/\text{TiO}_2} + S_{\text{O/TiO}_2} = S_{\text{TiN}} \quad (15)$$

Assuming that SiO<sub>2</sub> creeps rapidly at the considered temperature (instantaneous stress relaxation), the variation of surface overlapped by SiO<sub>2</sub> during  $dt$ ,  $dS_{\text{SiO}_2}$  (with  $S_{\text{SiO}_2} = S_{\text{SiO}_2/\text{TiO}_2} + S_{\text{Si}_3\text{N}_4}$ , see Fig. 7), is proportional to the quantity of oxygen having replaced nitrogen in the Si<sub>3</sub>N<sub>4</sub> phase to form silica [18,19,29], i.e. to the variation of the quantity of formed silica:

$$dS_{\text{SiO}_2} = A_1 S_{\text{Si}_3\text{N}_4} dy \quad (16)$$

where  $A_1$  is a constant and  $dy$  is the thickness variation of the SiO<sub>2</sub> layer during  $dt$ .

The quantity of formed SiO<sub>2</sub> is diffusion controlled, so in an early approximation,  $S_{\text{SiO}_2}$  is given by relation (17):

$$S_{\text{SiO}_2} = S_{\text{Si}_3\text{N}_4} (1 + bt^{1/2}) \quad \text{while} \quad S_{\text{SiO}_2} \leq S \quad (17)$$

with

$$b = \frac{A_1 k_{\text{Po/SiO}_2}^{1/2}}{\rho_{\text{SiO}_2}} \left( \frac{1 + M_{\text{Si}}/2M_{\text{O}}}{1 - 2M_{\text{N}}/3M_{\text{O}}} \right), \quad (18)$$

constant at a fixed temperature

and

$$\frac{S_{\text{O/TiO}_2}}{S} = 1 - \frac{S_{\text{SiO}_2}}{S} \quad (19)$$

In the third stage (stationary mode), when the whole sub-layer is filled with SiO<sub>2</sub> ( $S_{\text{SiO}_2} = S$ ), TiN oxidation is controlled by oxygen diffusion through SiO<sub>2</sub>, and the incremental mass gain of the TiN phase is expressed according to the relation (7c):

$$d\left(\frac{\Delta m_{\text{TiN}}}{S}\right) = \frac{1}{2} k_{\text{Po/SiO}_2}^{1/2} \frac{S_{\text{TiN}}}{S} t^{-1/2} dt \quad (7c)$$

The oxidation behaviour of the silicon nitride–titanium nitride composite for temperatures >1000 °C is then described by the following kinetic laws for each mode of the oxidation mechanism:

- if  $0 \leq t \leq t_1$  (first mode), where  $t_1$  is obtained according to the Eq. (14):

$$\frac{\Delta m}{S} = \frac{0.3}{a} k_{\text{Po/TiO}_2}^{1/2} \ln(at^{1/2} + 1) + 0.7 k_{\text{Po/SiO}_2}^{1/2} t^{1/2} + \frac{\Delta m_0}{S} \quad (20a)$$

$$\frac{\Delta m}{S} = (0.3 k_{\text{Po/TiO}_2}^{1/2} + 0.7 k_{\text{Po/SiO}_2}^{1/2}) t^{1/2} + \frac{0.7}{2} (k_{\text{Po/SiO}_2}^{1/2} - k_{\text{Po/TiO}_2}^{1/2}) bt + \frac{\Delta m'_0}{S} \quad (20b)$$

- if  $t_1 \leq t \leq t_2$  (second mode), with  $S_{\text{SiO}_2}(t_2) = S$
- if  $t \geq t_2$  (third mode)

$$\frac{\Delta m}{S} = k_{\text{Po/SiO}_2}^{1/2} t^{1/2} + \frac{\Delta m''_0}{S} \quad (20c)$$

where  $\Delta m_0$ ,  $\Delta m'_0$  and  $\Delta m''_0$  are constants.

## 5. Discussion

### 5.1. Evolution of kinetic parameters of TiN phase oxidation, at a fixed temperature

Oxidation rate of  $\text{Si}_3\text{N}_4$  phase is controlled by a single parameter (Eq. (6)), whereas the rate controlling parameter for TiN phase oxidation changes with the oxidation mode (Eqs. (7a)–(7c)). Fig. 8 presents a typical evolution of the kinetic parameters characterising the TiN phase oxidation at a fixed temperature, during the two first oxidation modes. The parabolic rate constants, and other kinetic constants were chosen according to bibliographical data, with respect to the condition  $k_{\text{PTi/TiO}_2} > k_{\text{PO/TiO}_2} \gg k_{\text{PO/SiO}_2}$  [4,6,30,34].

Two competitive mechanisms are responsible for the TiN oxidation: Titanium diffusion through  $\text{TiO}_2$  towards the surface, controlled by a first kinetic parameter (Eq. (7a)), and oxygen diffusion through  $\text{TiO}_2$  and/or  $\text{SiO}_2$  towards inner TiN particles, controlled by a second kinetic parameter (Eq. (7b)). The oxidation is controlled by the faster mechanism, i.e. the mechanism having the greater kinetic parameter. At the first oxidation stage, the kinetic parameter corresponding to titanium diffusion is higher than the oxygen diffusion one, then oxidation is controlled by titanium diffusion. The first kinetic parameter decreases with oxidation time, due to the porosity formation. In the same time, the second kinetic parameter, controlling oxygen diffusion, decreases too, due to the formation of  $\text{SiO}_2$ , which creeps into porosity. But the decrease of the second parameter being slower than the first one, the gap between the two parameters is progressively reduced. When the kinetic parameter corresponding to the oxygen diffusion is equal to the titanium diffusion one, after an oxidation time  $t_1$  (Eq. (14)), the oxidation process becomes controlled by oxygen diffusion. This new stage corresponds to the second oxidation mode. During this stage, the two kinetic parameters have the same value, the decrease of the Ti diffusion parameter being controlled by the decrease rate of the




Fig. 8. Variation of oxidation kinetic parameters of the TiN phase with time ( $k_{\text{PTi/TiO}_2} = 5.10^{-4} \text{ mg}^2 \text{ s}^{-1}$ ,  $k_{\text{PO/TiO}_2} = 10^{-4} \text{ mg}^2 \text{ s}^{-1}$ ,  $k_{\text{PO/SiO}_2} = 10^{-6} \text{ mg}^2 \text{ s}^{-1}$ ,  $a = 0.025$  and  $b = 0.0015$ ).

oxygen diffusion parameter. This parameter keeps decreasing throughout the second mode, with the growth and creep of  $\text{SiO}_2$  phase into porosity. It finally stabilises after a time  $t_2$ , when  $\text{SiO}_2$  overlaps the whole sub-layer, and its value remains constant during the third mode.

### 5.2. Temperature dependence of the mode time limits

The three oxidation modes are divided by time limits ( $t_1$  and  $t_2$ ), depending on temperature. The evolution trend of these limits was studied, for temperature variation in the 1000–1200 °C range.

The variation of mode time limits is due to the fact that parabolic rate constants depend on temperature. Those constants correspond to each elementary diffusional mechanism involved in the oxidation process:

$$k_{\text{PTi/TiO}_2} = k_{01} \exp\left(-\frac{E_{a1}}{RT}\right) \quad (21a)$$

$$k_{\text{PO/TiO}_2} = k_{02} \exp\left(-\frac{E_{a2}}{RT}\right) \quad (21b)$$

$$k_{\text{PO/SiO}_2} = k_{03} \exp\left(-\frac{E_{a3}}{RT}\right) \quad (21c)$$

where  $E_{a_i}$  are the activation energies of each diffusional mechanism, and  $k_{0_i}$  are direct ratio constants.

In order to evaluate the effect of the temperature variation on the mode time limits, characteristic parameters of these equations have been chosen, according to literature data [4,6,16,34]. The evolution of the parabolic rate constants with temperature, for the chosen parameters, is reported in Fig. 9. In agreement with the oxidation model, the parabolic constant for titanium diffusion is higher than the oxygen diffusion one in  $\text{TiO}_2$ , which is higher than the oxygen diffusion one in  $\text{SiO}_2$ , in the whole considered temperature range (1000–1200 °C). The values of the constants  $k_{\text{PTi/TiO}_2}$  and  $k_{\text{PO/TiO}_2}$  are of about the same magnitude order, whereas  $k_{\text{PO/SiO}_2}$  is very lower, especially in the lowest temperature range. When temperature increases, the gap




Fig. 9. Evolution of parabolic rate constants of the three diffusional mechanisms vs. temperature.




Fig. 10. Evolution of the time limits,  $t_1$  and  $t_2$ , of the two transient modes vs. temperature.

between  $k_{\text{P}_{\text{Ti}/\text{TiO}_2}}$  and  $k_{\text{P}_{\text{O}/\text{TiO}_2}}$  increases slightly, whereas the gap between  $k_{\text{P}_{\text{O}/\text{SiO}_2}}$  and other parabolic constants decreases rapidly.

The time  $t_1$ , separating the first and second transient modes, is obtained solving Eq. (14), which expresses the equality between the two kinetic parameters of Fig. 8. The solution is a very complex linear combination of  $k_{\text{P}_{\text{Ti}/\text{TiO}_2}}$ ,  $k_{\text{P}_{\text{O}/\text{TiO}_2}}$  and  $k_{\text{P}_{\text{O}/\text{SiO}_2}}$ , so its variation with temperature depends on the three activation energies  $E_{a_1}$ ,  $E_{a_2}$  and  $E_{a_3}$ . The  $t_1$  evolution is represented in Fig. 10. For the lowest temperature range, a weak variation of  $t_1$  is observed. But for higher temperature,  $t_1$  decreases rapidly when the temperature increases.

This complex evolution may be explained considering Eq. (14) and Fig. 8. When the temperature increases, the gap between the diffusion rates of titanium and oxygen in  $\text{TiO}_2$  also increases ( $E_{a_1} > E_{a_2}$ ), so the gap between the kinetic parameters of the two competitive mechanisms is greater at the beginning of oxidation (Fig. 8). The temperature increase also leads to the activation of the  $\text{SiO}_2$  formation, which reduces the oxygen diffusion rate towards inner TiN particles, so it accelerates the decrease of the second kinetic parameter. These first effects tend to increase the transitory time  $t_1$ . But the temperature increase reduces also the gap between oxygen diffusion rate through  $\text{TiO}_2$  and  $\text{SiO}_2$  ( $E_{a_3} > E_{a_2}$ ), and then limits the decrease of the second kinetic parameter. On another way, the decrease of the first parameter is accelerated. Then, these second effects tend to decrease the transitory time  $t_1$ . The  $t_1$  evolution with temperature (Fig. 10) may then be explained considering these two opposite effects: at the lower temperatures, the two effects are compensated each other, so  $t_1$  variation is low and at higher temperature, the second effect becomes predominant, and  $t_1$  decreases rapidly.

The third oxidation mode begins when a sufficient quantity of silica is formed to cover the whole outer surface of the material ( $S_{\text{SiO}_2} = S$  in Eq. (17)). Then time  $t_2$  is controlled only by oxygen diffusion rate through silica, and is expressed by the relation:

$$t_2 = A_2 \exp\left(\frac{E_{a_3}}{RT}\right) \quad (22)$$

where  $A_2$  is a constant.

## 6. Conclusion

The oxidation behaviour of silicon nitride–titanium nitride is studied in this paper, specially in the 1000–1200 °C temperature range. Based on microstructural investigations, an oxidation model has been proposed. This oxidation model consists of three successive modes. First  $\text{Si}_3\text{N}_4$  and TiN phases are independently oxidised, respectively into  $\text{SiO}_2$  and  $\text{TiO}_2$  phases.  $\text{Si}_3\text{N}_4$  oxidation is controlled by oxygen diffusion through  $\text{SiO}_2$ , while TiN oxidation is controlled by titanium diffusion through  $\text{TiO}_2$ . The titanium depletion involves the creation of porosity between TiN and  $\text{TiO}_2$ , which reduces the oxidation rate of the TiN phase. Secondly, when titanium diffusion rate is too low, oxygen diffuses towards inner TiN particles. The TiN oxidation is then controlled by oxygen diffusion through  $\text{TiO}_2$  and through  $\text{SiO}_2$  formed by  $\text{Si}_3\text{N}_4$  oxidation, which progressively fills porosity of the material sub-layer. Thirdly, when  $\text{SiO}_2$  forms an amorphous continuous layer under the  $\text{TiO}_2$  surface layer, oxidation of the TiN and  $\text{Si}_3\text{N}_4$  phases is controlled by oxygen diffusion through this silica layer.

Kinetic laws have been proposed for each of these three oxidation modes. Both phases forming a continuous network, oxidation kinetics of each phase may be considered independently.  $\text{Si}_3\text{N}_4$  oxidation is controlled, during the whole process, by oxygen diffusion through silica, the oxidation kinetic law being then parabolic. TiN oxidation is the result of two opposite diffusional mechanisms: titanium diffusion through  $\text{TiO}_2$  towards the surface, and oxygen diffusion through  $\text{TiO}_2$  and/or  $\text{SiO}_2$  towards inner TiN particles. During the first mode, kinetic parameters of the first mechanism is higher than the ones of the second mechanism, and TiN oxidation is controlled by titanium diffusion. Both kinetic parameters decrease during the two first modes, but the decrease rate of the second one is slower than the first one. When both parameters are equal, TiN oxidation becomes controlled by oxygen diffusion (second mode). The kinetic parameter controlling this mechanism decreases again, until  $\text{SiO}_2$  overlaps the whole sub-layer, and oxidation kinetic of TiN becomes parabolic (third mode). The time limits of these modes are temperature dependent, and have been expressed according to the activation energy of the different diffusional mechanisms taking place during oxidation process.

## References

- [1] M. Higuchi, M. Miyake, H. Kakeuchi, E. Kamjo, Electrically conductive sintered compact of  $\text{Si}_3\text{N}_4$  machinable by electrical discharge machinable and process of producing the same, US Patent 4 659 508, 1987.
- [2] C. Martin, P. Mathieu, B. Cales, Electrical discharge machinable ceramic composites, in: R.J. Brook (Ed.), Proceedings of Symposium on Ceramic Materials Research, E-MRS Spring Conference, Strasbourg (France), 1988.
- [3] A. Bellosi, S. Guicciardi, A. Tampieri, Development and characterization of electroconductive  $\text{Si}_3\text{N}_4$ -TiN composites, J. Eur. Ceram. Soc. 9 (1992) 83–93.
- [4] J. Desmaison, P. Lefort, M. Billy, Oxidation mechanism of titanium nitride in oxygen, Oxid. Met. 13 (6) (1979) 505–517.
- [5] M. Billy, Reactivity in nitrogen ceramics, in: Proceedings of the Science of Ceramics 14th International Conference, Stoke-on-Trent (UK), The Institute of Ceramics, 1987, pp. 45–60.

- [6] A. Bellosi, A. Tampieri, Y.Z. Liu, Oxidation behaviour of electroconductive  $\text{Si}_3\text{N}_4$ -TiN composites, *Mater. Sci. Eng. A127* (1990) 115–122.
- [7] A. Tampieri, E. Landi, A. Bellosi, The oxidation behaviour of monolithic TiN ceramic, *Br. Ceram. Trans. J.* 90 (1991) 194–196.
- [8] H. Ichimura, A. Kawana, High-temperature oxidation of ion-implanted TiN and TiAlN films, *J. Mater. Res.* 8–5 (1993) 1093–1100.
- [9] P. Lefort, J. Desmaison, M. Billy, Oxydation du nitruire de titane par l'oxygène: comportement du nitruire  $\text{TiN}_{0.95}$  pulvérulent, *C. R. Acad. Sci., C285 3* (1977) 361–369.
- [10] P. Lefort, J. Desmaison, M. Billy, Cinétique d'oxydation du nitruire de titane: comportement de plaquettes de nitruire  $\text{TiN}_{0.91}$  en atmosphère d'oxygène, *J. Less-Common Met.* 60 (1978) 11–24.
- [11] D.J. Choi, D.B. Fischbach, W.D. Scott, Oxidation of chemically-vapor deposited silicon nitride and single-crystal silicon, *J. Am. Ceram. Soc.* 72 (7) (1989) 1118–1123.
- [12] H. Du, R.E. Tressler, K.E. Spear, C.G. Pantano, Oxidation studies of crystalline CVD silicon nitride, *J. Electrochem. Soc.* 136 (5) (1989) 1527–1536.
- [13] H. Du, R.E. Tressler, K.E. Spear, Thermodynamics of the Si–N–O system and kinetic modeling of oxidation of  $\text{Si}_3\text{N}_4$ , *J. Electrochem. Soc.* 136 (11) (1989) 3210–3215.
- [14] H. Du, R.E. Tressler, K.E. Spear, M. Wang, Annealing studies of coupled  $\text{Si}_3\text{N}_4$  and  $\text{SiO}_2$  films, *J. Mater. Sci. Lett.* 8 (1989) 1341–1343.
- [15] L.U.J.T. Ogbuji, J.M. Smialek, Evidence from transmission electron microscopy for an oxinitride layer in oxidised  $\text{Si}_3\text{N}_4$ , *J. Electrochem. Soc.* 138 (10) (1991) L51–L53.
- [16] D.P. Butt, D. Albert, T.N. Taylor, Kinetics of thermal oxidation of silicon nitride powders, *J. Am. Ceram. Soc.* 79-11 (1996) 2809–2814.
- [17] K.L. Luthra, A mixed interface reaction/diffusion control model for oxidation of  $\text{Si}_3\text{N}_4$ , *J. Electrochem. Soc.* 138 (10) (1991) 3001–3007.
- [18] L.U.J.T. Ogbuji, S.R. Bryan, The  $\text{SiO}_2$ - $\text{Si}_3\text{N}_4$  interface, part I: nature of the interface, *J. Am. Ceram. Soc.* 78-5 (1995) 1272–1278.
- [19] L.U.J.T. Ogbuji, The  $\text{SiO}_2$ - $\text{Si}_3\text{N}_4$  interface, part II:  $\text{O}_2$  permeation and oxidation reaction, *J. Am. Ceram. Soc.* 78-5 (1995) 1279–1284.
- [20] B.W. Sheldon, Silicon nitride oxidation based on oxinitride interlayers with graded stoichiometry, *J. Am. Ceram. Soc.* 79 (11) (1996) 2993–2996.
- [21] M.H. Lewis, P. Barnard, Oxidation mechanism in Si–Al–O–N ceramics, *J. Mater. Sci.* 15 (1980) 443–448.
- [22] L. Wang, C. He, J.G. Wu, Oxidation of sintered silicon nitride materials, in: *Proceedings of the third International Symposium on Ceramic Materials and Components for Engines*, Las Vegas, American Ceramic Society, 1988, pp. 604–611.
- [23] D.R. Clarke, F.F. Lange, Oxidation of  $\text{Si}_3\text{N}_4$  alloys: relation to phase equilibria in the system  $\text{Si}_3\text{N}_4$ - $\text{SiO}_2$ -MgO, *J. Am. Ceram. Soc.* 63 (9-10) (1980) 586–593.
- [24] C.O. Meara, J. Sjoberg, Transmission electron microscopy investigation of the oxidation of hot isostatically pressed silicon nitride with and without sintering aids, *J. Am. Ceram. Soc.* 80 (6) (1997) 1491–1500.
- [25] G. Ziegler, J. Heinrich, G. Wötting, Review: relationships between processing, microstructure and properties of dense and reaction-bonded silicon nitride, *J. Mater. Sci.* 22 (1987) 3041–3086.
- [26] Y.G. Gogotsi, F. Porz, The oxidation of particulate-reinforced  $\text{Si}_3\text{N}_4$ -TiN composites, *Corros. Sci.* 33 (4) (1992) 627–640.
- [27] F. Peni, J. Crampon, R. Duclos, On the morphology and composition of the oxidized layer in  $\text{Si}_3\text{N}_4$ -based materials, *Mater. Sci. Eng. A163* (1993) 5–7.
- [28] Y.G. Gogotsi, F. Porz, G. Dransfield, Oxidation behavior of monolithic TiN and TiN dispersed in ceramic matrices, *Oxid. Met.* 39 (1/2) (1993) 69–91.
- [29] F. Deschaux-Beaume, T. Cutard, N. Fréty, C. Levailant, Oxidation of a  $\text{Si}_3\text{N}_4$ -TiN composite: microstructural investigation and modeling, *J. Am. Ceram. Soc.* 85 (7) (2002) 1860–1866.
- [30] P. Kofstad, *High temperature corrosion*, Elsevier Applied Science Publishers LTD, 1988, pp. 289–298.
- [31] G. Grathwohl, F. Thümmler, Creep of reaction-bonded silicon nitride, *J. Mater. Sci.* 13 (6) (1978) 1177–1186.
- [32] Y.G. Gogotsi, F. Porz, V.P. Yaroshenko, Mechanical properties and oxidation behavior of  $\text{Al}_2\text{O}_3$ -AlN-TiN composites, *J. Am. Ceram. Soc.* 75 (8) (1992) 2251–2259.
- [33] U.R. Evans, *The Corrosion and Oxidation of Metals*, Edward Arnold Publishers LTD, London, 1960, pp. 836–837.
- [34] J. Persson, M. Nygren, The oxidation kinetics of  $\beta$ -Sialon ceramics, *J. Eur. Ceram. Soc.* 13 (1994) 467–484.