HAL
open science

Probing the internal structure of magnetic nanocomposites – thermo-sensitive gels and lamellar films – respectively by small angle neutron scattering and neutron reflectivity

Siham Douadi-Masrouki, Bruno Frka-Petesic, Delphine El Kharrat, Olivier Sandre, Maud Save, Bernadette Charleux, Valérie Cabuil

To cite this version:

Siham Douadi-Masrouki, Bruno Frka-Petesic, Delphine El Kharrat, Olivier Sandre, Maud Save, et al.. Probing the internal structure of magnetic nanocomposites – thermo-sensitive gels and lamellar films – respectively by small angle neutron scattering and neutron reflectivity. The 5th International Symposium on Bioscience and Nanotechnology, Dec 2007, Kawagoe, Japan. hal-00196454

HAL Id: hal-00196454

https://hal.science/hal-00196454v1

Submitted on 30 Jun 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Probing the internal structure of magnetic nanocomposites – thermo-sensitive gels and lamellar films – respectively by small angle neutron scattering and neutron reflectivity

Siham Douadi-Masrouki[1], Delphine El kharrat[1], Olivier Sandre[1], Maud Save[2], Bernadette Charleux[2] and Valérie Cabuil[1]

[1]LI2C UMR7612, [2]LCP UMR76120, Centre National de la Recherche Scientifique / Université Pierre et Marie Curie - 4 place Jussieu case 51 75252 Paris Cedex 5 France

Magnetic nanoparticles (NPs) as building blocks

1) Synthesis



$Fe_3O_4 + Fe(NO_3)_3 \longrightarrow \gamma\text{-}Fe_2O_3$ (maghemite)

R. Massart *IEEE Trans. Magn.* 1981



We study nanocomposites consisting of the same iron oxide γ-Fe_2O_3 nanoparticles embedded in polymer matrices:

I) a **gel matrix** exhibiting a swelling transition triggered by temperature;

II) a **lamellar matrix** based on the self-assembly of a symmetrical diblock copolymer.

We use both neutron scattering & reflectivy techniques to probe the local structure at the mesoscopic scale.

Superparamagnetic behavior

Magnetization normalized by its saturation value follows Langevin's law $M_s = m_s\Phi$







I) Thermosensitive PNIPAM gels doped with magnetic NPs



STRUCTURAL STUDY BY SMALL ANGLE NEUTRON SCATTERING (SANS)

S1S Particles (d=6nm) + PTEA(11k)-b-PAM(30k) copolymers embedded in a 2% cross-linked PNIPAM gel vs. Temperature



Double Hydrophilic Diblock Copolymers



Molecular weights

Rhodia Inc.	PE	1 000 - 10 000 g/mol
	Neutral	10 000 - 60 000 g/mol

DHBC – particles solutions

DYNAMIC LIGHT SCATTERING



60 nm < D_H < 80 nm

STATIC LIGHT SCATTERING



J-F. Berret, O. Sandre, D. El kharrat, JACS 2006

CLUSTERS MORPHOLOGY BY TEM

- Dense clusters of nanoparticles with various sizes and shapes.
- Difference between hydrodynamic size (DLS) and core size (TEM) ascribed to neutral polymer shell protecting the clusters against aggregation.



STRUCTURAL STUDY BY SMALL ANGLE NEUTRON SCATTERING (SANS)

S1S Particles (d=6nm) + PTEA(5k)-b-PAM(30k) and PTEA(11k)-b-PAM(30k) copolymers



II) Evidencing the lamellar structure of copolymer films doped or not with magnetic NPs

By Atomic Force Microscopy



Nanoscope III (Digital Instrument),Tapping mode



$P(nBMA)_{425}$-b-PS_{490} Film deposited on silicon

e = 60.3 +/- 2.8 nm

(ellipsometric thickness)

$P(nBMA)_{405}$-b-PS_{460} Film deposited on silicon

e = 78.8 +/- 3.6 nm



Pico SPM LE (Molecular Imaging) Images by E. Lepleux (Scientec, Palaiseau, France)



poly(n-butylmethacrylate)-b-poly(styrene)

- Atom Transfer Radical Polymerization (ATRP)
- High molecular weight : Mn = 112 000 g/mol
- Low polydispersity: Ip ≈ 1.4
- Symmetrical Dibloc Copolymer: x=425 ≈ y=490

Preparation of thin lamellar film samples:

Solutions of P(nBMA)-b-PS in toluene are "spin-coated" on smooth substrates (mica or silicone). After deposition, films are annealed at 150°C under vacuum for at least 48h. Their thickness is measured by ellipsometry.



- Tapping mode AFM enables to image 2 types of defects at the surface of the films - **"islands" and "holes"** – typical of the lamellar order.
- The lamellar period should be measured from the height difference L_2-L_1 but the AFM tip is too large to reach the second bilayer.
- The lamellar period is 28 nm for an analogous PS-b-P(nBMA) of Mw=82,000 as measured by X-rays reflectivity. [2]





Macroscopic view→



PS-grated NP's



TEM + RuO_4 coloration



By Neutron Reflectivity

Neutron wavelengths : 0.5 - 25 Å

1-layer



EROS spectrometer LLB, CEA-Saclay, 2007



Multi-layers → interferences (over-oscillations)





Bi-layer thickness ≈ 39 nm for the pure $P(nBMA)_{425}$-b-PS_{490}] copolymer

Film	Layer number and thickness (nm)				Total thickness (nm)		rough-ness
Φ_{NPs}	L_1	L_2	L_3	$L_{average}$	RN	Ellipsometry	
0.05%	32.2	48.0	21.5	37.2	111.7	108.1	1.4
0.10%	32.8	48.0	33.3	38.0	114.0	109.4	3.5
0.15%	32.8	48.7	30.0	37.2	111.5	106.6	0.4

[$P(nBMA)_{425}$-b-PS_{490}]=20 g/L doped with γ-Fe_2O_3@PS1 at increasing volume fractions Φ_{NPs}

⇨ The insertion of increasing amount of magnetic nanoparticles leaves both the total thickness and the average period unchanged.

⇨ The nanoparticles are confined inside internal inter-penetrated layers.

⇨ The total thickness of the film and its roughness are proportional to the deposited materials amount.

C g/L	γ-Fe_2O_3@PS	Layer number and thickness (nm)						Total thickness	
		L_1	L_2	L_3	L_4	L_5	L_{moy}	nm	roughness
20	γ-Fe_2O_3@PS3	31.2	45.3	41.5	-	-	39.3	117.9	±1.6
30	γ-Fe_2O_3@PS1	34.0	46.1	49.0	54.5	-	45.9	183.6	±4.9
40	γ-Fe_2O_3@PS1	47.3	45.9	47.0	44.4	45.7	46.1	230.3	±17.4

Films doped at constant volume fraction Φ_{NPs} = 0.025 vol% and increasing deposited materials amount

Bibliography:

- [1] G. Coulon, B. Collin, D. Chatenay, Y. Gallot, "Kinetics of islands and holes on the free surface of thin diblock copolymer films", *J. Phys.* II France **3** (1993) 697
- [2] G. Vignaud, A. Gibaud, G. Grübel, S. Joly, D. Ausserré, J-F. Legrand, Y. Gallot, "Ordering of diblock PS-PBMA thin films: An X-ray reflectivity study" *Physica* B **248** (1998) 250
- [3] B. Toperverg, V. Lauter-Pasyuk, H. Lauter, O. Nokonov, D. Ausséré, Y. Gallot, "Morphology of off-specular neutron scattering pattern from islands on a lamellar film", Physica B **283** (2000) 60