



HAL
open science

Generalized model of resonant polymer-coated microcantilevers in viscous liquid media

Russel Cox, Fabien Josse, Michael Wenzel, Stephen Heinrich, Isabelle Dufour

► **To cite this version:**

Russel Cox, Fabien Josse, Michael Wenzel, Stephen Heinrich, Isabelle Dufour. Generalized model of resonant polymer-coated microcantilevers in viscous liquid media. *Analytical Chemistry*, 2008, 80, pp.5760-5767. hal-00293888

HAL Id: hal-00293888

<https://hal.science/hal-00293888>

Submitted on 15 Nov 2014

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

A Generalized Model of Resonant Polymer-Coated Microcantilevers in Viscous Liquid Media

Russell Cox, Fabien Josse, Michael J. Wenzel, Stephen M. Heinrich¹, Isabelle Dufour²*

Microsensor Research Laboratory and Department of Electrical and Computer Engineering, Marquette
University, Milwaukee, WI, USA

¹Department of Civil and Environmental Engineering, Marquette University, Milwaukee, WI, USA

² Université Bordeaux 1, CNRS, IMS Laboratory, Talence, France

fabien.josse@marquette.edu

*Author to whom all correspondence should be sent

Abstract

Expressions describing the resonant frequency and quality factor of a dynamically-driven, polymer-coated microcantilever in a viscous liquid medium have been obtained. These generalized formulas are used to describe the effects the operational medium and the viscoelastic coating have on the device sensitivity when used in liquid-phase chemical sensing applications. Shifts in the resonant frequency are normally assumed proportional to the mass of sorbed analyte in the sensing layer. However, the expression for the frequency shift derived in this work indicates that the frequency shift is also dependent on changes in the sensing layer's loss and storage moduli, changes in the moment of inertia, as well as changes in the medium of operation's viscosity and density. Not accounting for these factors will lead to incorrect analyte concentration predictions. The derived expressions are shown to reduce to well-known formulas found in the literature for the case of an uncoated cantilever in a viscous liquid medium and the case of a coated cantilever in air or in a vacuum. The theoretical results presented are then compared to available chemical sensor data in aqueous and viscous solutions.

KEYWORDS: Resonant Microcantilever, Viscoelasticity, Viscous Damping, Liquid-phase sensing, Quality Factor

INTRODUCTION

Polymer-coated microcantilevers have been extensively investigated for use as chemical sensor platforms.¹⁻⁴ Microcantilevers have shown high sensitivities in chemical vapor detection. In particular, polymer-coated cantilevers are often utilized in the dynamic (resonant) mode for detection in gas.^{2, 5-9} Several investigators have analyzed such devices by considering only the mass loading effect of the chemical analyte without consideration of the coating viscoelastic effects.^{3-4, 10} Others have explicitly included the effects of the coating properties,² while assuming operation in a vacuum. In this work, the effects of both the medium and the coating will be taken into account.

Application of microcantilevers to liquid-phase detection has mostly focused on static-mode detection because dynamically-driven microcantilevers suffer from low frequency stability in viscous liquid media.¹¹ The characteristics of uncoated dynamically-driven microcantilevers have previously been investigated in viscous liquid media accounting for the properties of the liquid media, including density and viscosity.¹² Recently, work has been done on characterizing the behavior of polymer-coated microcantilevers in a vacuum, which indicated significant chemically induced coating plasticization effects.¹ However, the effects of the polymer coating in a viscous liquid environment have not been studied, which includes plasticization and the properties of the viscous liquid. The present derivation extends previous work on uncoated and coated microcantilevers to obtain generalized formulas for the characteristics of a polymer-coated microcantilever operating in a viscous liquid medium.

THEORETICAL ANALYSIS

Generalized Equation of Motion: Figure 1 shows the length, L , width, b , and thickness, h_1 , of the microcantilever as well as the polymer layer's thickness, h_2 . The deflection function, $w(x,t)$, which represents the vertical displacement along the length of the beam as a function of time is also indicated.

Assuming that the microcantilever is a rectangular beam with $L \gg (h_1 + h_2)$ undergoing small transverse displacements, the equation of motion for a polymer-coated microcantilever operating in a vacuum is given by

$$(EI)^* \frac{\partial^4 w(x,t)}{\partial x^4} + \frac{m}{L} \frac{\partial^2 w(x,t)}{\partial t^2} = F(x)e^{j\omega t}, \quad (1)$$

where $(EI)^*$ is the beam's complex flexural rigidity, m is the microcantilever and the polymer layer's overall mass, and $F(x)$ is the position-dependent forcing function per unit length operating at an angular frequency of ω .¹ Since the polymer coating is usually viscoelastic, the flexural rigidity is complex and can be calculated by

$$(EI)^* = \left(\sqrt{(EI)'^2 + (EI)''^2} \right) e^{j\theta} \quad (2)$$

with

$$(EI)' = \left(E_1 I_1 + E_2' I_2 \right), \quad (3)$$

and

$$(EI)'' = \left(E_2'' I_2 \right). \quad (4)$$

E_1 is the Young's modulus of the microcantilever base layer, which is assumed to be purely elastic, E_2' and E_2'' are the storage modulus and loss modulus of the polymer layer, respectively, and I_1 and I_2 are the moments of inertia of the microcantilever base and polymer layer, respectively. For a system with a polymer layer, the moment of inertia can be approximated assuming a time-invariant neutral axis, found by using the Cauchy principal value theorem on the position of the time-variant neutral axis location.¹

The parameter θ in eq. (2) is the composite loss angle of the beam and is defined as

$$\theta = \tan^{-1} \left(\frac{h_2 E_2''}{h_1 E_1 + h_2 E_2'} \right). \quad (5)$$

Although not shown explicitly in eqs. (2)-(5), it is noted that the complex modulus of the coating depends on the operating frequency.

When operating in a viscous liquid medium, the medium exerts a force (per unit length) on the microcantilever, $F_{fluid}(x,t)$, and the equation of motion is

$$(EI) \frac{\partial^4 w(x,t)}{\partial x^4} + m/L \frac{\partial^2 w(x,t)}{\partial t^2} = F(x)e^{j\omega t} + F_{fluid}(x,t) \quad (6)$$

The $F_{fluid}(x,t)$ has been defined as¹²

$$F_{fluid}(x) = -g_1 \frac{\partial w(x,t)}{\partial t} - g_2 \frac{\partial^2 w(x,t)}{\partial t^2} \quad (7)$$

where g_1 represents the viscous damping caused by fluid shear and g_2 represents the displaced mass of the fluid per unit length.¹⁰ g_1 and g_2 are defined as¹³

$$g_1 = \frac{\pi}{4} \rho_L b^2 \Gamma_i(Re)\omega, \quad (8)$$

and

$$g_2 = \frac{\pi}{4} \rho_L b^2 \Gamma_r(Re), \quad (9)$$

respectively. Here, ρ_L is the density of the medium and $\Gamma_r(Re)$ and $\Gamma_i(Re)$ are the real and imaginary parts of the hydrodynamic function, $\Gamma(Re)$, of the microcantilever, given by

$$\Gamma(Re) = \Omega(Re)\Gamma_{circ}(Re) = \Omega(Re) \left(1 + \frac{4jK_1(-j\sqrt{jRe})}{\sqrt{jRe}K_0(-j\sqrt{jRe})} \right). \quad (10)$$

In eq. (10), $\Omega(Re)$ is the function used to correct the hydrodynamic function of a beam of circular cross section, $\Gamma_{circ}(Re)$, to that of a long, thin rectangular beam for which $(h_1+h_2) \ll b$ and $b \ll L$.¹² K_0 and K_1 are modified Bessel functions of the third kind. The hydrodynamic function is dependent on the Reynolds number,¹⁰ which is a measure of the ratio of inertial forces to the viscous forces acting on the beam, and is defined as

$$Re = \frac{\rho_L \omega b^2}{4\eta_L}, \quad (11)$$

where η_L is the viscosity of the fluid.

Assuming a sinusoidal deflection function, eq. (6) can be converted to fit the form of eq. (1), resulting in an equation of motion,

$$(EI)^* \frac{\partial^4 w(x,t)}{\partial x^4} + m_B^* \frac{\partial^2 w(x,t)}{\partial t^2} = F(x)e^{j\omega t}, \quad (12)$$

where m_B^* is the complex effective mass per unit length given by

$$m_B^* = \sqrt{\left(\frac{m}{L} + g_2\right)^2 + \left(\frac{g_1}{\omega}\right)^2} e^{j\phi}, \quad (13)$$

where

$$\phi = -\tan^{-1}\left(\frac{g_1/\omega}{m/L + g_2}\right). \quad (14)$$

Generalized Resonant Frequency: The deflection of the coated-microcantilever is composed of an infinite number of harmonic flexural modes. The resonant frequency for the i th mode of a coated-microcantilever in a viscous liquid medium can be found using the generalized equation of motion, eq. (12). It is commonly assumed that the Young's modulus of the base layer is frequency-independent. For the polymer layer, the Young's modulus depends on the frequency. However, a first approximation is to use the polymer properties at the resonant frequency and neglect their variation in the vicinity of the resonant peak. Assuming a frequency-dependent hydrodynamic function, the resonant frequency obtained by solving eq. (12) is given by

$$f_{res,i} = \frac{\alpha_i^2}{2\pi} \sqrt{\frac{k}{M}} \quad (15)$$

where α_i is the i th root of

$$\cos(\alpha_i) \cosh(\alpha_i) - 1 = 0, \quad (16)$$

$$k = \frac{(EI)' - \left(\left(\frac{g_1}{\omega} \right) + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} \left(\frac{g_1}{\omega} \right) \right)}{\left(\frac{m}{L} + g_2 + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} (g_2) \right)} (EI)''}{L^3}, \quad (17)$$

$$M = (m + Lg_2) + \frac{\left(\left(\frac{g_1}{\omega} \right) + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} \left(\frac{g_1}{\omega} \right) \right)}{\left(\frac{m}{L} + g_2 + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} (g_2) \right)} \left(\frac{g_1}{\omega} \right) L, \quad (18)$$

$$\frac{d}{d\omega} \left(\frac{g_1}{\omega} \right) = \frac{\pi}{4} \rho_L b^2 \Lambda_i(Re), \quad (19)$$

$$\frac{d}{d\omega} (g_2) = \frac{\pi}{4} \rho_L b^2 \Lambda_r(Re), \quad (20)$$

and $\Lambda_r(Re)$ and $\Lambda_i(Re)$ are the real and imaginary components of $\Lambda(Re)$, which is defined as the derivative of the hydrodynamic function. This function can be obtained as

$$\Lambda(Re) = 2\Omega(Re) \left(\frac{\left(K_1(-j\sqrt{jRe}) \right)^2 - K_2(-j\sqrt{jRe}) \left(K_0(-j\sqrt{jRe}) \right)}{\omega \left(K_0(-j\sqrt{jRe}) \right)^2} \right) + \Gamma_{circ}(Re) \frac{d}{d\omega} (\Omega(Re)). \quad (21)$$

Through the use of an iterative process, eq. (15) can be solved. Iterative correction uses an initial guess for ω (for example, the resonant frequency in a vacuum). A value for the Reynolds number can then be calculated, which in turn can be used to update the value of ω .

It can be shown that eq. (15) reduces to the well-known expression for the resonant frequency of a coated-microcantilever in a vacuum ($g_1=g_2=0$), given by

$$f_0 = \frac{\alpha_0^2}{2\pi} \sqrt{\frac{E_1 I_1 + E_2 I_2}{mL^3}}. \quad (22)$$

with $\alpha_0 \cong 1.875$ corresponding to the fundamental flexural mode.²

If there are only small dissipative effects from both the polymer and the viscous liquid medium, the resonant frequency simplifies to

$$f_{res} = f_0 \frac{1}{\sqrt{1 + Lg_2/m}}. \quad (23)$$

This form is analogous to that obtained in Ref. 12 for an uncoated microcantilever in a viscous liquid medium. When the medium is assumed inviscid, eq. (23) can be further simplified to a form analogous to the one presented in Ref. 14 as

$$f_{res} = f_0 \frac{1}{\sqrt{1 + L\pi\rho_L b^2 / (4m)}}. \quad (24)$$

If both the Young's modulus of the polymer layer and the Reynolds number are assumed frequency-independent near resonance (making the hydrodynamic function frequency-independent), the resonant frequency can be simplified to

$$f_{res,i} = \frac{\alpha_i^2}{2\pi L^2} \sqrt{\frac{(m/L + g_2)(EI)' - (g_1/\omega)(EI)''}{(m/L + g_2)^2 + (g_1/\omega)^2}}. \quad (25)$$

Quality Factor: Operation in a viscous liquid medium drastically decreases the frequency stability of microcantilevers in an oscillator configuration. It also decreases the accuracy of the determination of the resonant frequency using a frequency sweep due to the damping and broadening of the frequency response. Equation (12) can be used to calculate the quality factor of the system. The quality factor is best solved numerically in the general case because the analytical expression is cumbersome to obtain. This is done by solving eq. (12) numerically and calculating the upper and lower 3 dB frequencies through an iterative process. In high loss systems, the lower 3 dB frequency is zero, and the bandwidth can be found using only the upper 3 dB frequency. However, if both the Young's modulus of the polymer layer and the Reynolds number are again considered constant in the range of operational frequencies, the quality factor can be obtained from eq. (12) as

$$Q = \left(2 \left(1 - \sqrt{1 - \frac{(g_1/\omega)(EI)' + (m/L + g_2)(EI)''}{(m/L + g_2)(EI)' - (g_1/\omega)(EI)''}} \right) \right)^{-1}. \quad (26)$$

Assuming operation in a vacuum, g_1 and g_2 are both zero and eq. (26) reduces to the one presented in Refs. 1 and 2, which incorporates only the viscoelastic losses in the polymer layer:

$$Q_0 = \left(2 \left(-1 \sqrt{-\frac{(E_p)I}{(E)I}} \right) \right)^{-1}. \quad (27)$$

In low loss media, eq. (26) can further be approximated as

$$Q_{approx} = \frac{\left(\frac{m}{L} + g_2\right)(EI)' - \left(\frac{g_1}{\omega}\right)(EI)''}{\left(\frac{g_1}{\omega}\right)(EI)' + \left(\frac{m}{L} + g_2\right)(EI)''}. \quad (28)$$

For an uncoated cantilever, eq. (28) reduces to the estimation of the quality factor in low loss media from Ref. 12.

In practical applications, the losses caused by the medium and the polymer coating (i.e., the losses considered in this paper) are normally the dominant terms. However, other losses (thermoelastic losses, clamping losses, acoustic losses, losses from the squeeze film effect, etc...)¹⁰ can be taken into account when calculating the quality factor using the well-known equation for multiple loss systems,

$$\frac{1}{Q_{sum}} = \sum_i \frac{1}{Q_i}, \quad (29)$$

where Q_i is the quality factor associated with a particular loss source. Equation (29) is based on the assumption that the losses due to various sources are independent of one another.

In a previous paper,¹⁵ the viscoelastic losses in the layer and the viscous losses in the surrounding medium have been considered separately and combined using equation (29) to obtain an approximation of the total quality factor. In the case of low loss media, the quality factor obtained by using eq (29) with the viscoelastic and viscous losses is:

$$Q_{sum} = \left(\frac{\left(\frac{g_1}{\omega}\right)(EI)''}{\left(\frac{m}{L} + g_2\right)(EI)'} + \frac{(EI)''}{(EI)'} \right)^{-1} \quad (30)$$

In the present paper, the losses due to the polymer coating and the surrounding medium are not assumed to be independent of one another. In the case of small losses the quality factor may be expressed by eq. (28), which is the same as eq. (30) if $\left(\frac{g_1}{\omega}\right)(EI)''$ is neglected. However, when losses are more significant (e.g., when the medium is highly viscous and/or the coating losses are large), the

accuracy of the approximate quality factor expressions are questionable and a more accurate calculation of the quality factor (based on the generalized model presented here) is warranted.

Effects of Chemical Analyte Sorption into the Coating: Introduction of a chemical analyte into the operational medium will not only change the medium's viscosity and density, but will also affect the characteristics of the coated microcantilever through chemical sorption into the polymer layer. For example, the mass and thickness of the polymer layer will increase; the moment of inertia for both layers will change due to a change in the neutral axis location; and the complex Young's modulus of the polymer layer will change.

While the shifts in the resonant frequency due to some of these effects are negligible in comparison with the overall resonant frequency, they still can be significant with regards to the overall shift in the resonant frequency, Δf_{res} , which is used to determine the chemical concentration of the analyte in the medium.

Assuming only small variations in the properties of the polymer layer due to analyte sorption, the relative shift in the resonant frequency can be found as a function of the change in microcantilever mass, Δm , changes in the storage and loss moduli, $\Delta E_2'$ and $\Delta E_2''$, changes in the moments of inertia, ΔI_1 and ΔI_2 , and changes in viscosity and density which cause changes in the hydrodynamic function, thus Δg_1 and Δg_2 as

$$\frac{\Delta f_{res}}{f_{res}} \cong (\lambda_m \Delta m) + (\lambda_{E_2'} \Delta E_2' + \lambda_{E_2''} \Delta E_2'') + (\lambda_{I_1} \Delta I_1 + \lambda_{I_2} \Delta I_2) + (\lambda_{g_1} \Delta g_1 + \lambda_{g_2} \Delta g_2). \quad (31)$$

In eq. (31), the λ terms describe the sensitivities to various changes in the system, and are given as

$$\lambda_m = \left(\begin{array}{l} \frac{\left(\left(\frac{g_1}{\omega} \right) + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} \left(\frac{g_1}{\omega} \right) \right) \left(\frac{g_1}{\omega} \right) (EI)'}{2kLM \left(m/L + g_2 + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} (g_2) \right)^2} \\ + \frac{\left(\left(\frac{g_1}{\omega} \right) + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} \left(\frac{g_1}{\omega} \right) \right) (m/L + g_2) (EI)''}{2kLM \left(m/L + g_2 + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} (g_2) \right)^2} \\ - \frac{1}{2M} \end{array} \right) \quad (32a)$$

$$\lambda_{E_2'} = \frac{I_2}{2kL^3} \quad (32b)$$

$$\lambda_{E_2''} = - \frac{I_2 \left(\left(\frac{g_1}{\omega} \right) + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} \left(\frac{g_1}{\omega} \right) \right)}{2kL^3 \left(m/L + g_2 + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} (g_2) \right)} \quad (32c)$$

$$\lambda_{\eta_1} = \frac{E_1}{2kL^3} \quad (32d)$$

$$\lambda_{\tau_2} = \left(\frac{1}{2kL^3} \right) \left(E_2' - E_2'' \frac{\left(\left(\frac{g_1}{\omega} \right) + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} \left(\frac{g_1}{\omega} \right) \right)}{\left(m/L + g_2 + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} (g_2) \right)} \right) \quad (32e)$$

$$\lambda_{g_1} = - \left(\begin{array}{l} \frac{\left(\left(\frac{g_1}{\omega} \right) (EI)' + (m/L + g_2) (EI)'' \right)}{2kLM \left(m + Lg_2 + L \left(\frac{\omega}{2} \right) \frac{d}{d\omega} (g_2) \right) \omega} \\ + \left(\frac{L^2}{2M\omega} \right) \frac{\left(\left(\frac{g_1}{\omega} \right) + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} \left(\frac{g_1}{\omega} \right) \right)}{\left(m + Lg_2 + L \left(\frac{\omega}{2} \right) \frac{d}{d\omega} (g_2) \right)} \end{array} \right), \quad (32f)$$

and

$$\lambda_{g_2} = \frac{\left(\left(\frac{g_1}{\omega} \right) + \left(\frac{\omega}{2} \right) \frac{d}{d\omega} \left(\frac{g_1}{\omega} \right) \right) \left(\left(\frac{g_1}{\omega} \right) (EI)' + \left(\frac{m}{L} + g_2 \right) (EI)'' \right)}{2kM \left(m + Lg_2 + L \left(\frac{\omega}{2} \right) \frac{d}{d\omega} (g_2) \right)^2} - \frac{L}{2M}, \quad (32g)$$

and ω in Eqs. (32a-g) is evaluated at the resonant frequency.

It is noted that the swelling-induced change in the polymer thickness is included in the ΔI terms. All other terms besides those calculated from eq. (32a-g) (including higher-order terms) have been assumed negligible in deriving eq. (31) for small frequency shifts. Also, eq. (32d) and eq. (32e) have been shown to make negligible contributions to the frequency shift because of the insensitivity of the neutral axis position to the analyte sorption. (This is similar to what was shown in Ref. 2, in which swelling effects were neglected.) The effects due to ΔI_1 and ΔI_2 will therefore be disregarded. Variations in the viscosity and density can also affect the resonant frequency as indicated by the Δg_1 and Δg_2 terms in eq. (31). However, in practical applications, these shifts are normally assumed accounted for using differential measurement from a reference cantilever, a cantilever of identical geometry and polymer coating thickness which is not sensitive to the analyte. Therefore, changes in the viscosity and density will not be included in the discussion dealing with eq. (31). Equations (31) and (32) can then be used to analyze the sensitivity response of coated microcantilever chemical sensors.

RESULTS AND DISCUSSION

Simulations: Simulations are performed to illustrate the effects of coating and medium properties on a microcantilever of typical geometry. The polymer layer assumed in these simulations is polyisobutylene (PIB). The Young's modulus for PIB has been previously characterized in Ref. 16. Figures 2 and 3 show the frequency response of a polymer-coated microcantilever to different aqueous mixtures of glycerol and ethanol, respectively, using both eq. (15) for the exact calculation of the resonant frequency and eq. (25) for the approximate calculation of the resonant frequency that assumes that both the Young's modulus of the polymer layer and the hydrodynamic function are frequency-independent near resonance. The approximation made by eq. (25) is found to be valid for systems with

1 thin polymer layers and Reynolds numbers much greater than one. For low Reynolds numbers, Re , i.e.
2 high viscosity and/or low density fluid, the results indicate that the hydrodynamic function cannot be
3 considered frequency-independent. Therefore, g_1 and g_2 must be considered frequency-dependent in
4 calculating the resonant frequency for low Reynolds numbers. While ethanol has a higher viscosity
5 compared to water, its lower fluid density leads to the device having an overall higher resonant
6 frequency than that of water, as is shown in Fig. 3. This indicates that the resonant frequency is not just
7 dependent on the viscosity, but on the overall Reynolds number.
8
9

10 The difference between the calculated quality factor using the upper and lower 3 dB frequencies and
11 that obtained with eq. (26) has been observed to be negligible in aqueous solutions of both glycerol and
12 ethanol. Figures 4 and 5 compare the calculated quality factor with that of the low loss approximation
13 using eq. (28) for different aqueous mixtures of glycerol and ethanol, respectively which assumes the
14 Reynolds number is much greater than one. As expected, eq. (28) is shown to be inappropriate for high
15 viscosity media. The difference between the approximation and the more general model is found to
16 increase as the Reynolds number decreases. In the calculations, it is assumed that the Young's modulus
17 of the coating does not change as a function of the operational medium.
18
19

20 The quality factor also can change as a function of the polymer-coating thickness. Figure 6 gives the
21 calculated quality factor of a polymer-coated microcantilever as a function of PIB coating thickness
22 compared to both the approximation that the loss is from only the medium and the approximation that
23 the viscoelastic PIB coating contributes loss, but is independent of the losses caused by the medium.
24 Both approximations are calculated assuming that the hydrodynamic function is frequency-independent
25 and thus differ slightly from the exact calculation when the polymer layer thickness is zero. Figure 6
26 indicates that one should include the losses from the polymer coating. It also indicates that there is an
27 optimum coating thickness with regards to the quality factor around 1 μm of PIB for this configuration.
28 This behavior is shown for both the exact calculation of the quality factor as well as the approximation
29 assuming the losses are independent.
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
Chemical sorption into the polymer coating is simulated assuming an increase in polymer mass by up to 5% (45.85 pg), a storage modulus decrease by up to 10% (-6.73 MPa), and a loss modulus increase by up to 100% (+102.48 MPa) (Figs. 7 and 8). The latter two property changes represent the effects of coating plasticization and have been deduced from recent related work using guided SH-SAW sensors¹⁷ changes in the shear modulus of PIB upon exposure to different concentrations of toluene. Due to the approximately linear character of the experimental data, the data has been linearized with respect to concentration. This data was obtained for a higher frequency device (100MHz) and has served in the present simulation for a lower-frequency microcantilever device as a guide for choosing the *relative* variation in the PIB properties, i.e., the percent change, provided that the variations in property values correspond to the same concentration in the coating. The mass sorption is found to cause up to a 42 Hz decrease in the resonant frequency in water, whereas the coating plasticization effects contribute up to an additional 9.9 Hz decrease in the resonant frequency. In 40% glycerol (~3.6 cP), the same mass loading causes up to a 23.9 Hz decrease in the resonant frequency, whereas the coating plasticization effects contribute an additional 11.7 Hz decrease in the resonant frequency. This indicates that the sensitivity to mass loading decreases in higher viscosity (lower *Re*) solutions, whereas the sensitivity to changes in the Young's modulus increases in higher viscosity solutions.

38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
Comparison to Experimental Data: Recently performed experiments have shown the feasibility of dynamically-driven CMOS multilayer microcantilever chemical sensors in liquid environments.³ With a reference microcantilever to account for the effects of the medium, the response of a 150x140x8.2 μm CMOS-based microcantilever coated with 0.3 μm of PIB to 350 ppm ethylbenzene was found to result in a shift in the resonant frequency of about 85 Hz. However, the theoretical model used in Ref. 3 assuming only mass loading predicted a 63 Hz shift in the resonant frequency. Note that for the present geometry the shearing effects at the edge of the microcantilever can no longer be neglected since the length is not much greater than the width. The derived analytical expression for the shift in the resonant frequency can still be used if the values for g_1 and g_2 are calculated empirically.

For this microcantilever geometry in water, the polymer thickness is small compared to the base layer. In this case, $(EI)'' \gg (EI)''$ and the resonant frequency and quality factor can be calculated using eq. (25) and eq. (30), respectively. Assuming that $(EI)'' = 0$, from these two equations, g_1 and g_2 can be approximated, respectively, as

$$g_1 \cong \frac{(m/L + g_2)}{Q} \omega \quad (33)$$

and

$$g_2 \cong \left(\left(\frac{f_0}{f_{res}} \right)^2 \left(1 + \frac{1}{Q^2} \right)^{-1} - 1 \right) m/L \quad (34)$$

where the quality factor in water (and dilute analyte solution) was experimentally determined to be $Q=10$, and the measured resonant frequency in a vacuum and in the liquid were 400 kHz and 200 kHz, respectively.³

From eq. (34), g_2 is calculated to be roughly three times the mass per unit length of the microcantilever. From eq. (33), g_1 is given by

$$g_1 \cong \frac{4}{10} \omega \left(\frac{m}{L} \right). \quad (35)$$

The changes in the Young's storage and loss moduli used in Fig. 7 and 8 were obtained using the response of PIB to the sorption of 10 to 50 ppm of toluene. Similar coating plasticization caused by ethylbenzene can be assumed. The maximum ethylbenzene concentration used in Ref. 3 is 350 ppm. Thus, the maximum amount of coating plasticization will be assumed seven times larger. The change in the mass of the polymer can be calculated as:²

$$\Delta m = Kh_2bLC_A, \quad (36)$$

where K is the dimensionless partition coefficient and C_A is the concentration of the analyte in the medium of operation. The partition coefficient for ethylbenzene in liquid for PIB has been experimentally determined as 464.^{2, 17} The microcantilever used in Ref. 3 is multilayered with a silicon thickness of 5 μm , a silicon oxide thickness of 2.2 μm , and a silicon nitride thickness of 1 μm . The

1 resulting mass per unit length of the beam is calculated as 2.7181 milligrams per meter. The composite
2 Young's modulus for the beam is set at 112.9 GPa so that eq. (15) will produce the experimentally
3 obtained resonant frequency of 200 kHz in water. Since the Reynolds number for this configuration is
4 6000, the change in g_1 and g_2 can be neglected.
5
6
7
8

9 The calculated response of the microcantilever is shown in Figure 9 with only the mass loading and
10 the total differential shift (including plasticization effects). The responses are compared with the
11 experimentally measured resonant frequency shift that also accounts for changes in the medium
12 properties by use of a reference cantilever. For example, for a concentration of 300 ppm ethylbenzene,
13 using eq. (31) with only the mass loading effect, the decrease in the resonant frequency due to mass
14 sorption alone is calculated to be 54 Hz. Assuming up to a -70% decrease in the storage modulus and up
15 to a 700% increase in the loss modulus, an additional 11 Hz decrease in the resonant frequency can be
16 accounted for by coating plasticization, which compares well with the measured shift of 64 Hz.
17
18
19
20
21
22
23
24
25
26
27
28
29

30 CONCLUSIONS

31 Generalized expressions for the resonant frequency and quality factor of a dynamically driven,
32 polymer-coated microcantilever accounting for the effects of the medium and the polymer coating have
33 been presented. It is found that the resonant frequency and quality factor must be calculated taking into
34 account these effects. The resonant frequency was found to be significantly affected by non-mass
35 loading effects. It is also found that the resonant frequency's sensitivity to mass loading and other
36 system properties are dependent on the medium of operation. The generalized expressions obtained in
37 this work simplify to known special cases and can be used to estimate the contribution of non-mass
38 sorption effects in the response of dynamically-driven microcantilever chemical sensors.
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

REFERENCES

- (1) Sampath, U. *Analytical Modeling of Microcantilever-Based Dynamic Microsensors*, M.S. Thesis, Marquette University, Milwaukee, WI, 2005.
- (2) Sampath, U.; Heinrich, S.M.; Josse, F.; Lochon, F.; Dufour, I.; Rebiere D. *IEEE Trans. Ultrason. Ferroelectrics Freq. Contr.* **2006**, *53*, 2166-2173.
- (3) Vancura, C.; Li, Y.; Lichtenberg, J.; Kirstein, K.-U.; Hierlemann, A.; Josse, F. *Anal. Chem.* **2007**, *79*, 1646-1654.
- (4) Lochon, F.; Fadel, L.; Dufour, I.; Rebiere, D.; Pistre, J. *Mater. Sci. Eng., C* **2006**, *26*, 348-353.
- (5) Boisen, A.; Thaysen, J.; Jensenius, H.; Hansen, O. *Ultramicroscopy* **2000**, *82*, 11-16.
- (6) Rogers, B.; Manning, L.; Jones, M.; Sulchek, T.; Murray, K.; Beneschott, B.; Adams, J.D.; Hu, Z.; Thundat, T.; Cavazos, H.; Minne, S.C. *Rev. Sci. Instrum.* **2003**, *74*, 4899-4901.
- (7) Thundat, T.; Wachter, E.A.; Sharp, S.L.; Warmack, S.J. *Appl. Phys. Lett.* **1995**, *66*, 1695-1697.
- (8) Baselt, D.R.; Fruhberger, B.; Klaasen, E.; Cemalovic, S.; Britton Jr., C.L.; Patel, S.V.; Mlsna, T.E.; McCorkle, D.; Warmack, B. *Sens. Actuators, B* **2003**, *88*, 120-131.
- (9) Thundat, T.; Sharp, S.L.; Fisher, W.G.; Warmack, R.J.; Wachter, E.A. *Appl. Phys. Lett.* **1995**, *66*, 1563-1565
- (10) Basak, S.; Ramana, A. *J. Appl. Phys.* **2006**, *99*, no. 114906, 1-10.
- (11) Pinnaduwege, L.; Ji, H.-F.; Thundat, T. *IEEE Sensor J.* **2005**, *5*, 774- 785.
- (12) Sader, J. *J. Appl. Phys.* **1998**, *84*, 64-76.
- (13) Dufour, I.; Heinrich, S.; Josse, F. *IEEE ASME J. Microelectromech Syst.* **2007**, *16*, 44-49.

- 1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
- (14) Lindholm, U.; Kana, D.; Chu, W.-H.; Abramson, H. *J. Ship Res.* **1965**, *9*, 11-22.
- (15) Dufour, I.; Lochon, F.; Heinrich, S.; Josse, F.; Rebière, D. *IEEE Sensor J.* **2007**, *7*, 230- 236.
- (16) Ferry, J. *Viscoelastic Properties of Polymers*, 3rd ed.; Wiley: New York; 1980, p. 606.
- (17) Li, Z.; Jones, Y.; Hossenlopp, J.; Cernosek, R.; Josse, F. *Anal. Chem.* **2005**, *77*, 4595-4603.




Figure 1. A rectangular microcantilever shown with a polymer layer




Figure 2. The calculated resonant frequency of a $100 \times 20 \times 2 \mu\text{m}$ microcantilever coated with $0.5 \mu\text{m}$ of PIB in varying mixtures of glycerol (up to 70%, or ~ 23 cP) using eq. (15) (solid line) compared to an approximation (dashed line) calculated using eq. (25) which assumes that the Young's modulus and the Reynolds number are frequency-independent. The Reynolds number calculated using this resonant frequency for each varying mixtures of glycerol is shown on the axis above.




Figure 3. The calculated resonant frequency of a $100 \times 20 \times 2 \mu\text{m}$ microcantilever coated with a $0.5 \mu\text{m}$ of PIB in varying mixtures of ethanol using eq. (15) (solid line) compared to an approximation (dashed line) calculated using eq. (25) which assumes that the Young's modulus and the Reynolds number are frequency-independent. The Reynolds number calculated using this resonant frequency for each varying mixtures of ethanol is shown on the axis above.




Figure 4. Calculated quality factor of a 100x20x2 μm microcantilever coated with a 0.5 μm of PIB in varying mixtures of glycerol (up to 70%, or ~ 23 cP, solid line) compared with the small loss approximation Q_{approx} (dashed line) calculated using eq. (28).




Figure 5. Calculated quality factor of a 100x20x2 μm microcantilever coated with a 0.5 μm of PIB in varying mixtures of ethanol (solid line) compared with the small loss approximation Q_{approx} (dashed line) calculated using eq. (28).




Figure 6. The calculated exact value of the quality factor (solid line) of a $100 \times 20 \times 2 \mu\text{m}$ microcantilever coated with varying PIB thicknesses up to $2 \mu\text{m}$ compared with both the approximation assuming that the losses caused by the medium and the polymer-coating are independent (dashed line) and that the losses are from only the medium (short dashed line). Note both approximations assume a frequency-independent hydrodynamic function and thus differ from the calculated exact value for the quality factor when the polymer layer thickness is zero.




Figure 7. Shifts in the resonant frequency of a 100x20x2 μm microcantilever coated with a 0.5 μm PIB in water undergoing mass sorption of up to 45 pg with (dashed line) and without (solid line) coating plasticization effects




Figure 8. Shifts in the resonant frequency of a $100 \times 20 \times 2 \mu\text{m}$ microcantilever coated with a $0.5 \mu\text{m}$ of PIB in a 40% glycerol mixture undergoing mass sorption of up to 45 pg with (dashed line) and without (solid line) coating plasticization effects.




Figure 9. Comparison of experimentally measured values in Ref. 3 (dots) for the resonant frequency shift of a $150 \times 140 \times 8.2 \mu\text{m}$ microcantilever coated with $0.3 \mu\text{m}$ of PIB to the theoretically calculated frequency shift taking into account first mass sorption (solid line) and then mass sorption and plasticization effects (dashed line). Note that a reference cantilever is used in Ref. 3 to account for the effects of changes in the medium properties.