



**HAL**  
open science

## **Photoenhanced uptake of NO<sub>2</sub> on mineral dust: Laboratory experiments and model simulations**

M. Ndour, B. d'Anna, C. George, O. Ka, Yves Balkanski, J. Kleffmann, K. Stemmler,  
M. Ammann

### ► **To cite this version:**

M. Ndour, B. d'Anna, C. George, O. Ka, Yves Balkanski, et al.. Photoenhanced uptake of NO<sub>2</sub> on mineral dust: Laboratory experiments and model simulations. *Geophysical Research Letters*, 2008, pp.35. <10.1029/2007GL032006>. <hal-00307247>

**HAL Id: hal-00307247**

**<https://hal.science/hal-00307247v1>**

Submitted on 14 Jun 2021

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

## Photoenhanced uptake of NO<sub>2</sub> on mineral dust: Laboratory experiments and model simulations

Marieme Ndour,<sup>1</sup> Barbara D'Anna,<sup>1</sup> Christian George,<sup>1</sup> Oumar Ka,<sup>2</sup> Yves Balkanski,<sup>3</sup> Jörg Kleffmann,<sup>4</sup> Konrad Stemmler,<sup>5</sup> and Markus Ammann<sup>5</sup>

Received 12 September 2007; revised 28 November 2007; accepted 11 January 2008; published 12 March 2008.

[1] Mineral dust contains material such as TiO<sub>2</sub> that is well known to have photocatalytic activity. In this laboratory study, mixed TiO<sub>2</sub>-SiO<sub>2</sub>, Saharan dust and Arizona Test Dust were exposed to NO<sub>2</sub> in a coated wall flow tube reactor. While uptake in the dark was negligible, photoenhanced uptake of NO<sub>2</sub> was observed on all samples. For the mixed TiO<sub>2</sub>-SiO<sub>2</sub>, the uptake coefficients increased with increasing TiO<sub>2</sub> mass fraction, with BET uptake coefficients ranging from 0.12 to  $1.9 \times 10^{-6}$ . HONO was observed from all samples, with varying yields, e.g., 80% for Saharan dust. Three-dimensional modeling indicates that photochemistry of dust may reduce the NO<sub>2</sub> level up to 37% and ozone up to 5% during a dust event in the free troposphere. **Citation:** Ndour, M., B. D'Anna, C. George, O. Ka, Y. Balkanski, J. Kleffmann, K. Stemmler, and M. Ammann (2008), Photoenhanced uptake of NO<sub>2</sub> on mineral dust: Laboratory experiments and model simulations, *Geophys. Res. Lett.*, **35**, L05812, doi:10.1029/2007GL032006.

### 1. Introduction

[2] Following erosion from the ground, dust particles are mobilized by strong winds. Their chemical composition reflects that of the crustal materials from which they are produced. A typical composition is 60% SiO<sub>2</sub> and 10–15% Al<sub>2</sub>O<sub>3</sub> (by weight) [Usher *et al.*, 2003]. Beside these major elements, some other oxides are found. The percentages of these other oxides, namely Fe<sub>2</sub>O<sub>3</sub>, MgO, CaO and TiO<sub>2</sub>, are slightly more variable and dependent on source location. For instance, titanium dioxide (TiO<sub>2</sub>) is found in dust particles at mass mixing ratios ranging from 0.1 to 10% depending on the exact location from where the particles were uplifted [Hanisch and Crowley, 2003]. It has been shown that the uptake of HNO<sub>3</sub> on dust has a significant effect on the global ozone budget [Bauer *et al.*, 2004].

[3] Both titanium and iron oxides are used as photochemical sources of radicals. Iron oxides are used to induce the so-called Fenton or Photo-Fenton reactions [Deguillaume *et al.*, 2005]. Pure TiO<sub>2</sub> is used in a variety of remediation

processes due to its photocatalytic properties. The resulting free-radicals are very efficient oxidizers of organic and inorganic matter. For instance, pure TiO<sub>2</sub> has been demonstrated to be an effective photocatalyst for NO<sub>2</sub> reduction [Gustafsson *et al.*, 2006; Yumoto *et al.*, 2002]. It has also been suggested that TiO<sub>2</sub> present in fly ash particles may represent a sink of halocarbons in the troposphere [Kutsuna *et al.*, 1999]. However, the role of mineral dust aerosol as a photochemically active substrate that can modify the chemistry of the dust particles and their potential impact on the tropospheric composition has not been explored so far. Therefore, we investigated the effect of UV/visible light on the uptake kinetics of NO<sub>2</sub> on various mineral surfaces including SiO<sub>2</sub>/TiO<sub>2</sub>-based proxies and authentic dust particles.

### 2. Experimental

#### 2.1. Horizontal Coated Wall Reactor

[4] The experiments were performed in a 20 cm × 1.05 cm (i.d.) thermostated horizontal coated wall reactor, detailed by George *et al.* [2005], fitted with four halogen lamps (OSRAM Halostar starlite, 50 W) with an irradiance of 0.069 mW cm<sup>-2</sup> below 400 nm inside the reactor. With gas flows of ca. 850 mL min<sup>-1</sup>, no gas phase photodissociation of NO<sub>2</sub> was observed. NO<sub>2</sub> was introduced into the reactor via a movable injector and monitored at the reactor exit with a NO<sub>x</sub> chemiluminescence analyzer (THERMO 42C), which inlet was mounted with a carbonate denuder. The NO<sub>2</sub> uptake coefficients were determined by monitoring the loss of gas phase NO<sub>2</sub> as a function of time and exposed solid surface.

[5] Another set-up was run at lower NO<sub>2</sub> concentrations and higher irradiance using real mineral samples i.e., Arizona test dust and grinded Saharan sand. In this case, the irradiations of mineral dust substrates were performed using a slightly different experimental layout i.e., in a 50 cm × 0.8 cm (i.d.) Duran glass tubes installed in an air cooled lamp housing holding 7 fluorescence lamps (44 cm × 2.6 cm o. d.), in a circular arrangement surrounding the thermostated reactor tube. These experiments were performed with UV lamps (300–420 nm, 13.4 mW cm<sup>-2</sup>).

[6] The measurements are reported in terms of the dimensionless uptake coefficient ( $\gamma$ ), which simply defines the probability that a gas kinetic collision of a molecule on the surface leads to chemical conversion.  $\gamma$  is related to the measured first order rate coefficient  $k_w$  by:

$$k_w = \frac{\gamma_{\text{geom}} \langle C \rangle}{2r_{\text{tube}}} \quad (1)$$


<sup>1</sup>Institut de recherches sur la catalyse et l'environnement de Lyon, UMR5256, CNRS, Université de Lyon, Villeurbanne, France.

<sup>2</sup>Physics Department, University Cheikh Anta Diop, Dakar-Fann, Senegal.

<sup>3</sup>Laboratoire des Sciences du Climat et l'Environnement, CEA-CNRS-UVSQ, Gif-sur-Yvette, France.

<sup>4</sup>Physikalische Chemie/FB C, Bergische Universität Wuppertal, Wuppertal, Germany.

<sup>5</sup>Laboratory of Radio- and Environmental Chemistry, Paul Scherrer Institute, Villigen, Switzerland.



**Figure 1.** The data shown correspond to the NO<sub>2</sub> gas phase concentration at the exit of the flowtube after being exposed for 0.96 s to solid surfaces of SiO<sub>2</sub> (solid line in the dark and dash-dotted line, irradiated) and a TiO<sub>2</sub>/SiO<sub>2</sub> (dotted in the dark and dash-dot-dotted line, irradiated) in the dark and irradiated by the four halogen lamps.

$r_{\text{tube}}$ ,  $\gamma_{\text{geom}}$  and  $\langle c \rangle$  are the flow tube radius, geometric uptake coefficient and thermal molecular velocity, respectively. The mass-dependent  $\gamma_{\text{geom}}$  can be converted to a mass-independent  $\gamma_{\text{BET}}$  by taking into account the entire BET surface area of the sample instead of its geometric surface. All uptake coefficients reported below were obtained by considering the measured BET surface and were corrected for gas phase diffusion limitations.

[7] An indirect detection of the produced HONO was made by means of a NO/NO<sub>x</sub>-chemiluminescence detector, in combination with a sodium carbonate denuder tube for removing HONO from the gas stream. In addition a direct HONO detection was made by using the LOPAP device (Long Path Absorption Photometer) [Heland *et al.*, 2001].

[8] The various mineral oxide powders investigated, SiO<sub>2</sub> (DEGUSSA Aerosil 130) and TiO<sub>2</sub> (DEGUSSA, P25 80% anatase, 20% rutile; P25), were purchased from Degussa. TiO<sub>2</sub> and SiO<sub>2</sub> (0.5–2 g) powder was dissolved in 20 ml of water and was dripped uniformly into the Pyrex flow tube and dried overnight in an oven at 100°C. The resulting film covered the entire inner area of the tube and, to the eye, was fairly uniform in thickness. Saharan sand was collected from the south of Mauritania (Tagant) and was grinded. Arizona Test Dust (Ultrafine Grade A1, Ellis Components, Stonebroom, UK), was also used [Vlasenko *et al.*, 2005]. Some samples were also analyzed for anions by means of ion chromatography (Dionex 120 equipped with an IonPac AS14A-4-mm column).

## 2.2. LMDz General Circulation Model

[9] The LMDz version used in this study has a horizontal resolution of 3.8 degrees in longitude and 2.5 degrees in latitude over the whole globe. Interaction with Chemistry and Aerosols (INCA) is coupled on-line to the LMDz general circulation model. INCA prepares the surface and *in situ* emissions, calculates dry deposition and wet scavenging rates, and integrates in time the concentration of

atmospheric species with a time step of 30 min. The INCA-NMHC version 5 applied in this study is based on an earlier version which was developed to represent the background chemistry of the troposphere [Hauglustaine *et al.*, 2004].

[10] 43 photolytic reactions, 217 thermochemical reactions, and 5 heterogeneous reactions are taken into account by the model. The set of reactions and reaction rates are based on the scheme of Brocheton *et al.* [1999]. All reaction rates have been reviewed and updated with respect to the IUPAC and JPL compilations.

## 3. Results


[11] In the present study, solid TiO<sub>2</sub> diluted in SiO<sub>2</sub> at a mass mixing ratio of 1 wt% was used to mimic mineral dust at a relative humidity of 25%, consistent with those effectively reported for dust particles. For photoinduced processes, the uptake coefficients were normalized to the measured average irradiance  $I$  according to:

$$\Gamma_{\text{phot}} = \frac{\gamma_{\text{BET}}}{I} \quad (2)$$

In this case, the photochemical uptake coefficient  $\Gamma_{\text{phot}}$  has units of (mW cm<sup>-2</sup>)<sup>-1</sup>. During these experiments,  $I$  was equal to 0.069 mW.cm<sup>-2</sup> below 400 nm, i.e., in the wavelength range where TiO<sub>2</sub> can be photochemically activated. From  $\Gamma_{\text{phot}}$ , it becomes possible to estimate, assuming a constant quantum yield below 400 nm, the order of magnitude of the uptake coefficient at different irradiance. These uptake coefficients were implemented in the LMDz-INCA chemistry-climate model to evaluate the environmental significance of the reaction.

[12] The “dark” uptake of NO<sub>2</sub> has been observed, in agreement with previous studies, to be very low on all mineral solid surfaces exhibiting a time dependence with uptake coefficients  $\gamma_{\text{BET}}$  of ca. 10<sup>-9</sup> at long reaction times. Such steady state uptake coefficients are in agreement with initial uptake coefficients reported by Underwood *et al.* [2001]. Without irradiation, no significant reaction was observed and under those conditions, as previously reported, the uptake of NO<sub>2</sub> on dust needs to be regarded as non significant.

[13] However, once the solid sample is irradiated a very rapid chemical conversion is observed. Figure 1 shows the raw data (dark and light) for an uptake experiment on a surface made of SiO<sub>2</sub> and TiO<sub>2</sub>/SiO<sub>2</sub> at 1 wt% of TiO<sub>2</sub> when the Pyrex flowtube was irradiated with the halogen lamps. It is obvious that under irradiation, the uptake of NO<sub>2</sub> is driven by a fast chemical reaction on the solid film. In this case, the uptake of NO<sub>2</sub> has been photo-enhanced by ca. two orders of magnitude. Not only is the uptake rate drastically accelerated but it also appears to be catalytic in the sense that (as shown in Figure 1) it does not depend on time, i.e., no surface saturation has been observed on these synthetic samples over hours (even at NO<sub>2</sub> concentrations as large as 300 ppb). The measured uptake coefficients were observed to be strongly dependent on the NO<sub>2</sub> gas phase concentrations, in the range from 7 to 380 ppb, as shown in Figure 2. This behavior can be explained via a Langmuir-Hinshelwood mechanism.





**Figure 2.** Dependence of the uptake coefficient as a function of the NO<sub>2</sub> gas phase concentration. All experimental were conducted at 298 K,  $m(\text{dust}) = 25.3$  mg, and 25% relative humidity. Each point was obtained from measurements on fresh samples.

[14] Clearly these experiments on synthetic dust samples have demonstrated that under relevant atmospheric conditions mineral dust photochemistry should be considered as an important chemical pathway since the uptake coefficients (derived on the BET surface) were observed to be close to  $10^{-6}$ , up to two orders of magnitude larger than without light. *Gustafsson et al.* [2006] derived the uptake rate of NO<sub>2</sub> onto pure TiO<sub>2</sub> to be ca.  $8 \times 10^{-3}$  with a higher irradiance than used here. Taking the different light intensity into account and normalizing our uptake rate solely to the TiO<sub>2</sub> surface, both data sets are in good agreement.


[15] Nevertheless, we ensured that these photolytic chemical conversions also occur under even more realistic conditions. This was performed at very low NO<sub>2</sub> concentrations, under realistic irradiation using real mineral samples i.e., Arizona test dust and grinded Saharan sand. As shown in Figure 3 both samples do cause photochemical conversion of NO<sub>2</sub> once irradiated.

[16] Arizona test dust is known to have a very small content of TiO<sub>2</sub> (below 1 wt%) while Saharan sand may have large variable contents of the oxide [*Hanisch and Crowley, 2003; Karagulian and Rossi, 2005*]. On synthetic samples, we observed that the photochemical uptake coefficient  $\gamma_{\text{BET}}$  increases from 0.12 to  $1.9 \times 10^{-6}$  with increasing TiO<sub>2</sub> content from 1 to 5 wt%.


[17] The photocatalytic action of TiO<sub>2</sub> is initiated by the photo-production of excess electrons in the conduction band ( $e_{\text{cb}}^-$ ) and holes in the valence band ( $h_{\text{vb}}^+$ ). The electron reduces the oxygen contained in the gas flow or the nitrogen dioxide while the hole oxidizes water vapor that is also present in the gas flow. The associated reactions mechanism could be [*Hoffmann et al., 1995*]:




where the electrons,  $\text{O}_2^-$  and OH can react with nitrogen dioxide according to:



It must be underlined that these reactions are just a subset of a large number of possible reactions altering the final yield of each product. Depending on the acidity of the surface, the production of nitrite anions is linked to that of gaseous nitrous acid (HONO), known to be a very important source of hydroxyl radicals. Nitrous acid may accumulate during night-time before undergoing photolysis in the morning, but may also be produced during daytime with strong photo-



**Figure 3.** Conversion of NO<sub>2</sub> into HONO on UV-A (300–420 nm) irradiated mineral dust in presence of 24 ppb NO<sub>2</sub> and 24% relative humidity. (a) The formation of HONO (solid circles, right axis) and the removal of NO<sub>2</sub> (open circles) on a 32 mg deposited Saharan dust. (b) The formation of HONO (solid circles, right axis) and the removal of NO<sub>2</sub> (open circles) on a 56 mg deposited Arizona Test dust. The grey area at the top of the panels indicates the periods during which the film was exposed to NO<sub>2</sub> in the dark, the yellow area indicates the time when the film was irradiated.



**Figure 4.** Percentage change in free tropospheric NO<sub>2</sub> concentration during a dust episode that occurred on July 30, 2002 over the Western Sahara, due to photochemically enhanced uptake on dust.

chemical sources of 200–1800 pptv/h up to 60 times faster than all night-time sources [Kleffmann *et al.*, 2007].

[18] On the synthetic dust samples, an indirect identification of acidic gases such as HONO was made by connecting or disconnecting a potassium carbonate denuder at the inlet of the NO/NO<sub>x</sub>-chemiluminescence detector. Using this procedure, HONO was observed to be produced solely when the solid surfaces were irradiated. On synthetic dust surfaces (i.e., 1 wt. % TiO<sub>2</sub> in SiO<sub>2</sub>) HONO was produced with an average yield of 33% in experiments with 420 ppb of NO<sub>2</sub>. This yield is smaller than the one reported by [Gustafsson *et al.*, 2006] (i.e., 75%) on pure TiO<sub>2</sub>. This difference could be explained by different surface characteristics of the samples used. In addition, HONO was unambiguously detected under realistic conditions using Arizona test dust or grinded Saharan sand exposed to 24 ppb NO<sub>2</sub> (see Figure 3) by means of the LOPAP instrument, which selectively detects HONO. For the grinded Saharan sand sample, O., the HONO yield is about 80%. For the Arizona test dust, the yield was lower and a delayed emission of HONO was observed, indicating that surface acidity, microstructure and other factors control the release of HONO in real dust samples, while the loss of NO<sub>2</sub> was remarkably similar. Photochemical HONO formation was observed for the first time on real surfaces and not only on synthetic TiO<sub>2</sub> samples. Nitrate anions were also observed to be solely produced during the photoconversion of NO<sub>2</sub> on dust.

[19] Runs with the LMDz-INCA model shown in Figure 4 demonstrate the effect of photochemical conversion of NO<sub>2</sub> on dust into HONO and nitrates on the NO<sub>2</sub> concentrations during a dust episode that occurred during summer 2002 over the western Saharan, documented during the second phase of MINATROC 2 [de Reus *et al.*, 2005; Umann *et al.*, 2005]. For the simulations, a  $\Gamma_{\text{phot}}$  value of  $1.48 \cdot 10^{-5}$  mW

cm<sup>-2</sup>, determined for low NO<sub>2</sub> concentration on SiO<sub>2</sub>/TiO<sub>2</sub> surfaces, was considered. The simulated NO<sub>2</sub> concentrations decrease by 37% in the free troposphere in regions as the optical depth of the dust cloud averages 0.5 at 550 nm. Coincidentally, nitric acid and OH decrease by 54.0 and 9.2% respectively, over the same region (see Table 1). The decreases in these photochemical species lead to a simulated O<sub>3</sub> concentration decrease of 5.1%.

[20] When averaged over the globe, the decrease in simulated NO<sub>2</sub> concentrations in the free troposphere amounts to 3.0%. For nitric acid, OH and O<sub>3</sub>, the respective decrease averaged over the month of July are: 8.4, 1.7 and 1.4%.

#### 4. Conclusion

[21] In this study, by using NO<sub>2</sub> as a probe molecule, we demonstrated unambiguously, under atmospheric relevant conditions, that photochemistry of dust is important. Consequently, this new chemical pathway needs to be considered in forthcoming modelling studies in order to better assess the impact of dust on the atmospheric composition.

**Table 1.** Percentage Change and [Mix – Max Values] in NO<sub>2</sub>, OH, HNO<sub>3</sub>, and O<sub>3</sub> Concentrations During a Dust Episode on July 30, 2002, Over the Western Sahara Due to the Photochemical Reaction of NO<sub>2</sub> on Dust

	[28W–13W; 13N–34N] July 30, 2002	Global July Mean
NO <sub>2</sub>	–36.6 [–56.8 to –3.4]	–3.0 [–22.7 to 0.3]
OH	–9.2 [–13.0 to –3.5]	–1.7 [–8.9 to –0.1]
HNO <sub>3</sub>	–54.0 [–74.0 to –23.4]	–8.4 [–47.3 to –0.4]
O <sub>3</sub>	–5.1 [–6.8 to –3.3]	–1.4 [–4.4 to –0.12]

Indeed, we note that apart from NO<sub>2</sub>, which serves as electron acceptor, many other trace gas species or condensed constituents may be reduced or oxidized in a similar way on dust exposed to sunlight, potentially giving a wide impact of this photochemistry.

[22] **Acknowledgments.** CG is grateful to J.-M. Herrmann, G. Bergametti, E. Puzenat, and P. Conchon for helpful discussions. MN is grateful to the Agence Universitaire de la Francophonie and the Région Rhône-Alpes for financial support. Samples by R. Vernet, S. Borrmann, and F. Grousset and A. Vlasenko are acknowledged. Financial support by the French Atmospheric chemistry Programme (PNCA) is gratefully acknowledged.

## References

- Bauer, S. E., Y. Balkanski, M. Schulz, D. A. Hauglustaine, and F. Dentener (2004), Global modeling of heterogeneous chemistry on mineral aerosol surfaces: Influence on tropospheric ozone chemistry and comparison to observations, *J. Geophys. Res.*, *109*, D02304, doi:10.1029/2003JD003868.
- Brocheton, F., B. Aumont, G. Toupance, and C. Granier (1999), Sensitivity of global CTM models to the spatial representation of the emissions, in *Proceedings of EUROTRAC Symposium '98*, vol. 2, edited by P. M. Borrell and P. Borrell, pp. 560–564, WIT Press, Southampton, U. K.
- Deguillaume, L., M. Leriche, K. Desboeufs, G. Mailhot, C. George, and N. Chaumerliac (2005), Transition metals in atmospheric liquid phases: Sources, reactivity, and sensitive parameters, *Chem. Rev.*, *105*, 3388–3431.
- de Reus, M., H. Fischer, R. Sander, V. Gros, R. Kormann, G. Salisburry, R. Van Dingenen, J. Williams, M. Zollner, and J. Lelieveld (2005), Observations and model calculations of trace gas scavenging in a dense Saharan dust plume during MINATROC, *Atmos. Chem. Phys.*, *5*, 1787–1803.
- George, C., R. S. Strekowski, J. Kleffmann, K. Stemmler, and M. Ammann (2005), Photoenhanced uptake of gaseous NO<sub>2</sub> on solid-organic compounds: A photochemical source of HONO?, *Faraday Discuss.*, *130*, 195–210.
- Gustafsson, R. J., A. Orlov, P. T. Griffiths, R. A. Cox, and R. M. Lambert (2006), Reduction of NO<sub>2</sub> to nitrous acid on illuminated titanium dioxide aerosol surfaces: implications for photocatalysis and atmospheric chemistry, *Chem. Commun.*, 1359–7345, 3936–3938.
- Hanisch, F., and J. N. Crowley (2003), Ozone decomposition on Saharan dust: An experimental investigation, *Atmos. Chem. Phys. Discuss.*, *2*, 119–130.
- Hauglustaine, D. A., F. Hourdin, L. Jourdain, M. A. Filiberti, S. Walters, J. F. Lamarque, and E. A. Holland (2004), Interactive chemistry in the Laboratoire de Meteorologie Dynamique general circulation model: Description and background tropospheric chemistry evaluation, *J. Geophys. Res.*, *109*, D04314, doi:10.1029/2003JD003957.
- Heland, J., J. Kleffmann, R. Kurtenbach, and P. Wiesen (2001), A new instrument to measure gaseous nitrous acid (HONO) in the atmosphere, *Environ. Sci. Technol.*, *35*, 3207–3212.
- Hoffmann, M. R., S. T. Martin, W. Choi, and D. W. Bahnemann (1995), Environmental applications of semiconductor photocatalysis, *Chem. Rev.*, *95*, 69–96.
- Karagulian, F., and M. J. Rossi (2005), The heterogeneous chemical kinetics of NO<sub>3</sub> on atmospheric mineral dust surrogates, *Phys. Chem. Chem. Phys.*, *7*, 3150–3162.
- Kleffmann, J. (2007), Daytime sources of nitrous acid (HONO) in the atmospheric boundary layer, *Chem. Phys. Chem.*, *8*, 1137–1144.
- Kutsuna, S., M. Toma, K. Takeuchi, and T. Ibusuki (1999), Photocatalytic degradation of some methyl perfluoroalkyl ethers on TiO<sub>2</sub> particles in air: The dependence on the dark-adsorption, the products, and the implication for a possible tropospheric sink, *Environ. Sci. Technol.*, *33*, 1071–1076.
- Umann, B., F. Arnold, C. Schaal, M. Hanke, J. Uecker, H. Aufmhoff, Y. Balkanski, and R. Van Dingenen (2005), Interaction of mineral dust with gas phase nitric acid and sulfur dioxide during the MINATROC II field campaign: First estimate of the uptake coefficient  $\gamma_{\text{HNO}_3}$  from atmospheric data, *J. Geophys. Res.*, *110*, D22306, doi:10.1029/2005JD005906.
- Underwood, G. M., C. H. Song, M. Phadnis, G. R. Carmichael, and V. H. Grassian (2001), Heterogeneous reactions of NO<sub>2</sub> and HNO<sub>3</sub> on oxides and mineral dust: A combined laboratory and modeling study, *J. Geophys. Res.*, *106*, 18,055–18,066.
- Usher, C. R., A. E. Michel, and V. H. Grassian (2003), Reactions on mineral dust, *Chem. Rev.*, *103*, 4883–4939.
- Vlasenko, A., S. Sjogren, E. Weingartner, H. W. Gaggeler, and M. Ammann (2005), Generation of submicron Arizona test dust aerosol: Chemical and hygroscopic properties, *Aerosol Sci. Technol.*, *39*, 452–460.
- Yumoto, H., S. Matsudo, and K. Akashi (2002), Photocatalytic decomposition of NO<sub>2</sub> on TiO<sub>2</sub> films prepared by arc ion plating, *Vacuum*, *65*, 509–514.
- M. Ammann and K. Stemmler, Laboratory of Radio- and Environmental Chemistry, Paul Scherrer Institute, CH-5232 Villigen, Switzerland.
- Y. Balkanski, Laboratoire des Sciences du Climat et l'Environnement, CEA-CNRS-UVSQ, F-91191 Gif-sur-Yvette Cedex, France.
- B. D'Anna, C. George, and M. Ndour, IRCELYON, UMR5256, Université de Lyon, CNRS, F-69626 Villeurbanne, France. (christian.george@ircelyon.univ-lyon1.fr)
- O. Ka, Physics Department, University Cheikh Anta Diop, Dakar-Fann, Senegal.
- J. Kleffmann, Physikalische Chemie/FB C, Bergische Universität Wuppertal, D-42097 Wuppertal, Germany.