



HAL
open science

Magnetocaloric effect in the ternary silicide Gd_3NiSi_2

Sophie Tencé, Stéphane Gorsse, Etienne Gaudin, Bernard Chevalier

► **To cite this version:**

Sophie Tencé, Stéphane Gorsse, Etienne Gaudin, Bernard Chevalier. Magnetocaloric effect in the ternary silicide Gd_3NiSi_2 . *Intermetallics*, 2009, 17 (3), pp.115-119. 10.1016/j.intermet.2008.10.004 . hal-00358130

HAL Id: hal-00358130

<https://hal.science/hal-00358130v1>

Submitted on 24 May 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Magnetocaloric effect in the ternary silicide Gd_3NiSi_2

S. Tencé^{a,b}, S. Gorse^a, E. Gaudin^a, B. Chevalier^{a,*}

^aCNRS, Université de Bordeaux, ICMCB, 87 avenue du Docteur Albert Schweitzer, 33608 Pessac Cedex, France

^bCEA, IRAMIS, LLB, 91191 Gif-sur-Yvette Cedex, France

A B S T R A C T

Gd_3NiSi_2 annealed sample has been investigated by magnetization, electrical resistivity and specific heat measurements. This study reveals its ferromagnetic behavior below $T_C = 215$ K; only the gadolinium carries a magnetic moment with a saturation magnetization of $7.19 \mu_B/\text{Gd mol}$. Gd_3NiSi_2 exhibits a magnetocaloric effect higher in magnetic entropy change than the one recently reported for $\text{Gd}_6\text{Ni}_5/3\text{Si}_3$. This ternary silicide can be obtained as metallic ribbons where the structural disordering modifies strongly its magnetocaloric properties.

1. Introduction

It is well known that some binary compounds existing in the Gd–Si and Gd–Ni systems present interesting magnetocaloric effect (MCE). These materials can be used in the magnetic refrigeration which is a promising alternative to conventional gas compression refrigeration [1–3]. For instance, the binary silicide Gd_5Si_4 which orders ferromagnetically below $T_C = 335$ K [4], a Curie temperature higher than that reported for gadolinium ($T_C = 291$ K), shows an adiabatic temperature change $\Delta T_{\text{ad}} = 3.1$ K in a magnetic field of 1.92 T [5]. These data suggest that Gd_5Si_4 as Gd is an interesting candidate as magnetic refrigerant in the vicinity of room temperature. Moreover, the antiferromagnet Gd_3Ni ($T_N = 99$ K) which has the highest Gd content among the compounds existing in the Gd–Ni system, is considered as a potential magnetic refrigerant material [6]. Considering these studies, it is interesting to investigate the magnetocaloric properties of the ternary compounds existing in the Gd–Ni–Si system and rich in gadolinium (50% or more in order to minimize the inactive thermal mass of solid).

At this day, two ternary silicides $\text{Gd}_6\text{Ni}_5/3\text{Si}_3$ and Gd_3NiSi_2 correspond to the criterion defined above. The former, recently discovered by us, exhibits magnetocaloric properties [7]. It orders ferromagnetically at $T_C = 310$ K and exhibits an interesting adiabatic temperature change of $\Delta T = 3.1$ K in a magnetic field of 2 T. This value is comparable to that observed for Gd_5Si_4 . The second, Gd_3NiSi_2 was synthesized and characterized by X-ray diffraction by

Klepp and Parthé [8] but no investigation of its magnetic properties was performed. In this paper, we present and discuss the study of Gd_3NiSi_2 by magnetization, electrical resistivity and specific heat measurements. Its magnetocaloric properties are compared to those reported for intermetallics being connected to the Gd–Ni–Si system. Moreover, in order to study the influence of the structural disorder on the magnetocaloric properties of Gd_3NiSi_2 , we have prepared by melt-spinning technique metallic ribbons which have been characterized by magnetization measurements. The ferromagnetic materials presenting structural disorder are attractive for application as magnetic refrigerants [9,10]. For instance, the tailorable nature of their ordering magnetic temperature results from this disordering [11,12].

2. Experimental details

A polycrystalline Gd_3NiSi_2 sample was synthesized by arc-melting a stoichiometric mixture of pure elements (purity above 99.9%) in a high-purity argon atmosphere. Then, the sample was turned and remelted several times to ensure homogeneity; the maximum weight loss due to the melting process was equal to 0.2%. Annealing was done for one month at 1073 K by enclosing the sample (*annealed sample*) in an evacuated quartz tube. A part of this sample was then remelted in a quartz tube under a high-purity argon atmosphere and quenched (melt-spinning technique) onto a rotating copper wheel with a surface speed of about 40 m/s. The obtained ribbons were roughly 20–30 μm thick and 3 mm wide. The structural properties of annealed sample and ribbons were investigated by X-ray powder diffraction (Philips 1050-diffractometer and $\text{Cu K}\alpha$ radiation).

* Corresponding author. Tel.: +33 5 40006336; fax: +33 5 40002761.
E-mail address: chevalie@icmcb-bordeaux.cnrs.fr (B. Chevalier).

Magnetization measurements were performed on a powder, screened at 100 μm , of the annealed sample and ribbon using a Superconducting Quantum Interference Device (SQUID) magnetometer in the temperature range 1.8–350 K and applied fields up to 4.6 T. The two powders were loaded in a paraffin resin in order to immobilize the randomly oriented particles during the magnetization measurements. Electrical resistivity was measured only on the annealed sample (a bar of $1.5 \times 1.5 \times 5 \text{ mm}^3$) with a standard four probe method with silver paint contacts and a current of 10 mA in a temperature range 4.2–300 K. Heat capacity measurements were realized only on the annealed sample by a relaxation method with a Quantum Design PPMS system and using a two-tau model analysis. Data were taken in the 1.8–290 K temperature range. For these latter measurements, the sample was a plate of 10.8 mg weight obtained from the annealed sample. Finally, the very small thickness of the ribbons does not allow us to investigate with good accuracy their thermal properties.

3. Results and discussion

Fig. 1 displays the typical X-ray powder patterns of Gd_3NiSi_2 samples obtained after annealing or melt-spinning process. The investigation of the annealed sample detects no parasitic phase and confirms that this ternary silicide crystallizes in the orthorhombic $Pnma$ space group with the refined unit cell parameters $a = 11.410 \text{ \AA}$, $b = 4.158 \text{ \AA}$ and $c = 11.322 \text{ \AA}$ which agree with those reported previously (see JCPDS no. 72-0218) [8]. The XRD pattern of the ribbons reveals only the presence of Gd_3NiSi_2 (the investigation of the ribbons by microprobe analysis confirms their chemical homogeneity); this ternary silicide is stable after melting and rapid quenching. It is noted that the peaks of this last pattern are broadened and smaller than that observed for the annealed sample. This suggests the formation in the ribbon of a fine microstructure and a structural disordering; but the melt-spinning technique used here, does not allow to obtain an amorphous phase of Gd_3NiSi_2 . Mean crystallites sizes (D_C) forming the ribbon, were quantified by the Scherrer equation without a separation of strain: $D_C = \lambda / (\beta \cos \theta)$, where λ is wavelength of radiation ($\text{Cu K}\alpha$), β the parameter of the broadening of the diffraction line, and θ the diffraction angle. The errors were estimated to be $\Delta D_C \cong 10\%$. The crystallite sizes were about $D_C = 9 \text{ nm}$ in the Gd_3NiSi_2 ribbon whereas $D_C = 20 \text{ nm}$ for the annealed sample.

Fig. 2 shows the temperature dependence of the magnetization M measured in an applied magnetic field $\mu_0 H = 0.05 \text{ T}$ for the




Fig. 1. X-ray powder patterns of Gd_3NiSi_2 obtained after annealing (top) or after melt-spinning (bottom). For clarity, the Miller indexes are only given for $2\theta < 35^\circ$.




Fig. 2. Temperature dependence of the magnetization M measured in an applied magnetic field of $\mu_0 H = 0.05 \text{ T}$ for Gd_3NiSi_2 annealed sample. The inset presents the temperature dependence of the reciprocal magnetic susceptibility χ_m^{-1} , measured with $\mu_0 H = 1.5 \text{ T}$ (the solid line corresponds to the Curie-Weiss law as indicated in the text).

ternary silicide Gd_3NiSi_2 (annealed sample). This curve $M(T)$ presents a sharp increase of M at the Curie temperature $T_C = 215 \text{ K}$ (temperature defined as the maximum in the derivative curve $\partial(M)/\partial T$ versus T). This T_C -temperature is smaller than that reported recently for the ternary compound $\text{Gd}_6\text{Ni}_{5/3}\text{Si}_3$ ($T_C = 310 \text{ K}$) [7]. The curve $M(T)$ exhibits also a small shoulder around 60–70 K attributed to the binary silicide Gd_5Si_3 impurities, not detected by X-ray powder diffraction, which order magnetically in this temperature range [13]. The temperature dependence of the reciprocal magnetic susceptibility χ_m^{-1} of Gd_3NiSi_2 (inset of Fig. 2) follows above 275 K, a Curie-Weiss law (solid line) with $\theta_p = 234 \text{ K}$ as a positive paramagnetic Curie temperature and $\mu_{\text{eff}} = 7.98 \mu_B/\text{Gd mol}$ as magnetic effective moment. This last value is close to that calculated for a free Gd^{3+} ion ($7.94 \mu_B$) and indicates that the magnetic contribution of Ni species is negligible. A similar remark was previously reported for the $\text{Gd}_6\text{Ni}_{5/3}\text{Si}_3$ ternary compound [7].

The ferromagnetic character of Gd_3NiSi_2 annealed sample is confirmed by the field dependence of its magnetization M below T_C (Fig. 3(a)). M initially increases rapidly then tends to saturate at high fields. Below T_C , for instance at 6 K as shown in Fig. 3(b), this annealed sample behaves as a soft magnet with negligible coercivity and remanence. This behavior associated to the isotropic character of Gd^{3+} -ion is interesting for magnetic refrigeration. At 6 K, the measured saturation moment is $21.58 \mu_B \text{ mol}^{-1}$ or $7.19 \mu_B$ by Gd mol. This last value is slightly higher than that calculated $g_{\text{J}} = 7.00 \mu_B$ (g_{J} is the Landé factor and J the total angular momentum) for Gd^{3+} ion but is comparable to that reported for the binary compound Gd_3Ni ($7.21 \mu_B$ by Gd mol) [6] or the ternary silicide $\text{Gd}_6\text{Ni}_{5/3}\text{Si}_3$ ($7.10 \mu_B$ by Gd mol) [7]. A similar excess in the saturation moment was previously reported for the silicides ($\text{Gd}_x\text{Tb}_{5-x}$) Si_4 [14], this excess was thought to be due to the contribution from the gadolinium 5d electrons resulting from the charge transfer between Gd sites and their neighboring ions. Finally, we note that M just above T_C , for instance at 230 K (Fig. 3(a)), does not vary linearly with the applied magnetic field. This observation indicates the existence of short-range magnetic correlations above T_C .




Fig. 3. Field dependence of the magnetization of Gd_3NiSi_2 annealed sample at (a) various temperatures and (b) 6 K.

The existence of a ferromagnetic transition for Gd_3NiSi_2 is confirmed by the temperature dependence of its reduced electrical resistivity presented in Fig. 4. A sudden change of slope is detected at 214 K (the temperature where the derivative curve $\partial\rho/\partial T$ versus T exhibits a peak), in agreement with the T_C value extracted from the magnetization measurements. The decrease of $\rho(T)$ below 214 K could be associated with the loss of spin disorder scattering of the conduction electrons owing to the appearance of a ferromagnetic transition. At low temperatures, below 35 K, $\rho(T)$ data can be represented by a T^2 function (inset of Fig. 4) in reasonable agreement with the quadratic temperature dependence expected for ferromagnetic material. Above 35 K, $\rho(T)$ increases continuously but deviates from the linear dependence which characterizes the normal metals. A similar negative curvature of $\rho(T)$ curve below T_C




Fig. 4. Temperature dependence of the reduced electrical resistivity of Gd_3NiSi_2 (annealed sample). The inset presents the T^2 dependence of the resistivity at low temperature $T < 35$ K (the solid line shows the linear dependence).

was observed recently for the other ternary silicide $\text{Gd}_6\text{Co}_{1.67}\text{Si}_3$ [15]. This deviation detected in many compounds based on rare-earth elements [16] is attributed to the high value of their resistivity; the mean free path is short, of the order of a few interatomic distances.

The temperature dependence of the specific heat C_p of Gd_3NiSi_2 (annealed sample) is shown in Fig. 5. The sharp λ -type maximum on the specific heat curve at 213 K agrees with the T_C Curie temperature of this ternary silicide determined above by magnetization and electrical resistivity measurements. The shape of the peak is typical for a second-order phase transition. At low




Fig. 5. The heat capacity C_p of Gd_3NiSi_2 (annealed sample) between 1.8 and 290 K.

temperatures, below 18 K, the C_p/T versus T curve follows the Debye low-temperature approximation given by $C_p/T = \gamma + \beta T^2$ where γ is the contribution from the conduction electron and β is the lattice contribution [17]. The fitting of C_p/T data yields to an electronic coefficient $\gamma \cong 20 \text{ mJ/Gd mol K}^2$ which characterizes a metal.

The temperature dependence of the magnetization M of Gd_3NiSi_2 ribbon was measured as for the annealed sample at $\mu_0 H = 0.05 \text{ T}$ in zero-field-cooled (ZFC) and field-cooled (FC) modes; no irreversibility was detected by this measurement. The curve $M(T)$ relative to the ribbon presents a different behavior (Fig. 6): a brutal but small increase occurs around 215 K (the T_C temperature of the annealed sample) then between 200 and 6 K, $M(T)$ increases continuously with decreasing temperature. This measurement suggests that the ribbons contain two crystallographic forms of Gd_3NiSi_2 ; one is crystallized involving an increase of M around 215 K and the other presents a great atomic disorder inducing a random distribution of the magnetic interactions leading to a progressive increase of M below 200 K. A similar behavior of $M(T)$ was reported for Gd-based melt-spun ribbons [10] and for GdAl_2 treated by high-energy-ball milling [18]. For low milling time, this GdAl_2 sample contains an ordered ferromagnet phase and also an atomically disordered nanocrystalline material. Finally, we note that the magnetization at 6 K and at $\mu_0 H = 0.05 \text{ T}$ ($M = 7.64 \mu_B$ by $\text{Gd}_3\text{NiSi}_2 \text{ mol}$) for the ribbon is higher than that determined in similar conditions for the annealed sample ($M = 2.70 \mu_B$ by $\text{Gd}_3\text{NiSi}_2 \text{ mol}$) (Figs. 2 and 6). At 6 K, M for the ribbons increases more rapidly at low applied magnetic field which explains this difference (inset of Fig. 6); certainly this difference is induced by the nanocrystalline character of the ribbon.

At 6 K, the field dependence of the magnetization M for ribbon reveals no magnetic hysteresis (see inset of Fig. 6). M for this sample does not saturate in a field of 4.6 T unlike to that observed for the annealed sample (Fig. 3). Moreover the measured moment $18.40 \mu_B \text{ mol}^{-1}$ or $6.13 \mu_B$ by Gd mol is smaller than that determined for the annealed sample ($7.19 \mu_B$ by Gd mol). This difference could be associated to the presence of the atomically disordered nanocrystalline phase in the ribbon: (i) the excess of the magnetic moment by Gd-atom observed for the annealed sample and linked




Fig. 6. Temperature dependence of the magnetization M measured in an applied magnetic field of $\mu_0 H = 0.05 \text{ T}$ for Gd_3NiSi_2 ribbon. The inset presents the field dependence at 6 K of the magnetization of this sample.




Fig. 7. Temperature dependence at $\mu_0 H = 2$ and 4.6 T of the magnetic entropy change for Gd_3NiSi_2 annealed sample and ribbon.

to the charge transfer between Gd sites and their neighboring ions disappears in this phase since it is disordered and (ii) moreover, this disorder will certainly change the number of nearest Gd-Gd neighbors and the relative distance between Gd atoms. This will probably cause a change of the direction of Gd moment from the originally parallel alignment (ferromagnet) to a randomly distributed configuration (antiferromagnetic interactions become possible); in these conditions a decrease of M is possible below T_C .

In order to determine the magnetocaloric properties of Gd_3NiSi_2 annealed sample, its magnetization M was measured versus temperature between 140 and 260 K by step of 5 K and for applied field between 0 and 4.6 T by step of 0.15 T. The magnetic entropy change was calculated using the Maxwell formula, $\Delta S_M = \int_0^{\mu_0 H} [\partial M / \partial T]_{\mu_0 H} d\mu_0 H$, and the adiabatic temperature change, ΔT_{ad} ,




Fig. 8. Temperature dependence of the adiabatic temperature change for Gd_3NiSi_2 annealed sample.

Table 1

Curie temperature, peak entropy change and adiabatic temperature change at $\Delta H = 2$ T for Gd_3NiSi_2 annealed and ribbon and others related materials.

	T_C (K)	ΔS_M (J/kg K)	ΔT_{ad} (K)	$\Delta T_{ad}/T_C$	Ref.
Gd_3NiSi_2 annealed	215	-3.6	2.7	0.013	Present work
Gd_3NiSi_2 ribbon	215	-2.0	-	-	Present work
$Gd_6Ni_{5/3}Si_3$	310	-2.9	3.1	0.010	[7]
$Gd_6Co_{5/3}Si_3$	294	-2.8	3.0	0.010	[7]
Gd_7Pd_3	318	-2.5	-	-	[21]
Gd	294	-5.1	5.7	0.019	[22]

linked to the magnetocaloric effect was expressed as $\Delta T_{ad}(T; 0 \rightarrow \mu_0 H) = -T/C_0(T)\Delta S_M(T; 0 \rightarrow \mu_0 H)$, where $C_0(T)$ is the heat capacity at zero field. As reported in Refs. [19,20], this indirect determination of the magnetocaloric properties is only an approximation; in some cases, the accuracy is in the range 20–30%.

Figs. 7 and 8 show the temperature dependence of ΔS_M and ΔT_{ad} , respectively, for Gd_3NiSi_2 annealed sample. The curves of $\Delta S_M(T)$ and $\Delta T_{ad}(T)$ present one single peak at 215 and 220 K, respectively. The peak entropy change, ΔS_M^{PEAK} , reaches -3.6 and -6.3 $J\,kg^{-1}\,K^{-1}$, and the peak adiabatic temperature change, ΔT_{ad}^{PEAK} , is 2.7 and 5.0 K for a field change of 2 and 4.6 T, respectively. Comparable values were observed for others ternary silicides and intermetallics based on gadolinium, as shown in Table 1. $|\Delta S_M|$ of Gd_3NiSi_2 annealed sample is higher than to those obtained for $Gd_6Ni_{5/3}Si_3$ and $Gd_6Co_{5/3}Si_3$ [7]. Also the value of the comparative ratio $\Delta T_{ad}/T_C$ for this annealed sample is higher than those reported for the other ternary silicides but lower than that reported for pure gadolinium (Table 1).

The magnetic entropy change of Gd_3NiSi_2 ribbon (Fig. 7) was also evaluated from a series of isothermal $M(\mu_0 H)$ curves using the Maxwell formula. In addition to the peak at 215 K associated to the magnetic transition of the crystallized form of Gd_3NiSi_2 as observed for the annealed sample, the curve $\Delta S_M(T)$ relative to the ribbon exhibits a broad minimum between 50 and 150 K which can be attributed to the disordered form of Gd_3NiSi_2 . The Gd_3NiSi_2 ribbons exhibit lower peak value of $\Delta S_M = -3.8$ $J\,kg^{-1}\,K^{-1}$ for $\mu_0 H = 4.6$ T but a magnetocaloric effect that spans over a larger temperature range of approximately 200 K. Comparable behavior of $\Delta S_M(T)$ curve was obtained recently for Gd-based melt-spun ribbons made of crystallized nanoparticles embedded into a disordered amorphous matrix [10]. As the full width at half minimum, δT_{FWHM} , of $\Delta S_M(T)$ curve for the ribbon is greater than that of the annealed sample, thus giving rise to large relative cooling power (RCP) values of 890 and 390 $J\,kg^{-1}$ for $\mu_0 H = 4.6$ and 2 T estimated from the product of $|\Delta S_M^{PEAK}| \times \delta T_{FWHM}$. These RCP values are, respectively, 570 and 200 $J\,kg^{-1}$ at the same magnetic fields for the annealed sample. This comparison shows the interest in magnetic refrigeration to obtain sample in ribbon form.

4. Conclusion

The ternary silicide Gd_3NiSi_2 , presents a ferromagnetic ordering at 215 K. This behavior is associated with a magnetocaloric effect higher than that observed for the other ternary compound $Gd_6Ni_{5/3}Si_3$ existing in the Gd–Ni–Si system. Moreover, the synthesis of

Gd_3NiSi_2 as metallic ribbons leads to obtain a mixture containing two crystallographic forms of Gd_3NiSi_2 (one is crystallized and the other presents a great atomic disorder inducing a random distribution of the magnetic interactions) and to extend the temperature range where this compound can be used as magnetic refrigerant.

Acknowledgements

The authors would like to thank R. Decourt for his assistance during the specific heat measurements. Authors are indebted to the Conseil Régional d'Aquitaine for financial support; especially S.T. for a Ph.D. stipend. Also, this work was supported by the CNRS through the Exploratory program RM2 PE1.8-13.

References

- [1] Pecharsky VK, Gschneidner Jr KA. Advanced magnetocaloric materials: what does the future hold? *Int J Refrigeration* 2006;29:1239–49.
- [2] Brück E. Developments in magnetocaloric refrigeration. *J Phys D Appl Phys* 2005;38:R381–91.
- [3] Yu BF, Gao Q, Zhang B, Meng XZ, Chen Z. Review on research of room temperature magnetic refrigeration. *Int J Refrigeration* 2003;26:622–36.
- [4] Pecharsky VK, Gschneidner Jr KA. Tunable magnetic regenerator alloys with a giant magnetocaloric effect for magnetic refrigeration from ~ 20 to ~ 290 K. *Appl Phys Lett* 1997;70:3299–301.
- [5] Shimotomai S, Ido H. Magnetocaloric effect in $Gd_{5-x}Dy_xSi_4$ compounds. *J Appl Phys* 2006;99:08Q109–Q109-3.
- [6] Tripathy SK, Suresh KG, Nigam AK. A comparative study of the magnetocaloric effect in Gd_3Co and Gd_3Ni . *J Magn Magn Mater* 2006;306:24–9.
- [7] Gaudin E, Tencé S, Weill F, Rodriguez Fernandez J, Chevalier B. Structural and magnetocaloric properties of the ternary silicides $Gd_6M_{5/3}Si_3$ with $M = Co$ and Ni . *Chem Mater* 2008;20:2972–9.
- [8] Klepp K, Parthé E. Orthorhombic gadolinium nickel silicide Gd_3NiSi_2 with a filled-up Hf_2P_2 structure type. *Acta Crystallogr B* 1981;37:1500–4.
- [9] Gorsse S, Orveillon G, Chevalier B. Magnetic behavior and magnetocaloric effect of neodymium-based amorphous alloy. *J Appl Phys* 2008;103:044902–044902-6.
- [10] Gorsse S, Chevalier B, Orveillon G. Magnetocaloric effect and refrigeration capacity in $Gd_{60}Al_{10}Mn_{30}$ nanocomposite. *Appl Phys Lett* 2008;92:122501–122501-3.
- [11] Chevalier B, Bobet J-L, Sánchez Marcos J, Rodriguez Fernandez J, Gómez Sal JC. Magnetocaloric properties of amorphous $GdNiAl$ obtained by mechanical grinding. *Appl Phys A* 2005;80:601–6.
- [12] Franco V, Blázquez JS, Millán M, Borrego JM, Conde CF, Conde A. The magnetocaloric effect in soft magnetic amorphous alloys. *J Appl Phys* 2007;101:09C503–C503-3.
- [13] Canepa F, Cirafici S, Napolitano M. Magnetic properties of Gd_5T_3 intermetallic compounds ($T = Si, Ge, Sn$). *J Alloys Compd* 2002;335:L1–4.
- [14] Spichkin YI, Pecharsky VK, Gschneidner Jr KA. Preparation, crystal structure, magnetic and magnetothermal properties of $(Gd_xR_{5-x})Si_4$, where $R = Pr$ and Tb , alloys. *J Appl Phys* 2001;89:1738–45.
- [15] Gaudin E, Weill F, Chevalier B. Structural, magnetic and electrical properties of the ternary silicide $Gd_6Co_{1.67}Si_3$ derived from the hexagonal $Ho_4Co_{3.07}$ (or $Ho_6Co_{4.61}$) type structure. *Z Naturforsch* 2006;61b:825–32.
- [16] Patil NG, Ghosh K, Ramakrishnan S. Superconductivity and magnetism in the $La_{2-x}Nd_xRh_3Si_5$ system. *Phys Rev B* 1995;52:9679–90.
- [17] Gopal ESR. Specific heats at low temperatures. New York: Plenum; 1966.
- [18] Zhou GF, Bakker H. Mechanically induced structural and magnetic changes in the $GdAl_2$ Laves phase. *Phys Rev B* 1995;52:9437–45.
- [19] Pecharsky VK, Gschneidner Jr KA. Magnetocaloric effect from indirect measurements: magnetization and heat capacity. *J Appl Phys* 1999;86:565–75.
- [20] Pecharsky VK, Gschneidner Jr KA. Some common misconceptions concerning magnetic refrigerant materials. *J Appl Phys* 2001;90:4614–22.
- [21] Canepa F, Napolitano M, Cirafici S. Magnetocaloric effect in the intermetallic compound Gd_7Pd_3 . *Intermetallics* 2002;10:731–4.
- [22] Yu Dan'kov S, Tishin AM, Pecharsky VK, Gschneidner Jr KA. Magnetic phase transitions and the magnetothermal properties of gadolinium. *Phys Rev B* 1998;57:3478–90.