



Single Nanostructure Device fabricated by alternative technologies

J. Tallal, T. Pinedo-Rivera, K. Berton, D. Peyrade

► To cite this version:

J. Tallal, T. Pinedo-Rivera, K. Berton, D. Peyrade. Single Nanostructure Device fabricated by alternative technologies. EIPBN - The 51st EIPBN Electron, Ion, Photon Beam Technology and Nanofabrication, May 2007, Denver, United States. hal-00394410

HAL Id: hal-00394410

<https://hal.science/hal-00394410>

Submitted on 3 Oct 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Single-Nanostructure Device fabricated by alternative technologies

J. Tallal, T. Pinedo, K. Berton and D. Peyrade.

Laboratoire des Technologies de la Microélectronique, CNRS,
c/o CEA Grenoble 17, avenue des Martyrs, 38054 Grenoble Cedex, France

E-mail : david.peyrade@cea.fr

Keywords : Nanoimprint lithography, Dielectrophoresis, gold colloids, Single electron transistor

For the last ten years, alternative technologies for nanofabrication and nanostructure localisation/assembly have targeted new approaches for low-cost, high throughput fabrication of single nanostructure devices. For example, NanoImprint Lithography (NIL) ^[1] is now competitive with electron beam lithography for nanopatterning and many novel techniques have already been introduced for manipulation and localization of colloidal nanostructures using chemical functionalization ^[2], capillary forces ^{[3] [4]}, and dielectrophoresis (DEP) ^[5]. In this work, we demonstrate a new strategy to collectively fabricate Single Nanostructure Device (SND) by combining thermal NIL and carefully define an AC-DiElectroPhoresis (AC-DEP) trap.

First, a tri-layer NIL lift-off process detailed elsewhere ^[6] was developed to fabricate metallic nanoelectrodes with connexion pads on a 100 mm wafer using one imprint step (Fig1a). For localisation experiments (Fig.1 (b)), a droplet of gold colloid was deposited over the electrode gap, and the trapping of nanoparticles by AC-DEP was followed using real-time microscopic imaging (Fig.1b). Several dynamical regime were optically identified depending on the applied electric field: Brownian motion regime, Coulomb force regime and AC-dielectrophoresis regime (Fig.2).

The AC-DEP force ($\vec{F}_{DEP} \sim \Re(f_{CM}) \cdot \vec{\nabla} |E|^2$) influences the motion of uncharged polarizable particles in a dielectric medium when a nonuniform electric field is present. Here, $\Re(f_{CM})$ represents the real part of the Clausius-Mosotti (CM) factor, which gives a measure of the dielectric contrast between particles and the surrounding medium. As such, particles can be attracted to the electrodes or repelled from them using only the frequency dependence of $\Re(f_{CM})$. Real-time tracking of nanoparticles was used to determine the transition frequency f_0 where the DEP force shifted from attractive to repulsive behaviour (Fig.3). By working in the attractive regime near f_0 , we show that it is possible to find experimental conditions to trap a single gold particle (200 nm – 50 nm) with a rate of success up to 20% (Fig4.) for the biggest particles sizes. Figure 5 presents SEM pictures of several single nanostructure devices fabricated by this technique. Current-Voltage measurements from a 50 nm gold particle device show coulomb staircase in the temperature regime up to 50 K without any molecular tunnel barrier like observed in other works [2,6].

This talk will highlight electrode fabrication using NIL, real-time imaging and statistical control of the particle trapping process at the single nanostructure level. We will also detail electronic transport on these systems.

[1] S. Y. Chou, Peter R. Kausser *et al.* Appl. Phys. Lett, Vol. 67, p.3114 (1995).

[2] D.L. Klein, R. Roth *et al.* Nature., Vol. 389, p.699 (1997).

[3] Y. Cui, M.T. Björk *et al.* Nano-Letters, Vol. 4 (6), p.1093 (2004).

[4] D. Peyrade, M. Gordon *et al.* Microelectronic Engineering, Vol. 83, p.1521 (2006).

[5] H.A. Pohl. *Dielectrophoresis : The behaviour of Neutral Matter in Nonuniform Electric Fields* (Cambridge University Press, New-York, 1978).

[6] J.Tallal *et al.* J. Vac. Sci. Technol. B **23**, 2914 (2005)

[7] S.H. Hong *et al.* J. Vac. Sci. Technol. B **24**, 136 (2006)






Fig. 1 : Scheme of the nanofabrication process and dielectrophoretic localization experiments.

(a) NIL process for metallic (Ti 5nm /Au 35 nm) nanoelectrodes fabrication on SiO₂ (100nm)/ Si.

(b) Dielectrophoresis experimental set-up for direct imaging of gold colloid trapping.



(a) No electrical field applied (Brownian motion).

(b) DC electric field

(c) AC electric field (f < 1 kHz)

(d) AC electric field (f > 500 kHz)

Fig. 2 : Real time optical observation of 200 nm gold nanoparticles repartition inside the drop.




Fig. 3 : Experimental determination of the real part of the Clausius-Mossotti factor and comparison with a bilayer model.




Fig. 4 : Statistical analysis of the number of particles trapped for different AC-DEP frequencies and for several nanoparticle sizes.




Fig. 5 : SEM pictures of single Au nanoparticle trapping from different sizes by combining nanoimprint lithography and dielectrophoresis.




Fig. 6 : Current-Voltage curves measured for a junction with a single 50 nm Au nanoparticle as a function of the temperature (4K < T < 50K). [inset: SEM picture of the device]