



HAL
open science

Metal organic vapour phase epitaxial growth of indium-rich InGaN alloys with robust photoluminescence properties

M. Moret, S. Ruffenach, O. Briot, B. Gil

► **To cite this version:**

M. Moret, S. Ruffenach, O. Briot, B. Gil. Metal organic vapour phase epitaxial growth of indium-rich InGaN alloys with robust photoluminescence properties. *European Physical Journal: Applied Physics*, 2009, 45 (2), pp.1. 10.1051/epjap/2009007 . hal-00480143

HAL Id: hal-00480143

<https://hal.science/hal-00480143>

Submitted on 3 May 2010

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Metal Organic Vapour Phase Epitaxial growth of indium-rich InGaN alloys with robust photoluminescence properties

M.Moret, S.Ruffenach, O.Briot and B.Gil

Université Montpellier 2 – Groupe d'Etude des Semiconducteurs (UMR CNRS 5650) case courrier 0.74 – 34095 Montpellier cedex 5 - FRANCE

ABSTRACT :

We report the growth of indium-rich InGaN alloys by Metal-Organic Vapour Phase Epitaxy, using ammonia, trimethylgallium and trimethylindium as precursors. Compared to indium nitride, our alloy samples present substantial photoluminescence robustness with temperature. The analysis of the optical properties of these samples versus temperature indicates the existence of two non radiative recombination channels: one with a thermal activation temperature of 77 K and another one with an activation temperature ranging from 300K for InN up to 640K for $\text{In}_{0.72}\text{Ga}_{0.28}\text{N}$. The latter competes with the former at low temperatures whilst the former rules the optical properties at ambient conditions.

I. INTRODUCTION

Indium nitride and related heterostructures are promising materials for realizing arsenic-free optoelectronic devices operating in the near infrared portion of the electromagnetic spectrum. The band gap of indium nitride sits at 650 meV¹ and recent demonstrations using the Molecular Beam Epitaxy technique of InN based quantum well heterostructures with quantum confined stark effect²⁻⁴ indicate potential applications of these materials in various field as optical modulators, optical switches and other light emitting /detecting devices. In this paper we report the growth of indium-rich InGaN layers by Metal Organic Vapour Phase Epitaxy with photoluminescence properties robust with temperature as a probe of a fairly reasonable density of non radiative photoluminescence killing centres.

II. SAMPLES GROWTH

The samples were grown by low pressure metal-organic vapour phase epitaxy, using an AIXTRON AIX200/4RF-S reactor. The growth temperature was 550°C and reactor pressure 200 mbar for all samples, with a molar V/III ratio of 15000, in order to prevent any indium droplet formation. Trimethylindium (TMIn) and trimethylgallium (TMGa), provided by SAFC Hitech Limited, were used as group III element precursors, ammonia (NH₃) was the nitrogen source. The InGaN layers were grown using N₂ as carrier gas, since hydrogen damages InN, but hydrogen was used as carrier gas for GaN. The purification of H₂ and N₂, as well as NH₃ was ensured by a complete SAES setup of corresponding purifiers. The different Indium contents were obtained by changing the TMIn/TMGa ratio without changing the total molar flow. The growth rate of InGaN is insensitive to Ga content due to the similar low growth rate of both binaries, which are limited by the low decomposition rate of ammonia. The (In,Ga)N layers thicknesses were measured by SEM and are about 800nm for all the samples.

The InGaN layers were deposited on top of a GaN epilayer (typically 1 μm thickness), deposited onto a sapphire substrate. X ray rocking curve measurements were performed on GaN pseudo-substrate and indicate comparable defects densities in all of them. The samples were characterized by X-Ray diffraction to determine their composition and crystalline quality, the Theta/2theta measurement are displayed Figure 1.

III. PHOTOLUMINESNENCE RESULTS AND MODELISATION

In Figure 2 is reported the evolution of the photoluminescence intensity of an $\text{In}_{0.72}\text{Ga}_{0.28}\text{N}$ layers for temperature ranging from 4 to 300K. An extended InGaAs Detector was used together with a grating blazed at 1.5 μm . The trend is a collapse of the photoluminescence intensity with increasing temperature, as a probe of the presence of non radiative recombination channels in this sample and all other of ours. The figure [shows the robustness](#) of the intensity of the photoluminescence which in case of $\text{In}_{0.72}\text{Ga}_{0.28}\text{N}$ layers decreases by a factor 30 between 4K and room temperature. This collapse scales two decades for high quality InN films. We have recorded the evolution of the energy of the photoluminescence peaks with temperature. We find a red shift of 59 meV and 1 meV for InN and $\text{In}_{0.82}\text{Ga}_{0.18}\text{N}$ layers respectively. In contrast to this, we report observation of a 20 meV blue shift for $\text{In}_{0.72}\text{Ga}_{0.28}\text{N}$ layer. The InN value is comparable with the value reported for best samples in the literature ¹, to the best of our knowledge. Our InN data indicates an initial redshift up to 50K then a weak blue shift and a general trend that is easily fitted using a Varshni equation. This weak S-shape behaviour [is an indication of the weakly localized nature](#) of the excitons or e-h pair ⁵ which recombine at low temperature and a bound to free phase transition near 60K. Concerning the alloys, we are probing the more complex physics of recombination of bound or localized excitons or e-h pairs in strongly disordered systems. It is worthwhile noticing in particular that a simple line shape fitting of the photoluminescence lines performed in order to obtain the maximum of fluorescence energy indicates the onset of blue shift of the photoluminescence line for the 28-percent gallium-rich sample to occurs near 100-120 K (~ 10 meV activation energy) simultaneously when the photoluminescence intensity starts to decrease. We attribute this behaviour to simultaneous detrapping of excitons (or photo-created carriers) from shallow low energy potential fluctuations lakes surrounded by barriers of moderate heights and to their further retrapping to other higher energy regions of the crystal surrounded by higher potential barriers. This behaviour is different from the behaviour that is generally reported for gallium-rich InGaN alloys. There are several reasons to this. First, the value of the band gap bowing parameter is large for InGaN alloys (2.8 eV) ⁶. Fluctuations of the chemical alloy composition give deeper wells for gallium rich alloys than they give for indium-rich ones. The spontaneous production of shallow potential wells by strict chemical disorder is more favourable in case of indium rich alloys than for gallium rich ones. Second, the input parameters used to describe the physics of these materials in the context of quantum mechanics are very different.

This reflects the competition between the average spatial extension of the chemical disorder induced potential fluctuations and the spatial extension of carrier (electrons and holes) wavefunction.

Let us restrict ourselves here to electrons, for the sake of our discussion. The effective mass is very small for InN (0.07) while it is substantially high (0.22) for GaN ¹. Let us consider twenty percent alloy disorders near both ends of the full composition range. Effective mass arguments tell us that an electron can probe a more extended crystal region in the case of an indium-rich alloy than it would do it in case of a gallium rich one. Therefore the carrier trapping - detrapping processes are a priori more complicated for indium-rich alloys than they are for gallium-rich ones. This will be inferred later in this paper. We now examine the behaviour of the emitted photoluminescence intensity with increasing temperature. In the most general way, the photoluminescence intensity of excitons or e-h pairs is given by the following proportionality relation:

$$I \propto \frac{\tau}{\tau_{rad}} \quad \text{(Equation 1)}$$

, where τ is the photoluminescence decay time, τ_{rad} is the radiative photoluminescence decay time. Further introducing the non radiative part τ_{nr} of the decay time in equation 1 we get:

$$I(T) \propto \frac{\tau_{nr}}{\tau_{nr} + \tau_{rad}} = \frac{1}{1 + \frac{\tau_{rad}}{\tau_{nr}}} \quad \text{(Equation 2)}$$

Statistical physics arguments tell us that τ_{rad} is proportional to $T^{n/2}$ where n is the dimensionality of the crystal. Integer $n = 3$ in a bulk, 2 for a quantum well, 1 for a quantum wire and 0 for a zero dimensional confining centre (quantum dot or 3D localizing centre). The non radiative recombination channels (we supposed to have several ones) are thermally activated:

$$\frac{1}{\tau_{nr}}(T) = \sum_i \frac{1}{\tau_i}(T) \quad \text{(Equation 3)}$$

In general, the evolution of photoluminescence intensity is fitted in the context of an Arrhenius plot, that is to say by plotting the logarithm of the intensity versus the reciprocal temperature in order to obtain in a more or less readable manner, from the intensity behaviour at high

temperatures an activation temperature T_i that rules the non radiative recombination channel i. This gives a rough estimate of what happens. A complementary approach consists in adding to this a fit of the linear dependence of the photoluminescence intensity in order to correctly describe the complex statistics physics in the range of temperatures where radiative and non radiative recombination channels do compete. From the behaviour of the sample with 28 percents gallium we immediately remark the clear need to introduce two non radiative recombination channels in order to fit the experiment. This means that we have to handle the following equation:

$$I(T) \propto \frac{1}{1 + Ae^{\frac{T_0}{T}} + Be^{\frac{T_1}{T}}} \quad (\text{Equation 4})$$

, where A, B, T_0 and T_1 are fitting parameters.

Table 1 indicates the result of the full fitting procedure. The remarkable result is the constant value we get for $T_0 = 77$ K which correspond to an activation energy of some 6.6 meV. It is worthwhile noticing that this weak activation energy corresponds to the detrapping energy we always observe in our InN samples. Next we remark that T_1 increases with the alloy composition from 300 K (26 meV) for InN up to 640 K (55 meV) for $\text{In}_{0.72}\text{Ga}_{0.28}\text{N}$.

In Figures 3 and 4 are reported the results of the fitting procedures in the context of the reciprocal and direct temperatures respectively. A complementary plot which gives the evolution of the ratio: $(B/A)e^{(T_1-T_0)/T}$ for these samples is shown in Figure 5 where one can clearly see that the robustness of the photoluminescence in InGaN layers is correlated with the high values reached by this ratio at high temperatures: the relative values of A and B are such that the low temperature T_0 activated process does not dominate. Although it is difficult to make some more deterministic physics we have to remark in Table 1 the large values of B and their increase with increasing the alloy composition. This clearly indicates (having in mind that τ_{rad} is essentially a function of material parameters like the effective masses, the dielectric constant, ...; that is to say having in mind that τ_{rad} does not vary so much in these samples), that the characteristics non radiative decay time τ_1 decreases when increasing the alloy composition. This is consistent with: i) our X-ray diffraction patterns which are slightly worse for the alloy than it is for the binary compound as an indication of an increasing number of topological defects with increasing the alloy composition and:

ii) the behaviour of the absolute intensities of the photoluminescence features taken at 4K which decrease with increasing the alloy composition.

IV. CONCLUSION

In conclusion, this work reports the promising observation of the robustness of the photoluminescence intensity with temperature for indium-rich InGaN alloys grown by Metal Organic Vapour Phase Epitaxy (as far as we are aware the materials produced by Molecular beam Epitaxy do not exhibit this robustness). This demonstration indicates that this growth technique has reached a sufficient [degree of maturity to provide samples with interesting](#) optical properties in a near future. Further and unavoidable improvements of the crystalline quality of these materials will then open the way towards realization of heterostructures based on InN and related alloys, with remarkable and broad fields of application in the near infrared region.

This work was supported by the European Commission under the Sixth Framework Program (STREP project "INDOT", Contract No. NMP4-CT-2005-016956).

References:

- 1 For a general review, see for instance: W. Walukiewicz, S.X. Li, J. Wu, K.M. Yu, J.W. Ager, E.E. Haller, H. Lu, W.J. Schaff *J.Cryst growth*, 269 , 119,(2004)
- 2 M. Kurouchi, H. Naoi, T. Araki,Miyajima, and Y. Nanishi, *Jpn. J. Appl. Phys.*,44, L230 (2005).
- 3 T. Onashi, P. Holmström, A. Kikuchi and K. Kishino, *Appl. Phys. Lett.* 89, 041907 (2006).
- 4 S.-B. Che, T. Minuno, X. Wang, Y. Ishitani and A. Yoshikawa, *J. Appl. Phys.* 102, 083539 (2007).
- 5 S.Chichibu, Y.Kawakami and T.Soda, in "introduction to nitride semiconductor blue lasers and light emitting diodes", edited by S.Nakamura and S.Chichibu, Taylor and Francis, New ork, ISBN 0-7484-0836-3, 153, (2000)
- 6 V.Yu Davydov , A.A.Klochikhin, V.V. Emtsev, S.V. Ivanov, V.V.Vekshin , F.Bechstedt,J.Furthmuller, H.Harima , A.V.Mudryi , A.Hashimoto, .Yamamoto, J.Aderhold, J.Graul, ,E.E. Haller, *Physica Status Solidi (b)* R4, 330, (2002)
- 7 S. Pereira, M.R. Correia, T. Monteiro, E. Pereira, E. Alves, A.D. Sequeira, and N.Franco, *Appl. Phys Lett* 78, 2137, (2001)
- 8 W. Shan, W. Walukiewicz, E.E. Haller, B.D. Little, J.J. Song, M.D. McCluskey, N.M.Johnson, Z.C.Feng, M. Schurman, and R.A. Stall, *J. Appl. Phys* 84 , 4452, (1998)
- 9 J. Wu, W. Walukiewicz, K. M. Yu, J. W. Ager III, E. E. Haller, Hai Lu, and William J.Schaff., *Appl. Phys. Lett.* 80 4741, (2002).




Figure 1: theta-2theta X-ray diffraction features




Figure 2: Evolution of the photoluminescence spectra of $\text{In}_{0.72}\text{Ga}_{0.28}\text{N}$ layers with temperature




Figure 3: plot of the photoluminescence intensity versus reciprocal temperature




Figure 4: Plot of the photoluminescence intensity versus temperature.




Figure 5: relative amplitudes of the non radiative [recombination](#) channels

Table I: Summary of the fitting procedure and correlation function between the fit and the data

TABLE I	A	To (K)	B	T ₁ (K)	Correlation
InN	4.9 ± 0.5	77 ± 3	93 ± 14	304 ± 16	0.99958
In _{0.82} Ga _{0.18} N	2.4 ± 0.3	77 ± 5	66 ± 15	400 ± 30	0.99834
In _{0.72} Ga _{0.28} N	0.8 ± 0.1	78 ± 7	156 ± 31	638 ± 30	0.99801