



HAL
open science

Influence of ball milling on quasicrystal formation in melt-spun Zr-based glassy ribbons

Sergio Scudino, J Eckert, Hergen Breitzke, Klaus Lüders, Ludwig Schultz

► **To cite this version:**

Sergio Scudino, J Eckert, Hergen Breitzke, Klaus Lüders, Ludwig Schultz. Influence of ball milling on quasicrystal formation in melt-spun Zr-based glassy ribbons. *Philosophical Magazine*, 2005, 86 (03-05), pp.367-371. 10.1080/14786430500228499 . hal-00513557

HAL Id: hal-00513557

<https://hal.science/hal-00513557>

Submitted on 1 Sep 2010

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Influence of ball milling on quasicrystal formation in melt-spun Zr-based glassy ribbons

Journal:	<i>Philosophical Magazine & Philosophical Magazine Letters</i>
Manuscript ID:	TPHM-05-Apr-0123
Journal Selection:	Philosophical Magazine
Date Submitted by the Author:	28-Apr-2005
Complete List of Authors:	Scudino, Sergio; IFW Dresden, Institut für Metallische Werkstoffe Eckert, J; Technische Universität Darmstadt, FB 11 Material- und Geowissenschaften Breitzke, Hergen; Freie Universität Berlin, Fachbereich Physik Lüders, Klaus; Freie Universität Berlin, Fachbereich Physik Schultz, Ludwig; IFW Dresden, Institut für Metallische Werkstoffe
Keywords:	metallic glasses, quasicrystals, ball-milling
Keywords (user supplied):	



Influence of ball milling on quasicrystal formation in melt-spun Zr-based glassy ribbons

S. SCUDINO^{1*}, J. ECKERT², H. BREITZKE³, K. LÜDERS³ and L. SCHULTZ¹

¹ IFW Dresden, Institut für Metallische Werkstoffe, Postfach 270016, D-01171 Dresden, Germany

² FG Physikalische Metallkunde, FB 11 Material- und Geowissenschaften, Technische Universität Darmstadt, Petersenstraße 23, D-64287 Darmstadt, Germany

³ Fachbereich Physik, Freie Universität Berlin, Arnimallee 14, D-14195 Berlin, Germany.

Abstract

The effect of mechanical deformation on the formation of quasicrystals in $\text{Zr}_{57}\text{Ti}_8\text{Nb}_{2.5}\text{Cu}_{13.9}\text{Ni}_{11.1}\text{Al}_{7.5}$ glassy ribbons has been investigated. The mechanical treatment drastically affects the crystallization behavior and, in particular, suppresses primary quasicrystal formation. However, quasicrystals can be formed by the addition of the appropriate amount of zirconium. This indicates that if a particular short-range (e.g., icosahedral) is required for quasicrystal formation and if this short-range order is altered during milling, it can be restored by appropriately adjusting the chemical composition.

Keywords: glasses, quasicrystals, ball milling.

* Email: s.scudino@ifw-dresden.de

1. Introduction

More than fifty years ago Frank [1] proposed that metallic liquids might be characterized by an icosahedral short-range order (SRO). Another state of matter that is believed to possess icosahedral SRO is the glassy state [2,3]. The degree of icosahedral SRO is predicted to increase with increasing undercooling of the liquid [4]. Since metallic glasses may be considered as deeply undercooled liquids, it has been proposed that in glassy alloys the SRO characterizing the liquid may be quenched-in during vitrification [5]. This may subsequently promote the formation of quasicrystals (QC) upon crystallization of the glass. Recently, this assumption has been corroborated by Saida *et al.* [6] who observed a change of the primary devitrification product from quasicrystalline to *big cube* phase upon ball milling. The authors proposed that the distortion due to the mechanical treatment induces changes in the local icosahedral structure in the glassy state and, therefore, leads to a different crystallization behavior. However, QC formation directly during mechanical alloying has been reported for Al-based alloys [7] and recently in solid-state synthesized Zr-based glassy powders, which undergo QC formation upon crystallization [8,9]. This indicates that the SRO responsible for QC formation can be achieved also by solid-state reaction with no need of quenching from the melt.

In this work, this aspect has been further investigated by studying the influence of mechanical deformation on QC formation for melt-spun $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ glassy ribbons. The ribbons were subjected to ball milling up to the suppression of QC formation. The results demonstrate that the suppression of QC formation can be reversed by an appropriate variation of the chemical composition.

2. Experimental

Ribbons with a cross section of about $0.05 \times 3 \text{ mm}^2$ were prepared in a single-roller Bühler melt spinner at a wheel velocity of 14.3 m s^{-1} from pre-alloyed arc-melted ingots with

1
2
3 nominal composition $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$. Milling experiments starting from the
4
5 melt-spun $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ ribbons were performed using a Retsch PM400
6
7 planetary ball mill and hardened steel balls and vials. All sample handling was carried out in a
8
9 glove box under purified argon atmosphere (less than 1 ppm O_2 and H_2O). The ribbons were
10
11 milled for 100 h at a ball-to-powder mass ratio of 13:1 using a milling speed of 150 rpm. The
12
13 oxygen content, evaluated by carrier gas hot extraction, was found to be about 0.18 wt.%. The
14
15 microstructure was characterized by X-ray diffraction (XRD) ($Co K_{\alpha}$ radiation) and by
16
17 transmission electron microscopy (TEM). The thermal stability of the samples was
18
19 investigated by differential scanning calorimetry (DSC) at $40 K min^{-1}$ heating rate under a
20
21 continuous flow of purified argon.
22
23
24
25
26
27
28
29

30 **3. Results and discussion**

31
32 The characterization of the melt-spun $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ ribbon has been
33
34 reported elsewhere [10,11]. However, some key features have to be quoted here. The as-spun
35
36 ribbon is amorphous and is characterized by a multi-step crystallization behavior in which the
37
38 primary phase formed is a metastable icosahedral quasicrystalline phase of nanometer-scale
39
40 dimensions [10,11].
41
42

43 Fig. 1(a) shows the XRD pattern of $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ ribbons after milling for
44
45 100 h. The mechanical deformation does not induce crystallization, as shown by the XRD
46
47 pattern, which displays the diffuse diffraction maxima typical of amorphous materials.
48
49 However, the DSC scan ($40 K min^{-1}$) of the ball-milled (BM) ribbon (Fig. 2) shows some
50
51 differences with respect to the as-spun $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ ribbon [11]. The
52
53 exothermic DSC peaks are broader and are characterized by a convergent shift compared with
54
55 the parent as-spun material [11], which gives rise to a partial overlapping of the exothermic
56
57 signals. The values of T_g and T_{x1} are higher (646 and 703 K, respectively) than for the as-spun
58
59 ribbon (637 and 682 K, respectively), indicating that the mechanical treatment enhances the
60

1
2
3 thermal stability against crystallization. Finally, the crystallization enthalpy related to the first
4 exothermic DSC peak of the ribbon milled for 100 h (13.3 Jg^{-1}) is lower compared to the as-
5 spun ribbon [11], suggesting a decrease of the crystallized volume fraction.
6
7
8
9

10 The XRD pattern for the BM ribbon heated up to completion of the first crystallization
11 event is presented in Fig. 1(b). The diffraction peaks belonging to the QC phase
12 characterizing the XRD pattern of the as-spun ribbon [11] are no longer visible. Instead, the
13 XRD pattern shows extremely broad diffraction peaks, corresponding to an unidentified phase
14 of nanoscale dimensions, superimposed on the amorphous haloes.
15
16
17
18
19
20
21

22 It has been reported that the lack of QC formation in mechanically alloyed (MA)
23 $\text{Zr}_{62}\text{Ti}_{7.07}\text{Nb}_{2.21}\text{Cu}_{12.28}\text{Ni}_{9.81}\text{Al}_{6.63}$ glassy powders is due to preferential oxidation of Zr during
24 milling, which shifts the composition of the glassy phase outside of the range suitable for QC
25 formation [9]. If an adequate amount of elemental Zr is added, the oxidation drawback can be
26 bypassed and the MA glassy powders undergo QC formation upon crystallization [9].
27 Consequently, oxygen contamination might also be the reason for the suppression of QC
28 formation in the BM ribbon.
29
30
31
32
33
34
35
36
37

38 In order to test this hypothesis, 5 at.% elemental Zr was added to the BM ribbon.
39 Subsequently, the material was milled for 100 h at 150 rpm. The addition of elemental Zr to
40 the BM ribbon considerably alters the thermal stability as well as the microstructure evolution
41 of the material. The DSC scan of the BM ribbon + Zr is shown in Fig. 2. The partial
42 overlapping of the exothermic DSC peaks characterizing the BM ribbon is no longer
43 observable and the crystallization events are clearly resolved. The values of T_g and T_{x1} are
44 found to be decreased (612 and 660 K, respectively) with respect to the parent materials and
45 the value of the crystallization enthalpy (26.4 Jg^{-1}) is similar to that of the as-spun ribbon [11],
46 suggesting a similar transformed volume fraction. When the BM ribbon + Zr is heated above
47 the first crystallization event the XRD pattern [Fig. 1(d)] reveals the formation of a phase that,
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3 according to the scheme of Bancel *et al.* [12], can be indexed as an icosahedral
4
5 quasicrystalline phase with quasilattice constant $a_q = 0.480$ nm.
6
7

8 The icosahedral structure of the first crystallization product was corroborated by TEM
9
10 investigations. Fig. 3 shows a bright-field TEM image of the BM ribbon + Zr after heating up
11
12 to the completion of the first exothermic DSC peak. It reveals a homogeneous distribution of
13
14 particles with a size on the order of 10 - 20 nm. The electron diffraction pattern taken from the
15
16 precipitated particles is presented in the inset in Fig. 3. The pattern clearly exhibits five-fold
17
18 rotational symmetry. The distances between the diffraction spots along the radial directions
19
20 are related each to other by $\tau = (1 + \sqrt{5})/2$, the golden mean. In addition, the angles between
21
22 the spots are $2\pi/10 = 36^\circ$. This confirms the results from XRD, corroborating that the
23
24 particles precipitated in the first crystallization event have an icosahedral structure.
25
26
27
28
29
30
31

32 4. Conclusions

33
34 Mechanical treatment suppresses the formation of quasicrystals in melt-spun
35
36 $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ glassy ribbons. The suppression of QC formation due to the
37
38 mechanical deformation can be reversed by adequately adjusting the chemical composition.
39
40 These findings indicate that quasicrystal formation in the ball-milled ribbon is crucially linked
41
42 to the chemical composition rather than to the question whether there is a special quenched-in
43
44 short-range order.
45
46
47
48
49
50

51 Acknowledgements

52
53 The authors would like to thank M. Frey and H. Schulze for technical assistance, J. Acker and
54
55 W. Gruner for chemical analysis and C. Mickel for help with the TEM investigations. This
56
57 work was supported by the German Science Foundation under grants Ec 111/10-1,2 and Lu
58
59 217/17-1,2.
60

References

- 1
2
3
4
5
6 [1] F.C. Frank, Proc. R. Soc. London A **215** 43 (1952).
7
8 [2] S. Sachdev and D. R. Nelson, Phys. Rev. B **32** 4592 (1985).
9
10 [3] H. Jönsson and H. Andersen, Phys. Rev. Lett. **60** 2295 (1988).
11
12 [4] P.J. Steinhardt, D.R. Nelson, and M. Ronchetti, Phys. Rev. B **28** 784 (1983).
13
14 [5] Y. Shen, S.J. Poon, and G. Shiflet, Phys. Rev. B **34** 3516 (1986).
15
16 [6] J. Saida, M. S. El-Eskandarany, and A. Inoue, Scripta Mater. **48** 1397 (2003).
17
18 [7] J. Eckert, L. Schultz, and K. Urban, Appl. Phys. Lett. **55** 117 (1989).
19
20 [8] S. Scudino, J. Eckert, U. Kühn, and L. Schultz, Appl. Phys. Lett. **83** 2345 (2003).
21
22 [9] S. Scudino, C. Mickel, L. Schultz, J. Eckert, X. Y. Yang, and D. J. Sordelet, Appl. Phys.
23
24 Lett. **85** 4349 (2004).
25
26 [10] U. Kühn, J. Eckert, and L. Schultz, Appl. Phys. Lett. **77** 3176 (2000).
27
28 [11] S. Scudino, U. Kühn, L. Schultz, D. Nagahama, K. Hono, and J. Eckert, J. Appl. Phys. **95**
29
30 3397 (2004).
31
32 [12] P.A. Bancel, P.A. Heiney, P.W. Stephens, A.I. Goldman, and P.M. Horn, Phys. Rev.
33
34 Lett. **54** 2422 (1985).
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Figure captions

Figure 1. XRD patterns (Co K_{α} radiation) for: (a) as-milled $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ glassy ribbon milled for 100 h, (b) $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ ribbon milled for 100 h heated up to the completion of the first exothermic DSC event, (c) as-prepared $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ ribbon milled for 100 h + 5 at.% Zr and (d) $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ ribbon milled for 100 h + 5 at.% Zr heated to completion of the first exothermic DSC event.

Figure 2. DSC traces (heating rate 40 K min^{-1}) for: $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ glassy ribbon milled for 100 h and $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ ribbon milled for 100 h + 5 at.% Zr.

Figure 3. TEM image and corresponding diffraction pattern of the $Zr_{57}Ti_8Nb_{2.5}Cu_{13.9}Ni_{11.1}Al_{7.5}$ ribbon milled for 100 h + Zr heated to completion of the first exothermic DSC event.




Figure 1




Figure 2

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60




Figure 3

ew Only