



HAL
open science

SPIN-GLASS BEHAVIOUR OF NOVEL TERNARY URANIUM ALUMINIDE $U_3Co_4 + xAl_{12-x}$ ($x=0.55$)

Olivier Tougait, Robert Troc, Andrzej Zaleski, Henri Noel

► **To cite this version:**

Olivier Tougait, Robert Troc, Andrzej Zaleski, Henri Noel. SPIN-GLASS BEHAVIOUR OF NOVEL TERNARY URANIUM ALUMINIDE $U_3Co_4 + xAl_{12-x}$ ($x=0.55$). Philosophical Magazine, 2006, 87 (07), pp.1085-1095. 10.1080/14786430601026479 . hal-00513790

HAL Id: hal-00513790

<https://hal.science/hal-00513790>

Submitted on 1 Sep 2010

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



SPIN-GLASS BEHAVIOUR OF NOVEL TERNARY URANIUM ALUMINIDE $U_3Co_4 + xAl_{12-x}$ ($x=0.55$)

Journal:	<i>Philosophical Magazine & Philosophical Magazine Letters</i>
Manuscript ID:	TPHM-06-Jul-0264.R1
Journal Selection:	Philosophical Magazine
Date Submitted by the Author:	21-Sep-2006
Complete List of Authors:	Tougait, Olivier; Sciences Chimiques de Rennes, UMR 6226 CNRS-Universite de Rennes 1, Avenue du General Leclerc, Chemini Troc, Robert; Institute of Low Temperature and Structure Research Polish Academy of Sciences, Department of Magnetic Investigation Zaleski, Andrzej; Institute of Low Temperature and Structure Research Polish Academy of Sciences, Superconduction Noel, Henri; Sciences Chimiques de Rennes, UMR 6226 CNRS-Universite de Rennes 1, Avenue du Général Leclerc, 35042 Rennes, France, Chimique
Keywords:	actinides, magnetic properties, transport properties
Keywords (user supplied):	spin-glass behaviour






Figure 1
575x399mm (150 x 150 DPI)




Figure 3
576x403mm (150 x 150 DPI)




Figure 4
400x574mm (150 x 150 DPI)




Figure 5
400x574mm (150 x 150 DPI)

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60




Figure 6
574x400mm (150 x 150 DPI)




Figure 7
403x577mm (150 x 150 DPI)




Figure 8
577x403mm (150 x 150 DPI)