



HAL
open science

Discussion of the Surface Science of Quasicrystals

Patricia Thiel

► **To cite this version:**

Patricia Thiel. Discussion of the Surface Science of Quasicrystals. Philosophical Magazine, 2008, 88 (13-15), pp.2123-2129. 10.1080/14786430802186973 . hal-00513904


HAL Id: hal-00513904

<https://hal.science/hal-00513904>

Submitted on 1 Sep 2010

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Discussion of the Surface Science of Quasicrystals

Journal:	<i>Philosophical Magazine & Philosophical Magazine Letters</i>
Manuscript ID:	TPHM-08-Mar-0086.R1
Journal Selection:	Philosophical Magazine
Date Submitted by the Author:	30-Apr-2008
Complete List of Authors:	Thiel, Patricia; Iowa State University, Department of Chemistry
Keywords:	quasicrystals, surface physics
Keywords (user supplied):	quasicrystals, surface physics



Only

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Discussion of the Surface Science of Quasicrystals

Patricia A. Thiel

Ames Laboratory and Department of Chemistry, Iowa State University

Ames, IA 50011 USA

Abstract. This paper contains a short review of four aspects the surface science of quasicrystals, together with a challenging list of open questions to be addressed by the scientific community in the near future. The first issue concerns the ability of surface science to shed light on bulk atomic structure. The second is the use of surfaces as quasiperiodic templates, particularly for films of periodic metals. Here, enforcing quasiperiodicity in the film may lead to unusual magnetic, tribological, or adsorption properties. The third concerns the effects of surface phasons and phonons on dynamical interactions with adsorbates, such as sticking coefficient, as well as on diffusion between the surface and near-surface region. The final area is tribology, where studies of quasicrystals have suggested that both adhesion and phononic friction may be important.

Introduction.

At the recent conference “Quasicrystals—The Silver Jubilee”, a discussion panel consisting of Julian Ledieu, Vincent Fournée, Ronan McGrath, and Pat Thiel was asked (by the conference Chair, Ron Lifshitz) to consider the following questions:

1. In what ways can surfaces be more useful in testing the validity of structural models?
2. Using surfaces as quasiperiodic templates - just a toy or useful for something?
3. What are the potential effects of surface phonons/phasons on surface structure or properties?
4. Tribology - What have quasicrystals taught us that can be extrapolated to other materials?

This article is by no means an accurate record of the discussion that ensued, but is very much motivated by it. It reflects the author’s own views on the subject, and is provided here in the hope that it will inspire new research and lead to exciting discoveries.

1. Structural models.

In recent years, our community has been intrigued by the possibility that surface science may be able to help distinguish between different bulk structure models. This is because beautiful detail is provided by STM images, and this detail can be correlated with atomic arrangements in bulk structural models[1-4]. Both local motifs and longer-

1
2
3 range tilings have been examined. However, there has been no attempt to use the STM
4
5 data to distinguish between different models. There have been several successful attempts
6
7 to correlate an individual set of data with an individual model, but in each case the
8
9 question remained unanswered: Would a different model have provided a better or worse
10
11 fit?
12
13

14
15 Another complication is illustrated by the well-studied 5-fold surface of
16
17 icosahedral Al-Pd-Mn. Within a given model, there are two main families of possible
18
19 surface terminations [5]. At this point, the identity of the family remains controversial.
20
21 Papadopolos et al. argue in favor of a family in which cut Bergmans are a dominant motif
22
23 [6]. Krajci et al. choose the other family, in which cut Mackays are a dominant motif,
24
25 based on DFT [7]. The problem illustrated here is that uncertainty about the structural
26
27 model is convoluted with uncertainty about the type of preferred termination. This
28
29 problem exists mainly for the icosahedral phases.
30
31
32
33

34 At the Conference, the opinion was expressed that surface science in fact will not
35
36 be able to distinguish between different models. This may be too pessimistic, since the
37
38 different models differ significantly in their chemical decorations. Focusing on the
39
40 chemical decorations of local motifs—local adsorption sites—may be a successful
41
42 strategy. (The results would, however, be subject to uncertainty from the possibility of
43
44 surface segregation or selective depletion by evaporation.) How can the chemical
45
46 decorations of local motifs be measured? One approach might be to use adsorbates that
47
48 are sensitive to chemical environment to probe the adsorption sites, which is a strategy
49
50 that has been used successfully at bimetallic surfaces of periodic crystals [8].
51
52
53
54
55
56
57
58
59
60

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

In considering data from experimental surface science, it must be kept in mind that there are two main types of techniques. First are those that provide information that is averaged over a macroscopic surface area, typically 1-4 mm². Such an area includes many terraces. This category includes LEED, XPD, and LEIS. Second are those that provide microscopic information about individual features in real space. Chief among these is STM, providing information on the sub-nanometer scale. In STM, the main challenge is that of obtaining statistically-significant information about local motifs, and about characteristics of different terraces on a surface. While STM provides beautiful local detail at high magnification, that detail is lost at the low magnifications that are most useful for statistical averaging. It is important to know the degree to which surface features observed in STM are representative! Overcoming this problem is possible, but it is time-consuming and difficult, and there has been little attempt to do so to date. In the discussion at the Conference, it was noted that there may also be a strong bias introduced by the natural tendency of the experimentalists to choose the most beautiful STM images for publication; it is conceivable that some types of terraces do not image as well as others.

2. Quasiperiodic templates.

One intriguing possibility for using quasicrystals as templates, is in growth of magnetic films. Theoretical work has predicted unusual magnetic structures associated with quasiperiodicity [9-13]. To date, the search for quasiperiodic structure in films of magnetic metals has been intense, but unsuccessful. Studies of Fe, Ni, and Co deposited on d-Al-Ni-Co and i-Al-Pd-Mn have shown that the deposited metal either intermixes

1
2
3 with the substrate [14-16] [17], or otherwise fails to adopt quasiperiodic structure on the
4
5 atomic scale as would be necessary to test the theoretical predictions [18-21] [17]. This
6
7 has been disappointing, given that a number of other studies had reported pseudomorphic
8
9 growth, either short-range or long-range, of non-magnetic adsorbates on quasicrystals
10
11 [22-25] [17, 26], and it was naturally expected that pseudomorphism would be found in at
12
13 least some magnetic adsorbates as well.
14
15

16
17 However, it is possible that pseudomorphic growth can still be achieved by tuning
18
19 growth variables, namely flux and deposition temperature, along with their temporal
20
21 variation. These control the kinetics of formation of local structures, and they have not
22
23 yet been exploited in magnetic film growth. An especially interesting aspect of the
24
25 kinetics of film growth is the influence of specific adsorption sites acting as trap sites
26
27 [27], which may especially favor local pseudomorphic nucleation. Another possibility
28
29 for controlling growth is the use of surfactants. As an example, fluorine suppresses
30
31 interdiffusion when Fe films are grown on Cu, and the F can be removed cleanly by
32
33 electron stimulated desorption after growth [28]. Some work exploring the effect of In as
34
35 a surfactant in Au and Pt films on d-Al-Ni-Co quasicrystals has been reported. There, the
36
37 system is apparently dominated by the formation of Au-Al or Pt-Al surface alloys, and
38
39 the In surfactant did not prevent this, [29-33] although one can speculate that other
40
41 surfactants might be more effective.
42
43
44
45
46
47

48 Quasicrystals may also be useful as templates for non-magnetic pseudomorphic
49
50 films, in order to test whether basic properties are adopted by the pseudomorphic film.
51
52 Recent results show that a pseudomorphic monolayer of Pb on five-fold i-Al-Pd-Mn
53
54 exhibits an electronic pseudogap, which is an important result [25]. It would also be very
55
56
57
58
59
60

1
2
3 interesting to test friction forces on a pseudomorphic quasicrystalline film, to determine
4 whether the low friction associated with the substrate propagates to the film. Finally, the
5 adsorption properties of pseudomorphic films would be of significant interest; one report
6 has appeared recently on this subject [17], for C₆₀ adsorbed on a pseudomorphic Pb film
7 on d-Al-Ni-Co. Here, the adsorbate formed a hexagonal lattice, indicating that the
8 corrugation of the potential energy surface is sufficiently weak that adsorbate-adsorbate
9 interactions dominate. However, much remains to be explored, including not just the
10 static structure but also the adsorption dynamics as mentioned in the following section.
11
12
13
14
15
16
17
18
19
20
21
22
23
24

25 **3. Phonons and phasons.**

26
27 The effect of phonons and phasons at surfaces of quasicrystals has received some
28 attention [34-38], but relative to atomic or electronic structure the level of scrutiny has
29 been small. There are at least two surface phenomena that could be affected by these
30 types of dynamics: Mass transport between the surface and the bulk; and energy
31 dissipation at surfaces.
32
33
34
35
36
37

38
39 Phasons may facilitate mass transport between the surface and the bulk. Phasons
40 play a role in bulk self-diffusion, since measurements of diffusivity in i-Al-Pd-Mn have
41 been interpreted to mean that for some metals (Pd and Au), diffusion is assisted by
42 collective phason flips involving many (20 to 30) atoms [39]. This was based upon an
43 Arrhenius analysis of the diffusivity for these elements. The Arrhenius representation of
44 the data consisted of two straight lines intersecting at 720 K, indicating different
45 processes, with the low-temperature process (assigned as phason-assisted diffusion)
46 having a lower activation barrier and an extremely low pre-exponential factor. Very
47
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3 similar behavior was observed, and a similar interpretation was given, in a study of Al
4 migration from the bulk to the surface of i-Al-Cu-Fe [34]. In the latter work, migration
5 of Al to the surface was triggered by exposure to oxygen, which caused selective
6 oxidation of Al at the surface. The Arrhenius plot of the rate of Al diffusion showed two
7 straight lines intersecting at 770 K. From this, an activation barrier of 0.6 eV was
8 estimated for phason-flip transport of Al below 770 K. This barrier was at least a factor
9 of 2 lower than the barrier for normal vacancy-mediated self-diffusion of Al. Recently,
10 another study showed that when Pd and Mn were deposited on the surface of i-Al-Pd-Mn
11 and then were allowed to diffuse into the bulk by heating above room temperature,
12 diffusion into the bulk was characterized by anomalously low activation barriers. These
13 low barriers were attributed to phasons as well [38]. Overall, the evidence for phason-
14 assisted diffusion between surfaces of quasicrystals and the underlying bulk is tantalizing.

15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
Phason and phonon excitations represent channels of energy dissipation, both in
the bulk and at the surface. Energy dissipation at surfaces affects phenomena as diverse
as spectroscopic linewidths, adsorption probabilities (sticking coefficients), ballistic
diffusion, and tribological friction [40]. Spectroscopic linewidths of adsorbates on
surfaces are determined by the lifetimes of excited states, which in turn are determined by
the surface's efficiency in quenching the excited states. Sticking coefficients depend, in
some circumstances, on the ability of the surface to absorb the translational or other
energy components of the incoming gas particle. Ballistic diffusion occurs when an
adsorbate temporarily retains the energy released by the adsorption event, coming to rest
when that energy is absorbed by the substrate. In friction, also, energy dissipation is key.
It is discussed more fully in the following section. Other examples abound [40]. The main

1
2
3 point is that many phenomena in surface chemical dynamics share a common basis in
4 energy dissipation. Hence, any of these phenomena could reflect dynamic peculiarities of
5 quasicrystals that would be important in defining the surface properties of quasicrystals—
6 particularly in terms of their dynamic interactions with adsorbates—yet none has been
7 investigated. Hence, this is an interesting avenue of possible future research.

8
9
10
11
12
13
14
15 It is difficult to predict whether quasicrystals will be relatively more or less
16 efficient in surface energy dissipation. On one hand, phasons represent a channel for
17 energy dissipation that is not available in periodic crystals. On the other hand, there is
18 some expectation that cross sections for phonon excitations at surfaces may be relatively
19 small in quasicrystals [37].

20
21
22
23
24
25
26
27 Phasons themselves present interesting challenges to our understanding of
28 quasicrystals, as discussed by Widom elsewhere in this issue [41].
29
30
31
32
33

34 **4. Tribology.**

35
36 Classically, the friction coefficient, μ , is cast as the sum of two terms: One due to
37 adhesion between the sliding interfaces, and one due to mechanical resistance to
38 formation of the wear track, called ploughing [42]. These two terms alone are not
39 sufficient to account for measured values of μ between unlubricated metals, which leads
40 other factors to be invoked, such as junction growth, and phononic friction (excitation of
41 lattice phonons at the interface). Electronic friction (excitation of electron-hole pairs at
42 the interface) can also play a role, but its contribution is thought to be generally small
43 compared with phononic friction [43-45].
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Quasicrystals exhibit low coefficients of friction in dry sliding, relative to other materials of similar composition [46]. Because quasicrystals are hard, it has sometimes been suggested that their hardness alone may account for their low coefficients of friction [47]. However, over the past several years, there have been two major sets of studies focusing on the fundamental origin of low friction in quasicrystals. Both have pointed to factors other than hardness as being very important. In one set, comparisons were made between quasicrystals and a large group of related metals and oxides [48-55]. The friction coefficient was measured in high vacuum with a pin-on-disc tribometer under carefully standardized conditions. This work showed that the low friction of quasicrystals did not correlate with their hardness, but rather with their reversible work of adhesion when placed in contact with polar liquids. Both the adhesion and the friction coefficient, in turn, showed good correlation with the electronic structure, indicating this as a basic feature responsible for low friction in quasicrystals.

The other set of studies exploited atomic force microscopy to measure friction forces in a single-asperity, elastic contact in ultrahigh vacuum [56-63]. A quasicrystal sample was chosen that was quasiperiodic along one axis in the surface plane, and periodic along the orthogonal axis. Under these experimental conditions, neither adhesion nor hardness could play a role in the difference in friction forces measured in the two directions. On the atomically-clean surface, those friction forces were higher by a factor of eight when sliding occurred parallel to the periodic axis. Consideration of various possible explanations led to the conclusion that phononic or electronic friction were most probably lower in the quasiperiodic direction than the periodic direction. Because

1
2
3 phononic friction is generally thought to outweigh electronic friction, phononic friction
4
5 was concluded to be most viable [44, 45].
6
7

8 Have these two sets of experiments yielded incompatible results? The answer is
9
10 no, but they have certainly yielded different results. They are not incompatible, because
11
12 adhesion and phonon excitation both can contribute to low friction on quasicrystal
13
14 surfaces—they are not mutually exclusive. Their relative importance probably depends
15
16 upon the conditions of sliding, e.g. elastic vs. inelastic contacts [63]. Both studies
17
18 converge in the conclusion that hardness is not the root cause of low friction in
19
20 quasicrystals.
21
22
23

24 Regarding future directions in the tribology of quasicrystals, one opportunity
25
26 stems from the lack of solid evidence from which to decide whether the friction
27
28 anisotropy is due to electronic or phononic friction. This calls for further exploration.
29
30 That may come from molecular dynamics simulations of sliding interfaces [64].
31
32 Molecular dynamics models typically do not include electronic excitations. Thus, if such
33
34 a model can reproduce the friction anisotropy, it will serve as strong evidence for
35
36 phononic friction. This, in turn, will enable predictions of whether materials exhibit low
37
38 friction, from their fundamental properties.
39
40
41
42
43
44

45
46 In summary, many possibilities still exist for exciting fundamental research on the
47
48 surface physics and chemistry of quasicrystals.
49
50
51
52
53
54
55
56
57
58
59
60

Acknowledgments.

The participation of, and contributions by, Julian Ledieu, Ronan McGrath, and Vincent Fournée on the discussion panel at the conference “Quasicrystals—The Silver Jubilee” is gratefully acknowledged. Preparation of this manuscript was supported by the Office of Science, Basic Energy Sciences, Materials Science Division of the U.S. Department of Energy (USDOE). This manuscript has been authored by Iowa State University of Science and Technology under Contract No. DE-AC02-07CH11358 with the U.S. Department of Energy.

References.

- [1] R. McGrath, J. Ledieu, E.J. Cox, R.D. Diehl, J. Phys.: Condens. Matter 14 (2002) R119.
- [2] V. Fournée, P.A. Thiel, J. Phys. D: Appl. Phys. 38 (2005) R83.
- [3] H.R. Sharma, M. Shimoda, A.P. Tsai, Advances in Physics 56 (2007) 403.
- [4] P.A. Thiel, Ann. Rev. Phys. Chem. 59 (2007) 129.
- [5] B. Unal, C. Jenks, P. Thiel, submitted (2008).
- [6] Z. Papadopolos, G. Kasner, J. Ledieu, E.J. Cox, N.V. Richardson, Q. Chen, R.D. Diehl, T.A. Lograsso, A.R. Ross, R. McGrath, Phys. Rev. B 66 (2002) 184207.
- [7] M. Krajci, J. Hafner, J. Ledieu, R. McGrath, Phys. Rev. B 73 (2006) 024202.
- [8] B. Gleich, M. Ruff, R.J. Behm, Surface Sci. 386 (1997) 48.

- 1
2
3 [9] E.Y. Vedmedenko, H.P. Oepen, J. Kirschner, Phys. Rev. Lett. 90 (2003) 137203/1.
4
5
6 [10] E.Y. Vedmedenko, Ferroelectrics 305 (2004) 129.
7
8 [11] E.Y. Vedmedenko, U. Grimm, R. Wiesendanger, Phys. Rev. Lett. 93 (2004)
9 076407/1.
10
11 [12] E.Y. Vedmedenko, Modern Physics Letters B 19 (2005) 1367.
12
13 [13] E.Y. Vedmedenko, U. Grimm, R. Wiesendanger, Phil. Mag. 86 (2006) 733.
14
15 [14] Y. Weisskopf, R. Lüscher, M. Erbudak, Surface Sci. 578 (2005) 35.
16
17 [15] Y. Weisskopf, M. Erbudak, J.-N. Longchamp, T. Michlmayr, Surf. Sci 600 (2006)
18 2594.
19
20 [16] Y. Weisskopf, S. Burkardt, M. Erbudak, J.N. Longchamp, Surf. Sci. 601 (2007)
21 544.
22
23 [17] R. McGrath, This issue (Ordering of adsorbed species on quasicrystal surfaces).
24
25 [18] J.A. Smerdon, J. Ledieu, J.T. Hoefft, D.E. Reid, L.H. Wearing, R.D. Diehl, T.A.
26 Lograsso, A.R. Ross, R. McGrath, Phil. Mag. 86 (2006) 841.
27
28 [19] L.H. Wearing, J.A. Smerdon, L. Leung, T.A. Lograsso, A.R. Ross, R. McGrath,
29 Surf. Sci. 601 (2007) 3450.
30
31 [20] L.H. Wearing, J. Smerdon, L. Leung, S.S. Dhessi, J. Ledieu, P. Bencok, I. Fisher,
32 C.J. Jenks, R. McGrath, J. Phys: Condens. Matter. 20 (2008) 015005.
33
34 [21] S. Burkardt, This issue (Co nanocrystallites on icosahedral Al-Pd-Mn quasicrystal).
35
36 [22] K.J. Franke, H.R. Sharma, W. Theis, P. Gille, P. Ebert, K.H. Rieder, Phys. Rev.
37 Lett. 89 (2002) 156104.
38
39 [23] T. Cai, J. Ledieu, R. McGrath, V. Fournée, T.A. Lograsso, A.R. Ross, P.A. Thiel,
40 Surface Sci. 526 (2003) 115.
41
42 [24] J. Ledieu, J.T. Hoefft, D.E. Reid, J.A. Smerdon, R.D. Diehl, T.A. Lograsso, A.R.
43 Ross, R. McGrath, Phys. Rev. Lett. 92 (2004) 135507.
44
45 [25] J. Ledieu, L. Leung, L.H. Wearing, R. McGrath, T.A. Lograsso, D. Wu, V. Fournée,
46 Los Alamos Natl. Lab., Prepr. Arch., Condens. Matter FIELD Full Journal Title: Los
47 Alamos National Laboratory, Preprint Archive, Condensed Matter (2007) 1.
48
49
50
51
52
53
54
55
56
57
58
59
60

- 1
2
3 [26] K. Pussi, this issue (Low-Energy Electron Diffraction (LEED) Study of an
4 Aperiodic Thin Film of Cu on 5-fold i-Al-Pd-Mn).
5
6
7 [27] B. Unal, V. Fournée, K.J. Schnitzenbaumer, C. Ghosh, C.J. Jenks, A.R. Ross, T.A.
8 Lograsso, J.W. Evans, P.A. Thiel, Phys. Rev. B 75 (2007) 064205.
9
10
11 [28] W.F. Egelhoff, Jr., Surface Sci. 402-404 (1998) 32.
12
13 [29] M. Shimoda, J. Guo, T.J. Sato, A.P. Tsai, Materials Research Society Symposium
14 Proceedings 643 (2001) K11.5.1.
15
16 [30] M. Shimoda, J.Q. Guo, T.J. Sato, A.P. Tsai, Surface Sci. 482-485 (2001) 784.
17
18 [31] M. Shimoda, T.J. Sato, A.P. Tsai, J.Q. Guo, Journal of Alloys and Compounds 342
19 (2002) 441.
20
21 [32] M. Shimoda, T.J. Sato, A.P. Tsai, J.Q. Guo, Surf. Sci. 507-510 (2002) 276.
22
23 [33] M. Shimoda, Prog. Surf. Sci. 75 (2004) 87.
24
25 [34] M. Gil-Gavatz, D. Rouxel, P. Pigeat, B. Weber, J.-M. Dubois, Mater. Res. Soc.
26 Symp. Proc. 553 (1999) 75.
27
28 [35] T. Janssen, O. Radulescu, A.N. Rubtsov, Eur. Phys. J. B 29 (2002) 85.
29
30 [36] H.R. Sharma, K.J. Franke, W. Theis, P. Gille, P. Ebert, K.H. Rieder, Phys. Rev. B
31 68 (2003) 054205/1.
32
33 [37] W. Theis, H.R. Sharma, K.J. Franke, K.H. Rieder, Prog. Surf. Sci. 75 (2004) 227.
34
35 [38] F. Samavat, M. Gladys, C. Jenks, T. Lograsso, B.V. King, D.J. O' Connor, Surf. Sci
36 601 (2007) 5678.
37
38 [39] H. Mehrer, R. Galler, W. Frank, R. Blueher, A. Strohm, in: H.R. Trebin (Ed.),
39 Quasicrystals, Weinheim, 2003, pp. 312.
40
41 [40] J.C. Tully, Annu. Rev. Phys. Chem. 51 (2000) 153.
42
43 [41] A. Widom, This issue (Discussion of phasons in quasicrystals and their dynamics).
44
45 [42] I.M. Hutchings, Tribology: Friction and Wear of Engineering Materials, Boca
46 Raton, Florida, CRC Press, 1992.
47
48 [43] J. Krim, Am. J. Phys. 70 (2002) 890.
49
50 [44] T. Coffey, J. Krim, Phys. Rev. Lett. 95 (2005) 076101.
51
52
53
54
55
56
57
58
59
60

- 1
2
3
4
5 [45] M.S. Tomassone, J.B. Sokoloff, A. Widom, J. Krim, Phys. Rev. Lett. 79 (1997)
6 4798.
7
8 [46] J.M. Dubois, Useful Quasicrystals, Singapore, World Scientific, 2005.
9
10 [47] C.M. Mancinelli, C.J. Jenks, P.A. Thiel, A.J. Gellman, J. Mater. Res. 18 (2003)
11 1447.
12
13 [48] J.-M. Dubois, P. Brunet, W. Costin, A. Merstallinger, J. Non-Cryst. Sol. 334 & 335
14 (2004) 475.
15
16 [49] J.-M. Dubois, M.-C. de Weerd, J. Brenner, Ferroelectrics 305 (2004) 159.
17
18 [50] J.M. Dubois, J. Non-Cryst. Solids 334-335 (2004) 481.
19
20 [51] J.M. Dubois, V. Fournée, E. Belin-Ferré, in: E. Belin-Ferré, M. Feuerbacher, Y.
21 Ishii, D.J. Sordellet (Eds.), Quasicrystals 2003--Preparation, Properties and Applications,
22 Warrendale, Pennsylvania, 2004, pp. 287.
23
24 [52] E. Belin-Ferre, J.M. Dubois, International Journal of Materials Research 97 (2006)
25 985.
26
27 [53] J.M. Dubois, M.C. de Weerd, J. Brenner, M. Sales, G. Mozdzen, A. Merstallinger,
28 E. Belin-Ferre, Phil. Mag. 86 (2006) 797.
29
30 [54] M. Sales, A. Merstallinger, P. Brunet, M.C. de Weerd, V. Khare, G. Traxler, J.M.
31 Dubois, Phil. Mag. 86 (2006) 965.
32
33 [55] E. Belin-Ferre, J.-M. Dubois, Mat. Sci. Eng. A A449-A451 (2007) 971.
34
35 [56] J.Y. Park, D.F. Ogletree, M. Salmeron, C.J. Jenks, P.A. Thiel, Trib. Lett. 17 (2004)
36 629.
37
38 [57] J.Y. Park, D.F. Ogletree, M. Salmeron, R.A. Ribeiro, P.C. Canfield, C.J. Jenks, P.A.
39 Thiel, Phys. Rev. B 71 (2005) 144203.
40
41 [58] J.Y. Park, D.F. Ogletree, M. Salmeron, R.A. Ribeiro, P.C. Canfield, C.J. Jenks, P.A.
42 Thiel, Science 309 (2005) 1354.
43
44 [59] J.Y. Park, D.F. Ogletree, M. Salmeron, R.A. Ribeiro, P.C. Canfield, C.J. Jenks, P.A.
45 Thiel, Phys. Rev. B 72 (2005) 220201/1.
46
47 [60] J.Y. Park, D.F. Ogletree, M. Salmeron, R.A. Ribeiro, P.C. Canfield, C.J. Jenks, P.A.
48 Thiel, Phil. Mag. 86 (2006) 945.
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3 [61] J.Y. Park, D.F. Ogletree, M. Salmeron, R.A. Ribeiro, P.C. Canfield, C.J. Jenks, P.A.
4 Thiel, Phys. Rev. B 74 (2006) 024203.
5

6
7 [62] J.Y. Park, D.F. Ogletree, M. Salmeron, C. Jenks, P. Thiel, J. Brenner, J.M. Dubois,
8 J. Mat. Res. in press (2008).
9

10 [63] J.Y. Park, P.A. Thiel, J. Phys: Condens. Matter. submitted (2008).
11

12 [64] H.M. Harper, D.A. Rabson, in progress (2008).
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60