



HAL
open science

Cell encapsulation using biopolymer gels for regenerative medicine

Nicola C. Hunt, Liam M. Grover

► **To cite this version:**

Nicola C. Hunt, Liam M. Grover. Cell encapsulation using biopolymer gels for regenerative medicine. *Biotechnology Letters*, 2010, 32 (6), pp.733-742. 10.1007/s10529-010-0221-0 . hal-00565436

HAL Id: hal-00565436

<https://hal.science/hal-00565436>

Submitted on 13 Feb 2011

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Cell encapsulation using biopolymer gels for regenerative medicine

Nicola C. Hunt · Liam M. Grover

Received: 1 October 2009 / Revised: 13 January 2010 / Accepted: 18 January 2010 / Published online: 13 February 2010
© Springer Science+Business Media B.V. 2010

Abstract There has been a consistent increase in the mean life expectancy of the population of the developed world over the past century. Healthy life expectancy, however, has not increased concurrently. As a result we are living a larger proportion of our lives in poor health and there is a growing demand for the replacement of diseased and damaged tissues. While traditionally tissue grafts have functioned well for this purpose, the demand for tissue grafts now exceeds the supply. For this reason, research in regenerative medicine is rapidly expanding to cope with this new demand. There is now a trend towards supplying cells with a material in order to expedite the tissue healing process. Hydrogel encapsulation provides cells with a three dimensional environment similar to that experienced *in vivo* and therefore may allow the maintenance of normal cellular function in order to produce tissues similar to those found in the body. In this review we discuss biopolymeric gels that have been used for the encapsulation of mammalian cells for tissue engineering applications as well as a brief overview of cell encapsulation for therapeutic protein production. This review focuses on agarose, alginate, collagen, fibrin, hyaluronic acid and gelatin since they are widely used for cell encapsulation. The literature on the regeneration of

cartilage, bone, ligament, tendon, skin, blood vessels and neural tissues using these materials has been summarised.

Keywords Tissue engineering · Regenerative medicine · Hydrogels · Cell encapsulation · Biomaterials

Introduction

As the mean life expectancy of the developed world has increased, there has been an ever increasing demand for the development of new strategies for the repair of diseased and damaged tissues (Crimmins and Saito 2001). Ceramic, metallic and polymeric materials have been investigated widely for the direct replacement of tissues with good success (Zhang and Webster 2009). While the majority of licensed treatments consist of a synthetic material alone, there is a current trend towards the delivery of cells within the material matrix in order to expedite healing (Kretlow et al. 2009). Much of this work has involved the use of sponge-like scaffold materials exhibiting interconnected porosity (Rosa et al. 2008). Although within such structures, the cells are arranged spatially in three dimensions with respect to one another, they still attach to a two dimensional surface and as such do not exhibit a phenotype that would be expected in native tissue. Since cell

N. C. Hunt · L. M. Grover (✉)
School of Chemical Engineering, University
of Birmingham, Edgbaston B15 2TT, UK
e-mail: l.m.grover@bham.ac.uk

Table 1 Biopolymer gels used for cell encapsulation and tissue regeneration and their key features

Biopolymer	Protein/polysaccharide	Source	Gelation method	Mechanism of degradation	Cell adhesivity
Agarose	Polysaccharide	Seaweed	Thermal	Non-degradable	Low
Alginate			Ionotropic cross-linking	Ion exchange	
Collagen	Protein	Animal/human	Neutralisation	Enzymatic cleavage	High
Fibrin			Proteolytic cleavage		
Gelatin			Thermal		
HA	Polysaccharide		Chemical cross-linking		

HA hyaluronic acid

phenotype is critical to correct healing of the damaged tissue, a number of workers have attempted to deliver cells within a matrix that is more akin to the extracellular matrix (ECM) than sponge-like polymers or ceramics. The structure of a hydrogel is morphologically similar to that of the ECM and when used as an encapsulation medium (Bokharia et al. 2005), it enables the cell population to exhibit phenotypes more similar to those in vivo than when the cells are grown in monolayer culture (Abbott 2003). A vast range of different hydrogel based materials are available with contrasting chemistries which may or may not allow cell attachment (Lee and Mooney 2001). In this review, we discuss approaches that have been taken to repair diseased or damaged tissues using biopolymeric hydrogels for cell encapsulation. We give a basic overview of the most frequently used biopolymer gel materials (Table 1) and also discuss their application in the repair of a number of tissue types.

Biopolymer gels

Alginate

Alginate is a polysaccharide isolated from brown algae which has been used with great success as a wound dressing (Augst et al. 2006) and as a food additive. On dissolution in an aqueous medium, alginate forms a hydrocolloid, which gels ionotropically following the addition of multivalent cations. Alginate is formed from polysaccharides derived from a range of seaweeds found world-wide and consists of a mixture of β -D-mannuronic acid (M) and α -L-guluronic acid residues (Lee and Mooney 2001).

The ratio of M to G blocks can vary significantly depending upon the source of the raw materials used in alginate manufacture. Both cell adhesion and hydrogel stiffness can be influenced by M to G ratio (Wang et al. 2003). Since hydrogel formation occurs following electrostatic interaction between the carboxylic moieties on the G blocks of alginate and multivalent cations, the higher the ratio of G:M, the stiffer the resulting gel. Cell adhesion to alginate gels can be increased by covalently modifying the polymer with molecules such as RGD (Rowley and Mooney 2002).

Fibrin

Fibrin gels occur widely in the human body and are important in haemostasis following injury (Janmey et al. 2009). Fibrin gels form following the cleavage of fibrinogen by thrombin to expose regions on the fibrin molecules that interact allowing self assembly of protofibrils which aggregate and lengthen. At certain points in the fibrin network, branching occurs, which increases the volume of the gel. The presence of RGD motifs within the fibrin network allow cell adhesion and binding of a range of important growth factors. In the presence of mammalian cells, however, fibrin can degrade rapidly due to the localised secretion of proteolytic enzymes (Ye et al. 2000). To overcome this problem fibrin degradation inhibitors and fibrin stabilisers, such as aprotinin, factor XIII and ϵ -amino-*n*-caproic acid, have been added to the gels to maintain the structure over longer time periods (Mol et al. 2005; Park et al. 2005; Ye et al. 2000). Furthermore, the importance of sufficient thrombin and calcium to prevent excessive degradation has been identified (Eyrich et al. 2007).

Collagen

Collagen is the most abundant form of protein in humans, constituting 30% of all protein found in the body. There are 29 different forms of collagen in the body, the most ubiquitous which is type I collagen, which comprises triple α -helices, which in the correct environmental conditions self assemble to form a fibrillar structure (Pachence 1996). The self-assembling tendencies of type I collagen have led to it being used as a hydrogel for use in tissue engineering. Rat tail collagen, for example, may be dispersed in acid medium and when neutralised in culture forms gels which have been widely used since they allow cell adhesion. The two major limitations of collagen-based scaffolds are their weak nature and their extensive contraction by encapsulated cells. One group has sought to address both of these drawbacks by plastic compression of the collagen gel immediately after its formation (Brown et al. 2005).

Gelatin

Gelatin is formed from the hydrolysis of collagen. Two different forms of gelatin with different isoelectric points can be formed depending on the hydrolysis protocol. Gelatin dissolves in water at 60°C then gels as the solution cools to room temperature (Young et al. 2005). Gelatin is widely used in pharmaceutical and medical applications due to its biodegradable nature (Ikada and Tabata 1996; Miyoshi et al. 2005).

Hyaluronic acid

Hyaluronan is found throughout the body in a number of tissues, including skin and cartilage. Colloids of hyaluronic acid (HA) can be gelled by prior chemical modification of hyaluronan with thiols, methacrylates or tyramines, or can be cross-linked in situ using formaldehyde or divinyl sulphone. One of the key advantages of using HA gels for tissue engineering is that their degradation can be mediated by hyaluronidase, an enzyme secreted by a multitude of mammalian cell types (Peppas et al. 2006).

Agarose

Agarose can be formed into a gel that once heated to 90°C forms a polymer solution. When the temperature of this solution is lowered to room temperature gelation will occur. Agarose is used widely in molecular biology and since it is well accepted following implantation it has been evaluated for immunoisolation purposes (Lahooti and Sefton 2000a, b, c). The non-degradable nature of the gel, however, means that it has not been widely used in tissue engineering since scaffold materials used in tissue engineering applications should degrade over time to allow space for accumulation of new tissue.

The application of biopolymer gel encapsulation in regenerative medicine

Cell encapsulation in biopolymer hydrogels was initially investigated for immunoisolation of cells producing therapeutic proteins for treatment of diseases. Some of these studies are summarised in Table 2. More recently, encapsulation of mammalian cells has been used in the regeneration of an array of different tissues. Table 3 summarises a broad cross section of the literature covering the majority of the body tissues. The remainder of the review, however, will focus on the use of biopolymer gels for the encapsulation of cells for use in musculoskeletal, neural, skin, hepatic and cardiovascular tissue engineering.

Musculoskeletal tissue engineering

During embryogenesis musculoskeletal tissue develops from the mesoderm. Mesenchymal stem cells (MSCs) differentiate to form the individual musculoskeletal tissues, which include muscle, cartilage, bone, tendons and ligaments. The musculoskeletal system enables locomotion and with the ageing population, novel approaches to regenerate parts of the musculoskeletal system and therefore restore patient mobility are gaining increasing attention.

Muscle

In myogenesis MSCs differentiate to myoblasts, the muscle cell precursors, which further differentiate

Table 2 Biopolymer gel cell encapsulation for treatment of diseases with non-autologous cells

Biopolymer gel	Encapsulated cell type	Secreted therapeutic protein	Disease treatment	References
Agarose	Islet cells	Insulin	Diabetes	Gazda et al. (2007)
	Kidney cells	Hepatic lipase	Hyperlipidemia	Lahooti and Sefton (2000a)
	Fibroblasts	Alkaline phosphatase	Osteoporosis	Lahooti and Sefton (2000b)
Alginate	Fibroblasts	VEGF	Cardiovascular disease	Keshaw et al. (2005)
	Kidneys cells	Endostatin	Brain tumour	Joki et al. (2001), Read et al. (2001a, b)
	Myoblasts	Human factor IX	Haemophilia	Hortelano et al. (1996)
	Fibroblasts	Human factor IX	Haemophilia	Liu et al. (1993)
	Fibroblasts	Human growth hormone	Dwarfism	Chang et al. (1994)
	Islet cells	Insulin	Diabetes	Calafiore et al. (2006), Soon-Shiong (1999), Zimmermann et al. (2007)
	Collagen	Fibroblasts	Alkaline phosphatase	Osteoporosis

and fuse to form multinucleated myotubes. These myotubes mature into myofibres which bundle together to form the skeletal muscle (Berendse et al. 2003). Encapsulated skeletal myoblasts have been shown to remain viable and differentiate to form myotubules in collagen gel when mechanical conditioning is used after 7 day's culture in vitro. Cell alignment was shown to occur uniaxially in the direction of applied tension (Cheema et al. 2003).

Cartilage

Cartilage is found in joints and prevents bone to bone contact. The tissue consists of mainly chondrocytes and an ECM containing collagens type I and II and aggrecan (Sterodimas et al. 2009). A large amount of research has focussed on tissue engineering cartilage by the encapsulation of chondrocytes in a variety of hydrogels including fibrin, collagen, chitosan and alginate. Chondrocytes encapsulated in fibrin gels have been maintained for 5 weeks in vitro (Park et al. 2005). Park et al. (2005) also showed that addition of HA gel to the fibrin gel may be beneficial since after 4 weeks in vivo culture the degree of contraction was reduced and ECM production was higher in fibrin/HA gels when compared with pure fibrin gels. Chondrocytes encapsulated in pure HA gels have been evaluated both in vivo up to 12 weeks and in vitro up to 2 weeks post-encapsulation. The constructs were shown to maintain or increase in size and encapsulated chondrocytes were shown to

deposit ECM both in vivo and in vitro. The amount of ECM produced was also shown to be enhanced under mechanical loading (Chung et al. 2008).

Chondrocytes encapsulated in collagen and gelatin gels were shown to produce cartilage specific matrix over 21 days in vitro culture. The collagen gel was shown to contract after 1 day and an increase in cell number was observed throughout the first 7 days. The viable cell number however, fell gradually over the subsequent 14 days culture. In contrast, the viability of chondrocytes encapsulated in gelatin hydrogels was maintained, with no significant change in cell number (Hoshikawa et al. 2006). Maintaining the viability of encapsulated chondrocytes can be problematic due to insufficient perfusion of scaffolds with a large volume. The addition of microchannels to polymeric gels has been proven to maintain the viability and function of alginate encapsulated chondrocytes (Choi et al. 2007), and this may prove effective for other polymeric gels.

Ligament and tendon

Tendons and fibroblasts are rich in fibroblasts which secrete ECM containing collagen type I/III, elastin and proteoglycans (Carvalho et al. 2000; Chan and Leong 2008; Cheema et al. 2007; Cleary et al. 1967). Collagen and fibrin gel encapsulation of fibroblasts have been shown to have promise for tissue engineering of tendons and ligaments. Marenzana et al. (2006) showed that tendon fibroblasts encapsulated in

Table 3 A summary of key references from the current literature describing cell encapsulation for the regeneration of a number of tissues

Biopolymer gel	Encapsulated cell type	Engineered tissue	References
Agarose	MSCs	Cartilage	Pelaez et al. (2009)
Alginate	Dorsal root ganglia	Neural	Bellamkonda et al. (1995)
	Fibroblasts	Dermis	Hunt et al. (2009a)
	Chondrocytes	Cartilage	Choi et al. (2006), Hong et al. (2007)
	MSCs	Bone	Smith et al. (2007), Wang et al. (2003)
	Osteoblasts	Bone	Kong et al. (2003)
	Hepatocytes	Liver	Khattak et al. (2007)
	Neural progenitor cells	Neural	Zielinski and Aebischer (1994)
Chitosan	Chondrocytes	Cartilage	Hong et al. (2007)
	Fibroblasts	Neural	Zielinski and Aebischer (1994)
Collagen	Myofibroblasts	Skeletal muscle	Cheema et al. (2003)
	Fibroblasts	Dermis	Brown et al. (2005), Nazhat et al. (2006), Marenzana et al. (2006)
	Fibroblasts	Ligament	Murray et al. (2006)
	Fibroblasts	Tendon	Marenzana et al. (2006)
	Chondrocytes	Cartilage	Hoshikawa et al. (2006)
	Osteosarcoma cells	Bone	Bitar et al. (2007)
	Myofibroblasts	Cardiac muscle	Ye et al. (2000), Birla et al. (2005)
Fibrin	Myofibroblasts	Blood vessel	Mol et al. (2005)
	Smooth muscle cells	Blood vessel	Grassl et al. (2003)
	Fibroblasts	Dermis	Tuan et al. (1996), Brown et al. (1993), Meana et al. (1998), Cox et al. (2004)
	Fibroblasts	Ligament	Chun et al. (2003)
	Keratinocytes	Epidermis	Bannasch et al. (2000, 2008)
	Chondrocytes	Cartilage	Park et al. (2005), Eyrich et al. (2007), Mesa et al. (2006)
	MSCs	Bone	Catelas et al. (2006), Hou et al. (2008)
	Hepatocytes	Liver	Bruns et al. (2005)
	Dorsal root ganglia	Neural	Herbert et al. (1998)
	Urethral cells	Urethra	Bach et al. (2001)
Gelatin	Keratocytes	Corneal stroma	Alaminos et al. (2006)
	Chondrocytes	Cartilage	Hoshikawa et al. (2006)
	Hepatocytes	Liver	Wang et al. (2006)
Hyaluronic acid	Chondrocytes	Cartilage	Chung et al. (2008)
	Dorsal root ganglia	Neural	Horn et al. (2007)

collagen gels attached, spread and were orientated in the parallel to the long axis of the collagen fibrils. The fibroblasts produced tensile forces and remodelled the matrix (Marenzana et al. 2006). Ligament fibroblasts encapsulated in collagen gels proliferated and secreted further collagen up to day 14, then maintained the collagen level and cell number for a further 7 days culture. Gel contraction was seen to occur over the 21 days culture (Murray et al. 2006).

Similarly, ligament fibroblasts encapsulated in fibrin gels have been shown to proliferate, contract the gel and secrete ECM (Chun et al. 2003).

Bone

Bone tissue consists mainly of osteoblast secreted mineralised ECM containing collagen type 1, collagen type IV, fibronectin and heparan sulphate (Narayanan

et al. 2009; Williams et al. 1989). Fibrin gel encapsulation has been investigated as an approach for bone tissue engineering. Where MSCs have been used, their osteogenic differentiation is measured by expression of ALP, osteopontin, bone sialoprotein (BSP), and osteocalcin. MSCs encapsulated in fibrin gel have been shown to proliferate, but at a slower rate than in monolayer culture. Encapsulation was seen to enhance osteogenic differentiation and ECM production, compared with monolayer culture. Mineralised tissue was seen to accumulate in the pores that formed in the fibrin gel, which were surrounded by numerous cells (Hou et al. 2008). Catelas et al. (2006) also showed that MSCs encapsulated in fibrin gels proliferate, show osteogenic differentiation, and secrete mineralised tissue. They, however, observed that the MSCs did not fully differentiate to mature osteoblasts within the 28 days of *in vitro* culture.

Skin

Skin is composed of two anatomically distinct layers known as the epidermis and the dermis. It comprises loose connective tissue rich in collagen type I that contains blood capillaries, smooth muscle fibres, sweat glands and sebaceous glands and their ducts, hair follicles and sensory nerve endings. The epidermis consists mainly of tightly packed stratified keratinocytes upon a basement membrane (Fuchs 2008; MacNeil 2007; Williams et al. 1989). For tissue engineering skin fibrin has been used to encapsulate both fibroblasts, to develop a dermal analogue (Cox et al. 2004; Meana et al. 1998) and keratinocytes to create an epidermal analogue (Bannasch et al. 2000, 2008). Encapsulated fibroblasts were shown to proliferate within the fibrin matrix, but also allow for the stratification of the co-cultured keratinocytes on the surface of the gel both *in vivo* and *in vitro* (Meana et al. 1998). Fibrin-encapsulated keratinocytes applied to the surface of Alloderm produce a continuous epithelium with a cornified layer and basement membrane after 4 weeks *in vivo* (Bannasch et al. 2008).

Brown et al. (2005) and co-workers have shown that plastic compressed collagen gel can be used to encapsulate fibroblasts for tissue engineering the dermis. The compression was only seen to reduce cell viability of encapsulated human dermal fibroblasts by

10% as long as the gel did not become desiccated. A concern when increasing the collagen content of the hydrogel is that diffusion of nutrients and waste products through the scaffold would not be sufficient to maintain cell viability over extended periods of time. To address this problem Nazhat et al. (2007) incorporated micro-channels into the gels using soluble phosphate glass fibres and after 24 h the cell viability of encapsulated fibroblasts was seen to be greater than 80%.

We have shown that fibroblasts encapsulated in alginate hydrogel serve as a dermal analogue allowing for a stratified epithelium to form on the surface of the alginate from the surface seeded keratinocyte co-culture (Hunt et al. 2009a). Furthermore, we have shown that these cells remain mitotically inhibited up to 33 days encapsulation (Hunt et al. 2009b) and that the cells remain viable for at least 150 days encapsulation. The hydrogel was shown to degrade by acellular mechanisms *in vitro* to release the encapsulated fibroblasts, which were seen to subsequently secrete ECM (Hunt et al. 2009a). We have also observed that the alginate is not contracted by the encapsulated fibroblasts, and this may result in reduced detrimental scar contraction which is often seen in large skin wounds (Harrison and MacNeil 2008).

Neural tissue

Chronic neurological diseases and physical injuries can result in loss of neuronal cell bodies, axons and associated glia support. Since the central nervous system has limited or no capacity to replace the lost neurons, there is a significant interest in the engineering of neural tissue (Nisbet et al. 2008). One of the major challenges facing researchers in this area is stimulation of guided axonal extension (Norman et al. 2009). To this end, Horn et al. (2007) encapsulated chick dorsal ganglia in HA and fibrin gels which were evaluated both *in vitro*. Both gels were shown to support neurites within the first 60 h, but after 192 h a 50% increase in neurite length was seen in HA gels when compared with the fibrin gels. Despite this, when the neurons encapsulated in the HA gels were implanted, there was no restoration of spinal cord function. Herbert et al. (1998) also investigated the use of fibrin gels for neural tissue engineering. Encapsulated chick dorsal root ganglia were successfully

maintained in the hydrogels and displayed neurite outgrowth. Bellamkonda et al. (1995) showed that PC12 neural progenitor cells and chick dorsal ganglia encapsulated in agarose also produced neurites of 900 μm in length after 4 days in culture.

Another approach to neural regeneration is the localised and sustained release of nerve growth factor (NGF) to stimulate neural differentiation of precursor cells. For example, Zielinski and Aebischer (1994) have shown that a genetically modified fibroblast cell line provided sustained release of nerve growth factor (NGF) during encapsulation in chitosan hydrogels. The amount of NGF secreted was sufficient to induce the differentiation of co-cultured neural progenitor PC12 cells. The limitation of this approach, however, was that fibroblasts were seen to aggregate and after 2 weeks which resulted in necrosis in the centre of the aggregates.

Liver

Hepatic tissue is formed of hepatocytes which are organized into a polarized epithelium with distinct apical and basal domains (Dunn et al. 1989). Hepatocytes have a high metabolic activity and produce many liver specific molecules such as urea, amino acids, glycogen and bile. The successful tissue engineering of liver is often assessed by measuring the secretion of these liver specific products.

Hepatocytes encapsulated in fibrin showed maintained viability over the first 3 days culture *in vivo*, but thereafter showed significant loss despite the maintenance of an even distribution of cells. Neotissue formation, however, was observed with good integration into the host tissue after 7 days *in vivo* as well as maintained liver specific function and phenotype in viable cells (Bruns et al. 2005). In order to facilitate the diffusion of nutrients within hydrogels encapsulating hepatocytes to maintain cell viability and function, various approaches have been taken. For example, the incorporation of micro-channels into gelatin hydrogels was shown to maintain 90% viability and metabolic activity of the encapsulated hepatocytes after 45 days *in vitro* culture (Wang et al. 2006). Similarly, Khattak et al. (2007) have shown that perfluorocarbon incorporation can improve metabolic activity and viability of encapsulated hepatocytes for 2 weeks *in vitro* culture.

Cardiovascular tissue

The cardiovascular network is essential to maintaining the viability and functions of all living tissues. The network can become obstructed or damaged due to disease or injury and thus efforts towards the tissue engineering of blood vessels and cardiac tissue are being made (Stegemann et al. 2007). In order to engineer vascular tissue, myofibroblasts have been encapsulated in fibrin gels (Mol et al. 2005; Ye et al. 2000) and viability maintained for up to 6 weeks *in vitro*. The cells were also seen to proliferate and secrete collagen. Smooth muscle cells have also been encapsulated in fibrin gels in order to produce an arterial media equivalent. After 3 weeks *in vitro* culture the arterial equivalent was seen to have a 95% reduction in volume and was shown to accumulate collagen, which was aligned in the circumferential direction of the tubular structure. The accumulation of collagen and the gel contraction was associated with an increase in ultimate tensile strength of the construct (Grassl et al. 2003).

Cardiac tissue has successfully been engineered *in vivo* by encapsulation of neonatal cardiac myocytes in fibrin gel within a silicon chamber implanted near an artery to maintain cell viability. After 3 weeks the implant was found to be viable with large amounts of muscle tissue which contracted in response to electrical stimulation and had neovascularisation throughout (Birla et al. 2005).

Conclusion

Biopolymer gel encapsulation of mammalian cells is finding increasing application in engineering a variety of different tissues. This review has summarised the most widely used biopolymeric hydrogels in tissue regeneration as well as the response of a range of cell types to encapsulation. Researchers have studied a variety of factors including cell viability, growth, matrix production and differentiation. Due to the variation in culture conditions and material formulation, it is often difficult to make conclusions on the effectiveness of a particular polymeric gel for tissue regeneration applications and there is a need for an increase in systematic research in this field. What is clear is that alginate, collagen, fibrin, hyaluronic acid, and gelatin all show promise as materials for the

encapsulation of cells for tissue engineering of cartilage, bone, ligament, tendon, skin, blood vessels and neural tissues and there is no doubt that polymeric cell encapsulation has great potential in the future of regenerative medicine. The potential importance, however, of tailoring degradation, ensuring sufficient diffusion through the biopolymer scaffolds and mechanical conditioning to ensure success of tissue engineering by encapsulation of cells in biopolymer gels have been highlighted in this review.

References

- Abbott A (2003) Biology's new dimension. *Nature* 424:870–872
- Alaminos M, Sanchez-Quevedo MD, Munoz-Avila JI, Serrano D, Medialdea S, Carreras I, Campos A (2006) Construction of a complete rabbit cornea substitute using a fibrin-agarose scaffold. *Investig Ophthalmol Vis Sci* 47:3311–3317
- Augst AD, Kong HJ, Mooney DJ (2006) Alginate hydrogels as biomaterials. *Macromol Biosci* 6:623–633
- Bach AD, Bannasch H, Galla TJ, Bittner KM, Stark GB (2001) Fibrin glue as matrix for cultured autologous urothelial cells in urethral reconstruction. *Tissue Eng* 7:45–53
- Bannasch H, Horch RE, Tanczos E, Stark GB (2000) Treatment of chronic wounds with cultivated autologous keratinocytes as suspension in fibrin glue. *Zentralbl Chir* 125:79–81
- Bannasch H, Unterberg T, Fohn M, Weyand B, Horch RE, Stark GB (2008) Cultured keratinocytes in fibrin with decellularised dermis close porcine full-thickness wounds in a single step. *Burns* 34:1015–1021
- Bellamkonda R, Ranieri JP, Bouche N, Aebischer P (1995) Hydrogel-based 3-dimensional matrix for neural cells. *J Biomed Mater Res* 29:663–671
- Berendse M, Grounds MD, Lloyd CA (2003) Myoblast structure affects subsequent skeletal myotube morphology and sarcomere assembly. *Exp Cell Res* 291:435–450
- Birla RK, Borschel GH, Dennis RG, Brown DL (2005) Myocardial engineering in vivo: formation and characterization of contractile, vascularized three-dimensional cardiac tissue. *Tissue Eng* 11:803–813
- Bitar M, Salih V, Brown RA, Nazhat SN (2007) Effect of multiple unconfined compressions on cellular dense collagen scaffolds for bone tissue engineering. *J Mater Sci Mater Med* 18:237–244
- Bokharia MA, Akaya G, Zhang S, Birch MA (2005) The enhancement of osteoblast growth and differentiation in vitro on a peptide hydrogel—polyHIPE polymer hybrid material. *Biomaterials* 26:5198–5208
- Brown LF, Lanir N, Mcdonagh J, Tognazzi K, Dvorak AM, Dvorak HF (1993) Fibroblast migration in fibrin gel matrices. *Am J Pathol* 142:273–283
- Brown RA, Wiseman M, Chuo CB, Cheema U, Nazhat SN (2005) Ultrarapid engineering of biomimetic materials and tissues: fabrication of nano- and microstructures by plastic compression. *Adv Funct Mater* 15:1762–1770
- Bruns H, Kneser U, Holzhter S, Roth B, Kluth J, Kaufmann PM, Kluth D, Fiegel HC (2005) Injectable liver: a novel approach using fibrin gel as a matrix for culture and intrahepatic transplantation of hepatocytes. *Tissue Eng* 11:1718–1726
- Calafiore R, Basta G, Luca G, Lemmi A, Racanicchi L, Mancuso F, Montanucci MP, Brunetti P (2006) Standard technical procedures for microencapsulation of human islets for graft into nonimmunosuppressed patients with type 1 diabetes mellitus. *Transplant Proc* 38:1156–1157
- Carvalho HF, Felisbino SL, Covizi DZ, la Colleta HHM, Gomes L (2000) Structure and proteoglycan composition of specialized regions of the elastic tendon of the chicken wing. *Cell Tissue Res* 300:435–446
- Catelas I, Sese N, Wu BM, Dunn JCY, Helgersson S, Tawil B (2006) Human mesenchymal stem cell proliferation and osteogenic differentiation in fibrin gels in vitro. *Tissue Eng* 12:2385–2396
- Chan BP, Leong KW (2008) Scaffolding in tissue engineering: general approaches and tissue-specific considerations. *Eur Spine J* 17:S467–S479
- Chang PL, Hortelano G, Tse M, Awrey DE (1994) Growth of recombinant fibroblasts in alginate microcapsules. *Biotechnol Bioeng* 43:925–933
- Cheema U, Yang SY, Mudera V, Goldspink GG, Brown RA (2003) 3-D in vitro model of early skeletal muscle development. *Cell Motil Cytoskeleton* 54:226–236
- Cheema U, Nazhat SN, Alp B, Foroughi F, Anandagoda N, Mudera V, Brown RA (2007) Fabricating tissues: analysis of farming versus engineering strategies. *Biotechnol Bioproc Eng* 12:9–14
- Choi BH, Woo JI, Min BH, Park SR (2006) Low-intensity ultrasound stimulates the viability and matrix gene expression of human articular chondrocytes in alginate bead culture. *J Biomed Mater Res* 79A:858–864
- Choi NW, Cabodi M, Held B, Gleghorn JP, Bonassar LJ, Stroock AD (2007) Microfluidic scaffolds for tissue engineering. *Nat Mater* 6:908–915
- Chun J, Tuan TL, Han B, Vangness CT, Nimni ME (2003) Cultures of ligament fibroblasts in fibrin matrix gel. *Connect Tissue Res* 44:81–87
- Chung C, Erickson IE, Mauck RL, Burdick JA (2008) Differential behavior of auricular and articular chondrocytes in hyaluronic acid hydrogels. *Tissue Eng* 14A:1121–1131
- Cleary EG, Sandberg LB, Jackson DS (1967) Changes in chemical composition during development of bovine nuchal ligament. *J Cell Biol* 33:469–479
- Cox S, Cole M, Tawil B (2004) Behavior of human dermal fibroblasts in three-dimensional fibrin clots: dependence on fibrinogen and thrombin concentration. *Tissue Eng* 10:942–954
- Crimmins EM, Saito Y (2001) Trends in healthy life expectancy in the United States, 1970–1990: gender, racial, and educational differences. *Soc Sci Med* 52:1629–1641
- Dunn JCY, Yarmush ML, Koebe HG, Tompkins RG (1989) Hepatocyte function and extracellular-matrix geometry—long-term culture in a sandwich configuration. *Faseb J* 3(2):174–177
- Eyrich D, Brandl F, Appel B, Wiese H, Maier G, Wenzel M, Staudenmaier R, Goepferich A, Blunk T (2007) Long-term

- stable fibrin gels for cartilage engineering. *Biomaterials* 28:55–65
- Fuchs E (2008) Skin stem cells: rising to the surface. *J Cell Biol* 180:273–284
- Gazda LS, Vinerean HV, Laramore MA, Diehl CH, Hall RD, Rubin AL, Smith BH (2007) Encapsulation of porcine islets permits extended culture time and insulin independence in spontaneously diabetic BB rats. *Cell Transplant* 16:609–620
- Grassl ED, Oegema TR, Tranquillo RT (2003) A fibrin-based arterial media equivalent. *J Biomed Mater Res* 66A:550–561
- Harrison CA, MacNeil S (2008) The mechanism of skin graft contraction: an update on current research and potential future therapies. *Burns* 34:153–163
- Herbert CB, Nagaswami C, Bittner GD, Hubbell JA, Weisel JW (1998) Effects of fibrin micromorphology on neurite growth from dorsal root ganglia cultured in three-dimensional fibrin gels. *J Biomed Mater Res* 40:551–559
- Hong Y, Song HQ, Gong YH, Mao ZW, Gao CY, Shen JC (2007) Covalently crosslinked chitosan hydrogel: properties of in vitro degradation and chondrocyte encapsulation. *Acta Biomater* 3:23–31
- Horn EM, Beaumont M, Shu XZ, Harvey A, Prestwich GD, Horn KM, Gibson AR, Preul MC, Panitch A (2007) Influence of cross-linked hyaluronic acid hydrogels on neurite outgrowth and recovery from spinal cord injury. *J Neurosurg Spine* 6:133–140
- Hortelano G, Al Hendy A, Ofosu FA, Chang PL (1996) Delivery of human factor IX in mice by encapsulated recombinant myoblasts: a novel approach towards allogeneic gene therapy of hemophilia B. *Blood* 87:5095–5103
- Hoshikawa A, Nakayama Y, Matsuda T, Oda H, Nakamura K, Mabuchi K (2006) Encapsulation of chondrocytes in photopolymerizable styrenated gelatin for cartilage tissue engineering. *Tissue Eng* 12:2333–2341
- Hou TY, Xu JZ, Li Q, Feng JH, Zen L (2008) In vitro evaluation of a fibrin gel antibiotic delivery system containing mesenchymal stem cells and vancomycin alginate beads for treating bone infections and facilitating bone formation. *Tissue Eng* 14A:1173–1182
- Hunt NC, Shelton RM, Grover LM (2009a) An alginate hydrogel matrix for the localised delivery of a fibroblast/keratinocyte co-culture. *Biotechnol J* 4:730–737
- Hunt NC, Shelton RM, Grover LM (2009b) Reversible mitotic and metabolic inhibition of fibroblasts by alginate hydrogel encapsulation. *Biomaterials* 30:6435–6443
- Ikada Y, Tabata Y (1996) Gelatin hydrogel as a matrix to release protein drugs. *Abstr Paper Am Chem Soc Natl Meet* 21:5–25
- Janmey PA, Winer JP, Weisel JW (2009) Fibrin gels and their clinical and bioengineering applications. *Interface* 6:1–10
- Joki T, Machluf M, Atala A, Zhu JH, Seyfried NT, Dunn IF, Abe T, Carroll RS, Black PM (2001) Continuous release of endostatin from microencapsulated engineered cells for tumor therapy. *Nat Biotechnol* 19:35–39
- Keshaw H, Forbes A, Day RM (2005) Release of angiogenic growth factors from cells encapsulated in alginate beads with bioactive glass. *Biomaterials* 26:4171–4179
- Khattak SF, Chin KS, Bhatia SR, Roberts SC (2007) Enhancing oxygen tension and cellular function in alginate cell encapsulation devices through the use of perfluorocarbons. *Biotechnol Bioeng* 96:156–166
- Kong HJ, Smith MK, Mooney DJ (2003) Designing alginate hydrogels to maintain viability of immobilized cells. *Biomaterials* 24:4023–4029
- Kretlow JD, Young S, Klouda L, Wong M, Mikos AG (2009) Injectable biomaterials for regenerating complex craniofacial tissues. *Adv Mater* 21:3368–3393
- Lahooti S, Sefton MV (2000a) Effect of an immobilization matrix and capsule membrane permeability on the viability of encapsulated HEK cells. *Biomaterials* 21:987–995
- Lahooti S, Sefton MV (2000b) Agarose enhances the viability of intraperitoneally implanted microencapsulated L929 fibroblasts. *Cell Transplant* 9:785–796
- Lahooti S, Sefton MV (2000c) Microencapsulation of normal and transfected L929 fibroblasts in a HEMA-MMA copolymer. *Tissue Eng* 6:139–149
- Lee KY, Mooney DJ (2001) Hydrogels for tissue engineering. *Chem Rev* 101:1869–1880
- Liu HW, Ofosu FA, Chang PL (1993) Expression of human factor-IX by microencapsulated recombinant fibroblasts. *Hum Gene Ther* 4:291–301
- MacNeil S (2007) Progress and opportunities for tissue-engineered skin. *Nature* 445:874–880
- Marenzana M, Wilson-Jones N, Mudera V, Brown RA (2006) The origins and regulation of tissue tension: identification of collagen tension-fixation process in vitro. *Exp Cell Res* 312:423–433
- Meana A, Iglesias J, Del Rio M, Larcher F, Madrigal B, Fresno MF, Martin C, San Roman F, Tevar F (1998) Large surface of cultured human epithelium obtained on a dermal matrix based on live fibroblast-containing fibrin gels. *Burns* 24:621–630
- Mesa JM, Zaporozhan V, Weinand C, Johnson TS, Bonassar L, Randolph MA et al (2006) Tissue engineering cartilage with aged articular chondrocytes in vivo. *Plast Reconstr Surg* 118:41–49
- Miyoshi M, Kawazoe T, Igawa HH, Tabata Y, Ikada Y, Suzuki S (2005) Effects of bFGF incorporated into a gelatin sheet on wound healing. *J Biomater Sci Polym Ed* 16:893–907
- Mol A, van Lieshout MI, Veen CGD, Neuenschwander S, Hoerstrup SP, Baaijens FPT, Bouten CVC (2005) Fibrin as a cell carrier in cardiovascular tissue engineering applications. *Biomaterials* 26:3113–3121
- Murray MM, Forsythe B, Chen F, Lee SJ, Yoo JJ, Atala A, Steinert A (2006) The effect of thrombin on ACL fibroblast interactions with collagen hydrogels. *J Orthop Res* 24:508–515
- Narayanan K, Leck KJ, Gao SJ, Wan ACA (2009) Three-dimensional reconstituted extracellular matrix scaffolds for tissue engineering. *Biomaterials* 30:4309–4317
- Nazhat SN, Abou Neel EA, Kidane A, Ahmed I, Hope C, Kershaw M, Lee PD, Stride E, Saffari N, Knowles JC, Brown RA (2007) Controlled microchannelling in dense collagen scaffolds by soluble phosphate glass fibers. *Biomacromolecules* 8(2):543–551
- Nisbet DR, Crompton KE, Horne MK, Finkelstein DI, Forsythe JS (2008) Neural tissue engineering of the CNS using hydrogels. *J Biomed Mater Res B Appl Biomater* 87B:251–263

- Norman LL, Stroka K, Aranda-Espinoza H (2009) Guiding axons in the central nervous system: a tissue engineering approach. *Tissue Eng B* 15:291–305
- Pachence JM (1996) Collagen-based devices for soft tissue repair. *J Biomed Mater Res B Appl Biomater* 33:35–40
- Park SH, Park SR, Chung SI, Pai KS, Min BH (2005) Tissue-engineered cartilage using fibrin/hyaluronan composite gel and its in vivo implantation. *Artif Organs* 29:838–845
- Pelaez D, Huang CYC, Cheung HS (2009) Cyclic compression maintains viability and induces chondrogenesis of human mesenchymal stem cells in fibrin gel scaffolds. *Stem Cells Dev* 18:93–102
- Peppas NA, Hilt JZ, Khademhosseini A, Langer R (2006) Hydrogels in biology and medicine: from molecular principles to bionanotechnology. *Adv Mater* 18:1345–1360
- Read TA, Farhadi M, Bjerkvig R, Olsen BR, Rokstad AM, Huszthy PC, Vajkoczy P (2001a) Intravital microscopy reveals novel antivascular and antitumor effects of endostatin delivered locally by alginate-encapsulated cells. *Cancer Res* 61:6830–6837
- Read TA, Sorensen DR, Mahesparan R, Enger PO, Timpl R, Olsen BR, Hjelstuen MHB, Haraldseth O, Bjerkvig R (2001b) Local endostatin treatment of gliomas administered by microencapsulated producer cells. *Nat Biotechnol* 19:29–34
- Rosa AL, de Oliveira PT, Beloti MM (2008) Macroporous scaffolds associated with cells to construct a hybrid biomaterial for bone tissue engineering. *Expert Rev Med Dev* 5:719–728
- Rowley JA, Mooney DJ (2002) Alginate type and RGD density control myoblast phenotype. *J Biomed Mater Res* 60:217–223
- Smith AM, Harris JJ, Shelton RM, Perrie Y (2007) 3D culture of bone-derived cells immobilised in alginate following light-triggered gelation. *J Control Release* 119:94–101
- Soon-Shiong P (1999) Treatment of type I diabetes using encapsulated islets. *Adv Drug Deliv Rev* 35:259–270
- Stegemann JP, Kaszuba SN, Rowe SL (2007) Review: advances in vascular tissue engineering using protein-based biomaterials. *Tissue Eng* 13:2601–2613
- Sterodimas A, de Faria J, Correa WE, Pitanguy I (2009) Tissue engineering and auricular reconstruction: a review. *J Plast Reconstr Aesthet Surg* 62:447–452
- Tuan TL, Song A, Chang S, Younai S, Nimni ME (1996) In vitro fibroplasia: matrix contraction, cell growth, and collagen production of fibroblasts cultured in fibrin gels. *Exp Cell Res* 223:127–134
- Wang L, Shelton RM, Cooper PR, Lawson M, Triffitt JT, Barralet JE (2003) Evaluation of sodium alginate for bone marrow cell tissue engineering. *Biomaterials* 24:3475–3481
- Wang XH, Yan YN, Pan YQ, Xiong Z, Liu HX, Cheng B, Liu F, Lin F, Wu RD, Zhang RJ, Lu QP (2006) Generation of three-dimensional hepatocyte/gelatin structures with rapid prototyping system. *Tissue Eng* 12:83–90
- Williams PL, Warwick R, Dyson M, Banniston LH (1989) *Gray's anatomy*, 37th edn. Longman Group, London
- Ye Q, Zund G, Benedikt P, Jockenhoevel S, Hoerstrup SP, Sakyama S, Hubbell JA, Turina M (2000) Fibrin gel as a three dimensional matrix in cardiovascular tissue engineering. *Eur J Cardiothorac Surg* 17:587–591
- Young S, Wong M, Tabata Y, Mikos AG (2005) Gelatin as a delivery vehicle for the controlled release of bioactive molecules. *J Control Release* 109:256–274
- Zhang L, Webster TJ (2009) Nanotechnology and nanomaterials: promises for improved tissue regeneration. *Nano Today* 4:66–80
- Zielinski BA, Aebischer P (1994) Chitosan as a matrix for mammalian-cell encapsulation. *Biomaterials* 15:1049–1056
- Zimmermann H, Ehrhart F, Zimmermann D, Muller K, Katsen-Globa A, Behringer M, Feilen PJ, Gessner P, Zimmermann G, Shirley SG, Weber MM, Metzke J, Zimmermann U (2007) Hydrogel-based encapsulation of biological, functional tissue: fundamentals, technologies and applications. *Appl Phys Mater Sci Process* 89:909–922