

Ultrasound velocity in heavy ocular tamponade agents and implications for biometry.

M. A. Rehman Siddiqui, Muhammad Amer Awan, Andrew Fairhead, Hatem

Atta

▶ To cite this version:

M. A. Rehman Siddiqui, Muhammad Amer Awan, Andrew Fairhead, Hatem Atta. Ultrasound velocity in heavy ocular tamponade agents and implications for biometry.. British Journal of Ophthalmology, 2010, 95 (1), pp.142. 10.1136/bjo.2009.179309 . hal-00585175

HAL Id: hal-00585175 https://hal.science/hal-00585175

Submitted on 12 Apr 2011

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Ultrasound velocity in heavy ocular tamponade agents and implications for biometry

Authors:

M. A. Rehman Siddiqui,^{1,2} M. Amer Awan,¹ Andrew Fairhead,³

Hatem Atta²

Affiliations:

- 1) Tennent Institute of Ophthalmology, Gartnavel General Hospital, Glasgow,
- 2) Department of Ophthalmology, Grampian University Hospitals NHS Trust, Aberdeen;
- 3) The Department of Bio-Medical Physics and Bio-engineering, University of Aberdeen.

Competing interests: none to declare

Key words: Biometry, Heavy Silicone Oil, Cataract Surgery

Corresponding author:

M. A. Rehman SiddiquiDepartment of Ophthalmology,Grampian University Hospitals NHS Trust,

Aberdeen AB25 2ZN

Licence for Publication

The Corresponding Author has the right to grant on behalf of all authors and does grant on behalf of all authors, an exclusive licence (or non exclusive for government employees) on a worldwide basis to the BMJ Publishing Group Ltd to permit this article (if accepted) to be published in BJO and any other BMJPGL products and sublicences such use and exploit all subsidiary rights, as set out in our licence

(http://bjo.bmj.com/ifora/licence.pdf).

Abstract:

Purpose:

Heavy ocular tamponade agents are shown to be an effective tamponade in complicated retinal detachments. Combined oil removal and cataract surgery may be performed and ultrasound (US) provides a reliable means to measure the axial length of eyes. The aim of study was to evaluate the velocity of US in various tamponade agents.

Methods:

Five tamponade agents (SO 1000, SO 5000, Oxane HD, Densiron 68, and F-Decalin) were studied in vitro. Time of flight (T_1) was measured between an ultrasound transducer and the bottom of a container of the agent, and remeasured (T_2) after reducing the separation by 1 cm. The speed of sound in the particular material was calculated from the difference between T_2 and T_1 . Measurements were repeated over a range of temperatures from 18 - 42°C.

Results:

The speed of sound at 37°C ranged from 645 ± 8 m/s to 976 ± 10 m/s depending on the tamponade agent. In Densiron 68 and F-Decalin, the speed of sound was markedly reduced to 914 ± 10 m/s and 645 ± 8 m/s respectively. The temperature dependence of speed of sound varied between -2.2 and -3.6 m/s/°C depending on the particular oil. With 95% confidence, the true speed is believed to lie within \pm 5m/s of these values. The deviation from intended refraction was between 0.38 to 30.15 dioptres depending on the tamponade agent by using correction factor (CF) for SO 1000cs.

Conclusions:

Variability in the velocity of US should be taken into account when performing biometry. Biometry machines should be adjusted for various tamponade media when calculating IOL power.

Introduction:

Heavy silicone oil is an important adjunct to treat complicated retinal detachments including rhegmetogenous retinal detachments with large inferior retinal breaks and proliferative vitreoretinopathy (PVR).¹ Cataract development or progression of already existing cataract is a known complication of conventional silicone oil and heavy silicone oil.^{2,3} In case of accelerated cataract formation during the oil tamponade period a combined oil removal and lens extraction followed by the implantation of an intraocular lens (IOL) is desirable. Therefore, a precise biometry is required for IOL power calculation even in oil filled eyes, especially if the original vitreo-retinal disorder did not allow for accurate biometry prior to the tamponade use.

Ultrasound (US) biometry can be performed in silicone oil-filled eyes but the speed of sound is slower hence the axial length (AL) appears longer in silicone oil filled compared to vitreous filled eyes. This issue can be addressed by employing a conversion factor (CF) to ascertain the true AL of an eye.⁴ As far as we know there are no studies looking at the speed of sound in the heavy ocular tamponade agents.

The primary aim of our study was to evaluate velocity of US in heavier ocular tamponade agents. We also aimed to estimate CF for these agents and to determine the potential impact of using CF for conventional silicone oil (SO) 1000 cSt on postoperative refraction.

Methods:

We included five tamponade agents; silicone oil (SO) 1000 cSt , SO 5000 cSt (Medicel AG, Widnau, Switzerland), Oxane HD (Bausch & Lomb, Toulouse, France), Densiron 68 (Fluoron Co, Neu-Ulm, Germany)and F-Decalin (Fluoron Co, Neu-Ulm, Germany) and measured speed of sound in these materials in vitro. An US transducer (Panametrics model 5052PR; centre-frequency 5MHz) was used to measure the speed (Figure 1). Although a higher frequency than 5MHz is used for biometry, ultrasound velocity is regarded as being non-dispersive in most media, so these measurements should not be affected by frequency. Time of flight (T₁) was measured between the transducer and bottom of the container and remeasured (T₂) after reducing the separation by 1 cm. The speed of sound in the particular material was calculated from the difference between T₂ and T₁. All measurements were repeated over a temperature range of 18-42°C. The system was validated for water. The speed of sound in water was measured as 1487±10 m/s at 22° C and 1482.8 ±10 m/s at 20° C, whereas the true values are 1488 and 1482 respectively. We calculated CF of tamponade agent using this formula:

Conversion factor (CF) = Speed of sound in tamponade agent/ Speed of sound in vitreous humour

Where speed of sound in vitreous humour = 1532 m/s^{5}

We also calculated deviation from intended refraction if the standard CF for SO 1000 cSt was used in biometry for IOL power estimations.

Results:

The speed of sound ranged from 645 ± 8 m/s to 976 ± 10 m/s depending on the tamponade agent. However in case of heavy ocular tamponade agents there were significant differences in the speed. In Densiron 68 and F-Decalin, the speed of sound was markedly reduced to 914 ± 10 m/s and 645 ± 8 m/s respectively (Table 1). The temperature dependence of speed of sound varied between -2.2 and -3.6 m/s/°C depending on the particular oil (Figure 2). With 95% confidence, the true speed is believed to lie within \pm 5m/s of these values. The CF was calculated for these agents that ranged from 0.421 to 0.637 (Table 1). The deviation from intended refraction was between 0.38 to 30.15 dioptres depending on the tamponade agent by using CF for SO 1000cs (Table 2).

 Table 1: It shows speed of ultrasound in different ocular tamponade agents and their conversion factors.

Type of silicone oil	Speed (m/s) at 37°C	Conversion factor
SO 1000	976±10	0.637
SO 5000	970±10	0.633
Oxane HD	930±10	0.607
Densiron 68	914±10	0.597
F-Decalin	645±10	0.421

Table 2: It illustrates axial length (AL) measurements of various ocular tamponade agents and impact of using conversion factor for SO1000 on AL and refraction if we assume theoretical AL of 23.5mm.

Oil	AL measurements (mm)		Error (***)	
	AL _{SO} (**)	Adjusted with	AL (mm)	Refraction (D)
		CF _{SO1000}		
SO 1000	36.89	23.5	0.00	0.00
SO 5000	37.12	23.65	0.15	0.38
Oxane HD	38.71	24.66	1.16	2.9
Densiron 68	39.36	25.07	1.57	3.93
F-Decalin	55.82	35.56	12.06	30.15

(**) Calculated AL of tamponade filled eye when no CF was used.

(***) Errors in true AL measurements and desired refraction if CFs01000 was used for other tamponade agents.

Discussion:

Heavy ocular tamponade agents differ significantly in their ability to make contact with the inner surface of the vitreous cavity, which is determined by their specific gravity and interfacial tensions, and their viscosity and is critical to maintain the integrity of the tamponade over a longer period of time.⁶ In recent years, a marked decrease in the complication rate and an improvement in the anatomical and functional outcomes could be achieved with the introduction of new heavy tamponades, in particular new heavy silicone oils.⁷ Measurement of AL can be challenging in eyes filled with heavy tamponade agents. There are different techniques that can be utilised to measure AL in the eyes filled with heavy tamponade agents. Recently Roessler et al have shown accuracy and reproducibility of AL measurement in the eyes filled with conventional silicone oil and heavy silicone oil by using partial coherence laser interferometry (PCI).⁸ In few studies reliable AL measurements in silicone oil-filled eyes or incomplete silicone oil-filled eyes were determined by using magnetic resonance imaging and x-ray computed tomography.^{9,10} Although PCI can give reliable and accurate biometry estimations in normal eyes, it has limitations in patients with dense cataracts, corneal scarring and emulsified oil.¹¹ Other option is intraoperative biometry by A-scan US, following removal of heavy silicone oil. This method has shown comparable

postoperative refractive results to PCI for eyes filled with silicone oil.¹² Issues about sterilization of the biometry machine and prolongation of the operative procedure are likely to limit its benefits.

Preoperative US biometry can achieve accurate IOL power calculations in cases of heavy ocular tamponade agents if the velocity of US beam in these agents is known. A CF can then be calculated and inserted in the formula. Our study shows a significant reduction in speed of sound in heavy tamponade agents that can lead to an error in predicted AL from 1.16 mm to 12.06 mm (if a CF of standard SO 1000 cSt is used).

In terms of refractive outcomes, the predicted refraction can vary between 2.9 D and 30.15 D with same CF depending on the tamponade agents. Murray et al have demonstrated accurate prediction of required IOL power with US biometry by using CF of 0.71 for conventional SO 1300 cSt and their mean difference in actual and predictive refractive target was 0.74 to 1.31 D depending on placement of IOL.¹³ By using the CF values for the specific tamponade agents we can avoid refractive surprises. Our study findings are derived from an in vitro model and further studies are required to test the accuracy of these CF values in clinical practice.

It is important to take into account the variability in velocity of US in different tamponade agents when performing biometry. US machines should be adjusted for various heavy ocular tamponade agents when calculating IOL power.

References:

¹ Wong D, Van Meurs JC, Stappler T et al. A pilot study on the use of a perfluorohexyloctane/silicone oil solution as a heavier than water internal tamponade agent. Br J Ophthalmol 2005; 89:662-5.

² Casswell AG, Gregor ZJ. Silicone oil removal. I. The effect on the complications of silicone oil. Br J Ophthalmol 1987; 71:893-7.

³ Li W, Zheng J, Zheng Q et al. Clinical complications of Densiron 68 intraocular tamponade for complicated retinal detachment. Eye (Lond) 2010; 24: 21-8.

⁴ Murray DC, Potamitis T, Good P, Kirkby GR, Benson MT. Biometry of the silicone oil-filled eye. Eye (Lond) 1999; 13:319-24.

⁵ Hoffer KJ. Ultrasound velocities for axial eye length measurement. J Cataract Refract Surg 1994; 20:554-62.

⁶ Wetterqvist C, Wong D, Williams R et al. Tamponade efficiency of perfluorohexyloctane and silicone oil solutions in a model eye chamber. Br J Ophthalmol 2004; 88:692-6.

⁷ Heimann H, Stappler T, Wong D. Heavy tamponade 1: a review of indications, use, and complications. Eye (Lond) 2008; 22:1342-59.

⁸ Roessler GF, Huth JK, Dietlein TS et al. Accuracy and reproducibility of axial length measurement in eyes with silicone oil endotemponade. Br J Ophthalmol 2009; 93: 1492-4.

⁹ Takei K, Sekine Y, Okamoto F, Hommura S. Measurement of axial length of eyes with incomplete filling of silicone oil in the vitreous cavity using x ray computed tomography. Br J Ophthalmol 2002; 86:47-50

¹⁰ Bencic G, Vatavuk Z, Marotti M et al. Comparison of A-scan and MRI for the measurement of axial length in silicone oil-filled eyes. Br J Ophthalmol 2009; 93:502-5.

¹¹ Dietlein TS, Roessler G, Lüke C et al. Signal quality of biometry in silicone oil-filled eyes using partial coherence laser interferometry. J Cataract Refract Surg 2005; 31:1006-10.

¹² El-Baha SM, Hemeida TS. Comparison of refractive outcome using intraoperative biometry and partial coherence interferometry in silicone oil-filled eyes. Retina 2009; 29:64-8.

¹³ Murray DC, Durrani OM, Good P, Benson MT, Kirkby GR. Biometry of the silicone oil-filled eye: II. Eye (Lond) 2002; 16:727-30.

Legends:

Figure 1: It describes various instruments used in measuring speed of sound in ocular tamponade agents.

Figure 2: It shows speed of sound in different ocular tamponade agents and variation in speed depending on the temperature.



Brunni

Ultrasound pulsegenerator and receiver

Temperature meter

Heater holding samplecontainer Frame for positioning ultrasound transducer

