



HAL
open science

Influence of temperature on quasi-elastic scattering in GeO₂ glass

Silvia Caponi, Aldo Fontana, F. Rossi, Marco Zanatta

► **To cite this version:**

Silvia Caponi, Aldo Fontana, F. Rossi, Marco Zanatta. Influence of temperature on quasi-elastic scattering in GeO₂ glass. Philosophical Magazine, 2010, pp.1. 10.1080/14786435.2010.530618 . hal-00651155

HAL Id: hal-00651155

<https://hal.science/hal-00651155>

Submitted on 13 Dec 2011

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Influence of temperature on quasi-elastic scattering in GeO₂ glass

Journal:	<i>Philosophical Magazine & Philosophical Magazine Letters</i>
Manuscript ID:	TPHM-10-Jun-0286.R1
Journal Selection:	Philosophical Magazine
Date Submitted by the Author:	27-Sep-2010
Complete List of Authors:	Caponi, Silvia; University of Trento, Physics Fontana, Aldo; university of trento, physics Rossi, F.; Universita' di Trento, Fisica Zanatta, Marco; Università di Trento, Dipartimento di Fisica
Keywords:	glass, Raman spectroscopy, vitrification
Keywords (user supplied):	quasi elastic scattering, vitreous germania

SCHOLARONE™
Manuscripts

RESEARCH ARTICLE

Influence of temperature on quasi-elastic scattering in GeO₂ glassS. Caponi^{a,b*}, A. Fontana^{b,c}, F. Rossi^b, and M. Zanatta^b^a*IOM-CNR, c/o Università di Perugia, I-06123, Perugia, Italy;*^b*Dipartimento di Fisica, Università di Trento, I-38050 Povo, Trento, Italy;*^c*IPCF-CNR, UOS Roma, c/o Università di Roma "La Sapienza", I-00185 Roma, Italy;*

(October 6, 2010)

We report Raman scattering spectra for the network glass former vitreous germania (v-GeO₂) measured in the 10 K–1200 K temperature range. The results show an interesting temperature dependence of the quasi-elastic scattering. Comparing this study with acoustical attenuation measured by ultrasonic absorption and Brillouin light scattering, we found that the mechanism giving rise to quasi-elastic scattering in this system seems to be the same as the one causing the acoustic attenuation.

Keywords: glasses, vitreous germania, quasi elastic scattering, Raman light scattering

1. Introduction

During the past 10 years, many works have been devoted to study the structural and dynamical properties of complex materials [1–5]. One of the main problems is to understand the modification of the vibrational dynamics due to topological disorder of the system [6–11]. The fast dynamics in disordered systems includes two main contributions: the first is the low-frequency collective vibrations, the so-called boson peak (BP), and the second the relaxation dynamics that appears in light and neutron scattering spectra as quasielastic intensity (QES). Both these contributions are observed in spectra of all glass-forming systems as well as porous systems, polymers, and biological systems [13–21]. Hence, they are common features of dynamics in complex systems. Long times ago [22], the QES was assigned to the light coupling with relaxations of atoms or group of atoms between almost equivalent equilibrium positions described by a double well potential. This coupling can be direct or indirect; recently Sokolov et al. [19] have reported convincing results on v-SiO₂ and polystyrene in favor of the indirect mechanism. Substantially, according to this hypothesis, the contribution to the light scattering comes from the mechanical coupling of defects to the sound waves. Different studies were performed to relate the QES temperature and frequency behaviors with the damping of acoustic modes [16–19, 23]. In this paper, we report a detailed investigation of the low frequency Raman spectrum ($< 200 \text{ cm}^{-1}$) of vitreous and melted germania in a very large temperature range, from 10 K up to 1000 K, extending the temperature range investigated till now [21]. We compare our data with acoustic attenuation

*Corresponding author. E-mail: caponi@science.unitn.it

1 data in the framework of Jäckle model [22]. Our results suggest, indeed, that the
2 acoustic attenuation involves the same physical mechanisms responsible for QES
3 as discussed in this paper.
4
5

6
7 **2. Experimental and Results**
8

9 Our sample was prepared from GeO₂ powder (Aldrich, 99.99%) melted in platinum
10 crucibles for about 1h at 1600°C. The homogeneous and bubble free melt was
11 subsequently quenched in air. The absence of crystallization was checked before the
12 experiment by X-ray diffraction measurements. The samples were then polished in
13 order to obtain good optical surfaces.
14

15 Raman scattering experiments, in a 90° scattering geometry, were done using a
16 standard experimental setup Jobin-Yvon U1000 in a wide frequency range, from -
17 300 to 3000 cm⁻¹, in order to correctly subtract the underlying weak background of
18 luminescence [25]. The light polarizations were perpendicular, VV and orthogonal,
19 HV, to the scattering plane.
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42

43 Figure 1. pannel a) and b) Raman spectra at chosen temperatures as shown in the label. c) high frequency
44 part of spectra at some significant temperatures.

45 Figure 1 shows the depolarized reduced intensity measured on v-GeO₂, defined
46 as:
47

48
49
$$I_R^{Red}(\omega) = \frac{I^{Exp}(\omega)}{[n(\omega, T) + 1]\omega}; \tag{1}$$

50
51

52 where $I^{exp}(\omega)$ is the experimental datum and $n(\omega, T)$ is the Bose-Einstein popula-
53 tion factor.

54 In order to compare spectra taken at different temperatures, they are normalized
55 at the high frequency peaks, as shown in fig. 1c). The spectra show the BP, peaked
56 at ~ 50 cm⁻¹, and at lower frequency the QES. The lower panel, figure 1b) shows
57 that, increasing temperature up to room temperature, there is no intensity variation
58 of the BP. On the contrary, a strong increase of the scattering is observed at the
59
60

1 lower frequency. Above room temperature the scenario is different, fig. 1a). Here,
 2 increasing temperature, the QES present an increasing less marked than before,
 3 while the BP shifts to lower frequency increasing its intensity. The boson peak
 4 temperature behaviour is not the object of the present work and we do not discuss
 5 it further, this study can be found in ref. [26].

6 We can model the Raman intensity in HV polarization as the sum of QES and
 7 BP contributes [17]:
 8

$$9 \quad I_R^{Red} = I_{QES}(\omega) + I_{BP}(\omega); \quad (2)$$

10 where:

$$11 \quad I_{BP}(\omega) = C^v(\omega)g(\omega)\frac{[n(\omega, T) + 1]}{\omega}, \quad (3)$$

12 and

$$13 \quad I_{QES}(\omega) = C^{rel}(\omega)L(\omega, T), \quad (4)$$

14 are the QES and BP contribution to the spectrum. Here v indicates the vibrational
 15 part, and rel the relaxation part; $C(\omega)$ is the coupling light-vibration function and
 16 $g(\omega)$ is the vibrational density of states. The QES contribution is described by the
 17 function $L(\omega, T)$.

18 In the present investigation of the low frequency Raman scattering, we are able to
 19 measure the spectrum down to frequency shifts of 4 cm^{-1} . The increase below ~ 4
 20 cm^{-1} is caused by an elastic scattering due to a finite resolution of the spectrometer
 21 ($\sim 2 \text{ cm}^{-1}$). From the Raman spectra we have extracted the scattered intensity as
 22 function of temperature at 6 cm^{-1} integrating the signal in a frequency window
 23 of 1 cm^{-1} . The temperature dependence $I_{QES}(6\text{cm}^{-1})$ is shown in fig. 2 as dots:
 24 we can note a rapid increase up to $T = 500 \text{ K}$, then a plateau which extend
 25 up to 800 K and, finally, a strong increase at higher temperatures. It's worth to
 26 notice that, at the chosen frequency, the evolution of the QES is not influenced
 27 by the shift and the intensity variation of the BP. This is evidenced in figure
 28 2 where is also reported the evolution of the QES obtained from the squeezed
 29 spectra (triangles). In fact, dividing the x axis of the spectra by the frequency
 30 position of the Boson Peak maximum and scaling the Raman intensity imposing as
 31 well the conservation of the total number of vibrational states, a BP master curve
 32 has been obtained in a wide class of materials [13–15, 17]. This procedure, called
 33 *squeezing*, is well described in the case of GeO_2 in ref. [26], where the squeezed
 34 spectra are presented at chosen temperatures from the liquid to the glassy phase.
 35 In that representation, the evolution of the QES is completely disentangled by
 36 the eventual intensity modification due to the BP variations. As reported in fig.
 37 2, the comparison of the QE signals obtained in different ways presents slightly
 38 differences in the high temperature range, but the overview is not modified. In this
 39 work we try to understand the microscopic origin of QES analyzing its temperature
 40 evolution.
 41
 42
 43
 44
 45
 46
 47
 48
 49
 50
 51
 52
 53

54 3. Discussion

55 As already suggested in literature [22] the QES can be due to the scattering from
 56 structural defects or damped sound waves which are characteristic of glassy state.
 57 In fact the thermally activated relaxation process (TARP) can couple to light
 58
 59
 60

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60




Figure 2. Intensity of Quasi Elastic Scattering measured from the Raman spectra (dots) at 6 cm^{-1} as function of temperature; and intensity of Quasi Elastic Scattering at some chosen temperatures obtained from the squeezed spectra [26] in order to single out eventual contribution of the Boson Peak intensity variation (triangles).

directly, as was originally proposed by Jäckle [22] or indirectly, by coupling to phonons [19]. In order to compare our data with those obtained by the acoustic attenuation, we consider the internal friction, Q^{-1} , which is related to the QES scattering by $Q^{-1} \propto L(\omega)\omega$ [17]. In Eq. 4, the QES contribution, described by the function $L(\omega, T)$, can be formulated as [22]

$$L(\omega, T) \propto \int dV P(V) \frac{\tau(V)}{1 + \omega^2 \tau^2(V)} \tag{5}$$

where $\tau(V)$ is the relaxation time for potential barriers of height V , and $P(V)$ is the distribution of barrier heights. Different choices of the distribution of barriers have been proposed in literature [22–24, 27]. Concerning the model dependence of the analysis, it should be noticed that the frequency dependence it is found to be almost unaffected by the choice of the distribution function as already reported by Gilroy and Phillips [23] in the case of silica, while slight differences have been evidenced in the temperature evolution. We choose a Gaussian distribution, $P(V)$, of barriers V having a variance σ_V . This distribution has been already used in the case of vitreous germania to optimize the acoustic attenuation data in a wide frequency and temperature range [24, 29].

The results are shown in fig.3. Here we report the acoustic attenuation measured in the ultrasonic region (20 MHz) [30], the one measured by Brillouin light scattering (25 GHz) [28] and the rescaled QES data at 180 GHz. The continuous curves are computed with parameters: $\sigma_V = 1750\text{ K}$, $\tau_0 = 1.47 \cdot 10^{-14}\text{ s}$ and $A = 0.18$. The parameter are the same reported in ref. [29] where the analysis of the acoustic

1 attenuation has been analyzed over more than three decades in frequency.
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34

35 Figure 3. experimental data for Q^{-1} measured at 20 MHz (circles) [30], 25 GHz (stars). Lines are the
36 evaluation of the TARP model at the same frequencies and the extrapolation at 6 cm^{-1} . Dots are the
37 rescaled I_{QES} .
38

39 To report the QES intensity in fig 3, we normalized the data on the extrapolation
40 at 180 GHz. The good agreement between the QES and the acoustic attenuation
41 extrapolated between 10 K e 800 K at the same frequency indicates the common
42 origin of the two phenomena. At temperatures higher than 800 K the parallel ends
43 and the QES increases while the extrapolation of acoustical attenuation at higher
44 temperatures decreases. This difference could be due to the occurrence at these
45 temperatures (higher than T_g) of the structural modifications from the glassy state
46 to the liquid one, which contributes to QES with another relaxational process.
47
48
49
50

51 4. Conclusions

52
53 In conclusion, the similar spectral shape and temperature dependence of Raman
54 data, in comparison with the temperature dependence of the acoustical attenuation,
55 support the idea that QES and sound attenuation are due to the same mechanism.
56 Following the interpretation of ultrasonic absorption this mechanism is described
57 by a hopping model for structural defects with different atomic configurations of
58 the structure.
59
60

References

[1] T. S. Grigera, V. Martin-Mayor, G. Parisi, and P. Verrocchio, *Nature* **422**, 289 (2003).

[2] W. Goetze, and M. R. Mayr, *Phys. Rev. E* **61**, 587 (2000).

[3] S. N. Taraskin, Y. L. Loh, G. Natarajan, and S. R. Elliott, *Phys. Rev. Lett.* **86**, 1255 (2001).

[4] E. Fabiani, A. Fontana, U. Buchenau, *J. Chem. Phys.* **128**, 244507 (2008) and references therein.

[5] S. Caponi, M. Zanatta, A. Fontana, L. E. Bove, L. Orsingher, F. Natali, C. Petrillo, and F. Sacchetti *Phys. Rev. B* **79**, 172201 (2009).

[6] B. Ruzicka, T. Scopigno, S. Caponi, A. Fontana, O. Pilla, P. Giura, G. Monaco, E. Pontecorvo, G. Ruocco, and F. Sette, *Phys. Rev. B* **69**, 100201 (2004).

[7] O. Pilla, S. Caponi, A. Fontana, J. R. Goncalves, M. Montagna, F. Rossi, G. Viliari, L. Angelani, G. Ruocco, G. Monaco, F. Sette, *Journal of Physics: Condensed Matter* **16**, 8519 (2004).

[8] C. Masciovecchio, G. Baldi, S. Caponi, L. Comez, S. Di Fonzo, D. Fioretto, A. Fontana, A. Gessini, S. C. Santucci, F. Sette, G. Viliari, P. Vilmercati, and G. Ruocco, *Phys. Rev. Lett.* **97**, 035501 (2006).

[9] P. Benassi, S. Caponi, R. Eramo, A. Fontana, A. Giugni, M. Nardone, M. Sampoli, and G. Viliari *Phys. Rev. B* **71**, 172201 (2005).

[10] B. Rufflé, D. A. Parshin, E. Courtens, and R. Vacher, *Phys. Rev. Lett.* **100**, 015501 (2008) and references therein.

[11] W. Schirmacher, *Europhys. Lett.* **73**, 892 (2006).

[13] S. Caponi, S. Corezzi, D. Fioretto, A. Fontana, G. Monaco, and F. Rossi, *Phys. Rev. Lett.* **102**, 027402 (2009).

[14] G. Baldi, A. Fontana, G. Monaco, L. Orsingher, S. Rols, F. Rossi, B. Ruta, *Phys. Rev. Lett.* **102**, 195502 (2009).

[15] M. Zanatta, G. Baldi, S. Caponi, A. Fontana, E. Gilioli, M. Krish, C. Masciovecchio, G. Monaco, L. Orsingher, F. Rossi, G. Ruocco and R. Verbeni, *Phys. Rev. B* **81**, 212201 (2010).

[16] A. Fontana, F. Rossi, S. Caponi, E. Fabiani, U. Buchenau, A. Wischniewski, *J. Non-Cryst. Solids* **351**, 1928 (2005).

[17] S. Caponi, A. Fontana, F. Rossi, G. Baldi, and E. Fabiani *Phys. Rev. B* **76**, 092201 (2007).

[18] S.V. Adichtchev et al. *Journal of Non-Crystalline Solids* **353** 1491 (2007).

[19] A. P. Sokolov, V. N. Novikov, and B. Strube, *Europhysics Letters* **38**, 49 (1997).

[20] E. Duval, L. Savior, L. David, S. Etienne, and J. F. Lal, *Europhys. Lett.* **63**, 778 (2003)

[21] A. Brodin and L. M. Torell, *J. Raman Spectr.* **27**, 723 (1996).

[22] J. Jäckle, in *Amorphous Solids-Low Temperature Properties*, edited by W. A. Phillips, *Topics in Current Physics Vol. 24* Springer-Verlag, Berlin, 1981, p. 135; N. Theodorakopoulos and J. Jäckle, *Phys. Rev. B*, **14**, 2637 (1976).

[23] Gilroy K. S. and Phillips W. A., *Philos. Mag. B*, **43** 735 (1981).

[24] Rau S. et al., *Phys. Rev. B*, **52** (1995) 7179.

[25] A. Fontana, F. Rossi, and E. Fabiani, *J. Non-Cryst. Solids*, **352**, 4601 (2006).


[26] F. Rossi et al. present issue.

[27] R. Keil, G. Kasper, and S. Hunklinger, *J. Non-Cryst. Solids* **164/166**, 1183 (1993).


[28] Hertling J. et al., *J. Non-Cryst. Solids*, **226** (1998) 129.

[29] G. Baldi, P. Benassi, L. E. Bove, S. Caponi, E. Fabiani, D. Fioretto, A. Fontana, A. Giugni, M. Nardone, F. Scarponi, and M. Sampoli, *Euro. Phys. Lett.* **78**, 36001 (2007).

[30] Hunklinger S. and Schickfus M. v., *Amorphous Solids, Low Temperature Properties*, edited by Phillips W. A., Vol. 24 (Springer-Verlag, Berlin) 1981, pp. 81-105.




82x112mm (600 x 600 DPI)



106x86mm (600 x 600 DPI)

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60



304x182mm (600 x 600 DPI)

Review Only



Influence of temperature on quasi-elastic scattering in GeO₂ glass

Journal:	<i>Philosophical Magazine & Philosophical Magazine Letters</i>
Manuscript ID:	TPHM-10-Jun-0286.R1
Journal Selection:	Philosophical Magazine
Date Submitted by the Author:	27-Sep-2010
Complete List of Authors:	Caponi, Silvia; University of Trento, Physics Fontana, Aldo; university of trento, physics Rossi, F.; Universita' di Trento, Fisica Zanatta, Marco; Università di Trento, Dipartimento di Fisica
Keywords:	glass, Raman spectroscopy, vitrification
Keywords (user supplied):	quasi elastic scattering, vitreous germania

SCHOLARONE™
Manuscripts

RESEARCH ARTICLE

Influence of temperature on quasi-elastic scattering in GeO₂ glassS. Caponi^{a,b*}, A. Fontana^{b,c}, F. Rossi^b, and M. Zanatta^b^a*IOM-CNR, c/o Università di Perugia, I-06123, Perugia, Italy;*^b*Dipartimento di Fisica, Università di Trento, I-38050 Povo, Trento, Italy;*^c*IPCF-CNR, UOS Roma, c/o Università di Roma "La Sapienza", I-00185 Roma, Italy;**(September 27, 2010)*

We report Raman scattering spectra for the network glass former vitreous germania (v-GeO₂) measured in the 10 K–1200 K temperature range. The results show an interesting temperature dependence of the quasi-elastic scattering. Comparing this study with acoustical attenuation measured by ultrasonic absorption and Brillouin light scattering, we found that the mechanism giving rise to quasi-elastic scattering in this system seems to be the same as the one causing the acoustic attenuation.

Keywords: glasses, vitreous germania, quasi elastic scattering, Raman light scattering

1. Introduction

During the past 10 years, many works have been devoted to study the structural and dynamical properties of complex materials [1–5]. One of the main problems is to understand the modification of the vibrational dynamics due to topological disorder of the system [6–11]. The fast dynamics in disordered systems includes two main contributions: the first is the low-frequency collective vibrations, the so-called boson peak (BP), and the second the relaxation dynamics that appears in light and neutron scattering spectra as quasielastic intensity (QES). Both these contributions are observed in spectra of all glass-forming systems as well as porous systems, polymers, and biological systems [13–21]. Hence, they are common features of dynamics in complex systems. Long times ago [22], the QES was assigned to the light coupling with relaxations of atoms or group of atoms between almost equivalent equilibrium positions described by a double well potential. This coupling can be direct or indirect; recently Sokolov et al. [19] have reported convincing results on v-SiO₂ and polystyrene in favor of the indirect mechanism. Substantially, according to this hypothesis, the contribution to the light scattering comes from the mechanical coupling of defects to the sound waves. Different studies were performed to relate the QES temperature and frequency behaviors with the damping of acoustic modes [16–19, 23]. In this paper, we report a detailed investigation of the low frequency Raman spectrum ($< 200 \text{ cm}^{-1}$) of vitreous and melted germania in a very large temperature range, from 10 K up to 1000 K, extending the temperature range investigated till now [21]. We compare our data with acoustic attenuation

*Corresponding author. E-mail: caponi@science.unitn.it

2

1 data in the framework of Jäckle model [22]. Our results suggest, indeed, that the
 2 acoustic attenuation involves the same physical mechanisms responsible for QES
 3 as discussed in this paper.
 4

5 2. Experimental and Results

6
 7
 8
 9 Our sample was prepared from GeO₂ powder (Aldrich, 99.99%) melted in platinum
 10 crucibles for about 1h at 1600°C. The homogeneous and bubble free melt was
 11 subsequently quenched in air. The absence of crystallization was checked before the
 12 experiment by X-ray diffraction measurements. The samples were then polished in
 13 order to obtain good optical surfaces.
 14

15 Raman scattering experiments, in a 90° scattering geometry, were done using a
 16 standard experimental setup Jobin-Yvon U1000 in a wide frequency range, from -
 17 300 to 3000 cm⁻¹, in order to correctly subtract the underlying weak background of
 18 luminescence [25]. The light polarizations were perpendicular, VV and orthogonal,
 19 HV, to the scattering plane.
 20

21
 22
 23
 24
 25
 26
 27
 28
 29
 30
 31
 32
 33
 34
 35
 36
 37
 38
 39
 40
 41
 42
 43 Figure 1. panel a) and b) Raman spectra at chosen temperatures as shown in the label. c) high frequency
 44 part of spectra at some significant temperatures.

45 Figure 1 shows the depolarized reduced intensity measured on v-GeO₂, defined
 46 as:
 47

$$48 I_R^{Red}(\omega) = \frac{I^{Exp}(\omega)}{[n(\omega, T) + 1]\omega}; \quad (1)$$

49
 50
 51 where $I^{exp}(\omega)$ is the experimental datum and $n(\omega, T)$ is the Bose-Einstein popula-
 52 tion factor.
 53

54 In order to compare spectra taken at different temperatures, they are normalized
 55 at the high frequency peaks, as shown in fig. 1c). The spectra show the BP, peaked
 56 at ~ 50 cm⁻¹, and at lower frequency the QES. The lower panel, figure 1b) shows
 57 that, increasing temperature up to room temperature, there is no intensity variation
 58 of the BP. On the contrary, a strong increase of the scattering is observed at the
 59
 60

1 lower frequency. Above room temperature the scenario is different, fig. 1a). Here,
2 increasing temperature, the QES present an increasing less marked than before,
3 while the BP shifts to lower frequency increasing its intensity. The boson peak
4 temperature behaviour is not the object of the present work and we do not discuss
5 it further, this study can be found in ref. [26].

6 We can model the Raman intensity in HV polarization as the sum of QES and
7 BP contributes [17]:
8

$$9 \quad I_R^{Red} = I_{QES}(\omega) + I_{BP}(\omega); \quad (2)$$

10 where:

$$11 \quad I_{BP}(\omega) = C^v(\omega)g(\omega)\frac{[n(\omega, T) + 1]}{\omega}, \quad (3)$$

12 and

$$13 \quad I_{QES}(\omega) = C^{rel}(\omega)L(\omega, T), \quad (4)$$

14 are the QES and BP contribution to the spectrum. Here v indicates the vibrational
15 part, and rel the relaxation part; $C(\omega)$ is the coupling light-vibration function and
16 $g(\omega)$ is the vibrational density of states. The QES contribution is described by the
17 function $L(\omega, T)$.

18 In the present investigation of the low frequency Raman scattering, we are able to
19 measure the spectrum down to frequency shifts of 4 cm^{-1} . The increase below ~ 4
20 cm^{-1} is caused by an elastic scattering due to a finite resolution of the spectrometer
21 ($\sim 2 \text{ cm}^{-1}$). From the Raman spectra we have extracted the scattered intensity as
22 function of temperature at 6 cm^{-1} integrating the signal in a frequency window
23 of 1 cm^{-1} . The temperature dependence $I_{QES}(6\text{cm}^{-1})$ is shown in fig. 2 as dots:
24 we can note a rapid increase up to $T = 500 \text{ K}$, then a plateau which extend
25 up to 800 K and, finally, a strong increase at higher temperatures. It's worth to
26 notice that, at the chosen frequency, the evolution of the QES is not influenced
27 by the shift and the intensity variation of the BP. This is evidenced in figure
28 2 where is also reported the evolution of the QES obtained from the squeezed
29 spectra (triangles). In fact, dividing the x axis of the spectra by the frequency
30 position of the Boson Peak maximum and scaling the Raman intensity imposing as
31 well the conservation of the total number of vibrational states, a BP master curve
32 has been obtained in a wide class of materials [13–15, 17]. This procedure, called
33 *squeezing*, is well described in the case of GeO_2 in ref. [26], where the squeezed
34 spectra are presented at chosen temperatures from the liquid to the glassy phase.
35 In that representation, the evolution of the QES is completely disentangled by
36 the eventual intensity modification due to the BP variations. As reported in fig.
37 2, the comparison of the QE signals obtained in different ways presents slightly
38 differences in the high temperature range, but the overview is not modified. In this
39 work we try to understand the microscopic origin of QES analyzing its temperature
40 evolution.
41
42
43
44
45
46
47
48
49
50
51
52
53

54 3. Discussion

55 As already suggested in literature [22] the QES can be due to the scattering from
56 structural defects or damped sound waves which are characteristic of glassy state.
57 In fact the thermally activated relaxation process (TARP) can couple to light
58
59
60

Figure 2. Intensity of Quasi Elastic Scattering measured from the Raman spectra (dots) at 6 cm^{-1} as function of temperature; and intensity of Quasi Elastic Scattering at some chosen temperatures obtained from the squeezed spectra [26] in order to single out eventual contribution of the Boson Peak intensity variation (triangles).

directly, as was originally proposed by Jäckle [22] or indirectly, by coupling to phonons [19]. In order to compare our data with those obtained by the acoustic attenuation, we consider the internal friction, Q^{-1} , which is related to the QES scattering by $Q^{-1} \propto L(\omega)\omega$ [17]. In Eq. 4, the QES contribution, described by the function $L(\omega, T)$, can be formulated as [22]

$$L(\omega, T) \propto \int dV P(V) \frac{\tau(V)}{1 + \omega^2 \tau^2(V)} \quad (5)$$

where $\tau(V)$ is the relaxation time for potential barriers of height V , and $P(V)$ is the distribution of barrier heights. Different choices of the distribution of barriers have been proposed in literature [22–24, 27]. Concerning the model dependence of the analysis, it should be noticed that the frequency dependence it is found to be almost unaffected by the choice of the distribution function as already reported by Gilroy and Phillips [23] in the case of silica, while slight differences have been evidenced in the temperature evolution. We choose a Gaussian distribution, $P(V)$, of barriers V having a variance σ_V . This distribution has been already used in the case of vitreous germania to optimize the acoustic attenuation data in a wide frequency and temperature range [24, 29].

The results are shown in fig.3. Here we report the acoustic attenuation measured in the ultrasonic region (20 MHz) [30], the one measured by Brillouin light scattering (25 GHz) [28] and the rescaled QES data at 180 GHz. The continuous curves are computed with parameters: $\sigma_V = 1750 \text{ K}$, $\tau_0 = 1.47 \cdot 10^{-14} \text{ s}$ and $A = 0.18$. The parameter are the same reported in ref. [29] where the analysis of the acoustic

1 attenuation has been analyzed over more than three decades in frequency.
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34

35 Figure 3. experimental data for Q^{-1} measured at 20 MHz (circles) [30], 25 GHz (stars). Lines are the
36 evaluation of the TARP model at the same frequencies and the extrapolation at 6 cm^{-1} . Dots are the
37 rescaled I_{QES} .
38

39 To report the QES intensity in fig 3, we normalized the data on the extrapolation
40 at 180 GHz. The good agreement between the QES and the acoustic attenuation
41 extrapolated between 10 K e 800 K at the same frequency indicates the common
42 origin of the two phenomena. At temperatures higher than 800 K the parallel ends
43 and the QES increases while the extrapolation of acoustical attenuation at higher
44 temperatures decreases. This difference could be due to the occurrence at these
45 temperatures (higher than T_g) of the structural modifications from the glassy state
46 to the liquid one, which contributes to QES with another relaxational process.
47
48
49
50


51 4. Conclusions

52

53 In conclusion, the similar spectral shape and temperature dependence of Raman
54 data, in comparison with the temperature dependence of the acoustical attenuation,
55 support the idea that QES and sound attenuation are due to the same mechanism.
56 Following the interpretation of ultrasonic absorption this mechanism is described
57 by a hopping model for structural defects with different atomic configurations of
58 the structure.
59
60


References

- [1] T. S. Grigera, V. Martin-Mayor, G. Parisi, and P. Verrocchio, *Nature* **422**, 289 (2003).
- [2] W. Goetze, and M. R. Mayr, *Phys. Rev. E* **61**, 587 (2000).
- [3] S. N. Taraskin, Y. L. Loh, G. Natarajan, and S. R. Elliott, *Phys. Rev. Lett.* **86**, 1255 (2001).
- [4] E. Fabiani, A. Fontana, U. Buchenau, *J. Chem. Phys.* **128**, 244507 (2008) and references therein.
- [5] S. Caponi, M. Zanatta, A. Fontana, L. E. Bove, L. Orsingher, F. Natali, C. Petrillo, and F. Sacchetti *Phys. Rev. B* **79**, 172201 (2009).
- [6] B. Ruzicka, T. Scopigno, S. Caponi, A. Fontana, O. Pilla, P. Giura, G. Monaco, E. Pontecorvo, G. Ruocco, and F. Sette, *Phys. Rev. B* **69**, 100201 (2004).
- [7] O. Pilla, S. Caponi, A. Fontana, J. R. Goncalves, M. Montagna, F. Rossi, G. Viliari, L. Angelani, G. Ruocco, G. Monaco, F. Sette, *Journal of Physics: Condensed Matter* **16**, 8519 (2004).
- [8] C. Masciovecchio, G. Baldi, S. Caponi, L. Comez, S. Di Fonzo, D. Fioretto, A. Fontana, A. Gessini, S. C. Santucci, F. Sette, G. Viliari, P. Vilmercati, and G. Ruocco, *Phys. Rev. Lett.* **97**, 035501 (2006).
- [9] P. Benassi, S. Caponi, R. Eramo, A. Fontana, A. Giugni, M. Nardone, M. Sampoli, and G. Viliari *Phys. Rev. B* **71**, 172201 (2005).
- [10] B. Rufflé, D. A. Parshin, E. Courtens, and R. Vacher, *Phys. Rev. Lett.* **100**, 015501 (2008) and references therein.
- [11] W. Schirmacher, *Europhys. Lett.* **73**, 892 (2006).
- [13] S. Caponi, S. Corezzi, D. Fioretto, A. Fontana, G. Monaco, and F. Rossi, *Phys. Rev. Lett.* **102**, 027402 (2009).
- [14] G. Baldi, A. Fontana, G. Monaco, L. Orsingher, S. Rols, F. Rossi, B. Ruta, *Phys. Rev. Lett.* **102**, 195502 (2009).
- [15] M. Zanatta, G. Baldi, S. Caponi, A. Fontana, E. Gilioli, M. Krish, C. Masciovecchio, G. Monaco, L. Orsingher, F. Rossi, G. Ruocco and R. Verbeni, *Phys. Rev. B* **81**, 212201 (2010).
- [16] A. Fontana, F. Rossi, S. Caponi, E. Fabiani, U. Buchenau, A. Wischniewski, *J. Non-Cryst. Solids* **351**, 1928 (2005).
- [17] S. Caponi, A. Fontana, F. Rossi, G. Baldi, and E. Fabiani *Phys. Rev. B* **76**, 092201 (2007).
- [18] S.V. Adichtchev et al. *Journal of Non-Crystalline Solids* **353** 1491 (2007).
- [19] A. P. Sokolov, V. N. Novikov, and B. Strube, *Europhysics Letters* **38**, 49 (1997).
- [20] E. Duval, L. Savior, L. David, S. Etienne, and J. F. Lal, *Europhys. Lett.* **63**, 778 (2003)
- [21] A. Brodin and L. M. Torell, *J. Raman Spectr.* **27**, 723 (1996).
- [22] J. Jäckle, in *Amorphous Solids-Low Temperature Properties*, edited by W. A. Phillips, *Topics in Current Physics Vol. 24* Springer-Verlag, Berlin, 1981, p. 135; N. Theodorakopoulos and J. Jäckle, *Phys. Rev. B*, **14**, 2637 (1976).
- [23] Gilroy K. S. and Phillips W. A., *Philos. Mag. B*, **43** 735 (1981).
- [24] Rau S. et al., *Phys. Rev. B*, **52** (1995) 7179.
- [25] A. Fontana, F. Rossi, and E. Fabiani, *J. Non-Cryst. Solids*, **352**, 4601 (2006).
- [26] F. Rossi et al. present issue.
- [27] R. Keil, G. Kasper, and S. Hunklinger, *J. Non-Cryst. Solids* **164/166**, 1183 (1993).
- [28] Hertling J. et al., *J. Non-Cryst. Solids*, **226** (1998) 129.
- [29] G. Baldi, P. Benassi, L. E. Bove, S. Caponi, E. Fabiani, D. Fioretto, A. Fontana, A. Giugni, M. Nardone, F. Scarponi, and M. Sampoli, *Euro. Phys. Lett.* **78**, 36001 (2007).
- [30] Hunklinger S. and Schickfus M. v., *Amorphous Solids, Low Temperature Properties*, edited by Phillips W. A., Vol. 24 (Springer-Verlag, Berlin) 1981, pp. 81-105.



82x112mm (600 x 600 DPI)

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60




106x86mm (600 x 600 DPI)

View Only

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60



304x182mm (600 x 600 DPI)

Review Only