



**HAL**  
open science

# Migration of plasticizersphthalates, bisphenol A and alkylphenols from plastic containers and evaluation of risk

Albert Guart, Francisco Bono-Blay, Antonio Borrell, Silvia Lacorte

► **To cite this version:**

Albert Guart, Francisco Bono-Blay, Antonio Borrell, Silvia Lacorte. Migration of plasticizersphthalates, bisphenol A and alkylphenols from plastic containers and evaluation of risk. Food Additives and Contaminants, 2011, pp.1. 10.1080/19440049.2011.555845 . hal-00677969

**HAL Id: hal-00677969**

**<https://hal.science/hal-00677969v1>**

Submitted on 11 Mar 2012

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



**Migration of plasticizersphthalates, bisphenol A and alkylphenols from plastic containers and evaluation of risk**

Journal:	<i>Food Additives and Contaminants</i>
Manuscript ID:	TFAC-2010-373.R1
Manuscript Type:	Original Research Paper
Date Submitted by the Author:	29-Dec-2010
Complete List of Authors:	Guart, Albert; IDAEA-CSIC; Laboratorio Dr. Oliver-Rodés Bono-Blay, Francisco; Laboratorio Dr. Oliver-Rodés; IDAEA-CSIC Borrell, Antonio; Laboratorio Dr. Oliver-Rodés Lacorte, Silvia; CSIC, Environmental chemistry
Methods/Techniques:	Chromatography - GC/MS, Extraction, Method validation
Additives/Contaminants:	Packaging - bisphenol A, Environmental contaminants - Alkyl Phenols, Migration, Packaging - DEHP (phthalates)
Food Types:	Water

SCHOLARONE™  
Manuscripts

# 1 Migration of phthalates, bisphenol A and alkylphenols from plastic 2 containers and evaluation of risk

3  
4 Albert Guart <sup>a,b</sup>, Francisco Bono-Blay <sup>a,b</sup>, Antonio Borrell <sup>b</sup> and Silvia Lacorte <sup>a</sup>

5 <sup>a</sup> Department of Environmental Chemistry, IDAEA-CSIC, Jordi Girona 18-26, 08034  
6 Barcelona, Catalonia, Spain

7 <sup>b</sup> Laboratorio Dr. Oliver-Rodés, Moreres, 21 (Polígono Estruc), 08820 El Prat de  
8 Llobregat, Spain

## 9 10 11 **Abstract**

12 This study has investigated the potential migration of plasticizers, plastic components  
13 and additives from several plastic water bottles. Compounds studied were phthalates  
14 (dimethyl phthalate, di-n-butyl phthalate, benzylbutyl phthalate, bis(2-ethylhexyl)  
15 phthalate), bis(2-ethylhexyl) adipate, octylphenol, 4-nonylphenol and bisphenol A.  
16 Polycarbonate (PC), high density polyethylene (HDPE), low density polyethylene  
17 (LDPE), polyethylene terephthalate (PET) and polystyrene (PS) plastics used in the  
18 water bottling sector were tested using three kinds of total or specific migration tests: i)  
19 standard method UNE-EN ISO 177; ii) ultrasonic forced extraction and iii) standard  
20 method UNE-EN 13130-1. In addition, bottled waters contained in different plastic  
21 materials were analyzed to determine the potential migration of target compounds in  
22 real conditions. In all cases, samples were solid phase extracted using Oasis HLB 200  
23 mg cartridges and analyzed using GC-MS in scan acquisition mode. Bisphenol A and 4-  
24 nonylphenol were detected in incubated samples, indicating that migration from food  
25 plastics can occur at the experimental conditions tested. The total daily intake was  
26 calculated according to the levels detected in bottled water and the assessment of the  
27 consumers' risk was evaluated taking into consideration toxicological and legislative  
28 values.

29  
30 **Keywords:** migration; plasticizer; phthalate; alkylphenol; bisphenol A; nonylphenol;  
31 SPE; GC-MS.

## 34 Introduction

35 In the last years there has been an increase in the use of plastic materials in the food  
36 sector and consumer products, both for primary and secondary packaging. In the  
37 bottling industry, bottles are manufactured from specific polymers depending on the  
38 capacity of the container, each of them with unique characteristics as regards bottle  
39 strength, storage time, type of dispenser and disposal. Primary packaging is made with  
40 high density polyethylene (HDPE), polyethylene terephthalate (PET) and polycarbonate  
41 (PC) while caps are made of high density polyethylene (HDPE), low density  
42 polyethylene (LDPE) and polystyrene (PS) is used as septa in many caps (World  
43 Packaging Organization (WPO) 2008). These polymers contain additives such as  
44 antifogging, reinforcing and antistatic agents, blowing agents, colorants, fillers,  
45 lubricants, nucleating agents, optical brighteners, heat and light stabilizers, antiacids,  
46 antimicrobials, antioxidants, chain-breaking, photo- and hydroperoxide deactivating  
47 antioxidants, dehydrating agents, light screening pigments and UV absorbers (Bolgar  
48 2008; Piringer 2008). Mixtures of plastic components and additives can be made to  
49 obtain improved plastic characteristics. In addition, several water bottle formats, shapes  
50 and colours are used in the different bottling industries.

51 The safety of some of polymeric materials is nowadays a subject of concern in  
52 the bottling sector due to the potential migration of plasticizers and additives to water  
53 by a diffusion process (Biscardi et al. 2003), as described for bisphenol A (BPA) (Biles  
54 et al. 1997; Casajuana et al. 2003; Le et al. 2008; Loyo-Rosales et al. 2004), phthalates  
55 (Casajuana et al. 2003; Peñalver et al. 2000) or nonylphenol (NP) (Casajuana et al.  
56 2003). These substances are either plastic components, such as BPA used as monomer  
57 in the production of polycarbonate bottles (the so called “coolers”), or additives used to  
58 improve the plastic properties (such as NP), polymerization accelerators or agents to  
59 increase flexibility (phthalates) (Casajuana et al. 2003; Loyo-Rosales et al. 2004;  
60 Peñalver et al. 2000; Shen et al. 2007).

61 The presence of plastic components or additives in water can modify the  
62 organoleptic properties and if present at high concentrations, may trigger health  
63 problems due to the potential toxic properties of some chemicals. Epidemiological  
64 studies in test animals indicate an increase of some kinds of cancer, behaviour changes  
65 and anomalies in the reproductive and immunologic functions of some species  
66 (Casajuana et al. 2003; Rivas et al. 1997), reason that some of the target compounds are  
67 considered as endocrine disruptor compounds (EDC). Possible human health endpoints

1  
2  
3 68 affected by these agents include breast cancer and endometriosis in women, testicular  
4  
5 69 and prostate cancers in men, abnormal sexual development, reduced male fertility,  
6  
7 70 alteration in pituitary and thyroid gland functions, immune suppression, and  
8  
9 71 neurobehavioral effects (Environmental Protection Agency (EPA) 1997). For safety  
10  
11 72 reasons, polymers used for packaging which are in contact with food must be analyzed  
12  
13 73 before use to prevent migration of any of its components to the food (Council of Europe  
14  
15 74 2002).

16 75 Several methods are used to evaluate the potential migration of plastic  
17  
18 76 components or additives. The migration capacity varies depending on conditions used in  
19  
20 77 migration tests and depending on the type of food simulant. Nerín et al. (2002) used  
21  
22 78 different migration tests, one consisted in two sorbents (Tenax and Porapak) in contact  
23  
24 79 with plastic, and another consisted in a total dissolution procedure with  
25  
26 80 dichloromethane and methanol (Nerín et al. 2003). These migration tests were set up for  
27  
28 81 several plastic containers used in microwave ovens. Schmidt et al. performed a  
29  
30 82 quantitative determination of the plasticizers bis(2-ethylhexyl) adipate (DEHA) and  
31  
32 83 bis(2-ethylhexyl) phthalate (DEHP) in PET bottles and revealed maximum  
33  
34 84 concentrations of 0.046 and 0.71  $\mu\text{g L}^{-1}$ , respectively (Schmid et al. 2008). Casajuana et  
35  
36 85 al. (2003) detected BPA in HDPE and PET bottles at levels between 0.003 and 0.011  $\mu\text{g}$   
37  
38 86  $\text{L}^{-1}$  after exposing water bottles at sunlight for 10 weeks. BPA was also detected in  
39  
40 87 waters of public distribution system at levels of 0.006 and 0.025  $\mu\text{g L}^{-1}$ . The same  
41  
42 88 authors analyzed BPA in milk packed in Tetra Pack or HDPE bottles and concentrations  
43  
44 89 were between 0.28 and 2.64  $\mu\text{g kg}^{-1}$  of milk, depending on the brand (Casajuana et al.  
45  
46 90 2004). This indicates that fatty foods have a better ability to extract BPA from plastics  
47  
48 91 than water.

49  
50 92 This study has investigated the potential migration of plasticizers and additives  
51  
52 93 from several plastic containers. Three migration tests were conducted: i) the standard  
53  
54 94 method UNE-EN ISO 177 to test overall migration from plastics (not necessarily food  
55  
56 95 contact materials) where plastics are in contact with an adsorbent and incubated at 40°C  
57  
58 96 during 10 days (European Communities 1988); ii) ultrasonic forced extraction of  
59  
60 97 plastics incubated in water at different times and iii) the standard method UNE-EN  
98  
99 13130 (2005, Part 1) in which plastics were incubated at 40°C in water for 10 days. This  
100  
101 99 last method is described and legislated in the Spanish Royal Decree 866/2008  
(Ministerio de la Presidencia 2008) transposing Directives 82/711/EC (The Commission  
of the European Communities 1982), 85/572/CEE (The Commission of the European

1  
2  
3 102 Communities 1985), UNE-EN 1186 of 2002 and 2007/19/CE (The Commission of the  
4  
5 103 European Communities 2007). Analyses were performed using solid phase extraction  
6  
7 104 (SPE) followed by gas chromatography coupled to mass spectrometry (GC-MS).  
8  
9 105  
10 106

## 107 **Materials and methods**

### 108 *Chemicals and reagents*

109 Five phthalates, two alkylphenols and BPA were analyzed (Table 1). Analytical grade  
110 (98% purity) Phthalate Esters Mix including dimethyl phthalate (DMP), di-n-butyl  
111 phthalate (DPB), butyl benzyl phthalate (BBP), bis(2-ethylhexyl) phthalate (DEHP) and  
112 bis(2-ethylhexyl) adipate (DEHA) was purchased from Supelco (Bellefonte, PA, USA)  
113 at a concentration of 500  $\mu\text{g mL}^{-1}$  each in methanol. 4-nonylphenol (NP) was from  
114 Riedel-de Haën (Seelze, Germany) as a solid technical mixture of isomers; 4-tert-  
115 octylphenol (OP) was from Supelco (Bellefonte, PA, USA) as a solid and BPA was  
116 from Dr. Ehrenstorfer (Augsburg, Germany) as a solid. Stock standard solutions of each  
117 compound were prepared in ethyl acetate at a concentration of 5  $\mu\text{g mL}^{-1}$  and stored in  
118 the dark at  $-20^{\circ}\text{C}$  until use. The surrogate standards used were NP-d<sub>8</sub> (100  $\text{ng } \mu\text{L}^{-1}$ ),  
119 diphenylphthalate-d<sub>4</sub> (DPP-d<sub>4</sub>) and BPA-d<sub>16</sub> purchased as solids from Dr. Ehrenstorfer  
120 (Augsburg, Germany). The internal standard was anthracene-d<sub>10</sub>, purchased from  
121 Supelco.

122 200 mg Oasis HLB cartridges were from Waters (Milford, MA, USA) and used  
123 with a Baker vacuum system (prod. No. 7018-94, J.T. Baker, The Netherlands).  
124 Chromatography grade methanol, acetone, dichloromethane, n-hexane, ethyl acetate and  
125 HPLC water were purchased from Merck (Darmstadt, Germany).  
126

### 127 *Samples*

128 Polyethylene terephthalate (PET), polycarbonate (PC), two types of high density  
129 polyethylene (HDPE), low density polyethylene (LDPE) and polystyrene (PS) plastics  
130 used as cap septa were tested using three kinds of migrations test (see below). Prior to  
131 use, these plastics were rinsed with HPLC water and cut with scissors in circular chips  
132 of different diameter, according to the migration test used. In addition, bottled water  
133 samples in PET, PC and HDPE were analyzed to determine the presence of target  
134 compounds in real storing conditions.  
135

1  
2  
3 136 *Migration tests*  
4

5 137 Three methods were used to test the migration of phthalates, BPA and  
6 138 alkylphenols from water bottles, taps and septa. Except for UNE-EN ISO 177, specific  
7 139 migration tests were performed for all plastic types for comparability purposes.  
8 140 Although article filling is a conventional test to evaluate the migration of plastic  
9 141 components, total immersion was used because in our laboratory conditions, it was  
10 142 impossible to perform migration test of containers as big as 18 L (e.g. coolers).  
11 143 According to the specific migration test performed, values are given in  $\mu\text{g dm}^{-2}$  because  
12 144 the samples were extracted from bottles as sheets and not as filled samples (Table 3).  
13 145 Also, the migration tests used in this study can be considered as total immersion tests,  
14 146 where the two plastic layers, inside (in contact with food) and outside (in contact with  
15 147 the environment) are in contact with the food stimulant. In European standards, it is  
16 148 considered the most severe test.

17 149 All sample manipulation was done using polytetrafluoroethylene (PTFE) tubing  
18 150 and glass material to avoid external contamination of the samples.  
19 151

20 152 UNE-EN ISO 177 method was used as a screening tool for the determination of  
21 153 the overall migration of plasticizers, expressed as loss of weight in the incubated plastic  
22 154 and gain in the adsorbent. It applies to evaluate the tendency of plasticizers and  
23 155 additives to migrate from plastic materials to other materials placed in close contact  
24 156 with them. It cannot be compared with food legislation, although it shows the possible  
25 157 migration of plasticizers and represented the starting point for the next tests. First,  $\text{C}_{18}$   
26 158 disks of 47 mm diameter and the plastic samples cut at the same diameter were  
27 159 weighed. The plastic sample was placed in a “sandwich” made of the plastic chip placed  
28 160 in between two  $\text{C}_{18}$  adsorbent disks, as it is shown in Figure 1. The “sandwich” was  
29 161 placed under a weight of 5 kg, and was introduced in an oven at 40°C during 10 days, as  
30 162 described in Directive 82/711/EC and their modifications (Directive 93/8/EC and  
31 163 Directive 97/48/EC). After that, the “sandwich” was removed and the adsorbent disks  
32 164 and samples were re-weighed to determine the weight difference. All polymers were  
33 165 tested except LDPE and PS sample which were adhered to the sorbent and could not be  
34 166 weighed after incubation.

35 167 Ultrasonic extraction method was developed as an accelerated method to force  
36 168 the migration of plastic components and additives to water. Although the results  
37 169 obtained in this method are not comparables with legislated values, it permits to identify  
38 the compounds that tend to migrate. 1 g of 0.5-1  $\text{cm}^2$  plastic chips was introduced in

1  
2  
3 170 100 mL of unbuffered HPLC water (used as food simulant at pH>4.5, as described in  
4  
5 171 Directive 82/711/EC), and 5 ng of surrogates standards were added. Then samples were  
6  
7 172 incubated in an ultrasonic bath during 5, 10 and 15 min (Figure 1). Afterwards, 100 mL  
8  
9 173 of the incubated water was solid phase extracted (Céspedes et al. 2004) and analyzed by  
10  
11 174 GC-MS to identify target compounds. All assays were performed in triplicate.

12 175 UNE-EN 13130 method was used for the identification of plastic components  
13  
14 176 and to compare the concentrations obtained with legislated values (Table 1). 1 g of  
15  
16 177 plastic chips was introduced in 100 mL of unbuffered HPLC water (used as food  
17  
18 178 simulant at pH>4.5, as described in Directive 82/711/EC) and 5 ng of surrogates  
19  
20 179 standards were added. Samples were incubated in a water bath at a temperature of 40°C  
21  
22 180 during 10 days (Figure 1). After incubation, water was extracted by SPE and analyzed  
23  
24 181 by GC-MS. GC-MS was used because it permitted to simultaneously analyze  
25  
26 182 phthalates, alkylphenols and BPA, although UNE-EN 1313-13 describes the  
27  
28 183 determination of BPA in food stimulants by high performance liquid chromatography  
29  
30 184 (HPLC) with ultraviolet (UV) detection. All assays were performed in triplicate.

31 185

### 32 186 *Solid Phase Extraction procedure*

33 187 Resulting water from the migration tests was solid phase extracted using 200 mg Oasis  
34  
35 188 HLB SPE cartridges using a Baker vacuum system with 12 cartridges capacity. All  
36  
37 189 Baker vacuum system connections and tubing were of PTFE to avoid contamination of  
38  
39 190 target compounds. Cartridges were conditioned prior to sample loading with 10 mL of  
40  
41 191 hexane, followed by 10 mL of dichloromethane, 10 mL of methanol and 15 mL of  
42  
43 192 HPLC water, all by gravity. This extensive cartridge cleaning was performed to  
44  
45 193 eliminate any traces of target compounds. Then, 100 mL of water were preconcentrated  
46  
47 194 at a flow of 8-13 mL min<sup>-1</sup> and afterwards the cartridge was dried under vacuum during  
48  
49 195 1 hour. Elution was performed with 10 mL of dichloromethane:hexane (1:1) and 10 mL  
50  
51 196 dichloromethane:acetone (1:1). The extract was preconcentrated in a Turbovap nitrogen  
52  
53 197 evaporator and extracts were reconstituted with 240 µL of ethyl acetate and 10 µL of  
54  
55 198 anthracene d10 (10 ng µL<sup>-1</sup>) was added as internal standard.

56 199

### 57 200 *Instrumental analysis*

58 201 Samples were analysed by gas chromatography coupled to a quadrupole mass  
59  
60 202 spectrometer (Trace GC-2000 series from Thermo Electron, San José, CA, USA). The  
203 system was operated in electron ionization mode (EI 70 eV). The separation was



1  
2  
3 204 achieved with a 30 m x 0.25 mm I.D. DB-5MS column (J&W Scientific, Folsom, CA,  
4  
5 205 USA) coated with 5% phenyl-95% dimethylpolysiloxane (film thickness 0.25  $\mu\text{m}$ ). The  
6  
7 206 oven temperature was programmed from 70°C (holding time 2 min) to 135°C at 10°C  
8  
9 207  $\text{min}^{-1}$ , to 160°C at 3°C  $\text{min}^{-1}$ , to 175°C at 1°C  $\text{min}^{-1}$ , to 195 °C at 3°C  $\text{min}^{-1}$  and finally to  
10  
11 208 310°C at 10°C  $\text{min}^{-1}$ , keeping the final temperature for 5 min. 2  $\mu\text{L}$  were injected in the  
12  
13 209 splitless mode, keeping the split valve closed for 1 min. Helium was the carrier gas (1.2  
14  
15 210 mL  $\text{min}^{-1}$ ). Injector, GC interface temperature and ion source temperatures were 280°C,  
16  
17 211 280°C and 200°C, respectively.

18 212 Peak detection and integration were carried out using Xcalibur software. Full  
19  
20 213 scan data (from m/z 60 to 400) was used for the identification of target compounds in  
21  
22 214 the migration tests.

23 215

### 24 216 *Quantification and quality parameters*

25  
26 217 Internal standard quantification was performed using the deuterated surrogate standards  
27  
28 218 corresponding to each chemical family (alkylphenols, phthalates and BPA) to correct  
29  
30 219 any lose during sample manipulation. Calibration curves were constructed for all target  
31  
32 220 compounds over a concentration of 0.01-1  $\text{mg L}^{-1}$ . Limits of detection (LOD) were  
33  
34 221 calculated using 3 times the standard deviation of n=5 blank samples, which is an  
35  
36 222 adequate procedure when there is a contribution of target compounds in the blank  
37  
38 223 samples due to the extraction and MS analysis. This procedure provides higher LOD  
39  
40 224 than when calculated from a spiked sample at low concentration and using 3 times the  
41  
42 225 noise signal. However, it is more realistic and provides better accuracy by reducing the  
43  
44 226 risk of overestimation due to sample contamination by the ubiquitous presence of  
45  
46 227 phthalates in laboratory air and even in the MS injection port. Quality controls were  
47  
48 228 performed using HPLC water spiked at 1  $\mu\text{g L}^{-1}$  and were incubated in the absence of  
49  
50 229 any plastic using the ultrasonic extraction and the UNE-EN 13130 method, in triplicate  
51  
52 230 and using closed glass containers.

51 231

52 232

## 53 233 **Results**

### 54 234 *Performance of the 3 migration tests*

55  
56 235 Migration tests permit to assess the potential leaching or migration of plastic  
57  
58 236 components or additives. The UNE-EN ISO 177 method was used as a screening tool to  
59  
60 237 determine the migration of plasticizers but was not adequate to identify specific

1  
2  
3 238 compounds. To identify those compounds that migrate from plastic and quantify their  
4  
5 239 levels, ultrasonic and incubation of plastics at 40°C were used in combination of GC-  
6  
7 240 MS whose capabilities permitted the determination of target compounds from test  
8  
9 241 materials with good performance as regards to identification and precise quantification.  
10  
11 242 The identification of plastic components was done in scan acquisition mode, which  
12  
13 243 provided high selectivity and good identification capabilities and no response  
14  
15 244 enhancement was observed due to the migration of other polymerized plastic to the  
16  
17 245 extracts. The method allowed the determination of target analytes in water samples at  
18  
19 246 levels of sub  $\mu\text{g L}^{-1}$  (Table 1). The LOD of phthalates were high compared to other  
20  
21 247 studies (Peñalver et al. 2000) because they were calculated from the 3 times the  
22  
23 248 standard deviation of the blank samples which always contained traces of phthalates that  
24  
25 249 originate both from the extraction and from the GC injection port. The use of surrogate  
26  
27 250 standards to quantify each compound was necessary to achieve accurate results, taking  
28  
29 251 into consideration the loss of analytes during incubation or extraction. The recoveries of  
30  
31 252 the analytes were between 93 and 125% for the SPE-GC/MS method (Table 1).

32 253

#### 33 254 *Migration of plastic components and additives from bottled water and caps*

34 255 UNE-EN ISO 177 provides an unspecific method capable to determine the total mass of  
35  
36 256 compounds migrating from plastic containers. Table 2 proves that tested plastics  
37  
38 257 incubated at 40°C lost weight, which was gained by the adsorbent, although there was  
39  
40 258 some mismatch due to the fact that some volatile compounds were lost during  
41  
42 259 incubation at 40°C, as considered in UNE-EN ISO 177. For example, for the PC plastic,  
43  
44 260 there was a 0.1 mg increase in the plastic due to humidity increase in the weighing  
45  
46 261 process but the gain of 2.3 mg in the sorbent after incubation should be taken into  
47  
48 262 consideration. Overall, the lose in plastic weight provides first evidence on the overall  
49  
50 263 migration of plasticizers from incubated plastics although this method failed to identify  
51  
52 264 and quantify specific compounds prone to migrate.

53 265 Migration tests UNE-EN 13130 and ultrasonic incubation were able to identify  
54  
55 266 target compounds. Ultrasonic method is a fast extraction method and was developed in  
56  
57 267 an attempt to validate it by comparing the results with the incubation at 40°C. We found  
58  
59 268 that qualitatively, both methods provided similar information, but quantitatively,  
60  
270 269 compounds were extracted with different efficiency. Phthalates were not detected in any  
271  
270 271 of the plastics tested and in any of the treatments used, and indicates that either these  
271  
270 271 compounds were not added in the tested plastics or either that they do not migrate at the

1  
2  
3 272 conditions tested. The same holds for octylphenol. NP and BPA were the only  
4  
5 273 compounds identified. The recoveries of NP and BPA using the ultrasonic incubation  
6  
7 274 were of 45% and 76% for respectively, and using the UNE-EN 13130, recoveries were  
8  
9 275 92% and 97% for NP and BPA, respectively. The different recoveries using both  
10  
11 276 migration tests reflect the losses that occur during the incubation period, which are  
12  
13 277 higher when using ultrasonic extraction, especially for NP.

14 278 Ultrasonic incubation forces the migration of compounds by applying an  
15  
16 279 ultrasonic wave which enhances the detachment of plastic components or additives  
17  
18 280 which are released to water. Results showed that there was not any difference in the  
19  
20 281 migration of plastic compounds using different extraction times (5, 10 or 15 min) and  
21  
22 282 thus, an extraction time of 5 min was chosen. Using this technique, NP was identified in  
23  
24 283 the incubated plastics at levels of 0.212-0.242  $\mu\text{g dm}^2$  while BPA was only detected at  
25  
26 284 1.870  $\mu\text{g dm}^2$  in the PC plastic (Table 3).

27 285 UNE-EN 13130 describes the methods for determining the specific migration of  
28  
29 286 plastic materials and UNE-EN 1186 describes the methods for determining the overall  
30  
31 287 migration of materials, plastics and articles in contact with foodstuffs. This UNE-EN  
32  
33 288 13130 migration test was based on Part 1, guide to test methods for the specific  
34  
35 289 migration of substances from plastics (see also UNE-EN 1186, Part 1 guide for the  
36  
37 290 selection of conditions and test methods to calculate the overall migration). Using this  
38  
39 291 method, NP and BPA were quantified at levels of 0.332-1.282  $\mu\text{g dm}^2$  and 0.128-3.423  
40  
41 292  $\mu\text{g dm}^2$ , respectively (Table 3). This method was more efficient in extracting  
42  
43 293 plasticizers and additives from plastics than ultrasonic extraction, and was able to  
44  
45 294 determine NP in all types of plastic and BPA in PC, HDPE, LDPE and PS. Both NP and  
46  
47 295 BPA can be used as plastic additives to improve the quality of plastic.

48 296 These two last methods are complementary and provide similar information on  
49  
50 297 the migration potential, qualitatively. Ultrasonic bath provides a lower migration of  
51  
52 298 BPA and NP compared to the UNE-EN 13130 (Table 3). Among both methods,  
53  
54 299 ultrasonic extraction can be considered a fast extraction method but with lower  
55  
56 300 efficiency than UNE-EN 13130 and so far, is not validated yet. Most important is that  
57  
58 301 UNE-EN 13130 is based on a technical interpretation of Directive 2007/19/EC and  
59  
60 302 provides maximum legislated migration levels for a large number of compounds. Thus,  
303 this technique was further used to determine the migration levels of target compounds in  
304 the 5 polymers studied and to compare the specific migration levels with legislated  
305 values.

306

307 ***Polymers tested and migration levels according to UNE-EN 13130***

308 NP and BPA were the only compounds identified in PC, HDPE, LDPE and PS plastics  
309 and for PET and HDPE bottles NP was the only compound identified. The MS  
310 chromatogram of BPA in the PC sample with UNE-EN 13130 method is shown in  
311 Figure 2. PET was the plastic type for which NP migration was lower, followed by  
312 HDPE bottles and PC. For caps material, NP levels increased from LDPE<PS<HDPE  
313 with NP migration between  $0.413 \mu\text{g dm}^{-2}$  and  $1.282 \mu\text{g dm}^{-2}$ . Contrarily, BPA was not  
314 detected in PET or HDPE bottles while the highest migration was found in PC bottles at  
315  $3.423 \mu\text{g dm}^{-2}$ . BPA was also detected in caps and septa with levels ranging from  $0.128$   
316  $\mu\text{g dm}^{-2}$  to  $0.145 \mu\text{g dm}^{-2}$ .

317 PET is one of the most common polymers used in bottled water container for its  
318 lightness, its gas barrier and its possibility to be recycled, and it is generally used in  
319 volumes from 0.33 up to 8 L bottles. Although in general it is for a single use, some  
320 companies recycle up to 25% of this plastic in the manufacture of new bottles. NP was  
321 detected at a mean concentration of  $0.332 \mu\text{g dm}^{-2}$  (n=3) and BPA was not detected in  
322 any replicate in this kind of plastic (Table 3). Casajuana et al. (Casajuana et al. 2003)  
323 found the presence of DMP, DEP, 4-NP, DBP, BPA, BBP and DEHP in PET bottled  
324 water samples at levels of 0.002 to  $0.214 \mu\text{g L}^{-1}$  after 10 weeks storage at high  
325 temperature and using SPE-GC-MS. Contrarily, Loyo-Rosales et al. (Loyo-Rosales et  
326 al. 2004) describe that neither NP nor OP were found in extracts from water stored in  
327 PET containers after 240 h. This discrepancy is attributed to the migration test and  
328 conditions used. NP is not legislated by the European Community and thus, a  
329 comparison with maximum permissible levels cannot be withdrawn.

330 HDPE is characterized by its strength and resistance to many solvents and is  
331 used in bottles of 5-8 L. This material is also used in the manufacture of caps, since it is  
332 resistant and it has a good sealing capacity. NP was released at concentrations  $0.579 \mu\text{g}$   
333  $\text{dm}^{-2}$  and  $1.282 \mu\text{g dm}^{-2}$  for HDPE bottles and caps, respectively (Table 3). For HDPE  
334 caps, BPA was detected at  $0.145 \mu\text{g dm}^{-2}$  and no traces were found in HDPE bottles  
335 (Table 3). Other studies describe the presence of NP in water bottled in HDPE and PVC  
336 containers at a concentration of  $0.230 \mu\text{g L}^{-1}$  after 120 h at  $40^\circ\text{C}$  (Loyo-Rosales et al.  
337 2004).

338 PC, a more resistant plastic, is used in containers over 10 L capacity and after  
339 use, it is cleaned and reused. PC plastic is made of BPA monomers, which can migrate

1  
2  
3 340 from containers (Le et al. 2008). The BPA amount detected in PC plastic was of 3.423  
4  
5 341  $\mu\text{g dm}^{-2}$  and NP was detected at 0.694  $\mu\text{g dm}^{-2}$ . Another study using bottled water in PC  
6  
7 342 describes the migration of this compound from used and new bottles at 0.7  $\mu\text{g L}^{-1}$  and  
8  
9 343 1.0  $\mu\text{g L}^{-1}$ , respectively, after 7 days at room temperature (Le et al. 2008). Nerín et al.  
10  
11 344 (Nerín et al. 2003) detected that BPA migrated from PC plastic stored at room  
12  
13 345 temperature. Biles et al. (Biles et al. 1997) detected BPA in PC baby bottles and cups at  
14  
15 346 levels ranging from non detected to 5  $\mu\text{g L}^{-1}$ .

16 347 LDPE is the polymer used in the cooler caps, its structure is the same as HDPE  
17  
18 348 but the density is lower so LDPE is used in caps and not in bottles. NP and BPA  
19  
20 349 migrated as shown in Table 3 at levels of 0.413 and 0.128  $\mu\text{g dm}^{-2}$ , respectively.

21 350 Finally, PS was tested because it is used in the septum of several caps, such as  
22  
23 351 the ones used in coolers. The amounts detected were 0.801 and 0.136  $\mu\text{g dm}^{-2}$  for NP  
24  
25 352 and BPA, respectively. PS is one of the most produced plastics in food contact materials  
26  
27 353 and can be copolymerized with many monomers. Products formed from PS are hard and  
28  
29 354 transparent (Piringer 2008). However, cap septa are whitish due to additives that  
30  
31 355 improve the brittleness and the sensitivity to stress cracking (Piringer 2008). These  
32  
33 356 additives may migrate as it happens in other type of plastics.

34 357 The presence of phthalates and BPA in food in contact with plastic is legislated  
35  
36 358 in the European Union. Directive 2002/72/EC, Directive 2004/19/EC and Directive  
37  
38 359 2007/19/EC (transposed to the Spanish Royal Decree 866/2008) establishes migration  
39  
40 360 specific limits in food and food simulants of 600  $\mu\text{g kg}^{-1}$  or 100  $\mu\text{g dm}^{-2}$  for BPA, 1500  
41  
42 361  $\mu\text{g kg}^{-1}$  or 250  $\mu\text{g dm}^{-2}$  for DEHP, 300  $\mu\text{g kg}^{-1}$  or 50  $\mu\text{g dm}^{-2}$  for DBP and 30000  $\mu\text{g kg}^{-1}$   
43  
44 362 or 5000  $\mu\text{g dm}^{-2}$  for BBP. The levels for phthalates are explicit in Directive  
45  
46 363 2007/19/EC and are different according to i) whether the packing is a single or multiple  
47  
48 364 use article, ii) whether it is in contact with aqueous or fatty foods and 3) whether it is for  
49  
50 365 infants. So there are a variety of limits for different cases. From the different polymers  
51  
52 366 tested, none of the samples exceeded the legislated value of 100  $\mu\text{g dm}^{-2}$  for BPA.  
53  
54 367 These legislated levels are lower or equal with the former Directive 2002/72/EC, who  
55  
56 368 established migration specific limits in food and food simulants of 3000  $\mu\text{g kg}^{-1}$  for  
57  
58 369 BPA and 1500  $\mu\text{g kg}^{-1}$  for DEHP. Specifically, the levels of BPA decreased 5 times  
59  
60 370 from 2002 to 2007 Directives because the increasing information and studies on BPA  
371  
372 toxicity and the potential effects on humans if ingested daily (Bredhult et al. 2009;  
373 Ghisari et al. 2009; Huang et al. 2009; Le et al. 2008; Salian et al. 2009).

### 374 *Analysis of bottled water*

375 The presence of plasticizers in bottled water (PET, HDPE and PC) was determined  
376 using the same SPE-GC/MS method extracting 1 L of water. In 1.5 L PET bottles, 2 out  
377 of 10 samples contained one target compound; OP was detected in one sample at 0.003  
378  $\mu\text{g L}^{-1}$  and NP in another at 0.019  $\mu\text{g L}^{-1}$ . In HDPE bottles, OP was detected in two  
379 samples at 0.003  $\mu\text{g L}^{-1}$  and 0.004  $\mu\text{g L}^{-1}$ , (N=7, volume = 5-10 L). The trace presence  
380 of these compounds is attributed to the use of OP and NP in the production of the  
381 specific polymers which vary among brands.

382 Finally, all PC coolers (N=10, volume = 18.9-20 L) contained BPA at levels  
383 ranging from 1.60  $\mu\text{g L}^{-1}$  to 4.44  $\mu\text{g L}^{-1}$ , with an average concentration of 2.64  $\mu\text{g L}^{-1}$ .  
384 These levels are in agreement with other studies which indicate that BPA can migrate  
385 from both PC and epoxy resins containers in contact with water at levels of few  $\mu\text{g L}^{-1}$ .  
386 In a former study regarding the migration of BPA, the U.S. FDA (Food & Drug  
387 Administration of the United States) analyzed BPA in water coolers stored for 39 weeks  
388 and found BPA at levels between 0.1 and 4.7  $\mu\text{g L}^{-1}$  (Environmental Protection Agency  
389 (EPA) 1993). In a 1997 study, it was found that BPA migrated when exposing  
390 polymeric material to water, ethanol/water and Miglyol (an oil) to temperatures of 65°C  
391 for 10 days. In the case of water in contact with polycarbonate bottles where the BPA is  
392 the main monomer, the levels of BPA were from not detected to 5  $\mu\text{g L}^{-1}$  (Biles et al.  
393 1997). In another study, the migration of BPA in PC bottles filled with water and  
394 exposed to 100°C for 1 h showed BPA migration levels of  $0.23 \pm 0.12 \mu\text{g L}^{-1}$ , while  
395 levels increased to  $8.4 \pm 4 \mu\text{g L}^{-1}$  and  $6.7 \pm 4 \mu\text{g L}^{-1}$  after using a domestic dishwasher  
396 between 51 and 169 times (Unit on food contact materials, enzymes, flavourings and  
397 processing aids (CEF) et al. 2008).

### 399 *Daily Intake and toxicological values*

400 The Tolerable Daily Intake (TDI) is a set of reference values for the acceptable intake of  
401 a variety of nutrients, as well as energy. A way to express the toxicity of a chemical  
402 specie is to calculate the TDI, which represents a lifetime exposure level that is  
403 considered to be safe. In this study, BPA is the only compound considered for  
404 evaluating the TDI since it was the only one detected in all samples analyzed. Based on  
405 the migration data from bottled water, the total exposure to BPA from PC plastic was  
406 estimated to be of  $4.00 \cdot 10^{-5} \text{ mg BPA kg}^{-1} \text{ bw day}^{-1}$  (1.5 L water  $\text{day}^{-1}$ , 60 kg person and  
407  $1.60 \mu\text{g BPA L}^{-1}$ ) and an upper range exposure of  $1.48 \cdot 10^{-4} \text{ mg BPA kg}^{-1} \text{ bw day}^{-1}$  (2 L

1  
2  
3 408 water day<sup>-1</sup>, 60 kg person and 4.44 µg BPA L<sup>-1</sup>). The Scientific Committee on Food  
4  
5 409 (SCF) in 2002 considered that the overall oral No-Observed-Adverse-Effect Level  
6  
7 410 (NOAEL) for BPA was 5 mg kg<sup>-1</sup> bw day<sup>-1</sup> and set a temporary TDI of 0.01 mg kg<sup>-1</sup>  
8  
9 411 bw day<sup>-1</sup> (European Food Safety Authority (EFSA), 2006), which was changed in 2008  
10  
11 412 by a TDI of 0.05 mg kg<sup>-1</sup> bw day<sup>-1</sup> (Unit on food contact materials, enzymes,  
12  
13 413 flavourings and processing aids (CEF) et al. 2008). In a former study realized in 1993,  
14  
15 414 the U.S. EPA had already suggested a reference value of 0.05 mg kg<sup>-1</sup> of body weight  
16  
17 415 (Environmental Protection Agency (EPA) 1993). These organizations state that PC  
18  
19 416 products are safe for being used in products in contact with food and beverage and pose  
20  
21 417 no known risk to human health. The levels of BPA from PC coolers were below the  
22  
23 418 NOAEL and TDI, although it should be considered that BPA consumption from PC  
24  
25 419 bottled water is only a part of the total oral Daily Intake.

26  
27 420 Many studies have been carried out on the toxicity and potential estrogenic  
28  
29 421 effects of BPA using various animal models, cellular lines and at molecular and  
30  
31 422 biochemical level. These studies set the initial basis to carry out risk assessment studies  
32  
33 423 of BPA on humans. However, discrepancies have been observed in these on going  
34  
35 424 studies regarding both the effects of BPA and the levels that cause these effects. From a  
36  
37 425 toxicological point of view, if the aquatic toxicity is considered using *Daphnia magna*,  
38  
39 426 EC<sub>50</sub> values range between 1 and 20 mg L<sup>-1</sup> (Table 1), and although these  
40  
41 427 concentrations cannot be extrapolated to a human model toxicity, they are an indicator  
42  
43 428 that effects caused to a very sensitive specie are initiated at the mg level. Cespedes et al.  
44  
45 429 developed a more specific method to assess the estrogenicity of BPA using recombinant  
46  
47 430 yeast using the human estrogen receptor (Céspedes et al. 2004). It was demonstrated  
48  
49 431 that the estrogenicity of BPA is 1644 ± 380 µg L<sup>-1</sup>, much lower than the natural  
50  
51 432 hormone estradiol (0.04 µg L<sup>-1</sup>), used as positive control (Table 1). That means that at  
52  
53 433 concentrations below 1644 µg L<sup>-1</sup>, BPA does not activate the human estrogen receptor  
54  
55 434 and therefore does not trigger any estrogenic effect. Concluding, the concentration of  
56  
57 435 BPA from PC containers in the samples analyzed were below the aquatic toxicity, the  
58  
59 436 EC<sub>50</sub> obtained with the recombinant yeast assay and the legislated levels (Table 1).  
60  
61 437 However, epidemiological studies carried out by Vandenberg et al. indicate that BPA is  
62  
63 438 present in human fluids at concentration levels higher than those that induce effects *in*  
64  
65 439 *vitro* and one order of magnitude higher than the levels that induce effects in animal  
66  
67 440 models (Vandenberg et al. 2007). Another study detected that 92.6% of the examined

1  
2  
3 441 US population had BPA in urine due to the routine ingestion of this compound from  
4  
5 442 plastic food containers (Calafat et al. 2008).  
6  
7 443  
8  
9 444  
10 445

## 11 446 **Conclusions**

12 447 Given the increased use of plastic in the bottling packaging sector, migration tests  
13  
14 448 permit the identification of plasticizers and additives with endocrine disrupting  
15  
16 449 properties that can cause human health effect when ingested continuously. Out of the 3  
17  
18 450 migration tests used, the UNE-EN 13130 method permitted identification of  
19  
20 451 compounds leaching from plastics and the ability to compare the migration levels with  
21  
22 452 legislative values. The ultrasonic extraction was an alternative to evaluate compounds  
23  
24 453 migrating from different polymers and qualitatively had a comparative performance  
25  
26 454 although with less efficiency and therefore, is not yet a validated and accepted method.  
27  
28 455 From 5 polymers tested, phthalates were not present in the plastics while NP and BPA  
29  
30 456 were identified at concentrations from 0.128 up to 3.423  $\mu\text{g dm}^{-2}$ . PET and HDPE  
31  
32 457 bottles were the bottles with the lowest amount of EDCs. The biggest problem  
33  
34 458 compound was BPA which was detected in all polycarbonate bottled waters analyzed  
35  
36 459 and although the total daily intake was below the legislative values, it may contribute to  
37  
38 460 the total daily intake of this compound considering all types of food. Numerous studies  
39  
40 461 indicate that BPA causes adverse effects in experimental animals and the constant  
41  
42 462 exposure, metabolism and long term risk in humans is a matter of concern. The  
43  
44 463 European Food Safety Authority (EFSA), the US Environmental Protection Agency and  
45  
46 464 other Agencies are currently undertaking studies to integrate data from migration tests,  
47  
48 465 exposure levels and toxicity endpoints to assess the possible effects of BPA on humans  
49  
50 466 and initiate actions to protect human health. At this point, BPA has recently been  
51  
52 467 banned in Europe (by summer 2011).  
53

## 54 469 **Acknowledgments**

55 470 This work was supported by “el Departament d’Universitats, Recerca i Societat de la  
56  
57 471 Informació de la Generalitat de Catalunya” and A. Guart acknowledges the "Agència de  
58  
59 472 Gestió d’Ajuts Universitaris i de Recerca (AGAUR)" in the context of the program  
60  
473 "Talent-Empresa (TEM 2009)" for the scholarship. This study was financed by  
474 “Ministerio de Educación y Ciencia” in the context of the project “Desarrollo y



1  
2  
3 475 validación de un método analítico para la detección de residuos de plastificantes y  
4 surfactantes en aguas embotelladas” [PET2006\_0615]. Jorge Oliver-Rodés is thanked  
5 476  
6 for encouraging this study and for directing and facilitating the joint research activities.  
7 477  
8 Dr. B. Oliver-Rodés and M. C. Pastor are thanked for their positive inputs and  
9 478  
10 suggestions reflecting their long experience in the bottling sector. Dr. R. Chaler, D.  
11 479  
12 Fanjul and M. Comesaña are acknowledged for their assistance with the GC-MS.  
13 480  
14 481

## 482 **References**

- 15 482  
16  
17 483  
18  
19 484 Biles JE, McNeal TP, Begley TH, Hollifield HC. 1997. Determination of Bisphenol-A  
20 485 in Reusable Polycarbonate Food-Contact Plastics and Migration to Food-Simulating  
21 486 Liquids. *Journal of Agricultural and Food Chemistry* 45: 3541-3544.  
22 487 Biscardi D, Monarca S, De Fusco R, Senatore F, Poli P, Buschini A, Rossi C, Zani C.  
23 488 2003. Evaluation of the migration of mutagens/carcinogens from PET bottles into  
24 489 mineral water by Tradescantia/micronuclei test, Comet assay on leukocytes and  
25 490 GC/MS. *Science of the Total Environment* 302: 101-108.  
26 491 Bolgar M, Hubball J, Groeger J, Meronek S. 2008. Handbook for the chemical analysis  
27 492 of plastic and polymer additives. CRC Press, Taylor & Francis Group. ISBN: 978-1-  
28 493 4200-4487-4.  
29 494 Bredhult C, Sahlin L, Olovsson M. 2009. Gene expression analysis of human  
30 495 endometrial endothelial cells exposed to Bisphenol A. *Reproductive Toxicology* 28:  
31 496 18-25.  
32 497 Calafat AM, Ye X, Wong LY, Reidy JA, Needham LL. 2008. Exposure of the U.S.  
33 498 population to bisphenol A and 4-tertary-Octylphenol: 2003-2004. *Environmental*  
34 499 *Health Perspectives* 116, 39-44.  
35 500 Casajuana N, Lacorte S. 2003. Presence and release of phthalic esters and other  
36 501 endocrine disrupting compounds in drinking water. *Chromatographia* 57: 649-655.  
37 502 Casajuana N, Lacorte S. 2004. A new methodology for the determination of phthalate  
38 503 esters, Bisphenol A, Bisphenol A diglycidyl Ether and Nonylphenol in commercial  
39 504 whole milk samples. *Journal of Agricultural and Food Chemistry* 52, 3702-07.  
40 505 Céspedes R., Raldúa D., Saura U., Piá P., Lacorte S., Viana P., Barceló D. 2004.  
41 506 Integrated protocol for the determination of endocrine disrupting activity in the  
42 507 surface waters and sediments using biological techniques by recombinant yeast  
43 508 assay and chemical analysis by LC-ESI-MS. *Analytical Bioanalytical Chemistry*  
44 509 378, 697-708.  
45 510 Council of Europe. 2002. Partial agreement in the social and public health fields,  
46 511 technical document. Vol. no 2.  
47 512 European Food Safety Authority (EFSA), Scientific Panel on Food Additives,  
48 513 Flavouring, Processing Aids and Materials in Contact with Food. 2006. 2,2-Bis-(4-  
49 514 hydroxyphenyl)propane (Bisphenol A). *The EFSA Journal*.  
50 515 Environmental Protection Agency (EPA). 1993. Bisphenol A. Integration Risk  
51 516 Information System.  
52 517 Environmental Protection Agency (EPA). 1997. Special Report on Environmental  
53 518 Endocrine Disruption: An Effects Assessment and Analysis.  
54 519 Ghisari M, Bonefeld-Jorgensen EC. 2009. Effects of plasticizers and their mixtures on  
55 520 estrogen receptor and thyroid hormone functions. *Toxicology Letters* 189: 67-77.

- 1  
2  
3 521 Huang H, Leung LK. 2009. Bisphenol A downregulates CYP19 transcription in JEG-3  
4 522 cells. *Toxicology Letters* 189: 248-252.
- 5 523 Le HH, Carlson EM, Chua JP, Belcher SM. 2008. Bisphenol A is released from  
6 524 polycarbonate drinking bottles and mimics the neurotoxic actions of estrogen in  
7 525 developing cerebellar neurons. *Toxicology Letters* 176: 149-156.
- 8 526 Loyo-Rosales JE, Rosales-Rivera GC, Lynch AM, Rice CP, Torrents A. 2004.  
9 527 Migration of Nonylphenol from Plastic Containers to Water and a Milk Surrogate.  
10 528 *Journal of Agricultural and Food Chemistry* 52: 2016-2020.
- 11 529 Ministerio de la Presidencia. 2008. Spanish Royal Decree 866/2008. BOE 131, 25070-  
12 530 25120.
- 13 531 Nerín C, Acosta D. 2002. Behavior of Some Solid Food Simulants in Contact with  
14 532 Several Plastics Used in Microwave Ovens. *Journal of Agricultural and Food*  
15 533 *Chemistry* 50, 7488-7492.
- 16 534 Nerín C, Fernández C, Domeño C, Salafranca J. 2003. Determination of potential  
17 535 migrants in polycarbonate containers used for microwave ovens by high-  
18 536 performance liquid chromatography with ultraviolet and fluorescence detection.  
19 537 *Journal of Agricultural and Food Chemistry* 51: 5647-5653.
- 20 538 Piringer OG, Baner AL. 2008. Plastic Packaging. Interactions with Food and  
21 539 Pharmaceuticals. WILEY-VCH. ISBN: 978-3-527-31455-3.
- 22 540 Peñalver A, Pocurull E, Borrull F, Marcé RM. 2000. Determination of phthalate esters  
23 541 in water samples by solid-phase microextraction and gas chromatography with mass  
24 542 spectrometric detection. *Journal of Chromatography A* 872: 191-201.
- 25 543 Rivas A, Olea N, Olea-Serrano F. 1997. Human exposure to endocrine-disrupting  
26 544 chemicals: Assessing the total estrogenic xenobiotic burden. *TrAC - Trends in*  
27 545 *Analytical Chemistry* 16: 613-619.
- 28 546 Salian S, Doshi T, Vanage G. 2009. Impairment in protein expression profile of  
29 547 testicular steroid receptor coregulators in male rat offspring perinatally exposed to  
30 548 Bisphenol A. *Life Sciences* 85: 11-18.
- 31 549 Schmid P, Kohler M, Meierhofer R, Luzi S, Wegelin M. 2008. Does the reuse of PET  
32 550 bottles during solar water disinfection pose a health risk due to the migration of  
33 551 plasticisers and other chemicals into the water? *Water Research* 42: 5054-5060.
- 34 552 Shen HY, Jiang HL, Mao HL, Pan G, Zhou L, Cao YF. 2007. Simultaneous  
35 553 determination of seven phthalates and four parabens in cosmetic products using  
36 554 HPLC-DAD and GC-MS methods. *Journal of Separation Science* 30: 48-54.
- 37 555 Unit on food contact materials, enzymes, flavourings and processing aids (CEF), Unit  
38 556 on Assessment Methodology (AMU). 2008. Statement of EFSA on a study  
39 557 associating bisphenol A with medical disorders. *The EFSA Journal*.
- 40 558 UNE-EN 1186. Materials and articles in contact with foodstuffs. *Plastics*. 2002.
- 41 559 UNE-EN 13130. Materials and articles in contact with foodstuffs - *Plastics substances*  
42 560 *subject to limitation*. 2005.
- 43 561 UNE-EN ISO 177. *Plastics. Determination of migration of plasticizers*. 1988.
- 44 562 The Commission of the European Communities. 1982. Directive 82/711/EC. *Official*  
45 563 *Journal of the European Union*.
- 46 564 The Commission of the European Communities. 1985. Directive 85/572/EEC. *Official*  
47 565 *Journal of the European Union*.
- 48 566 The Commission of the European Communities. 2007. Directive 2007/19/EC. *Official*  
49 567 *Journal of the European Union*.
- 50 568 Vandenberg LN, Hauser R, Marcus M, Olea N, Welshons WV. 2007. Human exposure  
51 569 to bisphenol A (BPA). *Reproductive Toxicology* 24: 139-177.

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60

570 World Packaging Organisation (WPO). 2008. Market Statistics and Future Trends in  
571 Global Packaging. [www.worldpackaging.org](http://www.worldpackaging.org). Formato Design-Brazil.  
572  
573  
574

For Peer Review Only

Table 1. Plasticizers and additives studied, their molecular formula, water octanol coefficient (log K<sub>ow</sub>), toxicity using *Daphnia magna* and Recombinant Yeast Assay (RYA), limits of detection calculated from 3 times the standard deviation of the blank samples (n=5), recoveries calculated at 1 µg L<sup>-1</sup> and legislated values.

Compound	Acronym	Molecular formula	Log K <sub>ow</sub>	Aquatic toxicity <sup>a</sup> µg L <sup>-1</sup>	RYA <sup>b</sup> µg L <sup>-1</sup>	LOD µg L <sup>-1</sup>	Recoveries %	Legislative level µg dm <sup>-2</sup>	Legislative level <sup>c</sup> µg kg <sup>-1</sup>
Dimethyl phthalate	DMP	C <sub>10</sub> H <sub>10</sub> O <sub>4</sub>	1.60	45900	4080 ± 1200	0.010	112	nl	nl
Di-n-butyl phthalate	DBP	C <sub>16</sub> H <sub>22</sub> O <sub>4</sub>	4.50	2990	3960 ± 1500	0.230	104	50 <sup>c</sup>	300 <sup>cd</sup>
Benzylbutyl phthalate	BBP	C <sub>19</sub> H <sub>20</sub> O <sub>4</sub>	4.73	960	5160 ± 2160	0.190	125	5000 <sup>c</sup>	30000 <sup>cd</sup>
Di(2-ethylhexyl) adipate	DEHA	C <sub>22</sub> H <sub>42</sub> O <sub>4</sub>	6.11	nf	nf	0.080	97	nl	nl
Di(2-ethylhexyl) phthalate	DEHP	C <sub>24</sub> H <sub>38</sub> O <sub>4</sub>	7.60	160	2310 ± 1460	0.460	107	250 <sup>c</sup>	1500 <sup>cd</sup>
Bisphenol A	BPA	C <sub>16</sub> H <sub>15</sub> O <sub>2</sub>	3.32	1000-20000	1640 ± 380	0.009	97	100 <sup>c</sup>	600 <sup>ce</sup>
Octylphenol	OP	C <sub>14</sub> H <sub>22</sub> O	5.28	90-1140	180 ± 80	0.001	93	nl	nl
Nonylphenol	NP	C <sub>15</sub> H <sub>24</sub> O	5.92	90-470	78 ± 20	0.017	98	nl	nl

<sup>a</sup> EC50 – 48 hr, *Daphnia magna*.  
<sup>b</sup> EC50 - Recombinant Yeast Assay (EPA/630/R-96/012).  
<sup>c</sup> Spanish Royal Decree 866/2008  
<sup>d</sup> According Directive 2007/19/EC  
<sup>e</sup> According Directive 2004/19/EC  
 nf: not found, nl: not legislated


Table 2. UNE-EN ISO 177 weights for 4 test plastics where it is observed that plastics lose weight while the adsorbent gains weight.

	$\Delta m$ plastic mg	$\Delta m$ disks mg
<b>PET bottle</b>	-0.3	8.1
<b>HDPE bottle</b>	-2.7	5.0
<b>PC bottle</b>	0.1	2.4
<b>HDPE cap</b>	-5.1	5.9
<b>Blank</b>	–	0.3

Table 3. Compounds identified using ultrasonic extraction and the conditions specified in UNE-EN 13130 expressed in  $\text{mg dm}^{-2}$  of plastic  $\pm$  standard deviation and % recoveries of target compounds in the  $1 \mu\text{g L}^{-1}$  spiked HPLC water quality control.

Method	Compound	Bottles			Caps		Septum	Recov. (%)
		PET $\mu\text{g dm}^{-2}$	HDPE $\mu\text{g dm}^{-2}$	PC $\mu\text{g dm}^{-2}$	HDPE $\mu\text{g dm}^{-2}$	LDPE $\mu\text{g dm}^{-2}$	PS $\mu\text{g dm}^{-2}$	
Ultrasonic extraction	NP	<LOD	$0.242 \pm 0.005$	<LOD	<LOD	<LOD	$0.212 \pm 0.034$	45
	BPA	<LOD	<LOD	$1.870 \pm 0.088$	<LOD	<LOD	<LOD	76
UNE-EN 13130	NP	$0.332 \pm 0.022$	$0.579 \pm 0.008$	$0.694 \pm 0.091$	$1.282 \pm 0.178$	$0.413 \pm 0.004$	$0.801 \pm 0.176$	92
	BPA	<LOD	<LOD	$3.423 \pm 0.217$	$0.145 \pm 0.026$	$0.128 \pm 0.019$	$0.136 \pm 0.028$	97

Figure 1. Illustration of the three tests.



For Peer Review Only

Figure 2. GC-MS TIC chromatogram of PC sample with UNE-EN 13130 method.

