



Mechanical Study of Copper Bonded at Low Temperature Using Spark Plasma Sintering Process

Bassem Mouawad, Maher Soueidan, D. Fabregue, Cyril Buttay, Vincent Bley,
Bruno Allard

► To cite this version:

Bassem Mouawad, Maher Soueidan, D. Fabregue, Cyril Buttay, Vincent Bley, et al.. Mechanical Study of Copper Bonded at Low Temperature Using Spark Plasma Sintering Process. CIMA, Mar 2011, Beyrouth, Lebanon. pp.CD. hal-00687147v2

HAL Id: hal-00687147

<https://hal.science/hal-00687147v2>

Submitted on 12 Mar 2013

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Mechanical and microstructural study of copper bonded at low temperature using Spark Plasma Sintering process

B. Mouawad^{1, a}, M. Soueidan^{1, 2, b *}, D. Fabrègue^{3, c}, C. Buttay^{1, d} V. Bley^{4, e} and B. Allard^{1, f}

¹ Université de Lyon, INSA de Lyon, AMPERE-UMR 5005, Bât. L. de Vinci, 21, Av. J. Capelle, 69621 Villeurbanne Cedex – France.

² Lebanese Atomic Energy Commission, P.O. Box 11-8281, Riad El Solh 1107 2260 Beirut, Lebanon.

³ Université de Lyon, INSA de Lyon, MATEIS-UMR 5510, Bât. B.PASCAL, 25 avenue J. Capelle, F-69621 Villeurbanne Cedex, France.

⁴LAPLACE Laboratory, Paul Sabatier University, INPT, CNRS, 31062 Toulouse cedex 9 France

^abassem.mouawad@insa-lyon.fr, ^bmaher.soueidan@insa-lyon.fr, ^cdamien.fabregue@insa-lyon.fr,

^dcyril.butty@insa-lyon.fr, ^evincent.bley@laplace.univ-tlse.fr, ^fbruno.allard@insa-lyon.fr

* corresponding author: Maher SOUEIDAN

Usually, a high purity copper diffusion bonding using a conventional furnace gives a bonding strength of 65 and 190 MPa using uniaxial tensile test for samples bonded respectively at 400 and 800°C with a holding pressure of 3.45 MPa for 60 min at top temperature following a 30 min ramp [1]. Furthermore, a room-temperature Cu/Cu direct bonding using surface activated bonding method (SAB) gives a bonding strength of 6.47 MPa under ultra High vacuum conditions [2].

In this study, bonding of high purity polished copper was investigated using the Spark Plasma Sintering technique (SPS) showing the effect of SPS parameters on the bonding strength and on the microstructural behaviour. Mechanical characterization of the bonded samples was performed at room temperature using tensile test, followed by microhardness study and grain size evolution. The bonding strength were found to be at 261MPa, 150 MPa and 170 MPa at holding temperature respectively of 200°C, 250°C and 300°C respectively with a 16 MPa holding pressure and a dwell time of 20min. The optimum value of the bonding strength, microhardness and grain size was found to be at only 200°C. The values decrease when SPS temperature increase to 250°C and they increase at 300°C due to evolution of mechanical properties of copper. This study firmly establishes the occurrence of recovery and recrystallization during the bonding heat treatment leading to the evolution of the mechanical strength assembly.

Finally, we will show that the bonding strength of the samples assembled using SPS is close to the tensile strength of the bulk copper. To our knowledge, such results have not been reported yet.




Figure 1: SEM image of the fracture surface (after tensile test) for a polished sample bonded at 300°C, for about 20 minutes holding time with a holding pressure of 16 MPa.

[1] J. W. Elmer, J. Klingmann, and K. Van Bibber, Phys. Rev. ST Accel and Beams 4, 053502, (2001).

[2] T. H. Kim, M. M. R. Howlader, T. Itoh and T. Suga, J. Vac. Sci. Technol. A, 21(2), 449, (2003).