



HAL
open science

Checking of an optimal sound absorbing structure

Camille Perrot, F. Chevillotte, R. Panneton

► **To cite this version:**

Camille Perrot, F. Chevillotte, R. Panneton. Checking of an optimal sound absorbing structure. Symposium on the Acoustics of Poro-Elastic Materials (SAPEM 2008), Dec 2008, Bradford, United Kingdom. pp.89-91, 2008. hal-00732578

HAL Id: hal-00732578

<https://hal.science/hal-00732578>

Submitted on 20 Apr 2013

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Checking of an Optimal Sound Absorbing Microporous Structure

Bottom-up Approach for Microstructure Optimization of Sound Absorbing Materials

C. Perrot ^①, F. Chevillotte ^②, and R. Panneton ^③



UNIVERSITÉ DE SHERBROOKE

63

^① Université Paris-Est, Laboratoire Modélisation et Simulation Multi Echelle, MSME FRE3160 CNRS, 5 bd Descartes, 77454 Marne-la-Vallée, France

^② INSA de Lyon, Laboratoire Vibrations Acoustique, Bâtiment 303, 20 Avenue Albert Einstein, 69621 Villeurbanne Cedex, France

^③ Université de Sherbrooke, Groupe d'Acoustique de l'Université de Sherbrooke, Département de génie mécanique, QC J1K 2R1, Canada

Introduction




Fig 1. Linking micro-structure and acoustical macro-behaviour

A variety of performance demands are increasingly being placed on sound absorbing material systems.

A bottom-up approach for microstructure optimization of long-wavelength sound absorbing materials was recently presented using hybrid estimates based on direct numerical evaluation of macroscopic parameters and analytical models [1].

Results of this paper tend to demonstrate the existence of a microstructural configuration maximizing the area under the sound absorption spectrum, together with the optimal range of local characteristic lengths.

This is a crucial conclusion, notably for foam and fibrous materials manufacturers, which need to be confirmed with a more general formulation proposed by Lafarge (see [2]).

MOTIVATION

Need to increase or adapt the sound absorption spectrum of commonly used sound absorbing materials

- Inefficient materials in the low frequency range
- Need to adapt the absorption spectrum to the emission spectrum

OBJECTIVE

Improve our general understanding of relationships between microstructure and acoustic macro-behavior of porous media, see Fig. 1.

RESULTS SUMMARY

- For a given fiber radius, an optimal throat size controlling the sound absorption level can be found, corresponding to an intermediate resistivity
- Given an optimal throat size, the fiber radius essentially modulates the absorption curve
- The optimal absorption curve minimizes the viscous characteristic length at constant throat size (design guide)
- Practical investigation charts proposed to indicate local geometry parameters tending to maximize the sound absorption coefficient (validity corroborated by comparison with measured local geometry parameters)

PERSPECTIVES

- Optimization of real porous materials based on specific industrial fabrication processes
- Use molecular dynamics to tackle physical acoustics of nano-porous materials

Results




Fig 3. Throat size (left), fiber radius (center), and cross-section shape (right) effects. This section reports and quantifies differences obtained with the simplified and refined models, see Fig. 4.




Fig 4. Response surface of the performance index I representing the area under the sound absorption curve in the frequency range 0 - 10 000 Hz for varying (w-throat size, r-fiber radius) couples (top-left); and associated 2D practical chart (bottom-left). Response surfaces of the error E made on I when using the simplified model instead of the refined one (top-right); and corresponding practical chart (bottom-right).

Concluding Remarks

The optimal microstructural configuration is correctly estimated from a simplified model with only 3% of uncertainty on the global performances.

However, for very diluted (large porosities) porous structures, the simplified model underestimates significantly the material performances with uncertainties reaching up to 30%.

Moreover, in this limit, where the best absorbing structure may lie, the physics have to be reconsidered (because both the nonslip conditions for velocity and temperature loose their physical justifications).

More sophisticated computational methods such as molecular dynamics will be considered to tackle physical acoustics of nano-porous materials as a future work.

References:

1. C. Perrot, F. Chevillotte and R. Panneton, Bottom-up approach for microstructure optimization of sound absorbing materials, J. Acous. Soc. Am., 124(2), 940-948 (2008).
2. D. Lafarge, Milieux poreux et poreux stratifiés. Modèles linéaires de propagation, in Matériaux et acoustique 1, edited by M. Bruneau and C. Potel (Lavoisier, Paris 2006), pp. 143-188.
3. C. Perrot, R. Panneton and X. Olny, Periodic unit cell reconstruction of porous media: Application to open cell aluminum foams, J. Appl. Phys. 101, 113538-11 (2007).
4. C. Perrot, F. Chevillotte and R. Panneton, Dynamic viscous permeability of an open-cell aluminum foam: computations vs experiments, J. Appl. Phys., 103, 024909-8 (2008).
5. C. Perrot, R. Panneton and X. Olny, Computation of the dynamic thermal dissipation properties of porous media by Brownian motion simulation: Application to an open-cell aluminum foam, J. Appl. Phys. 102, 074917-13 (2007).
6. D. L. Johnson, J. Koplik, and R. Dashen, Theory of dynamic permeability and tortuosity in fluid-saturated porous media, J. Fluid Mech. 176, 379-402 (1987).
7. J. F. Allard, Propagation of sound in porous media, Modelling sound absorbing materials, edited by Elsevier Applied Science, (Elsevier Science Publishers LTD, New York and London, 1993), pp. 284.

Numerical Calculations

Bottom

A. Model geometry [3]

• **Motionless solid fibers**

• **l and r as local characteristic lengths**

• **Cross-section shapes of a foam ligament evolves from a circle to a concave triangle**

Porosity (%) 86.2 90.9 92.6 94.6

Mirror symmetry

Periodicity by translation

Fig 2. A typical 2D hexagonal arrangement of solid fibers.

B. Computational method ([4]-[5])

Hybrid estimates based on direct numerical evaluation of macroscopic parameters and analytical models:

- Solve numerically the asymptotic low (steady Stokes) and high (electric) frequency viscous boundary value problems using the FEM
- Compute

2.1) the "standard macroscopic parameters", i.e., the static viscous permeability k_0 , the viscous characteristic length Λ , and the tortuosity α_∞ , as defined by Johnson et al. [6]

2.2) the additional macroscopic parameters, i.e., the static tortuosity α_0 , and the static thermal permeability k'_0 , as defined by Lafarge.

by appropriate volume averaging of the corresponding asymptotic velocity fields

- Derive the frequency-dependant viscous and thermal response functions such as the effective density $\rho(\omega)$ and bulk modulus $K(\omega)$ using analytical models of (3.1) Johnson et al. [6] and Allard and co-workers [7], and (3.2) Lafarge (refined model) [2].

Up