

Specific heat and magnetic susceptibility of single-crystalline ZnCrAlSe (x=0.15, 0.23)

E. Malicka, T. Groń, A. Ślebarski, A.W. Pacyna, J. Goraus, M. Fijalkowski,

J. Heimann

▶ To cite this version:

E. Malicka, T. Groń, A. Ślebarski, A.W. Pacyna, J. Goraus, et al.. Specific heat and magnetic susceptibility of single-crystalline ZnCrAlSe (x=0.15, 0.23). Journal of Physics and Chemistry of Solids, 2011, 72 (8), pp.974. 10.1016/j.jpcs.2011.05.008 . hal-00768586

HAL Id: hal-00768586 https://hal.science/hal-00768586

Submitted on 22 Dec 2012

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Author's Accepted Manuscript

Specific heat and magnetic susceptibility of singlecrystalline $ZnCr_{2-x}Al_xSe_4$ (x = 0.15, 0.23)

E. Malicka, T. Groń, A. Ślebarski, A.W. Pacyna, J. Goraus, M. Fijałkowski, J. Heimann

PII:S0022-3697(11)00136-3DOI:doi:10.1016/j.jpcs.2011.05.008Reference:PCS 6465

To appear in:Journal of Physics and
Chemistry of Solids

Received date:23 January 2011Revised date:4 May 2011Accepted date:16 May 2011



www.elsevier.com/locate/jpcs

Cite this article as: E. Malicka, T. Groń, A. Ślebarski, A.W. Pacyna, J. Goraus, M. Fijałkowski and J. Heimann, Specific heat and magnetic susceptibility of singlecrystalline $ZnCr_{2-x}Al_xSe_4$ (x = 0.15, 0.23), *Journal of Physics and Chemistry of Solids*, doi:10.1016/j.jpcs.2011.05.008

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting galley proof before it is published in its final citable form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Specific heat and magnetic susceptibility of single-crystalline $ZnCr_{2-x}Al_xSe_4$ (x = 0.15, 0.23)

E. Malicka^{a,*,1}, T. Groń^b, A. Ślebarski^b, A.W. Pacyna^c, J. Goraus^b,

M. Fijałkowski^b, J. Heimann^b

^aUniversity of Silesia, Institute of Chemistry, ul. Szkolna 9, 40-006 Katowice, Poland ^bUniversity of Silesia, Institute of Physics, ul. Uniwersytecka 4, 40-007 Katowice, Poland °The Henryk Niewodniczański Institute of Nuclear Physics, Polish Academy of Sciences, ul. Radzikowskiego 152, 1150 31-342 Kraków, Poland

ABSTRACT

A correlation between the second critical field H_{c2} of the helix to paramagnetic transition and the magnetic specific heat C-peak was found in $ZnCr_{2-x}Al_xSe_4$ spinel single crystals with x =0.15, 0.23. The specific heat peak is anomalously sharp for all finite magnetic fields used here and this points to a first order magneto-structural transition (from cubic to tetragonal symmetry). The C(T)-peak is increasingly suppressed as the external field increases. Approaching the Neel temperature T_N , a broad ac-magnetic susceptibility peak is observed for zero dc-magnetic field. That peak does not show an energy loss and thus points towards a return to a second order type of transition. The magnetic contribution to the specific heat displays a sharp peak at $T_{\rm N}$ and is maximal at the spin fluctuation temperature $T_{\rm sf} = 34$ K. $T_{\rm sf}$ is related to the maximum of the magnetic susceptibility at $T_{\rm m} = 40$ K (at 50 kOe) in the spin fluctuation region, as evidenced by the entropy exceeding 90% of the entropy calculated classically for the complete alignment of the Cr spins, (2-x)Rln(2S+1). The X-ray photoelectron spectroscopy (XPS) data indicate that Al-substitution does not affect $Cr^{3+} 3d^{3}$ electronic configuration.

Keywords: A. chalcogenides; B. crystal growth; C. photoelectron spectroscopy; D. magnetic properties; D. specific heat

*Corresponding author. Tel.:+48 323591627

E-Mail address: ewa.malicka@us.edu.pl (E. Malicka)

¹Address: Chemistry Department, University of Silesia, ul. Szkolna 9, 40-006 Katowice, Poland

1. Introduction

It is well known in literature that ZnCr₂Se₄ spinel is a matrix of various diluted systems where effects of site disorder, lattice frustration and random distribution of spin interactions create novel potential applications in spin-based electronic technology. ZnCr₂Se₄ reveals a spectacular transition to an antiferromagnetic (AFM) state at Néel temperature $T_{\rm N} = 20$ K with the dominating ferromagnetic (FM) interactions evidenced by large positive Curie-Weiss temperature $\theta_{CW} = 115$ K [1,2] and accompanied by a structural transformation from cubic $Fd\overline{3}m$ to tetragonal $I4_1/amd$ symmetry with a small contraction along the c axis [3], although, the structural investigations using synchrotron radiation defined the latter symmetry as orthorhombic Fddd [4]. Previous neutron-diffraction investigations [1,2] of ZnCr₂Se₄ spinel showed a helical AFM spin structure below ordering temperature having an FM arrangement in the (001) planes with a turning angle of 42° between the spins in adjacent (001) planes. Recently, sharp first-order phase transition anomalies in specific heat and negative thermal expansion (NTE) strongly suppressed by external magnetic fields at T_N were found [5]. Moreover, a metamagnetic transition at critical field H_{c1} of about 10 kOe for T = 2K, a breakdown of the conical spin arrangement at the critical field H_{c2} of about 65 kOe for T = 2 K, and full saturation magnetisation of about $3\mu_B$ per Cr ion above H_{c2} for the FM state in $ZnCr_2Se_4$ single crystal occurred [5]. At a temperature smaller than T_N , the zero-field-cooling

(ZFC) and field-cooling (FC) susceptibilities diverge, which suggests a spin frustration effect [5]. The complex ac dynamic magnetic susceptibility used to study the influence of temperature on critical fields in polycrystalline ZnCr₂Se₄ spinel [6] showed a parallel spin coupling in FM clusters in the range between $T_{\rm N} = 20.7$ K and $\theta_{\rm CW} = 55.1$ K as well as a strong drop of the value of the second critical field $H_{\rm c2}$ with temperature suggesting a spin frustration of the re-entrant type.

Magnetic investigations carried out on the stoichiometric single crystals of the ZnCr_{2-x}Al_xSe₄ spinel system with x = 0.15 and 0.23 [7] and non-stoichiometric polycrystalline Zn_xCr_yAl_zSe₄ spinels (0.13 $\leq z \leq 0.55$) [8,9] showed similar values of T_N , θ_{CW} and effective magnetic moments (Fig. 1). They also revealed saturation magnetic moment appeared to be decreased with rising Al- content (Fig. 1). For large Al-substitution, i.e. for z = 0.55, a spin-glass-like behaviour of cluster type with randomly oriented magnetic moments was observed as the ZFC-FC splitting went up to freezing temperature $T_f = 11.5$ K and the critical fields connected both with a transformation of the AFM spin spiral via conical magnetic structure into FM phase disappeared [8].

The present contribution reports XPS, magnetic and specific heat measurements for $ZnCr_{2-x}Al_xSe_4$ compensated spin array harbouring mixed couplings doped with the octahedrally coordinated nonmagnetic Al ions with x = 0.15 and 0.23. The novelty in this work are the specific heat studies, which are related both to the critical fields and critical temperature of the magnetic phase transitions. Therefore, an anomalous sharpness of the magnetic and specific heat peaks at higher magnetic fields as well as the correlation between the spin fluctuation temperature and the temperature corresponding to the maximum of magnetic susceptibility in the paramagnetic (PM) state were the main reason to revisit the $ZnCr_{0.85}Al_{0.15}Se_4$ and $ZnCr_{1.77}Al_{0.23}Se_4$ single crystals.

2. Experimental

2.1. Synthesis and crystal structure

Single crystals of ZnCr₂Se₄ spinel admixed with Al ions were grown from binary selenides ZnSe and Al₂Se₃ by the chemical vapour transport method with anhydrous CrCl₃ as the transporting agent. The method has been described in detail elsewhere [7]. Presence of aluminium in the obtained single crystals was checked by wavelength-dispersive X-ray fluorescence spectrometry (PW1410, Philips, Almelo, The Netherlands) with the following measurement conditions: side-window silver target X-ray tube operated at 50kV and 40mA; vacuum; K_{α} lines; flow-proportional counter (counter gas 90 % Ar + 10 % CH₄) for Al and Cr, flow-proportional counter with scintillation counter for Zn and Se; LiF(200) analyzing crystal for Zn, Cr and Se, PET(002) for Al; 40s counting time for Zn, Cr, Se and 100s for Al. Crystal structure determinations were performed with graphite monochromated Mo K α radiation using a KM-4 Xcalibur single-crystal diffractometer (Oxford Diffraction). The structure refinement was performed using the SHELXL-97 program package [10]. The compositions studied in this article are the same as reported in [7].

2.2. X-ray photoelectron spectroscopy (XPS)

X-ray photoelectron spectroscopy (XPS) spectra were taken using a PHI 5700/660 Physical Electronic spectrometer with monochromated Al K α radiation. The photoelectron spectra were analyzed by a hemispherical mirror analyzer with energy resolution of about 0.3 eV. In order to obtain free of contamination fresh surface, the samples were scraped in situ in 10^{-10} hPa vacuum. Overviews of the binding energy in the range -2 to 1400 eV and the corelevel characteristic peaks for Cr 2p have been measured. The background was subtracted using the Tougaard's approximation.

2.3. Magnetic and specific heat measurements

The ac mass susceptibility was measured using a Lake Shore 7225 ac susceptometer up to almost 60 kOe in the temperature range $4.2\div300$ K. Specific heat was measured with Quantum Design Physical Properties Measurement System (QD-PPMS) heat capacity option in temperature range $1.8\div300$ K and at magnetic field up to 70 kOe.

3. Results and discussion

3.1. X-ray photoelectron spectroscopy (XPS)

Figure 2 shows the Cr 2*p* XPS spectra of ZnCr₂Se₄ and ZnCr_{1.77}Al_{0.23}Se₄ single crystals with the spin-orbit splitting between the final Cr 2*p*_{3/2} and Cr 2*p*_{1/2} states of 9.5 eV. The Cr 2*p*_{3/2} states are split into two peaks at 574.2 and 575.2 eV. The peak separation with the binding energy difference ΔE about 1 eV is typical of the 3*d* elements with localized magnetic moment of 3 µ_B. Such a value of ΔE was reported for ZnCr₂Se₄ and for a number of other chalcogenide spinels [11,12]. It is important to notice that the splitting of the 2*p*_{3/2} states can be observed experimentally only for the 3*d* elements with localized magnetic moments larger than 2 µ_B [13,14]. Moreover, a linear relationship has been reported between the magnitude of the splitting of the 2*p*_{3/2} levels and the valence state of the 3*d* transition metals [13]. Based on these findings, it can be concluded that Cr ions in the ZnCr_{1.77} Al_{0.23}Se₄ single crystal have the electronic state Cr³⁺ 3*d*³, independently of the Al-substitution.

3.2. Magnetic properties

The results of temperature dependences of real χ' and imaginary χ'' components of ac magnetic susceptibility and specific heat at different external magnetic fields as well as the ac magnetic susceptibility versus magnetic field at different temperatures are presented in Figs. 3-5 for ZnCr_{1.85}Al_{0.15}Se₄ and in Figs. 6-8 for ZnCr_{1.77}Al_{0.23}Se₄. For $H_{dc} = 0$, $\chi'(T)$ manifests in

Fig. 3 a broad peak on approaching the Néel temperature T_N accompanied with lack of loss of energy visible in $\chi''(T)$, and points towards a second-order transition typical for conventional antiferromagnets. Similar behaviour has been observed for ZnCr₂Se₄ [5,6] and Zn_xCr_yAl_zSe₄ [7-9] spinels. On the other hand, the peak in C(T) for $H_{dc} = 0$ in Fig. 4 at T_N is anomalously sharp and points towards a first-order transition in accordance with the structural transformation from cubic Fd3m to tetragonal $I4_1/amd$ symmetry [3]. Application of magnetic field anomalously narrows the peak in $\chi'(T)$ curve in Fig. 3, especially, for $H_{dc} \ge 30$ kOe, and its intensity decreases at lower temperatures as in the case of specific heat peaks suggesting the first-order transition accompanied with a rapid energy lost visible in $\chi''(T)$. At 50 kOe, an additional broad peak at T_m in $\chi'(T)$ occurs, revealing the FM order in the PM state. The PM region is characterized by large positive Curie-Weiss (CW) temperature of 114 K (see Table 1). In the case of specific heat, the increasing magnetic field consistently suppresses the peak in C(T) curve in Fig. 4 and shifts it to lower temperatures pointing towards the first-order transition.

Figure 5 shows the ac magnetic susceptibility versus magnetic field at different temperatures for ZnCr_{1.85}Al_{0.15}Se₄ with the critical fields indicated by H_{c1} and H_{c2} . The first critical field, H_{c1} , connected with the metamagnetic transition and the breakdown of the spiral spin structure [3,5], slightly decreases with temperature while the second critical field, H_{c2} , connected with the breakdown of the conical spin arrangement [5,6], drops strongly with temperature. Beyond H_{c2} , magnetization reaches the FM state [7-9], and above T_N , both critical fields disappear. Low sensitivity to temperature of H_{c1} correlates well with the AFM order in the orthorhombic structure. On the other hand, strong sensitivity of H_{c2} to temperature means that FM coupling is weaker than AFM one, although the FM short-range interactions exist far above T_N in the cubic (spinel) structure reaching a maximum at T_m . It means that the increasing external magnetic fields extends the FM order from one side and

shifts both the AFM order and structural transformation from the other towards the lower temperatures.

The results for $ZnCr_{1.77}Al_{0.23}Se_4$, presented in Figs. 6-8, are similar to the ones for $ZnCr_{1.85}Al_{0.15}Se_4$, and they are considered in the context of increasing Al content in the sample. The values of T_N at 10, 30 and 50 kOe (Figs. 3 and 6), a peak of C(T) at 20, 40 and 60 kOe (Figs. 4 and 7) and $H_{c1} = 12.5$ kOe at 4.3, 6 and 12 K are the same for both single crystals (Figs. 5 and 8). Only H_{c2} at 4.3 K has a larger value for a sample with x = 0.15 compared to x = 0.23. It means that the larger Al-content, the lower value of H_{c2} at low temperatures. Similar results were found for $Zn_xSb_yCr_zSe_4$ [15]. Next, for $Zn_xSn_yCr_zSe_4$ the values of H_{c1} were of the same order, while the values of H_{c2} rapidly decreased with Sn-substitution, especially, when Sn-ions occupied octahedral sites in the spinel structure [16]. It is worth noticing that the peak in C(T) in Fig. 7 is fully suppressed by a magnetic field of 70 kOe where the helical spin arrangement is completely destroyed, indicating that the FM order dominates in the whole temperature range. Similar behaviour of the specific heat peaks and magnetic transitions may suggest that the strong magnetic field retains the cubic spinel structure in the whole range of temperatures, removing the structural instability observed in weak magnetic fields. This idea, of course, requires X-ray examinations in the strong magnetic field.

3.3. Specific heat studies

Figure 9 displays specific heat in zero magnetic field versus temperature in wide *T*-range for $ZnCr_{1.77}Al_{0.23}Se_4$. Above 50 K, *C*(T) can be well fitted by expression [17]:

$$C(T) = 9Rn \left(\frac{T}{\theta_D}\right)^3 \int_0^{\theta_D/T} \frac{x^4 e^x}{(e^x - 1)^2} dx,$$
(1)

where *R* is the universal constant, n = 7 is the number of atoms in the formula unit and θ_D is Debye temperature. The least-square fit of this expression to the experimental data yield

reasonable values of Debye temperature θ_D : ~358 K and 315 K for ZnCr_{2-x}Al_xSe₄ crystals with x = 0.15 and 0.23, respectively. The data of C(T) for B = 0 obtained for the sample with x = 0.15 are very similar to those obtained for the sample with x = 0.23, so they are not presented here. The θ_D values are of the same order for both compounds, although they are slightly higher for the one richer in chromium. We attribute the differences of θ_D to different elastic properties (bulk modules) of both spinels. On the other hand, the coupling between the spins and lattice may be realized via an exchange-striction mechanism similar to a spin-Peierls transition [5]. This results from the fact that volume energy (-pV) correlates to Zeeman energy (- σ H), because the Al-doped unit cell has a slight distortion visible in the anion parameter u, and its volume (V) is larger in comparison with the ZnCr₂Se₄ matrix (see Table 1). In this case, Al-doping should act as negative crystal pressure (-p) since the ionic radius of Al³⁺ is smaller than the Cr³⁺ one [18].

In the temperature region of $T < \sim 50$ K, the deviation observed between the measured and calculated C(T) data can be attributed to the magnetic ordering state in both compounds at $T < T_N$ and high energy spin fluctuations. The evidence for the magnetic phase transition (strongly field dependent) results from either the magnetic or specific heat data (c.f. Figs. 6 and 7), whereas the $\chi'(T)$ component of ac magnetic susceptibility clearly shows a broad maximum at $T_m \sim 40$ K and at 50 kOe for $ZnCr_{1.77}Al_{0.23}Se_4$ (see Table 1), which supports the high energy spin fluctuations. The inset to Fig. 9 shows the magnetic contribution ΔC to specific heat, where the difference $\Delta C = C_{exp} - C$ expresses the measured specific heat reduced by the calculated one on the base of the Debye theoretical model (Eq. 1). ΔC displays a sharp peak at $T = T_N$ and a maximum at ~ 34 K, characteristic for magnetic fluctuations. For $T < T_N$, $\Delta C(T)$ can be described by the expression for an anisotropic spiral structure with an activation gap in magnon dispersion [19] $\Delta C \sim T^3 exp(-E_g/k_BT)$ and the spin fluctuation contribution to ΔC of $\delta T^3 ln(T/T_{sf})$, with the spin fluctuation temperature $T_{sf} = \sim 34$ K.

Figure 10 shows entropy $S(T) = \int_{0}^{T} \frac{C(T)}{T} dT$ calculated at different magnetic fields B for

ZnCr_{1.85}Al_{0.15}Se₄ (the entropy S(T) is the same for the sample with x = 0.23, and it is not presented in this paper). S(T) goes up slowly to zero as $T \rightarrow 0$ in order to meet the third thermodynamic law. At temperature $T_{\rm N} = 21.3$ K (B = 0), the value of the magnetic and phonon contribution to the entropy is only ~8.2 J/(mol·K), i.e., much lower than the magnetic contribution $S_m = (2-x)Rln(2S+1) = 21.31 J/(mol·K)$ calculated per molecule for S = 3/2 of Cr^{3+} . The values of S_m for the spinels under study and the $ZnCr_2Se_4$ matrix (for comparison) are collected in Table 1. Figures 4 and 7 clearly show that application of magnetic fields strongly suppresses the magnetic transition in doped ZnCr₂Se₄ (the same effect has been observed for pure $ZnCr_2Se_4$ [5]) and shifts the peak in C/T to lower temperatures. The anomaly is fully suppressed by the field of 7 T. To estimate the magnetic contribution to entropy S, we calculated magnetic entropy ΔS at T_N, by integrating [C(T, B = 0) – C(T, B = 7) T)]/T over the transition region, which is only ~ 6 % of the full magnetic entropy expected for the complete alignment of the Cr spins. Almost the same result has been obtained recently for $ZnCr_2Se_4$ [5]. This anomaly was interpreted in Ref. 5 as a result of spin fluctuations in the paramagnetic regime. Our specific heat data fully confirm this explanation. We also note that the alloying does not significantly change magnetic properties of the ZnCr₂Se₄ sample.

Figures 11 and 12 show the standard procedure with metamagnetic transitions to plot the phase diagrams H_c vs. T, T_N vs. H and C_m vs. H for ZnCr_{1.85}Al_{0.15}Se₄ and ZnCr_{1.77}Al_{0.23}Se₄. Metamagnetic threshold connected with the first critical field H_{c1} does not depend on temperature below T_N and it does not correlate with specific heat for both single crystals. On the other hand, both diagrams show a strict correlation between the second critical field H_{c2} , Néel temperature T_N and the temperature position of specific heat peak C_m suggesting that the

structural instability can be removed by a magnetic field, because a magnetostrictive coupling is possible in this case.

4. Conclusions

The XPS spectra of the $ZnCr_{2-x}Al_xSe_4$ single crystals with x = 0.15 and 0.23 revealed the binding energy difference of about 1 eV characteristic for 3d elements with localized magnetic moment of 3 μ_B . This finding is fully consistent with the results of bulk magnetic measurements. The first critical field connected with the metamagnetic transition and the breakdown of the spiral spin structure is temperature-independent below T_N and it does not correlate with specific heat for both single crystals under study. The second critical field connected with the breakdown of the conical spin arrangement strongly depends on temperature and the magnetic field applied. It correlates well with the magnetic and specific heat transitions. The values of the Debye temperature θ_D , estimated from the Debye theory, are of the same order for both compounds, although they are slightly higher for the one richer in chromium. These differences in θ_D may suggest their different elastic properties allowing the magnetostrictive coupling between magnetic and lattice excitations. Estimation of the magnetic contribution to specific heat showed a maximum at 34 K, characteristic for magnetic fluctuations, also visible in the ac magnetic susceptibility with the broad maximum at 40 K and in static magnetic field of 50 kOe. The magnetic and specific heat investigations of the single crystals under study provide experimental evidence that the structural transformation is inextricably linked to the magnetic order.

Acknowledgments

This work is partly founded from science Grant No. N N204 145938.

References

- F.K. Lotgering, in: Proceedings of the International Conference on Magnetism, Nottingham, 1964 (London, Institute of Physics, 1965).
- [2] R. Plumier, J. Phys. (Paris) 27 (1966) 213-219.
- [3] R. Kleinberger, R. de Kouchkovsky, C.R. Acad. Sci. Paris, Ser. B 262 (1966) 628-630.
- [4] M. Hidaka, M. Yoshimura, N. Tokiwa, J. Akimitsu, Y.J. Park, J.H. Park, S.D. Ji, K.B. Lee, phys. status solidi (b) 236 (2003) 570-577.
- [5] J. Hemberger, H.-A. Krug von Nidda, V. Tsurkan, A. Loidl, Phys. Rev. Lett. 98 (2007) 147203(4).
- [6] T. Groń, E. Malicka, A.W. Pacyna, Physica B 404 (2009) 3554-3558.
- [7] E. Malicka, A. Waśkowska, T. Mydlarz, D. Kaczorowski, J. Alloys Compd. 440 (2007) 15.
- [8] T. Groń, E. Malicka, H. Duda, A.W. Pacyna, T. Mydlarz, R. Sitko, M. Pawełczyk, J. Phys. Chem. Solids 70 (2009) 1175-1180.
- [9] E. Malicka, T. Groń, A.W. Pacyna, E. Maciążek, H. Duda, M. Pawełczyk, R. Sitko, B. Zawisza, J. Alloys Compd. 480 (2009) 67-69.
- [10] G.M. Sheldrick, SHELXL-99. Program for Crystal Structure Refinement, University of Göttingen, 1999.
- [11] E. Malicka, A.Waśkowska, J.Heimann, T. Mydlarz, R. Sitko, D. Kaczorowski, J. Solid State Chem. 181 (2008) 1970-1976.
- [12] V. Tsurkan, St. Plogmann, M. Demeter, D. Hartmann, M. Neumann, Eur. Phys. J. B 15 (2000) 40-403.

- [13] S. Plogmann, T. Schlathölter, J. Braun, M. Neumann, Yu.M. Yarmoshenko, M.V.
 Yablonskikh, E.I. Shreder, E.Z. Kumarev, A. Wrona, A. Ślebarski, Phys. Rev. B 60 (1999)
 6428-6438.
- [14] A. Ślebarski, M. Neumann, B. Schneider, J. Phys.: Condens. Matter 13 (2001) 5515-5518.
- [15] E. Malicka, T. Groń, H. Duda, A.W. Pacyna, J. Krok-Kowalski, Acta Phys. Pol. A 116 (2009) 964-966.
- [16] T. Groń, I. Jendrzejewska, E. Maciążek, A.W. Pacyna, H. Duda, P. Zajdel, J. Krok-Kowalski, Acta Phys. Pol. A 116 (2009) 971-973.
- [17] C. Kittel: Introduction to Solid State Physics (John Wiley & Sons, Inc., New York, 1960).
- [18] R.D. Shannon, Acta Cryst. A 32 (1976) 751-767.

Accef

[19] L.J. Sundström, Low Temperature Heat Capacity of the Rare Earth Metals, in *Handbook on the Physics and Chemistry of Rare Earth*, Vol. 1 (Eds. K.A. Gschneidner, Jr. And Le R. Eyring) North-Holland Publishing, Amsterdam, 1978, p. 379.

Figure captions

Fig. 1. The dependence of the Néel (T_N) , freezing (T_f) and saturation magnetization (μ_{sat}) on Al content in single-crystalline ZnCr_{2-x}Al_xSe₄ [7] and polycrystalline Zn_xCr_yAl_zSe₄ [8] spinels.

Fig. 2. Cr 2p – XPS spectra of the ZnCr_{1.77}Al_{0.23}Se₄ and ZnCr₂Se₄ single crystals.

Fig. 3. Real χ' and imaginary χ'' components of ac magnetic susceptibility vs. temperature *T* recorded at $H_{ac} = 1$ Oe with f = 120 Hz taken at different external magnetic fields for ZnCr_{1.85}Al_{0.15}Se₄. The Néel T_N and T_m temperatures are indicated by arrows.

Fig. 4. Specific heat, C, versus temperature T taken at different external magnetic fields for $ZnCr_{1.85}Al_{0.15}Se_4$.

Fig. 5. Ac magnetic susceptibility, χ_{ac} , vs. static magnetic field H recorded at internal oscillating magnetic field $H_{ac} = 1$ Oe with internal frequency f = 120 Hz taken at different temperatures for ZnCr_{1.85}Al_{0.15}Se₄. The critical fields H_{c1} and H_{c2} are indicated by arrows.

Fig. 6. Real χ' and imaginary χ'' components of ac magnetic susceptibility vs. temperature *T* recorded at $H_{ac} = 1$ Oe with f = 120 Hz taken at different external magnetic fields for ZnCr_{1.77}Al_{0.23}Se₄. The Néel T_N and T_m temperatures are indicated by arrows.

Fig. 7. Specific heat, *C*, versus temperature *T* taken at different external magnetic fields for $ZnCr_{1.77}Al_{0.23}Se_4$.

Fig. 8. Ac magnetic susceptibility, χ_{ac} , vs. static magnetic field H recorded at internal oscillating magnetic field $H_{ac} = 1$ Oe with internal frequency f = 120 Hz taken at different temperatures for ZnCr_{1.77}Al_{0.23}Se₄. The critical fields H_{c1} and H_{c2} are indicated by arrows.

Fig. 9. Specific heat C vs. temperature T in zero magnetic field for $ZnCr_{1.77}Al_{0.23}Se_4$ and the

best fit of Debye expression (solid red line), $C(T) = 9Rn \left(\frac{T}{\theta_D}\right)^3 \int_0^{3\theta_D/T} \frac{x^4 e^x}{(e^x - 1)^2} dx$, to the

experimental data denoted as C_{exp} (circles). Inset: magnetic contribution $\Delta C = C_{exp} - C$ to the specific heat vs. temperature *T*. In the temperature region $T < T_N$, $\Delta C(T)$ expresses magnetic contribution $\Delta C \sim T^3 \exp(-E_g/k_B T)$ due to anisotropic spiral structure with an activation gap in magnon dispersion (dashed red line) and the spin fluctuation contribution $\Delta C \sim \delta T^3 \ln(T/T_{sf})$, with the spin fluctuation temperature $T_{sf} = -34$ K (denoted by arrow).

Fig. 10. Entropy S vs. temperature T at different magnetic fields B for $ZnCr_{1.85}Al_{0.15}Se_4$.

Fig. 11. The phase diagrams for $ZnCr_{1.85}Al_{0.15}Se_4$: critical fields H_{c1} and H_{c2} vs. temperature *T*, Néel temperature T_N vs. magnetic field *H* and temperature position of specific heat peak C_m vs. magnetic field *H*.

Fig. 12. The phase diagrams for $ZnCr_{1.77}Al_{0.23}Se_4$: critical fields H_{c1} and H_{c2} vs. temperature *T*, Néel temperature T_N vs. magnetic field *H* and temperature position of specific heat peak C_m vs. magnetic field *H*.

Highlights

>Al-substitution does not affect the Cr₃₊ $3d_3$ electronic configuration. > χ ''(T) reveals energy loss only in the case of the first-order transition. > The larger Al-content, the lower value of H_{c2} at low temperatures. > Larger Al-content makes easier the transfer of phonon momentum to the electron gas.

Accepted manuscript

























Specific heat, C_p , versus temperature *T* taken at different external magnetic fields for $ZnCr_{1.77}Al_{0.23}Se_4$. The specific heat peak is anomaly sharp for all magnetic fields and points towards a first-order transition in accordance with the structural transformation from cubic to tetragonal symmetry.

Accepted manuscript

