



HAL
open science

Simultaneous measurement of thermal lens and temperature map in ytterbium-doped fluoride crystal

Justine Boudeile, Julien Didierjean, Frédéric Druon, François Balembois, Patrick Georges, Jean-Louis Doualan, Patrice Camy, Abdelmjid Benayad, Vivien Menard, Richard Moncorgé

► To cite this version:

Justine Boudeile, Julien Didierjean, Frédéric Druon, François Balembois, Patrick Georges, et al.. Simultaneous measurement of thermal lens and temperature map in ytterbium-doped fluoride crystal. *Advanced Solid-State Photonics*, Jan 2008, Nara, Japan. hal-00808709

HAL Id: hal-00808709

<https://hal.science/hal-00808709v1>

Submitted on 6 Apr 2013

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Simultaneous measurement of thermal lens and temperature map in ytterbium-doped fluoride crystals

J. Boudeile, J. Didierjean, F. Druon, F. Balembos and P. Georges

Laboratoire Charles Fabry de l'Institut d'Optique, CNRS, Univ. Paris-Sud

Campus Polytechnique, RD 128, 91127 Palaiseau Cedex

e-mail adress: justine.boudeile@institutoptique.fr

J.L. Doualan, P. Camy, A. Benayad, V. Ménard and R. Moncorgé

Centre de recherche sur les Ions et les Matériaux pour la Photonique (CIMAP), CNRS 663 CEA-CNRS-ENSI Caen

Université de Caen, 6 Boulevard Maréchal Juin, 14050 Caen Cedex

Abstract : We report on the simultaneous characterization of temperature map and thermal lensing in $\text{Yb}^{3+}:\text{CaF}_2$ and $\text{Yb}^{3+}:\text{SrF}_2$ crystals under high-power pumping with/without laser operation. This *in situ* measurement would allow proper designs of high-power cavities.

©2008 Optical Society of America

OCIS codes: 140.5680 Rare earth, solid state laser, 140.3480 Laser, diode-pumped

1- Introduction

Interest in Yb^{3+} -doped materials is still growing, owing to the increasing availability of high power InGaAs laser diodes emitting around 980nm. Ytterbium has very attractive properties including a weak quantum defect, and no problem of concentration quenching. Fluoride crystals, having the cubic Calcium fluoride structure, are well-known to be transparent in a large wavelength region (from IR to VUV) and mix the advantages of the oxide crystals and glass. In particular, they feature broad absorption and emission bands. Fluoride ytterbium-doped crystals are therefore very promising for the development of solid-state lasers and amplifiers[1,2]. Here, we present the experimental assessment of both the temperature map and the thermal lens (TL) properties of $\text{Yb}^{3+}:\text{CaF}_2$ and $\text{Yb}^{3+}:\text{SrF}_2$ under high power pumping, with or without laser operation.

2- Experimental set up

The experimental setup is shown in Fig.1. The 5 mm 3-at % $\text{Yb}^{3+}:\text{CaF}_2$ or 3-at % $\text{Yb}^{3+}:\text{SrF}_2$ is directly pumped with a 120 W 400 μm core fiber-coupled laser diode (LIMO) emitting at 980 nm. The probe beam, generated by a fiber-coupled LED emitting at 660 nm, is collimated and superposed with the pump beam. The crystal is imaged through a magnifying system composed of two lenses to a Shack-Hartmann wave-front sensor (HASO64, Imagine Optics). A bandpass filter at 660 nm is placed in front of the analyzer to remove the parasitic beams. With pump off, a reference wavefront is recorded to cancel all static aberrations from the optical elements and the cold crystal. The reference is subtracted from the measured wavefront when the pump is on. Simultaneously, an 8 μm -12 μm high resolution thermal camera with a germanium objective is used to measure the temperature map of one facet of the crystal.




Fig. 1. (a) Experimental setup and (b) zoom of the laser cavity design. PM = plane mirror and IR = interferential filter.

3- Experimental results

The TL dioptric power versus absorbed pump power is plotted in Fig. 2 for CaF₂ and SrF₂ crystals with or without laser operation. We notice that all TL dioptric powers (D_{th}) are negative. Since the thermal lens focal length (f_{th}) is inversely proportional to D_{th} , the measured thermal lenses are divergent for both crystals. This result can be understood as follows. The TL dioptric power can be expressed as [3]:

$$D_{th} = \frac{1}{f_{th}} = \frac{\eta_h P_{abs}}{2\pi w_p^2 \kappa_c} \left[\left(\frac{dn}{dT} \right) + (n-1)(1+\nu)\alpha_T + 2n^3 \alpha_T C_r \right] = \frac{\eta_h P_{abs} \chi}{2\pi w_p^2 \kappa_c} \quad (1)$$

where η_h is the fractional thermal load, P_{abs} the absorbed pump power, w_p the pump beam waist radius, κ_c the thermal conductivity, n the refractive index, ν the Poisson's ratio, α_T the coefficient of thermal expansion, C_r the photo-elastic constant, χ the thermo-optic coefficient. The absolute values of the $(n-1)(1+\nu)\alpha_T$ and $2n^3 \alpha_T C_r$ terms are similar and compensate each other. So, the last term of χ determines the sign of D_{th} , all the other terms being positive. Since the values of (dn/dT) for the CaF₂ and SrF₂ are equal to $-10.6 \cdot 10^{-6} \text{ K}^{-1}$ and $-12 \cdot 10^{-6} \text{ K}^{-1}$ respectively, divergent thermal lenses are expected.




Fig 2. TL dioptric power versus absorbed pump power for CaF₂:Yb³⁺ and SrF₂:Yb³⁺ crystals with and without laser operation.

The values of TL focal lengths for CaF₂:Yb³⁺ and SrF₂:Yb³⁺ crystals are equal to -119 cm for an absorbed power of 40 W and -113 cm for an absorbed power of 18 W respectively (fig. 2). Note that the CaF₂:Yb³⁺ crystal needs a higher absorbed pump power to measure the same TL focal length. This difference could be explained by the lower values of the thermal conductivity κ_c and the coefficient of thermal expansion α_T for the SrF₂:Yb³⁺ crystal: the SrF₂ crystal is not as efficient as CaF₂ to dissipate the heat. Therefore, the temperature gradient is higher in SrF₂ and TL focal length increases more quickly with absorbed power.

Using the expression of the TL dioptric power (1), and taking into account the divergence of the pump beam in the expression of w_p , we are able to fit the measured TL dioptric power with laser effect versus incident power (fig. 3). The values of the parameters for the fits are summarized in Table 1.

Crystals	CaF ₂ :Yb ³⁺ (3%)	SrF ₂ :Yb ³⁺ (3%)
κ_c (W.m ⁻¹ K ⁻¹)	6.0	3.3
η_h	0.07	0.07

Table 1. Parameters used for the fit of the TL dioptric power.

When operating in laser condition, the fractional thermal load η_h was set to a value slightly higher than the quantum defect $1-(\lambda_p/\lambda_l)$ where λ_p is the pump wavelength and λ_l the laser wavelength (quantum defects for CaF₂ and SrF₂ are equal to 0.067 and 0.069 respectively). Indeed, the intracavity power is high enough to consider that the laser

extraction efficiency is equal to one over the whole lasing crystal volume. Given this assumption, the good agreement with the experimental data indicates that the heat generated in these crystals is mostly due to the quantum defect, and that the contribution of nonradiative effects is negligible.




Fig. 3. The TL dioptric power versus incident power fitted for (a) $\text{CaF}_2:\text{Yb}^{3+}$ and (b) $\text{SrF}_2:\text{Yb}^{3+}$ crystals with laser effect or not.

The evolution of the temperature gradient in the crystal (ΔT) versus incident pump power is shown in Fig. 4 with or without laser operation. A weak temperature gradient is observed for both crystals when the laser is off. This result corroborates the weak measured TL dioptric power without laser operation.




Fig. 4. Temperature gradient versus incident pump power for (a) $\text{CaF}_2:\text{Yb}^{3+}$ and (b) $\text{SrF}_2:\text{Yb}^{3+}$ crystals with or without laser operation

4- Conclusion

To our best knowledge, this is the first combined measurement of both thermal lens properties and temperature map in ytterbium-doped CaF_2 and SrF_2 crystals. These *in situ* measurements indicate different interesting quantitative results: first the presence of a small negative thermal lenses resulting from various competing (thermo-optics and thermo-mechanical) effects; second, strong differences of behaviour between lasing and not lasing conditions which is important since it may imply high thermal shocks; third, that the thermal loads are mainly due to the quantum defect implying very few other parasitic non-radiative processes.

5- References

- [1] M. Siebold, J. Hein, M. C. Kaluza, and R. Uecker, "High-peak-power tunable laser operation of $\text{Yb}:\text{SrF}_2$," *Opt. Lett.* **32**, 1818-1820 (2007)
- [2] V. Petit, J.L. Doualan, P. Camy, V. Menard and R. Moncorgé, "CW and tunable operation of Yb^{3+} -doped CaF_2 ," *Appl. Phys. B* **78**, 681-684 (2004)
- [3] S. Chenais, F. Druon, S. Forget, F. Balembois, P. Georges, "on thermal effects in solid-state lasers: The case of ytterbium-doped materials", *Progress Quantum Elect.*, **30** (4), 89-153 (2006)