



Anisotropy of the Sommerfeld Coefficient in Magnesium Diboride Single Crystals

Z. Pribulova, Thierry Klein, Jacques Marcus, C. Marcenat, F. Levy-Bertrand, M. S. Park, H. G. Lee, B.W. Kang, S. I. Lee, S. Tajima, et al.

► To cite this version:

Z. Pribulova, Thierry Klein, Jacques Marcus, C. Marcenat, F. Levy-Bertrand, et al.. Anisotropy of the Sommerfeld Coefficient in Magnesium Diboride Single Crystals. Physical Review Letters, 2007, 98 (13), pp.137001. <10.1103/PhysRevLett.98.137001>. <hal-00957175>

HAL Id: hal-00957175

<https://hal.science/hal-00957175v1>

Submitted on 10 Mar 2014

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

Anisotropy of the Sommerfeld Coefficient in Magnesium Diboride Single Crystals

Z. Pribulova,^{1,2,*} T. Klein,^{1,2} J. Marcus,¹ C. Marcenat,³ F. Levy,³ M. S. Park,⁴ H. G. Lee,⁴ B. W. Kang,⁴ S. I. Lee,⁴ S. Tajima,⁵ and S. Lee⁶

¹*Institut Néel–CNRS, F-38042 Grenoble Cedex 9, France*

²*Université Joseph Fourier, F-38041 Grenoble, France*

³*CEA-Grenoble, Département de Recherche Fondamentale sur la Matière Condensée, F-38054 Grenoble, France*

⁴*NVCRICS and Department of Physics, Pohang University, Pohang 790-784 Republic of Korea*

⁵*Department of Physics, Osaka University, Osaka 560-0043, Japan*

⁶*Superconductivity Research Laboratory, ISTEC, Shinonome 1-10-13, Koto-ku, Tokyo 135-0062, Japan*

(Received 21 December 2006; published 28 March 2007)

The anisotropic field dependence of the Sommerfeld coefficient γ has been measured down to $B \rightarrow 0$ by combining specific heat and Hall probe magnetization measurements in MgB₂ single crystals. We find that $\gamma(B, \theta)$ is the sum of two contributions arising from the σ and π band, respectively. We show that $\gamma_\sigma(B, \theta) = B/B_{c2}(\theta)$ where $B_{c2}(\theta) = B_{c2}^{ab}/\sqrt{\sin^2\theta + \Gamma^2\cos^2\theta}$ with $\Gamma \sim 5.4$ (θ being the angle between the applied field and the c axis) and $\gamma_\pi(B, \theta) = \gamma_\pi(B) = B/B_\pi(B)$. The “critical field” of the π band B_π is fully isotropic but field dependent increasing from ~ 0.25 T for $B \leq 0.1$ T up to 3 T $\sim B_{c2}^c$ for $B \rightarrow 3$ T. Because of the coupling of the two bands, superconductivity survives in the π band up to 3 T but is totally destroyed above for any orientation of the field.

DOI: 10.1103/PhysRevLett.98.137001

PACS numbers: 74.70.Ad, 74.25.Op, 74.72.-h

It is now well established that the anisotropy parameter (Γ) of magnesium diboride (MgB₂) is strongly field and temperature dependent [1,2]. This is a direct consequence of the coexistence of two weakly coupled superconducting bands. As suggested by point contact spectroscopy [3] or small angle neutron scattering [4] experiments, the so-called π band is very sensitive to magnetic field and, above some “crossover” field on the order of 0.5–1 T, the anisotropy is then mainly given by the parameters of the quasi-2D σ band leading to $\Gamma = \Gamma_{H_{c2}} = H_{c2}^{ab}/H_{c2}^c$ (~ 5 –6 at low temperature, H_{c2}^{ab} and H_{c2}^c being the upper critical fields parallel to the ab planes and c axis, respectively). On the other hand, at low field, the anisotropy has to be averaged over the entire Fermi surface [5] leading to $\Gamma \sim \Gamma_{H_{c1}} \sim 1$ in good agreement with H_{c1} measurements [2].

Similarly, as a consequence of this suppression of the π band, preliminary measurements of the Sommerfeld coefficient $\gamma = \lim_{T \rightarrow 0} C_{el}/T$ (C_{el} being the electronic contribution, to the specific heat) by Bouquet *et al.* [6] clearly showed that its field dependence is highly nonlinear. However, the details of the nature of the superconducting state remained unknown. We will show here that, above ~ 0.3 T, superconductivity is induced in the π band by coupling with the σ band leading to a shrinking of the vortex core from $\xi_\pi(0) \sim 350$ Å down to $\xi_\pi = \xi_\sigma^c \sim 100$ Å for $B \sim 3$ T. Superconductivity is completely destroyed in this band above 3 T for any orientation of the magnetic field.

We present the first detailed analysis of the angular and field dependence of γ by combining specific heat and Hall probe magnetization measurements. In classical superconductors, the angular dependence of γ is determined by the B/B_{c2} ratio with $B_{c2} = B_{c2}^{ab}/\sqrt{\sin^2\theta + \Gamma^2\cos^2\theta}$ (θ being the angle between the c axis and the field). We show that, in

MgB₂, the contribution of the σ band to γ is directly proportional to $B/B_{c2}(\theta)$, whereas the contribution of the π band is isotropic but highly nonlinear in field. For $T \geq 10$ K, the influence of the small gap is smeared out by the temperature and $\Delta C_p/T = f(B/B_{c2}(T, \theta))$. Specific heat measurements have been performed on single crystals of MgB₂ grown under high pressure [7,8] (with typical dimensions of few hundred microns) using an ac technique. This high sensitivity technique is very well adapted to measure C_p of very small samples and to carry continuous measurements during field sweeps at a given temperature. We were thus able to obtain the field dependence of the Sommerfeld coefficient continuously on the entire field range for different θ values. A precise *in situ* calibration of the thermocouple used to record the temperature oscillations was obtained from measurements on ultrapure silicon.

Figure 1 displays this field dependence for $H \parallel c$ and $H \parallel ab$ (at $T = 2$ K). As previously observed by Bouquet *et al.*, the γ vs H_a curve is nonlinear. Those measurements suggested that γ is isotropic below 0.2 T, becoming anisotropic for $H \geq 0.5$ T. However, for fields up to a few H_p , the first penetration field, the measurements are strongly hysteretic reflecting different vortex distributions in the sample [see [9] and inset of Fig. 1(a)]. The proximity of H_p may thus cast some doubt on the field dependence of γ observed in [6] at low field. As shown in the inset of Fig. 1(a), the first penetration field H_p can be clearly identified on the ascending branch of zero field cooled cycles as $\gamma = 0$ up to $H_a = H_p$ and rises sharply above this field due to the fast proliferation of vortices in the sample. Vortices remain pinned in the samples for decreasing fields and $\gamma \neq 0$ down to $H_a = 0$. To clearly identify the field dependence of γ in this region it was important to




FIG. 1. Magnetic field dependence of the Sommerfeld coefficient γ at $T = 2.5$ K for $H \parallel c$ and $H \parallel ab$. In the inset: low field dependence showing the hysteretic behavior related to flux penetration and pinning. (b) Sommerfeld coefficient γ for $H \parallel c$ and $H \parallel ab$ as a function of the average field B . In the inset: average field B deduced by Hall probe magnetometry (see sketches) as a function of the applied field H_a .

determine the *true* induction B in the sample. We thus performed Hall probe magnetization measurements on the same sample for both field directions using a miniature Hall probe array [see sketches in Fig. 1(b)]. The induction B at the surface of the sample has been averaged over ~ 25 points for $H \parallel c$ and ~ 10 points for $H \parallel ab$ (the average field is hereafter noted B). The B vs H_a curves are displayed in the inset of Fig. 1(b) and the corresponding γ vs B curves in Fig. 1(b). As shown, γ is perfectly linear and isotropic at low field (note that, as expected γ vs B is completely reversible). However, the linear regime is only visible up to ~ 0.1 T and γ remains isotropic up to $B \sim 0.3$ T.

As discussed in [6], in MgB_2 the nonlinear behavior can be qualitatively understood by writing $\gamma = \omega\gamma_\pi + (1 - \omega)\gamma_\sigma$, where ω is the relative weight of the π band (on the order of $\frac{1}{2}$ [10]). Assuming that all excitations are localized in the vortex cores, i.e., that $\gamma_i \propto \gamma_N(\xi_i/a_0)^2$ for $B < B_i = \Phi_0/2\pi\xi_i^2$ and $\gamma_i = \gamma_N$ for $B > B_i$ (with $i = \pi$ or σ), one gets two linear behaviors corresponding to $B < B_\pi$ and $B > B_\pi$, respectively [introducing $a_0 \sim \sqrt{(\Phi_0/B)}$]. The low field linear behavior is hence clearly visible but limited on a very restricted field range and, as discussed below, the high field linear behavior is only observed for $\theta \neq 0$ (for $B > 3$ T).

To get a better description of $\gamma(B, \theta)$, we measured the angular dependence of the Sommerfeld coefficient for various applied fields [see inset of Fig. 2(a), at $T = 2$ K]. In a classical single gap superconductor γ is fully determined by the B/B_{c2} ratio. In clean systems, deviations from the above mentioned linear behavior may be expected [11], but γ still remains a function of B/B_{c2} . Obviously such a simple behavior does not hold in MgB_2 since γ is isotropic up to ≈ 0.3 T and its anisotropy then rises up to 5–6 for $B \rightarrow B_{c2}$. However, as shown in Fig. 2(a), subtracting from $\gamma(\theta)$ a constant for each H_a value, i.e., taking $[\gamma/\gamma_N - \omega a(B)]/(1 - \omega)$ instead of γ/γ_N , leads to a collapse of all the data on a single curve when plotted as a function of $B/B_{c2}(\theta) \propto B\sqrt{\sin^2\theta + \Gamma^2\cos^2\theta}$ [12] with $\Gamma = \Gamma_{H_{c2}} = 5.4$. We here assumed that $\gamma_\pi(B, \theta)$ is isotropic and hence depends only on B [$\gamma_\pi/\gamma_N = a(B)$] and that $\gamma_\sigma(B, \theta)/\gamma_N = [\gamma/\gamma_N - \omega a(B)]/(1 - \omega) = f(B/B_{c2}(\theta))$. It is important to note that we made *no assumption* on the form of the function f and directly got $\gamma_\sigma(B, \theta) = [B/B_{c2}(\theta)]\gamma_N$ as expected in classical (dirty) superconductors. Note also that γ appears to be fully isotropic below 0.3 T but, in this field range, the contribution of the σ band is less than a few percent and the corresponding variation is at the limit of our experimental resolution [13].

The $a(B) = \gamma_\pi/\gamma_N$ values are displayed in the inset of Fig. 2(b) (solid symbols) together with direct determinations from magnetic field sweeps for the indicated θ values: $\gamma_\pi/\gamma_N = [\gamma/\gamma_N - (1 - \omega)B/B_{c2}(\theta)]/\omega$ (open symbols). For $B \geq 3$ T, $\gamma_\pi = \gamma_N$ showing that superconductivity is completely destroyed in this band at high field. This is further emphasized in the field dependence of γ at fixed $\theta \neq 0$ values [Fig. 2(b)] which clearly shows that γ becomes perfectly linear for $B \geq 3$ T in all directions. Note that the linear fits intercept the $B = 0$ axis at $\omega \sim 0.5$ in good agreement with numerical calculations [10]. With this ω value, we did *not* observe any linear high field behavior for $H \parallel c$ but γ can be rather described by a $(B/B_{c2})^\alpha$ law (with $\alpha \sim 0.4$ – 0.5). As discussed in [14], it is then possible to introduce an *effective* field dependent ξ_{eff} value: $\xi_{\text{eff}}(B) = \sqrt{\omega\xi_\pi(B)^2 + (1 - \omega)\xi_\sigma^2}$ with $a(B) = [\xi_\pi(B)/a_0]^2$ (for $B \leq 3$ T). This effective value, combined with a field dependent penetration depth can then be used to describe all physical properties (see also




FIG. 2. (a) $[\gamma/\gamma_N - \omega a(B)]/(1 - \omega)$ as a function of B/B_{c2} with $B_{c2} = B_{c2}^{ab}/\sqrt{\sin^2\theta + \Gamma^2\cos^2\theta}$ (with $\omega \sim \frac{1}{2}$ and $\Gamma \sim 5.4$), in the inset γ/γ_N as a function of θ for the indicated values of the applied field. (b) Field dependence of the Sommerfeld coefficient for the indicated field directions showing that γ becomes linear for $B \geq 3$ T. In the inset: field dependence of the contribution of the π band: $\gamma_\pi/\gamma_N = a(B)$ deduced from the angular measurements (solid squares) and magnetic sweeps at the indicated angles (open symbols, see text for details).

[15]). The $\xi_\pi(0)$ value would correspond to a critical field for the π band on the order of $B_\pi(0) = 0.25$ T but superconductivity still survives in this band due to the coupling with the σ band leading to a shrinking of the vortex core from $\xi_\pi \approx 350$ Å below 0.1 T down to $\xi_\pi = \xi_\sigma^{ab}$ for $B \sim 3$ T = B_{c2}^c . However, it is important to note that, since the π band is isotropic, it can have only one θ independent B_{c2} value and superconductivity is hence destroyed in this band in all direction for $B \geq 3$ T.

As expected the $\xi_\sigma^{ab} \sim 100$ Å and $\xi_\sigma^c \sim 20$ Å values are very close to the BCS single band estimate: $\hbar v_{F,\sigma}/\pi\Delta_\sigma \sim 130$ Å and ~ 20 Å in the ab planes and along the c direc-

tion, respectively ($v_{F,\sigma}$ being the Fermi velocity of the σ band $\sim 4.6 \times 10^7$ cm/s and $\sim 0.7 \times 10^7$ cm/s for the two crystallographic directions and Δ_σ the large gap value ~ 7.0 meV). More surprisingly, the as-deduced ξ_π value (~ 350 Å) is also quite close to $\hbar v_{F,\pi}/\pi\Delta_\pi \sim 400$ –500 Å [taking an average $v_{F,\pi}$ value on the order of $(5$ – $6) \times 10^7$ m/s [5,16] and $\Delta_\pi \sim 2.4$ meV]. Indeed, it has been suggested by Zhitomirsky *et al.* [16] that this single band estimate should not be applicable in MgB₂ and that in the clean limit $\xi_\pi^c/\xi_\sigma^c \leq \sqrt{\omega\langle v_{F,\pi}^2 \rangle / (1 - \omega)\langle v_{F,\sigma}^2 \rangle} \sim 1 - 2$ for reasonable $\langle v_{F,\pi}^2 \rangle / \langle v_{F,\sigma}^2 \rangle$ values [5,16]. Similarly, it has been shown that, in the dirty limit, $\xi_\pi^c/\xi_\sigma^c \sim 3$ for $D_\pi/D_\sigma \sim 4$ [17] (where D_i is the diffusivity of the i band), i.e., for a σ band which would be much dirtier than the π band. This numerical ξ_π value obviously deserves further theoretical investigation.

As discussed in [6], an effective anisotropy ratio can be defined as the ratio of the magnetic fields in the ab plane and c axis which correspond to the same γ value but, as pointed out in [6], the choice of the corresponding field is then arbitrary and an almost linear increase of Γ with field was proposed. However, we have seen that superconductivity is completely destroyed in the π band for $B \geq 3$ T and Γ is hence expected to be equal to 5.4 above 3 T. We have calculated this field dependent anisotropy $\Gamma(B)$, writing $\gamma(B, \theta) = \gamma(B\sqrt{\sin^2\theta + \Gamma(B)^2\cos^2\theta}, \theta = 90^\circ)$, i.e., introducing an effective field dependent $B_{c2}^* = B_{c2}^{ab}/\sqrt{\sin^2\theta + \Gamma(B)^2\cos^2\theta}$ and writing that $\gamma = f(B/B_{c2}^*)$. The corresponding $\Gamma(B)$ values have been reported on Fig. 3 (open symbols and lines) for $\theta = 0^\circ$, 30° , and 60° together with the $\Gamma_\lambda = \frac{\lambda_c}{\lambda_{ab}}$ values deduced from




FIG. 3. Field dependence of the anisotropy ratio (see text for details) together with $\Gamma_\lambda = \frac{\lambda_c}{\lambda_{ab}}$ values deduced from small angle neutron scattering data (closed squares: from [4], closed triangle: from [16]).




FIG. 4. (a) Magnetic field dependence of the specific heat at $T = 9$ K showing that, at high temperature, C_p/T scales as $B/B_{c2}(\theta)$. In the inset: same dependence plotted as a function of the applied field H_a for $\theta = 0^\circ, 30^\circ, 60^\circ$, and 90° .

small angle neutron scattering data (closed squares: from [4], closed triangle: from [18]). As shown the same effective anisotropy (saturating at 5.4 for $B \geq 3$ T) is obtained for all angles and a very reasonable agreement is obtained between specific heat and SANS data confirming that $\Gamma_\lambda = \Gamma = \Gamma_\xi$. Note that Γ stays on the order of 1 up to B_π and then sharply increases reaching $\Gamma_{H_{c2}}$ for $B \geq B_{c2}^c$.

Finally, we have investigated the influence of the temperature on the field and angular dependence of C_p . The inset of Fig. 4 displays the field dependence of C_p/T at $T = 9$ K for the indicated θ values. In this temperature range superconductivity in the π band is reduced due to thermal activation over the small gap and, as shown in the main panel of Fig. 4, all curves can then be rescaled directly as a function of $B/B_{c2}(\theta)$ clearly showing that a classical behavior is recovered at high temperature (except that Γ is temperature dependent).

We have shown that, the contribution of the σ band to the specific heat $\gamma_\sigma(B, \theta) = [B/B_{c2}(\theta)]\gamma_N$ whereas the contribution of the π band is isotropic but highly nonlinear in field: $\gamma_\pi(B, \theta) = \gamma_\pi(B) = [B/B_\pi(B)]\gamma_N$ for $B \leq 3 \text{ T} \sim B_{c2}^c$ and $\gamma_\pi = \gamma_N$ for $B \geq 3$ T. We hence show that superconductivity can be induced in the π band by coupling with the σ band but only up to B_{c2}^c and no superconductivity is observed in this band for $B \geq 3$ T.

We would like to thank M. Konczykowski and V. Mosser for their help in the Hall probe magnetization measurements. Z.P. thanks the Slovak Science and Technology Agency for partial support, Contracts No. APVT-51-016604 and No. LPP-0101-06. S.L. thanks the New Energy and Industrial Technology Development Organization (NEDO) for partial support.

*Present address: Centre of Low Temperature Physics IEP SAS & FS UPJS, Watsonova 47, SK-04001 Kosice, Slovakia.

- [1] L. Lyard *et al.*, Phys. Rev. B **66**, 180502(R) (2002); S. L. Bud'ko, V. G. Kogan, and P. C. Canfield, Phys. Rev. B **64**, 180506 (2001); M. Angst *et al.*, Phys. Rev. Lett. **88**, 167004 (2002); U. Welp *et al.*, Phys. Rev. B **67**, 012505 (2003).
- [2] L. Lyard, P. Szabo, T. Klein, J. Marcus, C. Marcenat, K. H. Kim, B. W. Kang, H. S. Lee, and S. I. Lee, Phys. Rev. Lett. **92**, 057001 (2004).
- [3] P. Szabó *et al.*, Phys. Rev. Lett. **87**, 137005 (2001); P. Samuely *et al.*, Physica (Amsterdam) **385C**, 244 (2003).
- [4] R. Cubitt, M. R. Eskildsen, C. D. Dewhurst, J. Jun, S. M. Kazakov, and J. Karpinski, Phys. Rev. Lett. **91**, 047002 (2003).
- [5] V. G. Kogan and S. L. Bud'ko, Physica (Amsterdam) **385C**, 131 (2003).
- [6] F. Bouquet, Y. Wang, L. Sheitkin, T. Plackowski, A. Junod, S. Lee, and S. Tajima, Phys. Rev. Lett. **89**, 257001 (2002).
- [7] S. Lee, H. Mori, T. Masui, Y. Eltsev, A. Yamamoto, and S. Tajima, J. Phys. Soc. Jpn. **70**, 2255 (2001).
- [8] C. U. Jung, J. Y. Kim, P. Chowdhury, Kijoon H. P. Kim, Sung-Ik Lee, D. S. Koh, N. Tamura, W. A. Caldwell, and J. R. Patel, Phys. Rev. B **66**, 184519 (2002).
- [9] L. Lyard, T. Klein, J. Marcus, R. Brusetti, C. Marcenat, M. Konczykowski, V. Mosser, K. H. Kim, B. W. Kang, H. S. Lee, and S. I. Lee, Phys. Rev. B **70**, 180504(R) (2004).
- [10] A. Y. Liu, I. I. Mazin, and J. Kortus, Phys. Rev. Lett. **87**, 087005 (2001); A. A. Golubov *et al.*, J. Phys. Condens. Matter **14**, 1353 (2002); H. J. Choi *et al.*, Nature (London) **418**, 758 (2002); I. I. Mazin *et al.*, Phys. Rev. Lett. **89**, 107002 (2002).
- [11] V. G. Kogan, Phys. Rev. B **66**, 020509(R) (2002); V. G. Kogan and N. V. Zhelezina, Phys. Rev. B **69**, 132506 (2004).
- [12] Small deviations from the $B_{c2} = B_{c2}^{ab}/\sqrt{\sin^2\theta + \Gamma^2\cos^2\theta}$ law may be expected in two gap superconductors but those deviations are extremely small at low temperature: A. Rydh, U. Welp, A. E. Koshelev, W. K. Kwok, G. W. Crabtree, R. Brusetti, L. Lyard, T. Klein, C. Marcenat, B. Kang, K. H. Kim, K. H. P. Kim, H.-S. Lee, and S.-I. Lee, Phys. Rev. B **70**, 132503 (2004).
- [13] The anisotropy of the σ band might also be compensated by a small anisotropy of the π band [5,16].
- [14] T. Klein, L. Lyard, J. Marcus, Z. Holanova, and C. Marcenat, Phys. Rev. B **73**, 184513 (2006).
- [15] M. Eisterer, M. Zehetmayer, H. W. Weber, and J. Karpinski, Phys. Rev. B **72**, 134525 (2005).
- [16] M. E. Zhitomirsky and V.-H. Dao, Phys. Rev. B **69**, 054508 (2004).
- [17] A. E. Koshelev and A. A. Golubov, Phys. Rev. Lett. **90**, 177002 (2003).
- [18] D. Pal, L. DeBeer-Schmitt, T. Bera, R. Cubitt, C. D. Dewhurst, J. Jun, N. D. Zhigadlo, J. Karpinski, V. G. Kogan, and M. R. Eskildsen, Phys. Rev. B **73**, 012513 (2006).