



**HAL**  
open science

## **The relationship between the normal state Fermi liquid scattering rate and the superconducting state**

Manuel Nunez-Regueiro, Gaston Garbarino, Maria Dolores Nunez Regueiro

### ► **To cite this version:**

Manuel Nunez-Regueiro, Gaston Garbarino, Maria Dolores Nunez Regueiro. The relationship between the normal state Fermi liquid scattering rate and the superconducting state. *Journal of Physics: Conference Series*, 2012, 400, pp.022085. <10.1088/1742-6596/400/2/022085>. <hal-00977955>

**HAL Id: hal-00977955**

**<https://hal.science/hal-00977955v1>**

Submitted on 11 Apr 2014

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

# The relationship between the normal state Fermi liquid scattering rate and the superconducting state

Manuel Núñez-Regueiro<sup>1</sup>, Gastón Garbarino<sup>1†</sup> and María Dolores Núñez-Regueiro<sup>2#</sup>

1 Institut Néel, Centre National de la Recherche Scientifique (CNRS) & Université Joseph Fourier (UJF), 25 Avenue des Martyrs, F-38042 BP166 Grenoble Cedex 9 France

2 Laboratoire de Physique des Solides, Bât. 510, Université de Paris-Sud, Orsay, France

nunez@grenoble.cnrs.fr

**Abstract.** Many superconductors show a low temperature electrical resistivity of Fermi liquid type  $\rho=AT^2$ . We show empirically that there exists a relationship between  $A$  and  $T_c$  when both vary under an external parameter, such as pressure. The more resistive the compound the higher the  $T_c$ . Through the analysis of Landau theory of FL, we find that it is a general feature of FL, due to the fact that the scattering that is the main cause of  $\tau$  is the same one that bounds the pairs that condensed at  $T_c$ . We devise a method that allows the determination of the coupling constant  $\lambda$ , which is validated through application to  $^3\text{He}$ 's superfluid transitions and  $\tau$ 's extracted from different properties. This method works for conventional superconductors, but fails with heavy fermions.

## 1. Introduction


The standard electrical resistance of a metal is controlled by electron-phonon scattering yielding a  $\rho = \alpha T$  dependence at high temperatures and a  $\rho = \beta T^n$ ,  $n \sim 5$  dependence at low temperatures. However, in some special materials, the low temperature electrical resistivity is of the type  $\rho = AT^2$ . It has long been attributed to electron-electron scattering (e-e-s) and is considered as the signature of a Fermi liquid (FL) behavior for the electronic spectra of the studied compound. The term  $A$  has been related to the electronic linear term of the specific heat  $\gamma$  of each material through the Rice-Kadowaki-Woods[1,2] relation  $A \propto \gamma^2$  through their common dependence on the effective mass  $m^*$ . The precise origin of the  $AT^2$  term has been elucidated for certain materials: direct Coulomb scattering for ultra-pure alkali metals[3] or spin fluctuations for heavy fermion materials [4].

---

<sup>†</sup> Present address : European Synchrotron Radiation Facility (ESRF), 6 Rue Jules Horowitz 38043 BP 220 Grenoble

<sup>#</sup> Deceased

A number of superconductors of different type present the  $\rho = AT^2$  dependence above the superconducting transition at  $T_c$ : heavy fermions,  $A-15$  compounds, borocarbides, etc. It is natural to expect that the pre-transitional scattering is related the pairing interaction, as has been shown, e.g. for aluminum, where the  $\rho = AT^2$  has been traced down to phonon mediated e-e-s [5]. In particular, it would be interesting to study the  $T_c$  vs  $A$  correlation. However, this can only be done properly if both properties vary simultaneously under a external parameter, e.g. pressure. A long term study of superconductors, together with the reanalysis of published data has allowed us to determine a direct relationship between the coefficient  $A$  and the superconducting transition temperature,  $T_c$ , that we present on Fig. 1. It is clear from the figure that  $T_c$  is a monotonous increasing function of  $A$ , thus the stronger the scattering the stronger the  $T_c$ . The empirical relationship that follows from the results shown on this figure has never been reported (nor even addressed).



**Figure 1** Empirical relation between  $T_c$  and the coefficient  $A$  of the quadratic temperature term for different values of an external parameter is applied, pressure unless specified otherwise.  $PrPt_2B_2C$ (blue squares)[6];  $Y-Pd-B-C$ (blue dots)[7];  $YNi_2B_2C$ (blue diamonds)[Our data];  $Nb_3Sn$  ( $\alpha$  or  $e^-$  irradiation, green dots)[8];  $V_3Si$  (green squares)[Our data];  $MgB_2$ (red diamonds)[9];  $UPt_3$ (magenta squares)[10];  $Sr_2RuO_4$ (magenta diamonds)[11];  $UBe_{13}$ (magenta dots)[12];  $(TMTSF)_2ClO_4$  (brown dots)[13],  $(TMTSF)_2PF_6$  (brown squares)[13].

## 2. Theory

We can understand this relationship within Landau theory for Fermi liquids as follows.

### 2.1. Theoretical relationship between $\tau$ and $T_c$

We reduce the inverse quasiparticle-quasiparticle scattering time and the transition temperature to the superfluid phase, to the Landau amplitude scatterings within the  $s$ - $p$  approximation. From standard Landau FL theory[14] we obtain the inverse quasiparticle-quasiparticle scattering time  $\tau^{-1}$ ,

$$\tau^{-1} = \frac{m^{*3} \langle W(\theta, \phi) \rangle (k_B T)^2}{8\pi^4 \hbar^6} = \frac{m^* \langle W(\theta, \phi) \rangle N(k_F)^2 (k_B T)^2}{8\pi^2 \hbar^2 V^2 E_F} \quad (1)$$

Where  $m^*$  is the effective mass,  $V$  the volume,  $N(k_F)$  the density of states at the Fermi level,  $\langle W(\theta, \phi) \rangle$  is the transition probability which describes the scattering of two quasiparticles whose momenta are related by the standard angles  $\theta$  and  $\phi$ , the bracket indicating the angle average through the Abrikosov-Khalatnikov angles;  $k_B$  the Boltzmann constant and  $\hbar$  the Planck's constant. Developing in Legendre polynomials within the  $s$ - $p$  approximation[15] we obtain for the triplet transition probability

$$W_{\uparrow\uparrow}(\theta, \phi) = \frac{2\pi}{\hbar} \left| \frac{A_{\uparrow\uparrow}(\theta, \phi)}{N(k_F)} \right|^2 \sim \left| \frac{(1 + A_0^a)}{N(k_F)} \right|^2 \quad (2)$$

and

$$(\tau \cdot T^2)^{-1} \sim \frac{m^* k_B^2 (1 + A_0^a)^2}{4\pi \hbar^3 V^2 E_F} \propto (1 + A_0^a)^2 \quad (3)$$

where  $A_{\uparrow\uparrow}(\theta, \phi)$  is the triplet scattering amplitude and  $T_F$  the Fermi temperature and  $A_l^\sigma$  the Landau scattering amplitudes (we have taken  $A_0^s=1$ ). A similar result,  $(\tau \cdot T^2)^{-1} \propto (2A_1^{ep})^2$ , is obtained for singlet scattering taking  $A_l^s = A_l^a = A_l^{ep}$ , as in this case the interaction does not depend on spin direction.

Now, following Ref. [16], Patton and Zaringhalam [17] (PZ) estimated the transition temperature to a condensed state as a function of the Landau scattering amplitudes,  $T_F$  being the Fermi temperature and  $\lambda_{\uparrow\uparrow}$  the triplet coupling constant, and  $\alpha$  a parameter,

$$T_c = 1.13\alpha T_F e^{1/\lambda_{\uparrow\uparrow}}$$

$$\lambda_{\uparrow\uparrow} = A_{\uparrow\uparrow}(\pi, \phi) / 3 \cos(\phi) = \sum_l (-)^l (A_l^s + A_l^a) / 12 \approx -(1 + A_0^a) / 6 \quad (4)$$

where we have limited the development to  $l=0,1$  within the  $s$ - $p$  approximation and we have neglected singlet scattering. For singlet scattering, neglecting triplet scattering, we have  $\lambda_{\uparrow\downarrow} \approx 2A_1^{ep}$ . From (3) and (4) we conclude that  $(\tau T^2)^{-1} \propto (\lambda_{\uparrow\uparrow})^2$ , the same for singlet scattering. Thus

$$T_c \propto e^{-\zeta / \sqrt{(\tau T^2)^{-1}}} \quad (5)$$

### 2.2. Electrical resistivity formula


The FL resistivity of metals[18] is given by  $\rho_{ee} = \frac{m^*}{ne^2 \tau_R}$ , where  $n$  is the carrier density,  $m^*$  the effective mass,  $e$  the electronic charge and  $\tau_R = \text{number} \times \tau$ . From (1), (2) and (4) we find now that

$$\rho_{ee} \approx \frac{m^{*2} k_B^2 (1 + A_0^a)^2}{ne^2 4\pi \hbar^3 V^2 E_F} T^2 \quad A \approx \frac{m^{*2} k_B^2}{ne^2 4\pi \hbar^3 V^2 E_F} \lambda_{\uparrow\uparrow}^2 \quad (6)$$

A similar result can be obtained for singlet scattering.

### 3. The case of Helium 3

We can test formula (5) adapting it for the most studied Fermi liquid, i.e.  ${}^3\text{He}$ ; it becomes  $T_c / T_F^{**} = \alpha e^{-\zeta / \sqrt{(\tau T^2)^{-1}}}$  (7), where  $T_F^{**}$  is the Fermi temperature renormalized by all the interactions at each pressure. We plot  $T_c / T_F^{**}(P)$  data as a function of the thermal conductivity scattering rates [19] and fit with expression (7) with  $\alpha$  and  $\zeta$  as adjustable parameters (Figure 2). We can thus extract the coupling constant  $\lambda = \sqrt{(\tau T^2)^{-1}} / \zeta$ . The obtained values  $0.2 < \lambda < 0.4$  are in very good agreement with theoretical calculations [20]. We must note, though, that all pressure effects other than those on  $\tau$  are probably taken into account by the renormalization with  $T_F^{**}(P)$ . The application on  ${}^3\text{He}$  confirms our analysis based on the idea that the pre-transitional scattering determines  $T_c$ .




**Figure 2** Superfluid transition temperature  $T_c$  of  ${}^3\text{He}$  normalized by  $T_F^{**}(P)$ , the Fermi temperature renormalized by all the interactions at each pressure, as a function of the inverse square root of the scattering time extracted from the thermal conductivity multiplied by the square of the temperature.


Fitting with  $T_c / T_F^{**} = \alpha e^{-\zeta / \sqrt{(\tau T^2)^{-1}}}$  (blue line) allows the determination of the parameter  $\zeta$  and the coupling constant  $\lambda = \sqrt{(\tau T^2)^{-1}} / \zeta$  in excellent agreement with theory [20].

### 4. Application to superconductors

Having shown the utility of expression (5), we come back to the superconductors of Figure 1. As  $A \propto (\tau T^2)^{-1}$ , we can now attempt an equivalent type of fit  $T_c = \theta e^{-\zeta / \sqrt{A}}$ . We must bear in mind, though, that application of elementary FL to materials with complex Fermi surfaces is bound to be cumbersome. In this case other parameters that are now present besides  $\lambda$  in  $A$ , may vary, as well.



**Figure 3** The dependence of  $T_c$  on  $\sqrt{A}$  and the fit with expression  $T_c = \theta e^{\zeta/\sqrt{A}}$  (solid black) for a  $V_3Si$  sample (Our data). The agreement of the obtained  $\lambda$  with published data [21] is excellent.



**Figure 4** The same type of fit shown for the compounds of Fig. 1, presented now with each  $T_c$  normalized to the fitting parameter  $\theta$  and as a function of  $\lambda = \sqrt{A}/\zeta$ . The values of  $\lambda$  we obtain for *A-15* compounds and borocarbides agree within 10% with those obtained from other methods, while those of heavy fermions are much lower than reported previously.

Also, we ignore the pressure dependence of the  $\theta$  parameter ( $\theta \propto 1.13\hbar\omega_D$  for conventional superconductors, where  $\omega_D$  is the Debye frequency). We show on Fig. 3 an example of a fit on the  $V_3Si$  data, that allows us to obtain  $\theta$  and  $\zeta$ , and hence the coupling constant  $\lambda = \sqrt{A}/\zeta$ . It yields  $\lambda \approx 0.87$  at ambient conditions, in excellent agreement with the value obtained from tunneling methods  $\lambda = 0.89$  [21]. Thus, the variation of  $T_c$  and  $A$  seems to be controlled mainly by the variation of  $\tau$ .

Applying the same procedure to the compounds of Fig. 1, we can obtain for each material the corresponding  $\theta$  and  $\zeta$ . Plotting now  $T_c/\theta$  against  $\lambda = \sqrt{A}/\zeta$  we obtain Fig. 4. All the dispersed data of Fig. 1 collapse onto one single curve, that scales the compounds according to their respective superconducting coupling constants, derived from their resistivity coefficients  $A$ . For heavy fermions, the variation of  $A$  with pressure seems to be controlled by  $m^*$  not  $\tau$ , invalidating our method. The fact that our analysis works properly on irradiated  $Nb_3Sn$ , suggests that it may be interesting to study the variation of  $T_c$  and  $A$  in heavy fermions by using irradiation, not pressure, as defects should have a stronger effect on the scattering rate  $\tau$  than on  $m^*$ .

## References

- [1] Rice M J 1968, *Phys. Rev. Lett.* **20** 1439
- [2] Kadowaki K and Woods S B 1986, *Sol. State Comm.* **58** 507
- [3] Lawrence W E and Wilkins J W 1972, *Phys. Rev. B* **6** 4466
- [4] von Löhneysen H, Rosch A, Vojta M, Wölfle P 2007, *Rev. Mod. Phys.* **79**, 1015-1075
- [5] MacDonald A H 1980, *Phys. Rev. Lett.* **44** 489
- [6] Falconi R, Durán A, Núñez-Regueiro M and Escudero, R. 2011, *Phys. Status Sol. A*, in press
- [7] Núñez-Regueiro M et al. 1994, *Physica C* **235-240**. 2093
- [8] Gurvitch M, Ghosh A K, Lutz H and Strongin M 1980, *Phys. Rev. B* **22** 128
- [9] Monteverde M et al 2001, *Science* **292**, 75
- [10] Willis P O et al. 1985, *Phys. Rev. B* **31** R1654
- [11] Forsythe D et al. 2002, *Phys. Rev. Lett.* **89** 166402
- [12] Thompson J D et al. 1987, *Phys. Rev. B* **35** 48; Aronson M C et al. 1989, *Phys. Rev. Lett.* **63** 2311
- [13] Doiron-Leyraud, N. et al. 2010, *EPJB* e2010-10571-4
- [14] Baym G and Pethick C 1978, Landau-Fermi Theory and Low Temperature Properties of Normal Liquid  $^3He$  *The Physics of Liquid and Solid Helium* (Part II) Eds. K H Bennemann and J B Ketterson (New York, Wiley) Chapter 1 pp 1-118
- [15] Dy K S and Pethick C J 1969, *Phys. Rev.* **185** 373
- [16] Pethick CJ et al. 1986, *Phys. Rev. Lett.* **57** 1955
- [17] Patton B R and Zaringhalam A 1975, *Phys. Lett.* **55A** 95
- [18] Hess D W 1987, *J. Low Temp. Phys.* **68** 311
- [19] Greywall D S 1984, *Phys. Rev.* **B29** 4933
- [20] Rasul J W, Li T and Beck H 1989, *Phys. Rev.* **B39** 4191
- [21] Kihstrom K E, Simon R W and Wolf S A 1985, *Physica B&C* **135**, 1985