



HAL
open science

Effects of water re-saturation conditions and associated extractives leaching on thermal softening of wet wood

Iris Brémaud, Sandrine Bardet, Joseph Gril, Patrick Perre

► **To cite this version:**

Iris Brémaud, Sandrine Bardet, Joseph Gril, Patrick Perre. Effects of water re-saturation conditions and associated extractives leaching on thermal softening of wet wood. Final Conference of COST Action FP0904 “Thermo-Hydro-Mechanical Wood Behaviour and Processing, May 2014, Skellefteå, Sweden. pp.8-9. hal-01085279

HAL Id: hal-01085279

<https://hal.science/hal-01085279>

Submitted on 21 Nov 2014

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Effects of water re-saturation conditions and associated extractives leaching on thermal softening of wet wood

Iris Brémaud^{1,2}, Sandrine Bardet¹, Joseph Gril¹, Patrick Perré^{2,3}

¹Wood Team, LMGC, CNRS, Université Montpellier 2, France

²LERFoB, ENGREF-AgroParisTechn, INRA, Nancy, France

³LGPM, Ecole Centrale Paris, France

iris.bremaud@univ-montp2.fr

Keywords: DMA, destabilization, glass transition, hardwood, specimens' histories

Thermal softening, or thermo-activated viscoelasticity, is involved in several industrial and/or traditional craftsmanship techniques processing of wood. More fundamentally, it represents a very useful probe of chemical differences and/or of physical histories of wood samples [1,2,3,4,5]. Thermal softening of wet (= water-saturated) wood occurs at much lower temperature than that of completely (anhydrous) dried wood [6,7]. Softening of oven-dry wood happens at temperatures above 150°C, a temperature level at which wood amorphous polymers start to degrade [3,8]. Therefore, the characterisation of wet wood is the unique method that allows thermal softening to be distinguished from thermal degradation. Thermal softening of wet wood is also easier, or at least less energy consuming, in several applied processes. In many cases, it is not always practically feasible to start from green (e.g. never-dried) wood, either for scientific experiments or in real-scale applications, so that air-dry wood may need to be re-saturated. However, it is known that water re-saturated wood behaves differently from never-dried wood [4,5,9]. In addition, soaking wood in water is susceptible to remove secondary metabolites (extractives), some of which are known to modify viscoelastic properties of various wood species [10,11]. The objective of the present work is to provide insight on how thermal softening (studied by Dynamic Mechanical Analysis – DMA) of several hardwoods is affected by conditions (duration and temperature) of water re-saturation, and by additional effects of extractives leaching during these re-conditioning processes.

The study is based on five wood types from four hardwood species, chosen for contrasted chemical composition: black locust, oak, poplar, and beech (including normal wood and tension wood). Radial specimens for DMA ($40 \times 4 \times 0.6 \text{ mm}^3$, $R \times T \times L$) were cut from naturally air-dried wood and prepared following a careful matching procedure. Three replicate specimens were tested for each modality of pre-treatment. Nearly 100 specimens were tested by DMA in total. Each DMA specimen was matched with a specimen designed for monitoring oven-dry weight losses due to a given pre-treatment. Pre-treatments included (see Figure 1): cold water (just after re-saturation, after 2 months and 10 months), 40°C water (4h and 96h), 70°C water (6h), 98°C water (2h), all cooled down slowly to ambient temperature again, and an overnight extraction in cold acetone followed by exchange with water. Tests were conducted in tension, using a TA Instrument Dynamic Mechanical Analyser, at frequencies 0.1, 1, 10 and 25Hz. Evolution with temperature, from 20°C to 100°C, was studied using 5 minutes isothermal steps every 5°C.




Figure 1. Illustration of the different pre-treatment modalities tested in this work, through an example of the evolution with temperature of loss tangent ($\tan\delta_r$, at 0.1Hz) for black locust wood. Error bars = $2 \times$ standard deviation between 3 specimens




Figure 2. Comparison of the thermal softening behaviour just after re-saturation (filled symbols) and after re-conditioning at 98°C (empty symbols) of 5 different wood types: oak (squares), black locust (circles), poplar (triangles), beech (diamonds; filled: normal wood, hatched: tension wood). (a) Storage modulus E' , (b) loss modulus E'' , (c) loss tangent $\tan\delta$, all at 0.1Hz

Results show that the thermal softening behaviour just after re-saturation appears to include a kind of “secondary transition” in the range of 50-60°C (Figure 2c for $\tan\delta$), which is consistent with previous findings [4,5]. However, the amplitude of this phenomenon is not similar for all tested wood types (see Figure 2). This disappears after re-conditioning above the glass transition temperature T_g (pre-treatments at 70°C or 98°C), which also leads to a reduction of the maximum of loss modulus and loss tangent and an apparent increase in T_g . Longer pre-treatments at lower temperature partially lead to similar results but even 10 months in cold water did not remove the “secondary transition”, whereas 40°C pre-treatment did but could not reduce as much the maximum of viscosity. Pre-treatments in water removed between 2 and 8% of extractives, depending on species and conditions. Results without re-conditioning but after cold acetone extraction show species-dependant effects notably on loss tangent $\tan\delta$, which strongly suggests an additive effect of extractives, and of physical re-conditioning, on the thermal softening behaviour of hardwoods.

REFERENCES

1. Olsson, A.-M., Salmén, L. In: *Viscoelasticity of biomaterials*. ACS, Washington. pp. 133-143, 1992
2. Olsson, A.-M., Salmén, L. *Nordic Pulp and Paper Research Journal* 3, 140-144, 1997
3. Assor, C., Placet, V., Chabbert, B., Habrant, A., Lapierre, C., Pollet, B., Perré, P. *Journal of Agricultural and Food Chemistry* 57:6830–6837, 2009
4. Furuta, Y., Norimoto, M., Yano, H. *Mokusai Gakkaishi*, 44(2), 82-88, 1988
5. Kojiro, K., Furuta, Y., Ishimaru, Y. *Journal of Wood Science*, 54: 95-99, 2008
6. Back, E., Salmén, L. *Tappi Journal*, 65(7), 107-110, 1982
7. Salmén, L. *Journal of Materials Science* 19, 3090-3096, 1984
8. Placet, V., Passard, J., Perré, P. *Journal of Materials Science* 43, 3210-3217, 2008
9. Bardet, S., Kojiro, K., Gril, J. In: *Mechanics, Models and Methods in Civil Engineering, Lecture Notes in Applied and Computational Mechanics* 61, 157-162, 2012
10. Brémaud, I., Amusant, N., Minato, K., Gril, J., Thibaut, B. *Wood Science and Technology* 45, 461-472, 2011
11. Brémaud, I., Minato, K., Langbour, P., Thibaut, B. *Annals of Forest Science* 67, 707-714, 2010

ACKNOWLEDGMENTS

Presented experiments were conducted by the first author (I. Brémaud) while at LERFoB Nancy, and subsequent analyses conducted while at LMGC Montpellier in collaboration with LGPM Ecole Centrale Paris. Our thoughts and thanks go to the late Patrice Marchal for his generous and high quality technical help at LERFoB.