

A model of the heat conduction for functionally graded laminate with uniformly distributed micro inclusions

Monika Wragrowska, Czeslaw Wozniak, Olga Szlachetka

▶ To cite this version:

Monika Wragrowska, Czeslaw Wozniak, Olga Szlachetka. A model of the heat conduction for functionally graded laminate with uniformly distributed micro inclusions. PAMM, 2012, 12, pp.413-414. hal-01117991

HAL Id: hal-01117991

https://hal.science/hal-01117991

Submitted on 18 Feb 2015

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

A model of the heat conduction for functionally graded laminate with uniformly distributed micro inclusions

Monika Wagrowska^{1,*}, Czesław Woźniak², and Olga Szlachetka¹

The aim of the contribution is to formulate an asymptotic model of heat conduction for functionally graded two component laminate reinforced by periodically spaced micro inclusions.

1 Introduction

Laminate occupies region $(0,L)\times\Xi$ when Ξ is a regular region on Ox^2x^3 - plane. The composite is made of a large number $p,\ \frac{1}{p}<<1$, of layers with the same thickness $l,\ l=\frac{L}{p}$ and every layer has a symmetry plane $x_n=\frac{l}{2}+(n-1)\ l,\ n=1,...,p$. The scheme of this composite is shown in Figure 1.




Fig. 1: A cross section of a functionally graded laminate and its fragment with periodically spaced micro inclusions.

2 Modelling Procedure

In order to obtain the model of this laminate we introduce material fractions φ_A , φ_B such that $\varphi_A + \varphi_B = 1$, $\varphi_A \in C^1\left([0,L]\right)$, and $\forall x^1 \in (0,L) \left[\varphi_A\left(x^1\right) \in (0,1) \text{ and } l \left|\partial_1\varphi_A\left(x^1\right)\right| << 1\right]$. It has to be remembered that the lamina materials A and B have an extra reinforcement micro periodic spaced micro inclusions. Every lamina is made of the isotropic material having heat conductivity k_A and k_B and specific heat c_A and c_B , respectively. The uniform distribution of micro inclusions in every lamina is characterized by constant heat conductivity k_R specific heat c_R and by constant fraction coefficient ν_R , $\nu_R << 1$.

In the first step of modelling we homogenize reinforcement material independently with isotropic component materials. The effective heat conductivities and specific heat in every lamina after homogenization take the form:

$$K_{A}^{1} \equiv \frac{k_{A}k_{R}}{\nu_{R}k_{A} + (1-\nu_{R})k_{R}}, \quad K_{A}^{2} = K_{A}^{3} \equiv (1-\nu_{R})k_{A} + \nu_{R}k_{R}, \quad C_{A} \equiv (1-\nu_{R})c_{A} + \nu_{R}c_{R},$$

$$K_{B}^{1} \equiv \frac{k_{B}k_{R}}{\nu_{R}k_{B} + (1-\nu_{R})k_{R}}, \quad K_{B}^{2} = K_{B}^{3} \equiv (1-\nu_{R})k_{B} + \nu_{R}k_{R}, \quad C_{B} \equiv (1-\nu_{R})c_{B} + \nu_{R}c_{R}.$$

$$(1)$$

In the second step of modelling [1, 2] we shall deal with functionally graded laminate made of two orthotropic materials having material properties given by formulas (1).

¹ Warsaw University of Life Sciences-SGGW, ul. Nowoursynowska 156, 02-787 Warszawa, Poland

² Technical University of Łódź, al. Politechniki 6, 90-924 Łódź, Poland

^{*} Corresponding author: e-mail monika_wagrowska@sggw.pl, phone +48 225 935 111, fax +48 225 935 103

The idea of the modelling is based on the concept of the local layer [1] which has a form similar to that given above but has a symmetry plane at an arbitrary but fixed $x \in (0, L)$. We also introduce a local periodic shape function $q_x(\cdot)$ defined on $\begin{bmatrix} x - \frac{l}{2}, \ x + \frac{l}{2} \end{bmatrix} \text{ as } g_x \left(x - \frac{l}{2} \right) = g_x \left(0 \right) = g_x \left(x + \frac{l}{2} \right) = 0, g_x \left(x - \frac{l}{2} \varphi_A \left(x \right) \right) = \frac{l}{2}, g_x \left(x + \frac{l}{2} \varphi_A \left(x \right) \right) = -\frac{l}{2} \text{ and is linear in } \left(x - \frac{l}{2}, x - \frac{l}{2} \varphi_A \left(x \right) \right), \left(x - \frac{l}{2} \varphi_A \left(x \right), x + \frac{l}{2} \varphi_A \left(x \right) \right), \left(x + \frac{l}{2} \varphi_A \left(x \right), x + \frac{l}{2} \right), x \in (0, L).$ The modelling procedure is based on two assumptions. The first assumption is strictly related to the asymptotic passage

 $l \to 0$. Let for every $x \in (0, L)$ f_x stand for K_A^1 , K_A^2 , K_A^3 , C_A , K_B^1 , K_B^2 , K_B^3 , C_B , then for $x \in (0, L)$ $f_x \in L^2_{loc}(R)$.

If
$$l \to 0$$
 then $f_x \rightharpoonup \langle f_x \rangle \equiv \frac{1}{l} \int_{x-\frac{l}{2}}^{x+\frac{l}{2}} f_x(y) dy$ for every $x \in (0, L)$.

The second assumption is that the temperature field $\theta_x(\cdot)$ in every local layer is assumed in the form: $\theta_x(y,t) = \vartheta(y,t) + \varphi(y,t) = \varphi(y,t)$ $g_x\left(y^1\right)\psi\left(y,t\right), y^1 \in \left(-l/2,l/2\right), \quad y=\left(y^1,y^2,y^3\right)\in \left(-l/2,l/2\right)\times\Xi, \text{ where } \vartheta\left(\cdot\right), \psi\left(\cdot\right) \text{ are new unknown functions.}$ From the above assumptions applying limit passage $l \to 0$ and taking into account the heat flux continuity at the interfaces we obtain the averaged heat fluxes in the form:

$$Q^{1}(\mathbf{x},t) \equiv -\tilde{K}^{1}(x^{1}) \partial_{1} \vartheta(\mathbf{x},t), Q^{2}(\mathbf{x},t) \equiv -\tilde{K}^{2}(x^{1}) \partial_{2} \vartheta(\mathbf{x},t), Q^{3}(\mathbf{x},t) \equiv -\tilde{K}^{3}(x^{1}) \partial_{3} \vartheta(\mathbf{x},t),$$
(2)

where

$$\tilde{K}^{1}(x^{1}) \equiv \frac{K_{A}^{1}K_{B}^{1}}{K_{A}^{1}\varphi_{B}(x^{1}) + K_{B}^{1}\varphi_{A}(x^{1})},
\tilde{K}^{2}(x^{1}) = \tilde{K}^{3}(x^{1}) \equiv K_{A}^{2}\varphi_{A}(x^{1}) + K_{B}^{2}\varphi_{B}(x^{1}),
\tilde{C}(x^{1}) \equiv C_{A}\varphi_{A}(x^{1}) + C_{B}\varphi_{B}(x^{1}), \quad x^{1} \in (0, L).$$
(3)

and the balance equation:

$$\partial_1 Q^1(\mathbf{x}, t) + \partial_2 Q^2(\mathbf{x}, t) + \partial_3 Q^3(\mathbf{x}, t) + C(x^1) \partial_t \vartheta(\mathbf{x}, t) = 0.$$
(4)

Formulas (3), (4) represent the proposed model equations of heat conduction for a functionally graded media with microperiodic inclusions under consideration.

3 **Final Remark**

The obtained system of equations for functionally graded laminate with uniformly distributed micro inclusions is characterized by continuous and nonperiodic coefficients.

References

- [1] C.Woźniak, B.Michalak, and J.Jedrysiak, (eds.), Thermomechanics of heterogeneous solids and structures, tolerance averaging approach, Wydawnictwo Politechniki Łódzkiej, Łódź (2008).
- [2] C.Woźniak et al. (eds.), Mathematical modelling and analysis in continuum mechanics of microstructured media, Wydawnictwo Politechniki Śląskiej, Gliwice (2010).