

Analysis of the expansion phenomenon during the extrusion process: Experiments and model



Magdalena KRISTIAWAN &
Guy DELLA VALLE



Ludovic Club, March 26, 2014 - Lyon






- **Objective of this work**

- ✓ Test the validity of Ludovic® simulation for starch extrusion
- ✓ Show how to integrate the **phenomenological model of expansion** with Ludovic®'s interface

Aims: Extend the Ludovic ®'s capability **to predict macro & microstructure of starchy foam**

Concept map: Structure of Ludovic®



Input variables of models =
Extrusion's output variables at die exit (calculated by Ludovic®)





EXPERIMENTS

1) Raw material - Maize starches

Starch	Product	Amylose / Amylopectine
A	Amylomaize	70 / 30
B	Blend of A : D = 2 : 1	47 / 53
C	Blend of A : D = 1 : 2	23.5 / 76.5
D	Waxy maize	0 / 99

Molecular structure



2) Extrusion – Plasticizer : water

Control variables	Water content <i>MC</i>	Product temperature <i>T_p</i> °C	SME kWh/t
Min	0.21	105	101
Max	0.36	186	580

Experimental sets:


- Low MC with Med & High *T_p*
- High MC with Low & Med *T_p*

$$Q = 12 - 35 \text{ kg/h}$$


$$N = 80 - 240 \text{ rpm}$$

Extruder configurations: Clextral BC45 & Slit die

Profil 1: Low / Medium %water (MC), $L_{\text{total}} \text{ barrel} = 1000 \text{ mm}$




Profil 2: High %water (MC) – Low $T_p^\circ \text{ C}$, $L_{\text{total}} \text{ barrel} = 1250 \text{ mm}$




3) Determination of melt viscosity using Rheopac

Top view



- An in-line rheometer
- A slit die with **twin rectangular channels** attached to the die head of the extruder
 - Channel **1** for **the measurement**
 - Channel **2** for **bypass a part of the total flow rate Q** by adjusting the piston valves



- Principle
 - **Vary the local shear rate** in the Channel 1
 - **Keep constant** the Q, SME and die head P **in extruder**
 - **Measurement of ΔP / ΔL and Q_1 in the Channel 1** to obtain shear viscosity

Using *Rabinowitsch correction*

General rheological model for the plasticized starch

- Power law fluid with Non-newtonian and Shear thinning behavior

$$\eta = K \dot{\gamma}^{n-1}$$

Case 1) Dependency of K and n only on **temperature (T)** and **moisture content (MC)**

$$K = K_o \left[\frac{E}{R} \left(\frac{1}{T} - \frac{1}{T_o} \right) - \alpha (MC - MC_o) \right]$$

$$n = a_1 T + a_2 MC + a_3 TMC$$

Case 2) Dependency of K and n on thermomechanical history through **a specifc mechanical energy (SME) term**

$$K = K'_o \left[\frac{E}{R} \left(\frac{1}{T} - \frac{1}{T_o} \right) - \alpha (MC - MC_o) - \beta (SME - SME_o) \right]$$



$$n = n_o + a_1 T + a_2 MC + a_3 SME + a_4 TMC + a_5 TSME + a_6 MCSME$$



RESULTS & DISCUSSIONS

Shear viscosity of molten starch: SME (+) then viscosity (-)

Effect of Specific Mechanical Energy:
Complex dependency with amylose, water content & temperature



Determination of shear viscosity parameters for Ludovic® input

Rheopac data:

$$\eta = K \dot{\gamma}^{n-1};$$

$$K, n = f(MC, T_p, SME)$$

Starch	A	B	C	D
Amylose content	0.7	0.47	0.245	0
K'₀ (Pa.s)	1.13E+07	4.15E+05	7.54E+07	1.34E+06
E/R (K)	11,298	5,638	9,869	9,350
α	14.49	14.86	38.94	26.32
β (kJ/kg)⁻¹	0	2.68E-04	1.25E-03	1.59E-03
n₀	0	0	0.34	0
a₁ (°C)⁻¹	2.69E-03	1.87E-03	1.06E-06	8.92E-04
a₂	0	6.13E-01	9.69E-01	0
a₃ (kJ/kg)⁻¹	0	0	2.08E-05	1.56E-04
a₄ (°C kJ/kg)⁻¹	0	2.68E-03	1.09E-05	1.44E-02
a₅ (°C)⁻¹	0	0	0	0
a₆ (kJ/kg)⁻¹	0	8.36E-05	2.18E-04	0

$$n = a_1 T + a_2 MC + a_3 TMC$$

$$K = K_o \left[\frac{E}{R} \left(\frac{1}{T} - \frac{1}{T_o} \right) - \alpha (MC - MC_o) \right]$$

Compute new parameters
 $K, n = f(MC, T_p)$

Create Set of data points
 $(T_p, \dot{\gamma}, SME, \eta)$

How to activate SME coupling in viscosity law for Ludovic® material input ?

Product

Current name: Starch D

Product Name: Starch D

Thermal Characteristics Viscosity

1) Create Set of Points



Viscosity Law = $f(\text{Temp}, \text{Shear Rate}, \text{Total Dissipated Energy})$

Parameter 1 : Temperature
Parameter 2 : Shear Rate
Parameter 3 : Standard: Total Dissipated Energy

Temp (°C)	Shear Rate (s ⁻¹)	Total Dissipated Energy	Viscosity (Pa.s)
90	10	20	6041.661948
90	10	30	5967.904831
90	10	45	5858.954026
90	10	67.5	5699.245857
90	10	101.25	5467.809122
90	10	151.875	5138.155868
90	10	227.8125	4680.563793
90	10	341.71875	4069.438693
90	10	512.578125	3299.050944


Points Count: 1,573

view SOP Import Excel Export to Delete Digitize Test SOP Modify Cancel




Ludovic simulation: Experimental set (Amylose 0.0, Water 0.25, Tp 158 ° C, SME 131 kWh/t)

Sensibility to thermomechanical history (SME, Tp, MC)





Melt viscosity $\eta = K\dot{\gamma}^{n-1}$

— K, n = f(Water, Tp)
— K, n = f(SME, Water, Tp)




Ludovic simulation: Experimental set (**Amylose 0.70**, **MC 0.21**, **T_p 166 ° C**, **SME 750 kJ/kg**)

Sensibility to thermal conductivity k




Ludovic simulation

Sensibility to melting temperature T_m




The higher amylose content,
the broader melting endotherme
(Mateev 2001)



Ludovic simulation: Experimental set (Amylose 0.70, MC 0.21, T_p 166 ° C, SME 750 kJ/kg)

Sensibility to melting temperature T_m





Without SME - viscosity coupling

Total SME (kJ/kg)




Negligible effect of T_m !!!

Experiments vs Simulations




Experiments vs Simulations



Computing of starch destructurization using Ludovic

$$\% \text{ destructurization} = \frac{\Delta \text{ intrinsic viscosity}}{\text{initial intrinsic viscosity}}$$



Native maize starch

Amylose / Amylopectine	Intrinsic viscosity (ml/g)
0 / 100	185
24.5 / 75.5	159
47 / 53	132
70 / 30	104

Amylopectine (higher MW) is more sensitive to thermomechanical treatment than **amylose (lower MW)**



CONCLUSIONS

- The determination of **material properties** is primordial
 - The *rheological behavior* of molten polymer,
 $f(\text{thermomechanical history})$
 - The *thermal physical properties* of material,
 $f(T, \text{water content})$
- The computed **dissipated mechanical energy** is underestimated
 - Well correlation between $\text{SME}_{\text{computed}}$ and the $\text{SME}_{\text{experimental}}$
 - Well correlation between % starch destructurization and $\text{SME}_{\text{computed}}$

PERSPECTIVES

- **Integration of Ludovic® with phenomenological model of expansion**

- 1) **Coupling the model with Ludovic®**

- 2) Simulation and validation (experiments)


- **New Ludovic® outputs:**

- 1) **Macrostructure:**


- Indices Expansion Volumique (VEI)
- Indices Expansion Radial & Longitudinal
- Anisotropie factor

- 2) **Microstructure:**

- **Mean cell size (MCS)**
- **Mean cell wall thickness (MCWT)**
- **Finesse**




Concept map: Structure of Ludovic®




**Input variables of models =
Extrusion's output variables at die exit (calculated by Ludovic®)**

Context: Starchy material processing using extrusion-cooking


Expansion by extrusion cooking:
Relation with Glass transition temperature T_g



The bubble growth stops (solidification) at $T_p > T_g + 30^\circ C$



Concept map: Phenomenological model of expansion



$$\rho^* \approx z \otimes [\eta(\gamma)]^x \otimes [MC] \otimes [Tp] \otimes [E'(T\alpha)]^y$$

where $z, x, y = f(MC, Tp, \dots)$

Volumetric expansion indices VEI


$$VEI = \frac{\rho_m(1 - MC_m)}{\rho^*(1 - MC^*)}$$

$$VEI = \left(\frac{\eta(\dot{\gamma})}{a} \right)^n$$


$$\left. \begin{array}{l} a = a_1 MC + a_2 T_p + a_3 MC \cdot T_p + a_4 \ln(E'(T_\alpha)) \\ n = (n_1 MC + n_2 T_p + n_3 MC \cdot T_p) \cdot \ln(E'(T_\alpha)) \end{array} \right\}$$

Water = 0.245, 185°C, 150 kWh/t, h die = 3 mm

Higher Amylose% → higher E'(T_α) → higher η(ε)



Amylose 70%, 165°C, 200 kWh/t, h die = 3 mm





Thank you....



Discussion....



Ludovic Club, March 26, 2014 - Lyon

