



HAL
open science

First neutron studies of the magnetism and rattling modes in CePt₄Ge₁₂

Rose-Marie Galéra, Christine Opagiste, Mehdi Amara, Mohamed Zbiri,
Stéphane Rols

► **To cite this version:**

Rose-Marie Galéra, Christine Opagiste, Mehdi Amara, Mohamed Zbiri, Stéphane Rols. First neutron studies of the magnetism and rattling modes in CePt₄Ge₁₂. *Journal of Physics: Conference Series*, 2015, 592, pp.012011. 10.1088/1742-6596/592/1/012011 . hal-01141311

HAL Id: hal-01141311

<https://hal.science/hal-01141311>

Submitted on 11 Apr 2015

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

First neutron studies of the magnetism and rattling modes in $\text{CePt}_4\text{Ge}_{12}$

R. M. GALÉRA¹, C. OPAGISTE¹, M. AMARA¹, M. ZBIRI² and S. ROLS²

¹ Institut NÉEL, CNRS, Univ. Grenoble Alpes, BP 166, 38042 Grenoble, France

² Institut Laue-Langevin, CS 20156, F-38042 Grenoble, France

Abstract. The filled skutterudite $\text{CePt}_4\text{Ge}_{12}$ is reported to be at the border between an intermediate valence (IV) state and a Kondo lattice behavior. We report here the first inelastic neutron scattering experiments, carried out on the Ce compound and its non-magnetic counterpart $\text{LaPt}_4\text{Ge}_{12}$. Prior the neutron studies, the structural and magnetic properties of both samples have been determined. Inelastic neutron scattering spectra are dominated by phonon contribution for both compounds. A rattling vibration mode is observed at 6.9 meV and 7.5 meV for the Ce and La compounds, respectively. In $\text{CePt}_4\text{Ge}_{12}$ no crystal field excitation could be resolved. Only a small and wide extra contribution at high energy (22-28 meV) is observed. This result would be more consistent with an IV behavior.

1. Introduction

Rare-earth (RE) filled skutterudites exhibit a large variety of topological magnetic and electrical properties. Recently skutterudites with chemical formula $\text{MPt}_4\text{Ge}_{12}$ have been synthesized with $M=\text{Sr, Ba, La, Ce, Pr, Nd}$ and Eu [1-3]. Detailed macroscopic measurements on $\text{CePt}_4\text{Ge}_{12}$ suggest that this compound is at the border between an intermediate valence (IV) and a Kondo lattice behavior [4]. The magnetic susceptibility shows a wide bump around 80 K, typical of IV systems and the Sommerfeld coefficient, $\gamma=105 \text{ mJ mol}^{-1}\text{K}^{-2}$, is moderately enhanced compared to those of $\text{LaPt}_4\text{Ge}_{12}$ and $\text{PrPt}_4\text{Ge}_{12}$ ($76 \text{ mJ mol}^{-1}\text{K}^{-2}$ and $87 \text{ mJ mol}^{-1}\text{K}^{-2}$ respectively), but the A/γ^2 ratio $\gg 4 \times 10^{-7} \mu\text{W cm (mol. K/mJ)}^2$ is far below the universal Kadowaki-Woods relation $A/\gamma^2=1 \times 10^{-5} \mu\text{W cm (K mol./mJ)}^2$. However using the new relation proposed by Tsujii *et al.* [5], who take into account the degeneracy of the quasiparticles, the A/γ^2 value becomes closer to the universal value for a degeneracy 6, $A/\gamma^2=6.4 \times 10^{-6} \mu\text{W cm (K mol./mJ)}^2$.

Inelastic neutron scattering (INS) has been proved to be a very original and powerful technique to study heavy fermions and intermediate valence systems [6]. According to previous studies, in case of IV compounds the scattering function has a very particular behavior. At temperatures much lower than the characteristic Kondo energy, T_K (in IV systems T_K may vary from 100 up to 700 K), the scattering function presents a wide inelastic structure at high energy. This structure progressively shifts to low energies as the temperature increases and merges into a large quasi-elastic structure, as observed in CeSn_3 or CePd_3 [7]. On the other hand in Kondo systems, the Kondo energy is much smaller, of the order of few Kelvins, and the crystal field excitations (CEF) are well resolved.

With the aim to discriminate between intermediate valence or Kondo lattice behavior in $\text{CePt}_4\text{Ge}_{12}$ we undertook a first study by inelastic neutron scattering. Present results focuses on the inelastic response of $\text{CePt}_4\text{Ge}_{12}$ and its non-magnetic counterpart $\text{LaPt}_4\text{Ge}_{12}$.

2. Experimental details

The polycrystalline samples of $\text{LaPt}_4\text{Ge}_{12}$ and $\text{CePt}_4\text{Ge}_{12}$, as well as those of Pr-, Nd-, Sm and $\text{EuPt}_4\text{Ge}_{12}$, have been prepared by the conventional induction melting technique. Stoichiometric amounts of high purity elements, 99.9% rare earth, 99.95% Pt, 5N Ge, were melted in a water-cooled copper crucible under a highly purified argon atmosphere. Mass losses were negligible. After this first step, the as-melted samples contain the filled skutterudite phase but also a large amount of impurity phases, PtGe_2 and Ge. This indicates that the $\text{RPt}_4\text{Ge}_{12}$ phases are not congruent melting compounds. To achieve the skutterudite phase formation, the samples were sealed in quartz ampoules under high vacuum and annealed at 780°C for 10 days. The sample quality was checked by powder X-ray diffraction on a Philips PW1730 diffractometer using the $\text{Cu-K}\alpha$ radiation.

The magnetic measurements were performed on a polycrystalline sample of $\text{CePt}_4\text{Ge}_{12}$ in the temperature range 1.9 K-300 K and in fields up to 5 T, using a Quantum Design MPMS magnetometer (resolution $2 \times 10^{-11} \text{ Am}^2$). Two types of measurements were carried out, the thermal variation of the magnetization under an applied $H=100 \text{ Oe}$ and the variation with the applied field of the isothermal magnetization. The magnetic susceptibility of the compound is deduced from the $M(100 \text{ Oe}, T)/H$ curve for the first type of measurements and from the Arrott plots [8]: $M^2=f(H/M)$ for the second one.

Inelastic neutron scattering experiments were carried out with the time-of-flight spectrometer IN4C at ILL on polycrystalline samples of $\text{LaPt}_4\text{Ge}_{12}$ ($m=3.93 \text{ g}$) and $\text{CePt}_4\text{Ge}_{12}$ ($m=3.49 \text{ g}$). The incident neutron wavelength was $\lambda=1.5 \text{ \AA}$ and the full width at half maximum FWHM=1.7 meV. Within these conditions, the maximum scattering vector is $|Q|_{\text{max}}=7.41 \text{ \AA}^{-1}$. The spectra were collected in the temperature range 2-270 K.

3. Structural and magnetic properties

The refinements of the X-ray diffraction patterns were performed using the FullProf program [9]. Based on the structure type $\text{LaFe}_4\text{P}_{12}$, space group $Im\bar{3}$, the lattice parameters of $\text{LaPt}_4\text{Ge}_{12}$ and $\text{CePt}_4\text{Ge}_{12}$ are $8.6299(4) \text{ \AA}$ and $8.6193(3) \text{ \AA}$ respectively. In rare earth compounds, the lattice parameter is a fairly reliable indicator of the valence state of the rare earth ion. Figure 1 (left) shows the evolution of the lattice parameter from $\text{LaPt}_4\text{Ge}_{12}$ to $\text{EuPt}_4\text{Ge}_{12}$. This evolution is in good consistency with those already reported in the literature for the same $\text{RPt}_4\text{Ge}_{12}$ series. The evolution of the trivalent ionic radii in the lanthanide series is also reported in figure 1 together with the tetravalent, for Ce, and divalent, for Eu, radii.




Figure 1. Left: evolution of the lattice parameter in the $\text{RPt}_4\text{Ge}_{12}$ series and comparison with the ionic radii of trivalent R ions (dotted line is a guide for the eyes). The full star represent the ionic radius of Ce^{4+} and the full square the radius of Eu^{2+} respectively. Right: thermal evolution of the magnetic susceptibility. In inset the curve $\chi.T=f(T)$.

It is obvious that the Eu ion is divalent in $\text{EuPt}_4\text{Ge}_{12}$. However, within the experimental accuracy, no clear deviation from the trivalent valence is evidenced in $\text{CePt}_4\text{Ge}_{12}$. On the other hand the thermal variation of the susceptibility (see figure 1 (right)) is quite consistent with those of Ce-based IV compounds [7]. The susceptibility presents a large bump around 75-80 K, as previously reported in Ref. [4], and a slight increase at low temperatures. In IV systems a Fermi liquid-type behavior is expected at low temperatures leading to a weak but constant susceptibility. The susceptibility increase at low temperatures, observed in many IV systems, is ascribed to a weak amounts of paramagnetic impurities. From the curve $\chi.T=f(T)$, we determine a Fermi liquid susceptibility $\chi_0=3.38 \times 10^{-3} \text{ emu/mol}$.

4. Inelastic neutron scattering

Figure 2 shows the thermal and Q dependences of the INS spectra of $\text{CePt}_4\text{Ge}_{12}$. For Ce ions in the 2a site of the $Im\bar{3}$ space group one expects only one CEF excitation. The expected thermal evolution of such an excitation is a progressive decrease of its intensity with temperature. As seen in figure 2, the INS spectra show several inelastic structures. Two well resolved pics are observed at $6.9 \pm 0.1 \text{ meV}$ and $12.1 \pm 0.1 \text{ meV}$. At higher energies the structures broaden. Less resolved peaks around 15, 18, 21

and 27 meV can be pointed. Moreover, the progressive increase of their intensities with the temperature allows to definitively ascribe these structures to phonon contributions. However one can remark that at low Q and low temperature the INS signal is slightly stronger above 27 meV as expected for a magnetic contribution.




Figure 2. Thermal and Q dependences of the inelastic neutron scattering spectra of $\text{CePt}_4\text{Ge}_{12}$.

In figure 3 we compare the thermal and Q dependences of the INS spectra of $\text{CePt}_4\text{Ge}_{12}$ and $\text{LaPt}_4\text{Ge}_{12}$. At the first glance $\text{LaPt}_4\text{Ge}_{12}$ exhibits a behavior very similar to that observed in $\text{CePt}_4\text{Ge}_{12}$, confirming the phonon origin of the INS signal. While in the La spectra the second peak is still observed at 12.1 ± 0.1 meV, the first one is slightly shifted to higher energy at 7.5 ± 0.1 meV. The energy of the first peak in the La and Ce compounds is quite consistent with those reported in the literature for other skutterudites families and ascribed to the “rattling” or guest mode [10].

Ab initio phonon simulations reproduce rather well the experimental spectra for both samples and for instance the shift in energy of the low energy peak between La and Ce. Note that in the $\text{RO}_4\text{Sb}_{12}$ series a similar shift to the lower energies with increasing the atomic number of the rare earth is evidenced [10]. The estimated neutron-weighted partial phonon atomistic contributions bring into evidence that this first peak results essentially from the rare earth ion [11], confirming a rattling vibration mode. These results will be subject of a forthcoming detailed paper [11]. Nevertheless, as expected for transition metals and rare-earth containing compounds, with active d - and/or f - shells, respectively, the Ce phonon spectrum is better reproduced by the calculation including the effect of the spin polarization on the lattice, and therefore on the inter-atomic force constants [12].

Again at high energy, low Q and low temperature, the intensity of the Ce signal becomes significantly larger than the La one (left upper part in figure 3). This is coherent with the above observation in the lower part in figure 2. This extra and small signal could thus be associated with a large and weak magnetic feature as expected for IV compounds.




Figure 3. Thermal and Q dependences of the INS spectra of CePt₄Ge₁₂ and its non-magnetic counterpart LaPt₄Ge₁₂.

5. Conclusion

The present INS results on CePt₄Ge₁₂ clearly confirm that no “normal” CEF excitation exists in the explored energy range thus excluding a Kondo behavior. The magnetic susceptibility and some features in the Ce spectra (weak and wide signal at high energy) are much more reminiscent of IV compounds. The IV behavior in Ce compounds is generally attributed to a strong hybridization between the 4*f* electron and the conduction band (*s-f* coupling). Note that the behavior of the INS spectra appear very similar of those of CeOs₄Sb₁₂, where the absence of CEF excitation let suppose delocalised 4*f* electrons [10]. Also in the same ROs₄Sb₁₂ series heavy fermion behaviors have been reported in several other compounds. However in this series, the mass enhancement of the conduction electrons has been suspected to be induced by an electron-phonon coupling rather than a *s-f* coupling. Thought the interpretation of combined studies of inelastic X-ray scattering and X-ray absorption spectroscopy in the ROs₄Sb₁₂ series is not yet fully achieved, Tsutsui and coworkers [10] conclude that couplings exist between: the guest rattling modes, the 4*f* electrons and the conduction electrons, that may explain, for instance, the heavy fermion behavior of SmOs₄Sb₁₂.

Our results also evidence a “rattling” mode in both the La and Ce compounds but at higher energy (around 7 meV), than in the ROs₄Sb₁₂ (around 3 meV). At the moment results on the RPt₄Ge₁₂ series are too partial to conclude on the origin of the coupling.

References

- [1] Bauer E. *et al.* 2007 Phys. Rev. Lett. 99 217001
- [2] Gumenuik R. *et al.* 2008 Phys. Rev. Lett. 100 017002
- [3] M. Toda *et al.* 2008 J. Phys. Soc. Jpn 77 124702
- [4] Gumenuik R. *et al.* 2011 J. Phys.: Condens. Matter 23 465601
- [5] Tsujii N. *et al.* 2005 Phys. Rev. Lett. 94 057201
- [6] Loewenhaupt M. and Fischer K.H. 1993 Handbook of Magnetic Materials Vol. 7 p 503-608 Ed. K. H. J. Buschow
- [7] Holland-Moritz E. *et al.* 1982 Phys. Rev. B 25 7482, Murani A. P. 1983 Phys. Rev. B 28 2308, Galera R. M. *et al.* 1985 J. Magn. Magn. Mater. 52 103
- [8] Arrott A. 1957 Phys. Rev. 108 1394
- [9] Rodriguez-Carvajal J. 1990 Satellite Meeting on powder Diffraction of the XV Congress of the IUCr., Book of Abstracts
- [10] Tsutsui S. *et al.* 2012 Phys. Rev. B 86 195115
- [11] C. Opagiste, M. Zbiri, R. M. Galéra, S. Rols, M. Amara, to be published.
- [12] (a) M. Zbiri M. *et al.* 2010 J. Phys.: Condens. Matter 22 315701, (b) M. Zbiri *et al.* 2009 Phys. Rev. B 79 064511, (c) M. Zbiri *et al.* 2008 J. Phys.: Condens. Matter 20 285203.