



**HAL**  
open science

# Accuracy and reliability of different models used for the prediction of the migration from monolayer and multilayer materials

Olivier Vitrac, Daniel Goujot

## ► To cite this version:

Olivier Vitrac, Daniel Goujot. Accuracy and reliability of different models used for the prediction of the migration from monolayer and multilayer materials. 4. International Symposium on Food Packaging: Scientific Developments supporting Safety and Quality, Nov 2008, Prague, Czech Republic. 2008, 4th International symposium on food packaging: scientific developments supporting safety and quality. hal-01186898

**HAL Id: hal-01186898**

**<https://hal.science/hal-01186898>**

Submitted on 25 Aug 2015

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Accuracy and reliability of different models used for the prediction of the migration from monolayer and multilayer materials

Olivier Vitrac and Daniel Goujot


## Introduction

Although the EU regulation is still in a consolidation phase, 502 substances (including 230 monomers and 272 additives) among the 937, which are positively listed in EU directives on plastics in contact with food, are subjected to specific migration limits (SML) due to toxicological concern. To face such legal obligations, mathematical modeling, as introduced in article 8 of 2002/72/EC, is a competitive alternative to time-consuming migration tests. **As materials became more sophisticated (multi-layer multi-materials) or as modeling in semi-solid food was required (e.g. for consumer exposure assessment), only numerical techniques were available up to few years via commercial or freely available software.** However, numerical techniques have several drawbacks for end-users with mainly a chemical background: i) they may be computationally burdensome with non-optimized discretization schemes, ii) they may lead to unreliable accuracies for particular stiff problem (e.g. strong partitioning, very thin layers such as adhesive layers), iii) their implementation for legal purposes requires a validation procedure, which is not available. **To tackle the limitations of most of available software, this work addresses new exact analytical solutions i) to validate any migration software, ii) to implement efficient probabilistic modeling, iii) to allow real time calculations and transport coefficients identification.**

## Generic mathematical formulation for multilayer materials in contact with a semi-solid food

The canonical solution for the one-dimension migration of packaging substances into a continuously stirred liquid with a finite volume was proposed by Crank [1] with additional refinements discussed by Vergnaud [2]. The first analytical solution for a semi-solid or for a liquid including a mass transfer resistance (i.e. mass Biot or Sherwood number) was proposed by Sagiv [3] twenty-six years later. As the last solution involves a slow convergence with the number of terms, an equivalent but still approximated analytical solution was proposed by Vitrac and Hayert [4]. Very recently, we reformulated the "Sagiv problem" by introducing an efficient mathematical method known as "energy method" already used to solve multi-component convection-diffusion problem to derive exact analytical solutions for problems previously renowned "without analytical solution" [5].

The physical dimensionless formulation is introduced on a comprehensible case consisting in a bilayer material with a whole thickness  $l_s$  in contact with a semi-solid food on the right side. This formulation can be straightforwardly downgraded to a monolayer material or generalized to n-layer materials.



### Notations (SI units)

$A$ : surface contact area (m <sup>2</sup> )	$K_1$ : Partition coefficient between food and layer 1 (-)
$C_f$ : concentration in food (kg·m <sup>-3</sup> )	$K, K_2$ : Partition coefficient between food and the layer in contact, numbered 2 (-)
$C_s$ : residual concentration in the entire material (kg·m <sup>-3</sup> )	$L$ : dilution ratio = $l/l_f$
$C_s^{t=0}$ : initial concentration in layer 1	$l_s$ : whole thickness of the material (m)
$C_s^{t=0}$ : initial uniform concentration in layer 2	$l_f$ : equivalent food thickness = $V_f/A$
$c(x,t)$ : concentration in material at x and t (kg·m <sup>-3</sup> )	$t$ : dimensionless time = $t' \cdot D_2 / l_s^2$
$Bi$ : mass Biot number = $h \cdot l / D_2$ (-)	$t'$ : contact time (s)
$D_1$ : diffusion coefficient in layer 1 (m <sup>2</sup> ·s <sup>-1</sup> )	$x$ : dimensionless position (-)
$D_2$ : diffusion coefficient in the layer in contact, numbered 2 (m <sup>2</sup> ·s <sup>-1</sup> )	$x'$ : position (m)
$h$ : interfacial mass transfer coefficient in food (m·s <sup>-1</sup> ), it takes into account the effect of food texture	$V_f$ : volume of food (m <sup>3</sup> )
	$w_1$ : relative thickness of layer 1 (-)

### Transport equation (dimensionless form)

$$\frac{\partial c}{\partial t}(x,t) = \frac{D_1}{D_2} \frac{\partial^2 c}{\partial x^2}(x,t) \quad \text{for } \begin{cases} 0 < x < w_1 \\ t > 0 \end{cases}$$

$$\frac{\partial c}{\partial t}(x,t) = \frac{\partial^2 c}{\partial x^2}(x,t) \quad \text{for } \begin{cases} w_1 < x < 1 \\ t > 0 \end{cases}$$

### Contact conditions (dimensionless form)

$$K_2 \lim_{x \rightarrow 0} c(w_1 + h, t) = K_1 \lim_{x \rightarrow 0} c(w_1 - h, t) \quad \text{for } t > t_0$$

$$D_2 \lim_{x \rightarrow 0} \frac{\partial c}{\partial x}(w_1 + h, t) = D_1 \lim_{x \rightarrow 0} \frac{\partial c}{\partial x}(w_1 - h, t) \quad \text{for } t > t_0$$

### Boundary conditions (dimensionless form)

$$\frac{\partial c}{\partial x}(1, t) = Bi \cdot C_f(t) - \frac{Bi}{K_2} \cdot c(1, t)$$

$$\frac{\partial c}{\partial x}(0, t) = 0$$

## Exact analytical solutions for monolayer materials in contact with a semi-solid food

The **Goujot-Vitrac's solution** expands onto a basis of eigenfunctions, which are orthogonal for a bilinear operator described in [5]. This operator relies on a scalar product, which was optimized to handle a wide range of boundary conditions, such as any arbitrary sorption isotherm and a mass transfer resistance on the food side.

$$c(x,t) = a_0 + \sum_{n=1}^{\infty} a_n \cdot \cos(\lambda_n \cdot x) \exp(-\lambda_n^2 \cdot t)$$

$$\lambda_n \text{ are roots of } \tan(\lambda) = \frac{Bi \cdot K}{\lambda} + \frac{Bi \cdot L \cdot \tan(\lambda)}{\lambda^2}$$

$$a_0 = \frac{L \cdot C_f(t=0) + C_s(t=0)}{K + L}$$


$$a_n = \frac{\lambda_n \cdot \sin(\lambda_n) + K \cdot \lambda_n \cdot \left( \frac{1}{2 \cdot \sin(\lambda_n)} - \frac{\cos(\lambda_n)}{2 \cdot \lambda_n} \right)}{Bi}$$

It is worth to notice that all solutions are self-similar for any triplet  $(Bi, L, K/L, t)$

**Number of terms to achieve a maximum relative error in  $c(x,t)$  lower than  $10^{-5}$ .**

As this criterion is beyond the capabilities of common commercial migration software, it would give the number of terms required to validate a software for any migration condition, that is for any triplet  $(Bi, L, K/L, t)$ .

Only the Goujot-Vitrac's solution [5] guarantees a rapid decrease of the number of terms when the dimensionless diffusion time (t) increases. This property is related to the energy of the solution, which was proven to be strictly decreasing with t. In other words, the high frequency terms vanish rapidly with increasing t, whatever  $Bi, L$  and  $K/L$  values.



## Approximated analytical solution for monolayer materials in contact with a semi-solid food

Exact solutions suffer from transcendental equations, whose zeros cannot be expressed in terms of a finite sequence of algebraic operations. The **Vitrac-Hayert's solution** derived in [4] solves this issue by approximating the initial set of partial differential equations by a simple conditional ordinary differential equation, while providing an accurate estimate of the mass flux density at the interface. It has been shown that this class of solution has efficient properties to help the identification of transport coefficients from noisy or truncated desorption kinetics.

$$j = -\frac{\partial u}{\partial t} = \frac{b}{2} \cdot \left[ b - \sqrt{b^2 + 4 \cdot c} \right] + c \quad \text{if } j \geq 6 \cdot (1-u);$$

$$j = -\frac{\partial u}{\partial t} = Bi \cdot K \cdot \frac{\left(1 + \frac{L}{K}\right) \cdot u - \frac{L}{K}}{1 + \frac{1}{3} Bi \cdot K} \quad \text{otherwise.}$$

$$u(t) = C_s(t) / C_s(t=0)$$

$$b = Bi \cdot K \cdot \sqrt{\frac{3}{2} (1-u)}$$


$$c = Bi \cdot [L \cdot u + (K-L)]$$

The solution u is obtained by integrating over t:  $du/dt=f(u)$

## How accurate is the approximated solution for any contact condition

**Vitrac-Hayert's solution leads to accurate results without any bias on residual concentration ( $C_s$ ) and interface mass flux ( $j$ ) for any contact condition, while providing an easy numerical implementation in any programming language or even in a spreadsheet.**

Combined with a least-square method, it offers real time identifications of combined transport coefficients [4].



## Exact analytical solution for multilayer materials in contact with a semi-solid food (the first exact solution ever published)

An exact solution for multilayer materials has been recently derived [6] from the generalization of the scalar product defined in [5]. The solution expands on a basis of eigenfunctions, which depends on the considered layer. For concision, the solution for a bilayer material is presented here.

$$c(x,t) = a_0 + \sum_{n=1}^{\infty} a_n \exp(-\lambda_n^2 \cdot t) \cdot \begin{cases} \cos(r \cdot \lambda_n \cdot x) / g_n & \text{if } x < w_1 \\ \cos(x \cdot \lambda_n + f_n) & \text{if } x > w_1 \end{cases}$$

$$\lambda_n \text{ are roots of } \tan\left(\arctan\left(\frac{\lambda^2 \cdot Bi - L}{K_2 \cdot \lambda}\right) + (1-w_1) \cdot \lambda\right) \cdot K_2 \cdot \tan(r \cdot w_1 \cdot \lambda) = K_1 \cdot r \quad \text{with } r = \sqrt{\frac{D_2}{D_1}}$$

$$a_0 = K_1 \cdot \frac{w_1 \cdot L \cdot C_s^{t=0} + (1-w_1) \cdot L \cdot C_s^{t=0} + C_f(t=0)}{w_1 \cdot L \cdot K_2 + (1-w_1) \cdot L \cdot K_1 + K_1 \cdot K_2}$$

$$a_n = \frac{2}{b_n} \cdot \left( (K_1 \cdot C_s^{t=0} - K_2 \cdot C_s^{t=0}) \cdot \sin(\lambda_n \cdot w_1 + f_n) + (K_2 \cdot C_s^{t=0} - C_f(t=0)) \cdot \sin(\lambda_n + f_n) \right)$$

$$b_n = \left( \frac{L}{\lambda_n} + \frac{\lambda_n}{Bi} \right) \cdot \sin(\lambda_n + f_n) + \frac{D_1 \cdot K_1 \cdot \lambda_n \cdot w_1}{D_2 \cdot g_n} + K_2 \cdot \lambda_n \cdot (1-w_1)$$

$$f_n = \arctan\left( \frac{K_1 \cdot \sin(r \cdot w_1 \cdot \lambda_n)}{K_2 \cdot \cos(r \cdot w_1 \cdot \lambda_n)} \right) \cdot r \cdot K_1 \cdot \cos(r \cdot w_1 \cdot \lambda_n) - \lambda_n \cdot w_1$$


$$g_n = \sqrt{\left( \frac{K_1}{K_2} \cdot \cos(r \cdot w_1 \cdot \lambda_n) \right)^2 + \sin^2(r \cdot w_1 \cdot \lambda_n)} \cdot \frac{D_1}{D_2}$$

$$\text{atan2}(y,x) = \begin{cases} \frac{\pi}{2} \cdot \text{sgn}(y) - \text{atan}\left(\frac{x}{y}\right) & y > 0 \\ \frac{\pi}{2} \cdot \text{sgn}(x) - \frac{\pi}{2} & y = 0 \end{cases}$$

## Illustration on a bilayer material

How does the analytical solution expands over several layers ?

The example illustrates four practical cases with a same initial amount of migrant in the entire packaging. The scenarios are coded by the paired values:  $[C_1^{t=0} \ C_2^{t=0}] \cdot [K_1 \ K_2]$ :  
(a) monolayer, (b) material including a functional barrier (c) bilayer including similar materials, (d-e) bi-materials.




**UMR 1145 Food Process and Chemical Engineering Joint Research Unit**  
Agroparistech, site de Massy  
1, avenue des Olympiades  
91300 Massy, France

## Our approach

INRA is contributing to develop basic scientific and engineering supports for a reliable implementation of migration modeling for the packaging community (packaging and food industries, control and regulatory authorities, food safety agencies). As the approach was motivated by Chemical Engineering concepts, our work was concerned with pioneering valuable techniques of prediction from molecular mechanisms to a macroscopic description of food-packaging interactions. Three fields were particularly investigated with possible applications beyond the sole food packaging application:

- molecular mechanisms** involving in the control of transport coefficients (partition, diffusion coefficients) and in their activation with temperature and plasticizing effects;
- exact mathematical solutions of transport equations** for punctual assessment and probabilistic assessment of the contamination of food products by materials intended to be in contact;
- design of decision tools**, which act as expert systems and which can handle both missing properties and large uncertainties on input parameters.

Free implementation of last algorithms and methodologies on the **SAFE FOOD PACKAGING PORTAL**: <http://h29.univ-reims.fr>



QSPR-MS Diffusion Simulation interface showing a 3D plot of concentration, a parameter form table, and search options for strong D overestimates, robust D estimates, and search for recommended CPO and SML.

## Literature cited

- [1] Crank J. **The mathematics of diffusion**, 2<sup>nd</sup> Ed. Oxford University Press, 1975.
- [2] Vergnaud JM. **Liquid transport processes in polymeric materials**. Englewood Cliffs: Prentice-Hall, 1991.
- [3] Sagiv A. Exact solution of mass diffusion into a finite volume. **J. Membrane Sci.** 2001, 186,231-237.
- [4] Vitrac O, Hayert M. Identification of Diffusion Transport Properties from Desorption/Sorption Kinetics: An Analytical Based on a New Approximation of Fick Equation during Solid-Liquid Contact. **Ind. Eng. Chem. Res.** 2006, 45, 7941-7956.
- [5] Goujot D, Vitrac O., Exact solutions to mass diffusion in complex cases: solution for non linear isotherms. **AiChE J.** 2008, *submitted*.
- [6] Goujot D, Vitrac O., Exact solutions to mass diffusion in complex cases: solutions for multilayer materials. *To be published in AiChE J.*

## Contact

Dr Olivier Vitrac, Chargé de Recherche INRA  
E-mail: [olivier.vitrac@agroparistech.fr](mailto:olivier.vitrac@agroparistech.fr)  
Phone: +33 1 6993 5063  
Fax: +33 1 6993 5185