HAL
open science

Nanometric TiO 2 as NBBs for functional organic-inorganic hybrids with efficient interfacial charge transfer

P. Gorbovyi, M. Traoré, K. Chhor, Luc Museur, A. Kuznetsov, B.N. Chichkov, A.V. Kanaev

To cite this version:

P. Gorbovyi, M. Traoré, K. Chhor, Luc Museur, A. Kuznetsov, et al.. Nanometric TiO 2 as NBBs for functional organic-inorganic hybrids with efficient interfacial charge transfer. Chemical Engineering Transactions, 2011, 10.3303/CET1124033 . hal-01247291

HAL Id: hal-01247291

https://hal.science/hal-01247291

Submitted on 21 Dec 2015

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Nanometric TiO_2 as NBBs for functional organic-inorganic hybrids with efficient interfacial charge transfer

Gorbovyi P.,[1] Traoré M.,[1] Chhor K.,[1] Museur L.,[2] Kuznetsov A.,[3] Chichkov B.[3] and Kanaev A.[1*]

[1]Laboratoire d'Ingénierie des Matériaux et des Hautes Pressions (UPR 1311), Institut Galilée, Université Paris 13, 93430 Villetaneuse - France
[2]Laboratoires de physique des Lasers (UMR 7538), Institut Galilée, Université Paris 13, 93430 Villetaneuse - France
[3]Lazer Zentrum Hannover e.V., Hollerithallee 8, 30419 Hannover - Germany

The purpose of this work is to establish a fabrication method for new electronic materials: organic-inorganic p-MAPTMS / titanium-oxo-alkoxy hybrids. The size-selected 5.2-nm TiO_2 nanoparticles (Nano Building Blocks - NBB) are generated in a sol-gel reactor with turbulent fluids micromixing. The surface exchange between propoxy and MAPTMS groups under vacuum pumping results in a stable nanoparticulate precursor available for 2-photon laser polymerisation. The hybrids demonstrate quantum yield of photoinduced charges separation 6 % and can steadily trap photoinduced electrons at number density of 6% Ti atoms. The materials are suitable for 3D-microstructuring.

1. Introduction

Last decades hybrid materials deserved a great interest. Many progresses have been achieved in synthesis of these materials and understanding of their physical properties (Gómez-Romero and Sanchez, 2003; Kickelbick, 2006; Merhari, 2009; Sanchez et al, 2010). Titanium dioxide hybrids attract particular interest due to a high refractive index, biocompatibility and electron transport properties. A direct writing photonic structure was recently demonstrated using 2-photon fs-laser polymerisation in the TTIP-MAA (TTIP=titanium tetra-iso-propoxyde; MAA=methacrylic acid) materials (Sakellari et al, 2009). Titanium oxide hybrids are also capable accumulating Ti^{3+} centers useful in photochemical conversion and storage of solar energy (Cottineau et al, 2008a; Cottineau et al, 2008b).

Exceptional electronic properties of these hybrids are related to the inorganic component: TiO_2. A high electron-hole separation efficiency (below 16 %) has reported in the TiO_2 colloids (Henglein, 1982). The absorption of photon results in the electron transition form the valence band (VB) formed by 2p-orbitals of O^{2-} to the conduction band (CB) due to Ti^{4+} 3d-orbitals (Daude et al, 1977). The high photosensibility is also observed in TiO_2 aclogels with charge separation efficiency ~25 % (Kuznestov et al,

* corresponding author: kanaev@limhp.univ-paris13.fr

2005; Kuznestov et al, 2006a). In our previous works, we have developed new photochromic PHEMA/TiO_2 based hybrids (pHEMA=Poly(2-hydroxyethyl methacrylate) with high charge separation efficiency of 12 % and electron loading capacity of 14% Ti atome (Kameneva et al, 2005; Kuznestov et al, 2006b; Kuznestov et al, 2009). The charges separation and long-term storage is explained by the fact that VB hole rapidly escape into the organic component while CB electrons remain onto the organic component as Ti^{3+} polaron-like centre We also observed a strong correlation between the photosensitivity and the material structure.
The elaboration process is crucial for the electronic properties of the electronic hybrid. A control of the inorganic-organic interface permits to improve the charge separation and further increase the material photosensibility. The aim of this work is to propose an original elaboration process based on Nano Buiilding Blocks (NBBs) approach, which consists in selective fabrication of titanium-oxo-alkoxy nanoparticles, surface exchange and their assembling into a polymer, which allows the material morphology control.

2. Materials and methods

The synthesis schema by Kameneva et al (2005) has been generally adopted for the hybrid fabrication. However, the inorganic component morphology is poor defined in this approach with a generally broad size distribution. Because of that, substantially polydispersed samples are often subjected to analysis. To overcome this problem, we made use of the sol-gel reactor (figure 1)(Rivallin et al, 2005a; Rivallin et al, 2005b; Azouani et al, 2010).



Figure 1: Turbulent micromixing sol-gel reactor

The reactor assures homogeneous reaction conditions in the mixed fluids and permits generation of monodispersed oxo-TiO_2 nanoparticles of different sizes (Azouani et al, 2007). Its main part is the T-mixer of Hartridge and Roughton type, which operates at high Reynolds numbers $Re>10^3$. Two thermostatic stock solutions containing titanium tetra-iso-propoxyde (TTIP) and water in solvent (2-propanol) are injected into the mixer through two input tubes (Figure 1). This injection is exocentric: two fluids form a vortex before entering the main tube. Two reagents flow rates are maintained equal and varying form 2 to 12 m/s by applying an external gas pressure (N_2, purity 99.995 %). The diameters of two input (1.0 mm) and the main (2.0 mm) tubes are chosen for a continuity of the Reynolds number.

The static T mixer performance has been studied by several groups and a considerable narrowing of the particle size distribution has been shown (Marchisio et al, 2006; Gradl et al, 2006; Marchisio et al, 2009). In application to the sol-gel process, its advantage is related to the hierarchical growth mechanism of the structural units, which reactivity stepwisely decreases with each size increase.

Our approach consists, first, in generation of diluted monodispersed TiO_2 nanocolloids in 2-propanol, followed by the solvent replacement by MAPTMS and increase of the nanocolloid concentration. In present experiments, the sol particles were generated with TTIP concentration C_{Ti}=0.15 M and hydrolysis ratio H=2.0 at 20 °C. According to Azouani and al (2007), nanoparticles nucleate in these conditions; however, their growth is strongly prohibited. The reactor temperature was controlled by a thermo-cryostat *Haake, DC10K15*. TTIP of 98 % purity, 2-propanol (*Interchim*) and distillated water were used. A monomode optical fiber probe was developed to monitor in situ the particle size (2R) and the scattered light intensity (I) of He-Ne laser by photon-correlated spectroscopy method, using a 16-bit, 255 channels PC board plugged digital correlator (*PhotoCor Instruments*). The observation volume defined by a mutual positioning of two monomode optical fibres is small enough ($\approx 10^{-6}$ cm^3) to prohibit multiple scattering events. The measurements (I, R) were carried out in the automatic sampling mode with the data accumulation over 60 s, which permits rejection of nosy data due to rare dust particles, which prohibit observation of much smaller nanoparticles.

3. Results and discussions

The autocorrelation function (ACF) of the produced TiO_2 nanoparticles in 2-propanol is shown in figure 2a. The mean particle hydrodynamic radius of 2.60 nm is in agreement with previous measurements in similar experimental conditions (Azouani et al, 2007). At the humidity control, this size is stable on a long-time-scale exceeding a day, which explained by vanishing of the dominant contribution of oxolation reaction into the particles aggregation.

The solvent exchange is carried out at the next stage. MAPTMS was preliminary distillated in order to eliminate impurities and traces of inhibitors of spontaneous polymerization. The solvent exchange is performed by MAPTMS addition into the 2-propanol/TiO_2 nanocolloid under stirring and vacuum pumping through the LN trap overnight (12 hours). The 2-propanol elimination has been validated by Raman spectra

by the intensity decrease of the dominant symmetric [CCC] band situated at 818 cm^{-1} (Moran et al, 1998).



Figure 2: Characteristic ACFs of oxo-TiO_2 nanoparticles after preparation in the sol-gel reactor ([Ti]=0.15 M, H=2, T=20 °C, 2-propanol solution) (a) and after surface exchange with MAPTMS (C_{Ti}=1.5 M) (b).

The solvent exchange does not influence the particles size and aggregation state. Figure 2b shows the ACF of the 1.5-M MAPTMS-TiO_2 colloid, which was obtained after MAPTMS addition with the ratio of MAPTMS:2-propanol=1:10, which results in 10-times more concentrated colloids.

We have demonstrated in our previous work (Gorbovyi et al, 2010) that during the solvent exchange of 2-propanol with HEMA (2-hydroxyethyl methacrylate), a surface ligands replacement OEMA→O^iPr was possible. If the O^iPr ligands replacement takes place with MAPTMS, Si-O-Ti bounds have to be created. The vibration of these bounds (939 cm^{-1}) does not appear in the FTIR spectra of the sol. The interaction between MAPTMS and the inorganic nanoparticles is not enough strong for covalent bonding. For this reason the MAPTMS-TiO_2 hybrids seems to belong to the Class I hybrids Sanchez et al. (2010).

A polymerization of the MAPTMS-TiO_2 precursor was realized both thermally with addition of the AIBN initiator and by 2-photon process using femtosecond near-IR laser (Ti-sapphire, 800 nm) with addition of a photoinitiator. In the first case, non-colored transparent hybrids were obtained after 24 hours heating at temperature at 75° C. The

MAPTMS polymerization was monitored by Raman spectroscopy, observing characteristic vibrational peaks of C=C (1407 cm^{-1}) and $C=CH_2$ (1641 cm^{-1}) (Mabilleau et al, 2008). Figure 3 shows clearly that the intensity of the two C=C bands vanishes and, in the some time, the intensity of the C-C band at 1455 cm^{-1} increases indicating the elongation of the polymeric chain.



Figure 3: Raman Spectra of liquid MAPTMS-TiO_2 colloid C_{Ti}=1.5 M (a) and polymerised MAPTEMS (b) and hybrids C_{Ti}= 0.75 M (c) and C_{Ti}=3.0 M (d).

Our measurements show that some residual non-polymerized monomers remain in the hybrids with the increase of the nanoparticules loading.
Figure 4 shows microstruturing obtained by 2-photon laser polymerization realized with an original technique "on-the-fly" (Fadeela et al, 2006). Non-colored transparent hybrids were obtained with different shapes and structure.



Figure 4: Microstructures achieved with 2-photon laser polymerisation

The as prepared hybrids darken when they are irradiated by UV light. This photochromism is related to a broad-band visible absorption assigned to shallow

polaronic Ti^{3+} centres formed by CB-electron trapping onto Ti^{4+}. The structured hybrids conserve their photochromism, which can be seen in inset of figure 4, which shows the irradiated structure (rectangular parallelepiped) of figure 4a.

We have measured the photonic sensitivity of the prepared hybrids in pump probe experiments using nanosecond UV laser irradiation (Nd:Yag, 7 ns, 355 nm) with fluences of 10-80 mJ/cm^2. Our present results (figure 6) evidence the photoinduced charge separation efficiency of the prepared samples, $\eta = dN_{Ti3+}/dN_{abs\text{-}ph} = 6$ % and charges storage capacity of $Q = N_{Ti3+}/ N_{Ti4+} = 6$ %. Compared to pHEMA-TiO_2 hybrids (η =50 % et Q=12%) (Gorbovyi et al, 2010), pMAPTMS-TiO_2 hybrids seem to be less efficient.



Figure5 : Darkening kinetics of MAPTMS-TiO_2 hybrids (C_{Ti}=3.0 M or 1.8 $10^{21}cm^{-3}$, sample thickness 93 μm).

4. Conclusion

We developed a new method of elaboration of electronic hybrid materials based on inorganic TiO_2 nanoparticle precursor. The key point is fabrication of size-selected titanium-oxo-alkoxy nanoparticles in a sol-gel reactor with turbulent fluids micromixing. The surface exchange between propoxy and polymerisable groups under vacuum pumping results in a stable nanoparticulate precursor available for both thermal and laser polymerisation.

The p-MAPTMS / titanium-oxo-alkoxy hybrids were prepared, which show quantum yield of photoinduced charges separation 6 % and steadily trap photoinduced electrons at number density of 6% Ti atoms. 3D-laser microstructuring has been demonstrated in these materials.

This proposed method allows a control of the electron transfer over the extended internal organic-inorganic interface and optimization of the materials photosensibility.

References

Azouani R., Soloviev A., Benmami M., Chhor K., Bocquet J.-F., Kanaev A., 2007, J. Phys. Chem., C111-16243.

Azouani R., Michau A., Hassouni K., Chhor K., Bocquet J.-F., Vignes J.-L., Kanaev A., 2010, Chem Eng. Res. & Design, doi: 88-1123.

Cottineau T., Richard-Plouet M., Rouet A., Puzenat E., Sutrisno H., Piffard Y., Petit P.-E., Brohan L., 2008a, Chem. Mater. 20-1421.

Cottineau T., Brohan L., Pregelj M., Cevc P., Richard-Plouet M., Arcon D, 2008b, Adv. Func. Mater. 18-2602.

Daude N., Gout C., Jouanin C., 1977, Phys. Rev., B15-3229.

Fadeela E., Koch F., Chichkov B., Kuznestov A., Kameneva O., Biyurin N., Sanchez C., Kanaev A., 2006, Appl Phys A. 84-27.

Gómez-Romero P. and Sanchez C., Functional Hybrid Materials, 2003, Wiley-VCH, Weinheim.

Gradl J., Schwarzer H. C., Schwertfirm F., Manhart M., Peukert W., 2006, Chem. Eng. Proc., 45-908.

Gorbovyi P., Uklein A., Kostrov A., Tieng S., Traore M., Brinza O., Chhor K., Museur L., Kanaev. A., 2010, Matériaux 2010, ISBN 978-2-9528-1-403-4 Nantes.

Henglein A., 1982, Ber. Bunserges. Phys. Chem., 86-241.

Kameneva O., Kuznestov A., Smirnova L. A., Rozes L., Sanchez C., Alexandrov A., Bituyrin N., Chhor K., Kanaev A., 2005, J. Mater. Chem., 15-3380.

Kickelbick, 2006, Hybrid Materials: Synthesis, Characterization and Applications, Wiley-VCH, Weinheim.

Kuznestov A., Kameneva O., Alexandrov A., Bituyrin N., Sanchez C., Chhor C., Marteau P., Kanaev A., 2005, Phys. Rev., E71-021403.

Kuznestov A., Kameneva O., Alexandrov A., Bituyrin N., Chhor C., Kanaev A., 2006a, J. Phys. Chem., B110-435.

Kuznestov A., Kameneva O., Rozes L., Sanchez C., Bituyrin N., Kanaev A., 2006b, Phys. Letts.., 429-523.

Kuznestov A. I., Kameneva O., Bituyrin N., Rozes L., Sanchez C., Kanaev A., 2009, Phys. Chem. Chem. Phys., 11-1248.

Mabilleau G., Cincu C., Basle M. F., Chappard D., 2008, J. Raman Spectrosc. 39-767.

Marchisio D. L., Rivautella L., Barresi A. A., 2006, AIChE J. 52-1877.

Marchisio D. L., Omegna F., Barresi A. A., 2009, Chem. Eng. J. 146-456.

Merhari L., Ed., 2009, Hybrid Nanocomposite for Nanotechnology: Electronic, Optical, Magnetic and Biomedical Applications, Springer, Limoges.

Moran P. D., Bowmaker G. A., Cooney R. P., Finnie K. S., Bartlett J. R., Woolfrey J. L., 1998, Inorg. Chem., 37-2741.

Rivallin M., Benmami M., Gaunand A., Kanaev A., 2005a, Chem Phys Lett. 398-157.

Rivallin M., Benmami M., Kanaev A., Gaunand A., 2005b, Chem Eng. Res. & Design 83(A1)-67.

Sakellari I., Gaidukeviciute A., Giakoumaki A., Gray D., Fotakis C., Vamvakaki M., Farsari M., Reinhart C. Ovsianikov A., Chichkov B.N., 2010, Appl. Phys. A 100-359.

Sanchez C., Rozes L., Ribot F., Laberty-Robert C., Grosso D., Sassoye C., Boissiere C., Nicole L.R., 2010, Chimie 13-3.