



HAL
open science

High-performances carbonaceous adsorbents for hydrogen storage

Weigang Zhao, Vanessa Fierro, E. Aylon, M. T. Izquierdo, Alain Celzard

► **To cite this version:**

Weigang Zhao, Vanessa Fierro, E. Aylon, M. T. Izquierdo, Alain Celzard. High-performances carbonaceous adsorbents for hydrogen storage. NAMES10: NEW ACHIEVEMENTS IN MATERIALS AND ENVIRONMENTAL SCIENCES, Oct 2010, Nancy, France. 10.1088/1742-6596/416/1/012024 . hal-01295728

HAL Id: hal-01295728

<https://hal.science/hal-01295728>

Submitted on 8 Dec 2016

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

High-performances carbonaceous adsorbents for hydrogen storage

This content has been downloaded from IOPscience. Please scroll down to see the full text.

2013 J. Phys.: Conf. Ser. 416 012024

(<http://iopscience.iop.org/1742-6596/416/1/012024>)

View [the table of contents for this issue](#), or go to the [journal homepage](#) for more

Download details:

IP Address: 193.54.91.144

This content was downloaded on 08/12/2016 at 13:44

Please note that [terms and conditions apply](#).

You may also be interested in:

[Biosorption of model pollutants in liquid phase on raw and modified rice husks](#)

L Toniazzo, V Fierro, F Braghiroli et al.

[New families of carbon gels based on natural resources](#)

Andrzej Szczurek, Gisele Amaral-Labat, Vanessa Fierro et al.

[High surface area microporous carbon materials for cryogenic hydrogen storage synthesized using new template-based and activation-based approaches](#)

Gregory P Meisner and Qingyuan Hu

[Hydrogen storage in engineered carbon nanospaces](#)

Jacob Burress, Michael Kraus, Matt Beckner et al.

[The effect of structural and energetic parameters of MOFs and COFs towards the improvement of their hydrogen storage properties](#)

Emmanuel Tylanakis, Emmanouel Klontzas and George E Froudakis

[Activated carbon derived from waste coffee grounds for stable methane storage](#)

K Christian Kemp, Seung Bin Baek, Wang-Geun Lee et al.

[Hydrogen adsorption on a single-walled carbon nanotube material](#)

A Ansón, M Benham, J Jagiello et al.

[Adsorption of carbon dioxide by solution-plasma-synthesized heteroatom-doped carbon nanospheres](#)

Nanthiya Thongwicht, Oi Lun Helena Li, Wattanachai Yaowarat et al.

High-performances carbonaceous adsorbents for hydrogen storage

Weigang Zhao¹, Vanessa Fierro¹, E. Aylon², M. T. Izquierdo², Alain Celzard¹

¹ Institut Jean Lamour – UMR UHP - CNRS 7198, ENSTIB, 27 rue Philippe Séguin, F-88051 Epinal cedex 9

² Instituto de Carboquímica (CSIC), Miguel Luesma Castán, 4. 50018 Zaragoza, Spain

E-mail: Vanessa.Fierro@lcsm.uhp-nancy.fr

Abstract. Activated carbons (ACs) with controlled microporosity have been prepared and their H₂ storage performances have been tested in a gravimetric device. Such adsorbents are natural Chinese anthracites chemically activated with alkaline hydroxides, NaOH or KOH. Outstanding total storage capacities of hydrogen, as high as 6.6wt.% equivalent to excess capacity of 6.2 wt.%, have been obtained at 4MPa for some of these adsorbents. These values of hydrogen adsorption are among the best, if not the highest, ever published so far in the open literature. They are well above those of some commercial materials, e.g. Maxsorb-3, considered as a reference of high-performance adsorbent for hydrogen adsorption. Such exceptional storage capacities may be ascribed to a higher volume of micropores (< 2nm).

1. Introduction

Hydrogen is a renewable energy vector frequently proposed as an alternative to the current fossil fuel-based energy system to solve problems pertaining to energy distribution and environmental issues. However, the main drawback of hydrogen arises from its supercritical nature under standard conditions ($T_c = 33.19\text{K}$, $P_c = 1.296\text{MPa}$), giving it a very low density: only 90g m^{-3} at 1bar and 273K. The US Department of Energy set targets for hydrogen storage systems in light-duty vehicles in 2009. These targets correspond to a gravimetric capacity (i.e., the ratio between net useful energy and maximum system mass) of 4.5% or 1.5kWh kg^{-1} (formerly: 6% or 2kWh kg^{-1}) in 2010, and of 5.5% or 3kWh kg^{-1} (formerly: 9% or 3kWh kg^{-1}) in 2015 [1]. These new targets are still difficult to reach at room temperature. However, stationary applications are not limited by their weight and therefore technical solutions could be available in a shorter time.

The success of any future hydrogen economy depends on the development of inexpensive materials with sufficiently high hydrogen-storage capacity. Four alternatives for hydrogen storage can be anticipated: liquefaction, compression, physisorption, and storage in the form of metallic hydrides. Liquefaction and compression strategies have high operation costs. Moreover, compression needs high pressure operations, which causes high cost for both process and storage tank, and gives rise to safety issues related to high pressures. Metal hydrides have incomplete reversibility and low charge/discharge kinetics. Porous and high-surface area activated carbons (ACs) are among the most important candidates to store efficiently hydrogen due to their low price, high surface area and tunable nanoporosity. Hydrogen storage by physisorption on activated carbons can be an interesting option in

stationary applications, wherein weight and volume are not limiting factors. Expected benefits are lower pressures thus safer operations, fast kinetics and complete reversibility.

Anthracites combine low cost, low ash content and an ideal microtexture for getting a tunable nanoporosity. In this study, we have prepared ACs from Chinese anthracite by varying systematically the activation temperature and the amount of activating agent (NaOH or KOH). We compared their performances to that of Maxsorb-3.

2. Experimental

We have prepared ACs by chemical activation, and the commercial AC Maxsorb-3 (formerly AX21) from Kansai Coke and Chemicals Co., Ltd. (Japan) was used for the sake of comparison. All the materials were characterized by N₂ and H₂ adsorption at 77K.

2.1. AC's synthesis

The precursor of the ACs investigated here was Chinese anthracite from Taisi mine. It was first ground and sieved in order to collect the grains having an average size within the range 100 - 200 μ m. The anthracite powder was then physically mixed with alkaline hydroxide (XOH): either sodium (X = Na) or potassium (X = K) hydroxide lentils (typical size 5 mm), according to various weight ratios XOH / anthracite, R , ranging from 1.5 to 2.5. Additional ACs were synthesised by KOH activation with an R up to 5. The resultant mixture was introduced into a nickel crucible, and heat-treated in a horizontal furnace under a stream of nitrogen at constant heating rate of 5K min⁻¹ up to the final activation temperature, T . T was fixed within the range 973 – 1073K and maintained for 1h. The crucible was then allowed to cool down to room temperature under nitrogen flow. More details are given elsewhere [2, 3].

2.2. AC's characterisation

2.2.1. *N₂ adsorption.* N₂ adsorption isotherms were obtained at 77K using an automatic adsorption apparatus, ASAP 2020 from Micromeritics. The samples were outgassed for 48h under vacuum at 523K prior to N₂ adsorption. Surface areas, S_{BET} , were determined by the BET calculation method [4] applied to the adsorption branch of the isotherms. S_{BET} and pore volumes were estimated with a typical, maximum, uncertainty of 3%. The pore-size distributions (PSD) were calculated by application of the DFT model [5] supplied by Micromeritics software, considering slit-shaped pores.

2.2.2. *H₂ adsorption.* Determination of H₂ storage properties at 77 K for the ACs was carried with a gravimetric device from VTI Corporation (Miami, USA) at ICB (Zaragoza, Spain). The system consists of a fully computer-controlled microbalance, which automatically measures the weight of the carbon sample as a function of time, with the same hydrogen pressure and sample temperature under control. Hydrogen isotherms were obtained by setting pressure steps within the range 0 - 8MPa at 77K. For each run, approximately 500mg of activated carbon sample were placed into a bucket made from stainless steel mesh. Hydrogen pressure was gradually increased to prevent disruption of the microbalance, until the desired value was reached. A pressure transducer (accuracy 0.05% of the full pressure range up to 10MPa) was used to monitor hydrogen pressure in the system. More details have been given elsewhere [2, 3]. Repeatability was always found to be very satisfactory, leading to relative errors lower than 3% on each measurement.

3. Results and discussion

3.1. Effect of R and T

Figure 1 and Figure 2 show the effect of R and T , respectively, on H₂ storage capacity. Absolute (total) H₂ storage capacities are shown. The increase of R and T produced a nearly linear increase of H₂ storage for both activating agents. The slope of the fitted straight line of the H₂ storage capacity with T was higher for KOH than for NaOH.




Figure 1. Evolution of H₂ storage capacity with the activation ratio, R (▲ NaOH, ■ KOH).




Figure 2. Evolution of H₂ storage capacity with the activation temperature, T (▲ NaOH, ■ KOH).

H₂ storage capacity increased with both R and T , and was always higher on ACs produced by KOH activation. The use of KOH allowed obtaining S_{BET} values ranging from 1688 to 2772m² g⁻¹, whereas NaOH led to lower surface areas, within the range 1500 – 2065m² g⁻¹.

Figure 3 shows the evolution of the pore-size distribution of three ACs prepared with KOH when T increased from 1023 to 1073K, at $R=2$, and when R increased from 2 to 2.5, at $T=1023$ K. Increasing R and T increased the micropore volume but also the fraction of wider micropores (0.7-2 nm) and that of mesopores (> 2 nm).




Figure 3. PSDs of three ACs prepared by KOH activation (▲ $T=1023$ K and $R=2$, ■ $T=1073$ K and $R=2$ and ◆ $T=1023$ K and $R=2.5$).

In other words, the development of surface area by KOH activation is always accompanied of pore widening. Therefore, PSDs shifted to wider pores can lead to samples exhibiting higher H₂ adsorption capacities, provided that a high volume of micropores (< 2 nm) still exists.

3.2. Further H₂ storage improvements on KOH-ACs

Based on the previous experiments, we decided to continue our study using only KOH as activating agent and increasing R up to 5. We got ACs with S_{BET} as high as 3434 m² g⁻¹. These S_{BET} are considered as apparent surface areas, given that it is not physically possible to have carbon materials with a surface higher than 2630 m² g⁻¹.

Figure 4 shows the total hydrogen storage capacity of all the ACs prepared by KOH activation. Total hydrogen storage capacity as high as 6.6 wt.%, equivalent to 6.2 wt.% excess capacity, were obtained. The US DOE target for 2010 was 5.5 wt.% for hydrogen storage systems (AC + tank). However, the performances reached in this study are among the best reported by the latest reviews [6, 7] and recent literature in general, e.g. [8-10]. Therefore, our materials are among the best reported in the literature so far.




Figure 4. Total H₂ storage capacity (wt. %) as a function of S_{BET} .

We have already shown [2] that a linear relationship is observed between maximum hydrogen uptake at 77K and BET surface area only if the latter is not higher than typically $2630 \text{ m}^2 \text{ g}^{-1}$. Above such a value, a plateau is reached due to a saturation of H₂ storage capacity at $2630 \text{ m}^2 \text{ g}^{-1}$, and a slight decrease was found for the highest surface areas probably due to the broadening of the pores.

3.3. Comparison with Maxsorb-3

Maxsorb-3 has been claimed to adsorb about 6 wt. % of hydrogen at 77K and 5MPa, 5 wt. % being already reached at 2MPa [11]. Other results on the same material are about 3 wt. % at 80K and 10MPa [12] and, at room temperature: 1 wt. % at 5MPa [13], and 1.6 wt. % at 70MPa [12].




Figure 5. Total H₂ storage (wt. %) isotherms at 77K for Mawsorb-3 and for our best lab-made AC. Adsorption (full symbols) - desorption (open symbols).

Figure 5 shows the H₂ adsorption isotherm for the best of our ACs and Maxsorb-3. Our lab-made AC reached 6.6 wt. % whereas Maxsorb-3 reached "only" 5.8 wt. %. H₂ adsorption was totally reversible and desorption was fast. Our lab-made AC has a higher S_{BET} than Maxsorb-3: 3310 and 3203 m² g⁻¹, respectively. However, this small difference in the S_{BET} can not justify such a difference of H₂ storage capacity. The reason of the higher performances of our lab-made AC is based on its PSD shifted towards narrower pores. Our lab-made AC indeed presents a higher fraction of micropores (<2nm) calculated by the DFT method.

4. Conclusions

We have prepared highly microporous ACs by activation with NaOH or KOH, which showed outstanding performances for hydrogen storage at 77K. The ACs with the highest H₂ storage performances were obtained by KOH activation, using an activating agent to precursor weight ratio of 4 or higher, and activation temperatures higher than 1023K. Some of these ACs reached a total hydrogen storage capacity of 6.6 wt.%. These performances are well above those of the well-known commercial AC Maxsorb-3. Such exceptional hydrogen storage capacities may be ascribed to a higher volume of micropores (< 2nm) of our ACs when compared to Maxsorb-3.

Aknowledgements

We thank the financial support of the CPER 2007-2013 "Structuration du Pôle de Compétitivité Fibres Grand'Est" (Competitiveness Fibre Cluster), through local (Conseil Général des Vosges), regional (Région Lorraine), national (DRRT and FNADT) and European (FEDER) funds. Pr. Carrott from Universidade de Evora (Portugal) is gratefully acknowledged for providing us with the commercial activated carbon Maxsorb-3.

References

- [1] http://www1.eere.energy.gov/hydrogenandfuelcells/storage/pdfs/targets_onboard_hydro_storage_explanation.pdf (consulted 23/03/2011)
- [2] Fierro V, Szczurek A, Zlotea C, Marêché JF, Izquierdo MT, Albiniak A, Latroche M, Furdin G and Celzard A 2010 *Carbon* **48** 1902
- [3] Fierro V, Zhao W, Izquierdo MT, Aylon E and Celzard A 2010 *Int. J. Hydrogen Energ.* **35** 9038
- [4] Brunauer S, Emmet PH and Teller E 1938 *J. Am. Chem. Soc.* **60** 309
- [5] Tarazona P 1995 *Surf. Sci.* **331-333** 989
- [6] Yürüm Y, Taralp A and Veziroglu TN 2009 *Int. J. Hydrogen Energ.* **34** 3784
- [7] Zubizarreta L, Arenillas A and Pis JJ 2009 *Int. J. Hydrogen Energ.* **34** 4575
- [8] Wu HC, Li YY and Sakoda A 2010 *Int. J. Hydrogen Energ.* **35** 4123
- [9] Huang CC, Chen HM and Chen CH 2010 *Int. J. Hydrogen Energ.* **35** 2777
- [10] Suarez-Garcia F, Vilaplana-Ortego E, Kunowsky M, Kimura M, Oya A and Linares-Solano A 2009 *Int. J. Hydrogen Energ.* **34** 9141
- [11] Chahine R and Bose TK. 1994 *Int. J. Hydrogen Energ.* **19** 161.
- [12] de la Casa-Lillo MA, Lamari-Darkrim F, Cazorla-Amoros D and Linares-Solano A 2002 *J. Phys. Chem. B* **106** 10930
- [13] Ye Y, Ahn CC, Witham B, Fultz B, Liu J, Rinzler AG, Colbert D, Smith KA, Smalley RE 1999 *Appl. Phys. Lett.* **74** 2307