



HAL
open science

Effect of M-Ems On In-Mould Transient Flow During Continuous Casting

Luca Marioni, José-Rodolfo Alves Zapata, François Bay, Elie Hachem

► **To cite this version:**

Luca Marioni, José-Rodolfo Alves Zapata, François Bay, Elie Hachem. Effect of M-Ems On In-Mould Transient Flow During Continuous Casting. International Conference on Heating by Electromagnetic Sources (HES16), May 2016, Padoue, Italy. hal-01311019

HAL Id: hal-01311019

<https://hal.science/hal-01311019v1>

Submitted on 3 May 2016

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

EFFECT OF M-EMS ON IN-MOULD TRANSIENT FLOW DURING CONTINUOUS CASTING

L. Marioni ⁽¹⁾, J. Alves Z. ⁽¹⁾, F. Bay ⁽¹⁾ and E. Hachem ⁽¹⁾

⁽¹⁾ MINES ParisTech, Center for Materials Forming (CEMEF),
UMR CNRS 7635, BP 207, 06904 Sophia Antipolis, France

ABSTRACT. Electromagnetic braking (EMB) and electromagnetic stirring (EMS) are widely used to increase the efficiency in continuous casting process of steel. In particular, in-mould applications (M-EMS) allow decreasing the free surface fluctuation, controlling the velocity field and decreasing the turbulence of the flow. Since laboratory-scale tests are not fully representative of the process and industrial measurements are both expensive and difficult to carry out, numerical simulation is a strong tool to study and optimize these electromagnetic applications in steel industry. These simulations cannot fully model the process because the problem results to be strongly multiphysical and the simulation of all the phenomena involved would lead to huge computational costs, which is one of the main limits in the current situation. For this reason, this work aims at starting searching a coupling algorithm which could guarantee both computational efficiency and accuracy of the final results.

INTRODUCTION

In continuous casting processes the liquid metal is injected into the mould. The final steel shell is obtained after the solidification which starts in the mould and continues in the strands. Electromagnetic devices such as stirrers and brakers are well known technologies used to improve both the quality of the final product and the casting speed. The main defects of the final shell in terms of micro-structure and surface cracking can be directly related to in-mould phenomena: temperature variation, velocity and pressure of liquid steel, free-surface behaviour and slag entrainment are some of the main causes of defects in the final product. With the purpose of controlling the process and preventing the final product from defects, the process has been enhanced with electromagnetic devices such as stirrers (EMS) and brakers (EMB). The main difference is that the stirrers work under the supply of AC current and produce dynamics magnetic fields. Brakers are permanent magnets or circuits fed by DC current, thus they produce constant magnetic fields. Despite the differences they are based on the same idea that the superposition of a magnetic field to the metal flow will generate Lorentz forces which can drive the flow in accordance with the process' design. The physical phenomena occurring in the mould is a multiphysics problem which includes liquid flow, multiphase analyses, electromagnetic computation, heat transfer and solidification processes where each of these physics depends on the others. Numerical simulations are one of the main tools used to design the process because it is too complex to be solved analytically. Also, experimental data is very expensive and difficult to obtain because of the high temperature of the casting process. The main drawback of these simulations is the high computational effort required to simulate the highly interconnected phenomena such as electromagnetic field, multiphase fluid flow, heat transfer and solidification. The study of an efficient coupling is therefore essential to neglect non-relevant aspects of the modelling and obtain fast and

reliable simulation algorithms which can be exploited in the industrial world.

SIMULATION TEST CASE

The main purpose of the current work is to create an efficient coupling strategy able to simulate electromagnetic influence in continuous casting processes. For this reason, a simplified test case has been used. The commercial mould considered in the work has been taken from Singh's work [1], but only a quarter of it has been included in the simulation (see figure 1). A simplified electromagnetic stirrer has been positioned 3 cm away from the mould in the direction of the narrow face and between 50 and 70 cm under the free surface level. The EMS device is a solenoid fed by a pulsating AC current and produces a horizontal pulsating magnetic field directed from the narrow face in the direction of the nozzle plan. The geometry of the device is simplified since available data on commercial stirrers were not accurate enough to perform a simulation. In the current work we content to simulate a realistic Lorentz force field, since the aim is to study the interaction of the stirrer on the flow more than to obtain specific industrial results. The main data used in the simulation are reported in table I.




Figure 1: Mould geometry (one quarter of the commercial mould)

Table II: Process parameters

Simulated mould width	853 mm
Simulated mould thickness	101.6 mm
Nozzle port diameter	75 mm
Nozzle bore diameter (inner)	70 mm
Nozzle bore diameter (outer)	130 mm
Nozzle port angle	25 deg
SEN submergence depth	22 cm
Casting speed	1.4 m/min
Bulk velocity in SEN cross section	2.1 m/s
Thickness of the solidified shell	$0.57\sqrt{(z[\text{mm}]})$ mm
Kinematic viscosity of molten steel	$0.86 \times 10^{-6} \text{ m}^2/\text{s}$
Density of molten steel	$7000 \text{ kg}/\text{m}^3$
Resistivity of molten steel	$1.4 \times 10^{-6} (\Omega\text{m})^{-1}$
Resistivity of solids parts	$2 \times 10^{-8} (\Omega\text{m})^{-1}$
Inlet Reynolds number	2171000
Intensity of current	300 A
Frequency	3 Hz

MATHEMATICAL MODEL

Governing equations

The (A, ϕ) potential model has been used to model the electromagnetic field (EMF). Thus, the evolution in time of the EMF is describes by the following system:

$$\begin{cases} \mu_0^{-1} \cdot \nabla \times (\mu_r^{-1} \nabla \times A) = -\sigma(\partial_t A + \nabla \phi + u \times \nabla \times A) \\ \nabla \cdot (\sigma(\partial_t A + \nabla \phi + u \times \nabla \times A)) = 0 \end{cases} \quad (1)$$

where μ_0 and μ_r are the free space and material's relative magnetic permeability respectively. A is the magnetic vector potential, ϕ is the scalar electric potential, u is the medium velocity, and σ is the electrical conductivity. The convective term can be neglected from the first equation in system (1) because the Reynolds magnetic number is $Rem \ll 1$. The same term can be neglected also in the second equation of system (1) because $Rem \ll \mu\omega\sigma L^2$, which leads to $u \times \nabla \times A \ll \partial_t A$. For further justification to these assumptions, we refer to [2]. These conditions ensure that the EMF field is not affected by the fluid motion in EMS applications, while in EMB the convective term could not be neglected in the second equation of system (1). The electromagnetic volumetric force is computed as:

$$f_L = -\sigma(\partial_t A + \nabla \phi) \times \nabla \times A \quad (2)$$

where the convective term due to fluid motion has been neglected for the aforementioned reasons. Both the time evolving and time averaged Lorentz forces have been considered in two different simulations because the literature does not provide a unique criterion to accept the usage of the averaged field. Such criterion should be dependent on frequency [3], on the skin depth phenomenon and on the Stuart number [4]. The electromagnetic model is solved by using Nedelec edge finite elements [5].

The turbulent fluid flow has been modelled by the incompressible Navier-Stokes equation. The Lorentz forces have been considered as a source term. No buoyancy effect was considered, since it is negligible in comparison to inertia and electromagnetic influences. A variational multiscale (VMS) approach [6] has been used to model both the fine and the coarse level of turbulence. Both velocity and pressure fields have been enriched and stabilized according to [7]:

$$\begin{cases} \rho(\partial_t v_h, w_h)_\Omega + (\rho v_h \cdot \nabla v_h, w_h)_\Omega - \sum_{k \in T_h} (\tau_k \mathcal{R}_M, \rho v_h \nabla w_h)_K + (2\mu \varepsilon(v_h) : \varepsilon(w_h))_\Omega \\ \quad - (p_h, \nabla \cdot w_h)_\Omega + \sum_{k \in T_h} (\tau_c \mathcal{R}_C, \nabla w_h)_K = (f, w_h)_\Omega \quad \forall w_h \in V_{h,0} \\ (\nabla \cdot v_h, q_h)_\Omega - \sum_{k \in T_h} (\tau_k \mathcal{R}_M, \nabla q_h)_K \quad \forall q_h \in Q_h \end{cases} \quad (3)$$

with \mathcal{R}_M and \mathcal{R}_C the momentum and continuity residuals from the modelling of the fine scale, respectively. System (3) considers the fine scale modelling without explicitly tracking it. The stabilizing terms τ_k and τ_c (whose theoretical derivation is detailed in [6]) enable the model to overcome the instability of the classical formulation arising in convection dominated flows and to deal with the spurious pressure oscillations.

The coupled system has been simulated through the so called *two meshes two solvers approach* [4, 8, 9]. The electromagnetic problem has been solved with Matelec® over a domain which included the air and the simplified stirrer. The Lorentz forces have thus been

imported in Thercast ® which solves the mechanical problem over the fluid domain. This approach allows us to exploit specific solvers and optimized meshes for each involved physic.

Anisotropic mesh adaptation

In [10] a posteriori error estimate based on the length distribution tensor approach and the associated edge based error analysis is proposed. This error estimation algorithm is the base for the anisotropic meshing scheme adopted in the current work developed in [11] in the case of Navier-Stokes, multi-field re-meshing.

The mesh in the fluid domain is computed as output of an error optimization analysis performed along the edges and referred to user defined fields; we propose the mesh to be adapted according to the following multi-field vector:

$$v(x^i) = \left\{ \frac{u^i}{|u^i|}, \frac{|u^i|}{\max(|u^j|)}, \frac{\phi}{\max(\phi)}, \frac{|f^i|}{\max(|f^j|)} \right\} \quad (4)$$

where u is the velocity field, ϕ is the distance from the boundary, f is the volumetric force and i, j are the nodal indexes.

Two different strategies have been used to re-mesh:

- *Implicit-Static adaptation*: the mesh is anisotropically adapted to the boundaries and in the weak regions. The obtained mesh is then used as a fixed mesh during the whole computation.
- *Explicit-Dynamic adaptation*: the mesh is dynamically adapted during the computation according to the multicriteria vector (eq. (4)) computed from the solution.

In figure 2 we can see how the mesh is anisotropically adapted to the flow in the nozzle area.




Figure 2: Isotropic starting mesh (left) and anisotropically adapted mesh (right)

RESULTS

Flow simulation

The flow developed in the mould is the classical double-roll flow. In figure 3 the magnitude and the streamlines on the average velocity are plotted. The average velocity has been computed in the time interval [30; 55] s when a nominally steady state is reached. In figure 3 the abnormal width of the injection flow can be noticed, which is an already observed drawback in symmetric simulations [12]. This average flow is predictive of the macro-phenomena occurring in the mould, but lacks information regarding localized turbulence, which has a strong impact on metallurgical properties. The turbulence leads to short-time sub-flows detected by the non-average solution; this difference can be measured in term of standard deviation, defined as:

$$\sigma_u = \sqrt{\frac{\sum_{T_i=0}^{T_f} (|u|_i - |\bar{u}|)^2}{N}} \quad (5)$$

where u is the instantaneous velocity, \bar{u} is the average velocity, N is the number of time-steps and T_i represents the i -th time step.




Figure 3: Averaged velocity magnitude (left) and streamlines in the double-roll area (right)

In figure 4 the normalized standard deviation of velocity during the nominal steady state regime is plotted. We see that a large deviation is present in the main flow region and the maximum deviation occurs where the injected flow impacts on the narrow face; the flow in this region is highly turbulent and this turbulence has effect on the solidification of the first layer of solid metal. When the stirrer is turned on (figure 4 right) the standard deviation is decreased in the meniscus zone, which implies the flow to be closer to the steady state. Despite the low level of the magnetic field in the inner zone of the mould, EMS affects the injection flow as well. The flow is smoother and easily turns in the double-roll pattern, while in the non-stirred simulation the unstable flow close to the narrow face led to dynamic effects in the main injection flow. A second effect of the stirrer is to decrease the global velocity of the flow, which is important especially from a simulation point of view. In figure 5 left, the velocity profile along a vertical line 5 cm far from the central axis is plotted. We see that the horizontal velocity related to the main eddy ($z \cong 2m$) is high, especially when compared to the vertical velocity. This means that the simulated flow and its symmetric one (in the second half of the mould) would have a strong impact in this area, which would create turbulence and lead the global flow to be non-symmetric. For this reason, the flow with no EMS should be simulated without any symmetry condition. On the contrary, from figure 5 right we see that the horizontal velocity in the flow with EMS is lower as well as its ratio with the vertical velocity. This result implies that in the stirred case, the geometrical symmetry plane is more likely to behave like a mechanical symmetry plane. The main effects of the stirrer can be

detected close to the narrow face, along the symmetry plane and on the injection flow, but not in nozzle area. In figure 5 right the velocity across the exit central line of the nozzle is plotted and no sensible differences between the stirred and non-stirred solution are predicted.




Figure 4: Velocity standard deviation with no EMS (left) and with EMS (right)




Figure 5: Velocity profile at 5cm from central axis (left) and velocity magnitude at the nozzle exit port (right)

The computational effort of the simulation is not highly affected by the weak coupling between the EM and CFD simulations: in figure 6 an analysis of the computing time is presented. The dynamic mesh adaptation is computationally expensive even if the re-meshing has been performed every 14 time steps. As we can see in figure 7, this choice is not good in

terms of optimization. The anisotropic adaptation makes the elements to be stretched in the same direction as velocity: this means that the elementary stiffness contribution is the same for every direction and the final system is well conditioned. In-mould flow is far from being steady, so the velocity field can significantly change at every time step, so the mesh, which was optimized for the solution at a certain time-step, does not fit the new solution field. For this reason the resultant system is bad conditioned, except from the time-step when re-meshing is done, and a large number of iteration is needed to reach the convergence. On the contrary, the statically anisotropic mesh provides a mesh which is generally good for all the time steps and leads to a better conditioned system: the number of required iterations is decreased by 25% with respect to the isotropic mesh (with the same number of elements).




Figure 6: Computational time analysis for dynamic re-meshed simulation




Figure 7: Average number of iterations to solve the linear system

CONCLUSIONS

In this work a non-industrial EMS application was simulated. The flow has been simulated by using a VMS algorithm in order to take into account the small scale turbulence in an implicit way. The adopted anisotropic mesh adaptation algorithm allows the user to use a low number of elements; it also improves the conditioning of the final system, so less iterations are required to solve the problem. A weak coupling scheme is adopted to simulate the coupled electromagnetic-fluid mechanical phenomena. This scheme is computational light, but is able

to predict the main features of the simulated application. Finally, a mechanic symmetry condition is considered to be accurate in the stirred flow simulation.

ACKNOWLEDGEMENTS

The authors give thanks to Transvalor S.A. for funding this research and for the continuous support which allowed the complete exploitation of its software.

REFERENCES

- [1] Singh, R., Thomas, B.G and Vanka, S.P. (2014). Large eddy simulations of double-ruler electromagnetic field effect on transient flow during continuous casting. *Metallurgical and materials transactions B*, 45B,1098-1114.
- [2] Mureau, R. (1990). Magnetohydrodynamics, volume 3, Springer science.
- [3] Felten, F., Fautrelle, Y., Du Terrail, Y. and Metais, O. (2004). Numerical modelling of electromagnetically-driven turbulent flows using LES methods. *Applied Mathematical Modelling.*, 28, 15-27.
- [4] Barna, M., Javurek, M., Reite, J. and Lechner, M. (2009). Numerical Simulations of Mould Electromagnetic Stirring for Round Bloom Strands. *BHM Berg-und Huttenmannische Monatshefte*, 154, 518-522.
- [5] Nedelec, J. C. (1980). Mixed finite elements in \mathbb{R}^3 . *Numerische Mathematik.*, 35(3), 315-341.
- [6] Hughes, T.J.R., Feijóo1, G.R., Mazzei, L. and Quincy, J.B. (1998). The variational multiscale method - a paradigm for computational mechanics. *Computer Methods in Applied Mechanics and Engineering*,166(1:2),3-24.
- [7] Hachem, E., Rivaux, B., Kloczko, T., Digonnet, H. and Coupez, T. (2010). Stabilized finite element method for incompressible flows with high Reynolds number. *Journal of Computational Physic.*, 229(23), 8643-8665.
- [8] Fujisaki, K. (2001). In-Mold Electromagnetic Stirring in Continuous Casting. *IEEE Transactions on Industry Applications*,8, 2591-2598.
- [9] Thomas, B. G. and Chaudhary, R. (2009). State of the Art in Electromagnetic Flow Control in Continuous Casting of Steel Slabs: Modeling and Plant Validation in *6th International Conference on Electromagnetic Processing of Materials EPM*.
- [10] Coupez, T. (2011). Metric construction by length distribution tensor and edge based error for anisotropic adaptive meshing. *Journal of computational physics*,230, 2391-2405.
- [11] Coupez, T. and Hachem, E. (2013). Solution of high-Reynolds incompressible flow with stabilized finite element and adaptive anisotropic meshing. *Computer Methods in Applied Mechanics and Engineering*, 267,65-85.
- [12] Yuan, Q., Zhao, B., Vanka, P. and Thomas, B. G. (2005). Study of computational issues in simulation of transient flow ini continuous casting. *Steel Research International, Special Issue: Simulation of Fluid Flow in Metallurgy*, 76(1), 33-43.