



Enhancement of VCSEL performances with a new bonding process

Salvatore Pes, Fethallah Taleb, Cyril Paranthoen, Christophe Levallois,
Nicolas Chevalier, Olivier de Sagazan, Hervé Folliot, Mehdi Alouini

► To cite this version:

Salvatore Pes, Fethallah Taleb, Cyril Paranthoen, Christophe Levallois, Nicolas Chevalier, et al.. Enhancement of VCSEL performances with a new bonding process. 15è Journées Nano, Micro et Optoélectronique (JNMO 2016), May 2016, Les Issambres, France. . hal-01328013

HAL Id: hal-01328013

<https://hal.science/hal-01328013>

Submitted on 8 Jun 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Enhancement of VCSEL performances with a new bonding process

S. Pes^{1,2}, F. Taleb¹, C. Paranthoën¹, C. Levallois¹, N. Chevalier¹, O. De Sagazan³, H. Folliot¹, M. Alouini²

¹ Laboratoire FOTON UMR-CNRS 6082, INSA de Rennes, 35708 Rennes, France

² Institut de Physique de Rennes UMR-CNRS 6251, Université de Rennes 1, 35042 Rennes, France

³ IETR UMR-CNRS 6164, Université de Rennes 1, 35042 Rennes, France

e-mail: salvatore.pes@insa-rennes.fr

Motivations

Development of a new VCSEL technological process (called Through Silicon Holes Electroplated Copper process)

Main advantages:


- hybrid integration of (virtually any) III-V active region on Si host substrate
- mechanical stress-induced-free approach with respect to standard large area dissipative Cu surfaces solutions
- possibility of microelectronics, photonics and microfluidics on-chip integration
- fully compactibility with optical pumping and electrical injection schemes
- cost-effectiveness and potential industrial scalability

Demonstration of:

- 1.55 μm emitting InP-based SQW-OP-VCSELS
- Improved optical and thermal laser performances

QW-OP-VCSEL fabrication


Trough Silicon Holes Electroplated Copper (TSHEC) process [1]



[1] F. Taleb et al., 26th IPRM International Conference, 2014

Active region structure


SQW-based active region structure and PL characterization




- 8 nm 3x3 InGaAsP strained QWs on InP(001)
- Optimized Q_{1.18} barriers thickness → uniform pumping of the active region
- Micro-cavity length optimization to match maximum SQWs gain emission (CAD design + post-process InP phase layer thickness wet etching fine adjustments)
- SQWs emission at 1.52μm to compensate red thermal shift under operation
- FWHM = 50nm; low energy side HWHM = 20nm → smooth interfaces

Optical characterization

Influence of bottom H-DBR sizes on CW single mode VCSEL emission wavelength, output power and threshold



Experimental setup used for VCSEL characterization:
 ➤ Sample surface and mode profile imaging
 ➤ Real-time P_{inc}, P_{refl}, P_{abs}, P_{out} measurements
 ➤ Spectrum & temperature dependence analysis




For 20 μm diameter H-DBR at 20°C:

- Emission at 1.544 nm
- P_{th} = 7 mW
- P_{out} max > 2 mW in CW SM emission
- Lasing up to 55°C

Red shift, higher threshold and lower P_{out} max for higher H-DBR diameter


Thermal characterization

FEM thermal modelling




20 μm diameter H-DBR VCSEL FEM model

$$R_{th} = \frac{\Delta T}{P_{diss}}$$



Correlation between simulated thermal impedance and threshold absorbed power for different H-DBR diameters sizes

Preliminary thermal impedance measurements



$$R_{th} = \frac{\Delta \lambda}{\Delta P_{abs}} \left(\frac{\Delta \lambda}{\Delta T} \right)^{-1}$$

Experimental measurements of the thermal impedance in agreement with FEM simulations

Conclusions

- Development of TSHEC technology for active region and Si substrate integration
- Enhancement of optical and thermal performances with respect to previous VCSEL technology
- Study on bottom H-DBR size influence on VCSEL emission and thermal properties

Perspectives

- Further improvements of TSHEC technology → towards higher P_{out}, lower threshold, lower R_{th}, more reliable process
- Development of TSHEC technology for EP-VCSELS
- On chip microelectronics (temperature sensors, VCSEL driver, etc.)?

Acknowledgements

This work was supported by Brittany Region and French agencies ANR (Agence Nationale de la Recherche) and DGA (Direction Générale de l'Armement) within the ANR-ASTRID HYPOCAMP project (grant n° ANR-14-ASTR-0007-01)