



# Enhancing carbon-nanotubes luminescence With the help of plasmonic antennas





## Carbon nanotubes



Well-defined exciton peak @ Room temperature

Telecom-window range : *wavelength* ~ 1200 nm

Small in diameter but quite long  $\rightarrow$  single CNT

(Can be excited by current injection)

Nanotube  $d \sim nm$  $L \sim \mu m$  CNT are attractive light source

But...

with a very small quantum yield (less than 1%)!









Typically : in the sample 5 families of semiconducting carbon nanotubes

Characterized by a well-defined exciton peak





Typically : in the sample 5 families of semiconducting carbon nanotubes

Characterized by a well-defined exciton peak



### Carbon nanotubes + photonics crystals



LABORATOIRE

MONTPELLIER



Radiative Enhancement ~ 200

R. Miura et al. Nature communications 6580 (2014)



# Carbon nanotubes + photonics crystals



LABORATOIRE







Few carbon nanotubes (1 single) Quantum emitter Collection of Metallic scatterers Luminescence Enhancement?

Field of plasmonics (optics of metals) Purcell effect : how environment modify quantum emitter luminescence

Broad-band enhancement: for the 5 chiralities







# Plasmonics and plasmonics antennas





#### Prism coupling

Metallic nanoparticles Diffraction => Localized plasmon resonance

Can act as antennas in the visible regime :

- modify radiative pattern (directivity)
- modify luminescence intensity (energy extraction, Purcell effect)





## The patch antenna



#### Bottom metallic mirror:

- Light emits in one direction
- Increase electric field confinement

#### Finite size metallic nanoparticle:

- scatter the near-field
- Can increase of the power radiates by the emitter





Cavity (plasmonic) modes : cavity geometry defines resonant modes Large cavity (~1 $\mu$ m) many cavity modes (kind of continuum)

small antennas = high enhancement





The whole metallic disk radiates  $\rightarrow$  the plasmonic mode radiates

Purcell factor  $\sim 70$ 

Belacel et al. Nano Lett., 2013, 13 (4), pp 1516–1521





The purcell factor depends drastically on the dipole orientation







#### Unfortunately not favorable for CNT !!







MONTPELLIER

LABORATOIRE



Collection of individual scatterers



Microscopic scale: dipolar resonance
→ Large Purcell factor

150 nm

Random distribution of plasmonic
 nanoparticles
 → relax dipole/metal surface alignment





Patch: Colloidal nano-triangles made on silver coated with silica

Resonant @ 1280 nm with broad size dispersion





=> broad "resonance" peak (inhomogeneous broadening)

=> broad-band enhancement





Single emitter = Carbon Nanotube





Cartography of the sample luminescence (XY-map) From room temperature to 4 K





### The experimental setup: Reflectivity



Cartography of reflectivity of the sample surface (XY-map)



### Map of the sample luminescence

LABORATOIRE

JLOMB MONTPELLIER

XY-Map of the Total Intensity – Without particles



### Map of the sample luminescence

LABORATOIRE Δ

OMB

MONTPELLIER

XY-Map of the Total Intensity Without particles s



### Cartography of the sample : finer scale

LABORATOIRE



Inhomogeneity characteristic scale ~ 500 nm















-Strategy

Random antennas/ Random CNT

Improve CNT/antenna dipole matching

⇒Radiative enhancement ~ 200 ⇒ Usually ~ 50 ⇒ length scale ~ 50 nm







Large antennas = better directivity





## Scattering cross-section



