



HAL
open science

Design of Phosphonated Imidazolium-Based Ionic Liquids Grafted on γ -Alumina: Potential Model for Hybrid Membranes

Marie-Alix Pizzoccaro, Martin Drobek, Eddy Petit, Gilles Guerrero, Peter Hesemann, Anne Julbe

► **To cite this version:**

Marie-Alix Pizzoccaro, Martin Drobek, Eddy Petit, Gilles Guerrero, Peter Hesemann, et al.. Design of Phosphonated Imidazolium-Based Ionic Liquids Grafted on γ -Alumina: Potential Model for Hybrid Membranes. International Journal of Molecular Sciences, 2016, Special Issue "Ionic Liquids 2016 and Selected Papers from ILMAT III", 17 (8), pp.1212. 10.3390/ijms17081212 . hal-01373840

HAL Id: hal-01373840

<https://hal.science/hal-01373840>

Submitted on 1 Jul 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Article

Design of Phosphonated Imidazolium-Based Ionic Liquids Grafted on γ -Alumina: Potential Model for Hybrid Membranes

Marie-Alix Pizzoccaro ¹, Martin Drobek ¹, Eddy Petit ¹, Gilles Guerrero ^{2,*}, Peter Hesemann ² and Anne Julbe ^{1,*}

¹ Institut Européen des Membranes, UMR-5635 CNRS-UM-ENSCM, Université de Montpellier (CC047), Place Eugène Bataillon, F-34095 Montpellier cedex 5, France; marie-alix.pizzoccaro@etu.umontpellier.fr (M.-A.P.); martin.drobek@umontpellier.fr (M.D.); eddy.petit@univ-montp2.fr (E.P.)

² Institut Charles Gerhardt, UMR-5253 CNRS-UM-ENSCM, Université de Montpellier (CC1701), Place Eugène Bataillon, F-34095 Montpellier cedex 5, France; peter.hesemann@umontpellier.fr

* Correspondence: gilles.guerrero@umontpellier.fr (G.G.); anne.julbe@umontpellier.fr (A.J.); Tel.: +33-467-144-223 (G.G.); +33-467-149-142 (A.J.)

Academic Editor: Andreas Taubert

Received: 24 June 2016; Accepted: 20 July 2016; Published: 27 July 2016

Abstract: Imidazolium bromide-based ionic liquids bearing phosphonyl groups on the cationic part were synthesized and grafted on γ -alumina (γ -Al₂O₃) powders. These powders were prepared as companion samples of conventional mesoporous γ -alumina membranes, in order to favor a possible transfer of the results to supported membrane materials, which could be used for CO₂ separation applications. Effective grafting was demonstrated using energy dispersive X-ray spectrometry (EDX), N₂ adsorption measurements, fourier transform infrared spectroscopy (FTIR), and special attention was paid to ³¹P and ¹³C solid state nuclear magnetic resonance spectroscopy (NMR).

Keywords: imidazolium-based ionic liquids; γ -alumina; phosphonate coupling agent; grafting; solid state NMR; hybrid membrane

1. Introduction

In competition with amines, ionic liquids are known to interact strongly and reversibly with CO₂, making supported ionic liquid (IL) materials versatile solids for use in adsorptive or membrane CO₂ separation applications [1]. The most common systems are composed of ILs either impregnated or confined in matrices, which can be porous or non-porous (i.e., polymer, ceramic or hybrid matrices). These materials can have applications, for example, in batteries [2–4], as electrolytes [5] or as CO₂ separation systems [6,7]. Imidazolium-based ILs grafted onto the surface of porous supports are promising systems for a range of applications, including catalysis [8,9], chromatography [10–12] and gas separation [13,14]. These types of systems have been defined by Fehrmann et al. [15], as supported ionic liquids (SILs), which refer to either inert or catalytically-active covalently-bound monolayers of ILs. In these materials, the IL does not act like the bulk liquid anymore, but as a surface modifier. As reported by the authors, tailoring the chemical nature of the support, as well as its microstructure (pore size, size distribution, surface area, etc.), govern the grafting of the IL and its distribution on the support surface. Covalent linking of ILs on a ceramic oxide support appears as an attractive strategy to fine-tune solids with outstanding properties for CO₂ adsorption and with improved long-term stability. Ionic liquids can be grafted on mesoporous silica-based supports, such as MCM-41 [16] or SBA-15 [17], and they also can be incorporated within a silica hybrid matrix [18].

These mixed ionic-mineral phases have been the most widely-investigated systems for applications such as heterogeneous catalysis [13,19,20], gas separation [13,14] or CO₂ sorption [21].

γ -alumina (γ -Al₂O₃) is a commonly-used ceramic support, and its hydroxylated surface is attractive for anchoring or grafting active species for either gas separation or heterogeneous catalysis [22]. In addition, this material can be cast easily as a continuous membrane film and was thus selected in this work as a relevant support for grafting imidazolium-based ionic liquids. Controlling the chemical grafting of ILs in the pores of a porous material is much more challenging than their simple impregnation in a porous support, yielding the supported ionic liquid phase (SILP). Obviously, the choice of the functionalized imidazolium-based IL is a key parameter, but the characterization of the grafting reaction is a tricky task. The efficiency of the grafting step needs to be quantified, and the spatial proximity between the grafted sites needs to be determined.

Several functionalized imidazolium-based ILs have been reported in the literature with functional groups, such as trimethoxysilyl, thiol-, ether-, carboxylic acid-, amino- and hydroxyl-groups [23]. Each of these functional groups is adapted for grafting on a pre-functionalized support. Vangeli et al. [14] selected the trimethoxysilyl group to react with the hydroxyl groups of silica-based materials pre-treated with a piranha solution. The grafting reaction has been performed in two steps: (i) grafting of a silylated precursor and (ii) quaternization with 1-methylimidazole, yielding the imidazolium species. Despite the detection of carbon by elemental analysis and the measured decrease of support specific surface area after grafting, the demonstration of both the quaternization reaction and anchoring configuration were rather unclear.

The chemical modification of γ -alumina powders with organosilanes has been largely investigated in the literature [24,25]. As an alternative, grafting reactions could also be realized with phosphonate or phosphinate coupling functions. Randon et al. [26] have linked phosphoric acid and alkyl phosphonic acid to the surface of both titania and zirconia membranes in order to improve their performance for the ultrafiltration of bovine serum albumin (BSA) proteins. Caro et al. [27] modified a γ -Al₂O₃ membrane top-layer with alkyl/aryl phosphonic acids, thus resulting in an organophobic behavior. Guerrero et al. [28,29] studied the grafting of phenylphosphonic acid and its ester derivatives on both γ -Al₂O₃ and TiO₂ powders. The surface bonding modes were investigated by both diffuse reflectance infrared spectroscopy (DRIFT) and ³¹P solid-state magic angle spinning nuclear magnetic resonance spectroscopy (MAS NMR). The same authors also patented a process for modifying an inorganic substrate with organophosphorus coupling agents, relevant for antibacterial applications. In this work, imidazolium-based ILs with phosphonyl functional groups were used for their intrinsic antimicrobial properties [30].

The aim of the present work was to develop an optimized γ -Al₂O₃/imidazolium-based ILs system able to serve as a preliminary study for developing efficient gas separation hybrid membrane in which the IL will be effectively grafted on the pore surface. The approach involves the synthesis and characterizations of both the γ -Al₂O₃ support and the functionalized IL, followed by the investigation of the grafting reaction and the quantitative analysis of both the grafting step and the derived hybrid material. Two organophosphorus functionalized imidazolium-based ILs were selected (Figure 1): the 1-methyl-3-(3-(diethylphosphinyl)propyl)-imidazolium bromide (ImPE) and the 1-methyl-3-(3-((trimethoxysilyl)phosphinyl)propyl)-imidazolium bromide (ImTMSP). The synthesis of ImPE was carried out following the procedure described by Mu et al. [31], while the synthesis of ImTMSP was performed for the first time by adapting the work of McKenna et al. [32]. The modification of the γ -Al₂O₃ surface under either standard or forcing conditions was investigated by energy dispersive X-ray spectrometry (EDX) and N₂ adsorption measurements. In addition, key information was derived from fourier transform infrared spectroscopy (FTIR) and ³¹P, ¹³C solid state NMR analysis.




Figure 1. Representation of the structures of ImPE (1-methyl-3-(3-(diethylphosphinyl)propyl)-imidazolium bromide) (a) and ImTMSP (1-methyl-3-(3-((trimethoxysilyl)phosphinyl)propyl)-imidazolium bromide) (b).

2. Results and Discussion

γ -alumina (γ -Al₂O₃) was prepared from boehmite using a sol-gel process described by Leenaars et al. [33] and followed by a 3-h thermal treatment in air at 600 °C. As revealed by ¹H MAS NMR, hydroxyl groups are present on the alumina surface, and they are involved in the grafting reaction mechanism by condensation with ester functions (P-OX) of the organophosphonate coupling agent [34].

The surface of γ -Al₂O₃ powders was modified by treatment with an organic or aqueous grafting solution containing n-fold excess of either ImPE or ImTMSP ionic liquid. The quantity of IL used corresponds to the amount needed for a full surface coverage of the γ -Al₂O₃ particles (0.6 mmol, assuming an area of 25 Å² per ionic liquid molecule). Depending on the ILs used, different reaction conditions were applied (Table 1). In order to evidence the spectroscopic characteristics of physisorbed phases or unreacted species on the surface of γ -Al₂O₃, a grafting experiment was first performed with ImPE in “physisorption conditions”. Secondly, in standard reaction conditions, grafting with ImPE was achieved during several days in an alcoholic solvent, while grafting with ImTMSP was realized during either one night or three days in dry methylene chloride. Otherwise, as reported for the grafting of diethyl phenylphosphonate coupling agents on γ -Al₂O₃, the use of forcing reaction conditions (i.e., excess of coupling agent relative to full surface coverage, and high temperature) did not lead to dissolution-precipitation mechanism (no formation of bulk aluminum phosphonate phases) and improved the surface grafting density [28,35]. Therefore, finally, forcing reaction conditions were also tested with ImPE in aqueous medium for one night by increasing the reaction temperature up to 130 °C. After the grafting treatment, samples were centrifuged, washed with an ethanol-water solution to remove unreacted and physisorbed species and dried at 70 °C under vacuum before analysis (see Materials and Methods).

Table 1. Standard and forcing conditions for grafting the γ -alumina powders with organophosphonate imidazolium-based ionic liquids (ILs).

	IL	Solvent (mL)	T (°C)	Time (h)	N-Fold Excess	N (ILs) mmol	Sample
Standard conditions	ImPE	2-butanol (5)	90	288	6	3.6	ImPE1
	ImTMSP	CH ₂ Cl ₂ (14)	25	17	2	1.2	ImTMSP1
	ImTMSP	CH ₂ Cl ₂ (14)	25	72	2	1.2	ImTMSP2
	ImTMSP	CH ₂ Cl ₂ (14)	25	17	6	3.6	ImTMSP3
	ImTMSP	CH ₂ Cl ₂ (14)	25	72	6	3.6	ImTMSP4
Forcing conditions	ImPE	water (10)	130	17	2	1.2	ImPE2
	ImPE	water (10)	130	17	6	3.6	ImPE3
	ImPE	water (10)	130	17	12	7.2	ImPE4

The characteristics of unmodified and grafted γ -Al₂O₃ powders are summarized in Table 2. Average phosphorus weight percentages (wt % P) obtained from EDX showed the presence of phosphorus in all of the grafted samples. The proportions do not exceed a full surface coverage (i.e., 3.2 wt % P), which is coherent with the surface reactions of the ILs coupling agents on γ -Al₂O₃. The sample modified with a six-fold excess of ImPE in forcing reaction condition (ImPE3) exhibited a slight increase of P contents by comparison with the sample obtained with a six-fold excess in standard condition (ImPE1). This result suggests that a higher temperature with a short reaction time tends to

increase the rate of the surface modification reaction. For ImPE samples in forcing reaction conditions, an enhancement of ILs coupling agent excess in solution leads to an increase of the γ -Al₂O₃ surface coverage. In the case of ImTMSP samples, the P contents measured on modified γ -Al₂O₃ were in the range of the values obtained for the samples modified by ImPE. Nevertheless, no heat activation was needed with ImTMSP, suggesting a difference of reactivity, while the $-\text{PO}(\text{OSiMe}_3)$ function is known to be more reactive [28]. Finally, the efficiency of grafting reactions with ImTMSP did not seem to depend on reaction times, but was rather sensitive to the excess value of the IL coupling agent in solution.

Table 2. Characteristics of the γ -alumina powders before and after grafting reactions.

Sample	C _{BET}	wt% P ^a	P nm ⁻² b
γ -Al ₂ O ₃	82	0	/
ImPE1	60	0.90 ± 0.05	0.9
ImPE2	63	0.62 ± 0.02	0.6
ImPE3	59	1.12 ± 0.04	1.1
ImPE4	55	1.42 ± 0.03	1.4
ImTMSP1	70	0.92 ± 0.04	0.9
ImTMSP2	66	0.92 ± 0.02	0.9
ImTMSP3	64	1.16 ± 0.10	1.1
ImTMSP4	63	1.00 ± 0.10	1.0

^a From EDX analysis; ^b average number of coupling molecules per nm².

Nitrogen adsorption experiments did not reveal any important variation of the specific surface area values between the crude γ -Al₂O₃ powder and the grafted samples series, which is consistent with only the surface modification. The results of adsorption measurements gave also access to the BET constant (C_{BET}) related to the affinity of the solid with N₂ molecules and so which is characteristic of the adsorbate/material surface interactions, as reported by Galarneau et al. [36]. The decrease of the C_{BET} value reflects a reduction of the enthalpy of adsorption of N₂ molecules on the surface and thus gives qualitative information about surface modification. All of the grafted samples showed a lower C_{BET} constant than the starting γ -Al₂O₃ powders (Table 2). For each kind of coupling agent, the increase of the weight percentage of phosphorus measured on the modified samples correlates with a decrease of the C_{BET} constant. In addition, from the weight percentage of phosphorus and the specific surface area, we can estimate the grafting density (P nm⁻²) on the surface of the γ -Al₂O₃ powders, assuming an area of 25 Å² per phosphonate molecule (Table 2). Therefore, a full surface coverage of the alumina particles should not exceed 4 P atoms by nm². In all of the grafted samples, values from 0.6 to 1.4 of the grafting density were obtained, suggesting that the surface coverage does not exceed about 30% of the full monolayer in all cases.

In comparison with the literature, it has been demonstrated that the grafting on Degussa γ -Al₂O₃ in organic media with the diethyl phenylphosphonate coupling molecule resulted in a 50% surface coverage [28]. Moreover, in the same study, the authors have also evidenced that the grafting with bis(trimethylsilyl)ester phenylphosphonate coupling agent led to a higher percentage of phosphorus atoms, consistent with the formation of bulk aluminum phosphonate phases. It was also pointed out that the use of the dialkyl ester derivatives in organic media allowed the control of the grafting and excluded the formation of phosphonate phases even under prolonged heating. The partial surface coverage obtained in this study with the diethyl imidazolium phosphonate coupling molecule could result from a possible steric hindrance effect on the γ -Al₂O₃ surface (due to both the alkyl chain and the imidazolium ring) and also from the low reactivity of the coupling function. Furthermore, the results obtained with ImTMSP showed that the control of the reaction condition parameters can allow the incorporation of coupling agent quantities consistent with sole surface coverage without any evidence of the formation of bulk aluminum phosphonate phases. Thus, additional grafting parameters have to be tested (i.e., grafting duration, concentration, temperature, etc.) in order to optimize the reaction conditions and maximize the γ -alumina surface coverage.

The reaction of organophosphorus derivatives on the γ -Al₂O₃ surface is supposed to involve both coordination of the oxygen of the phosphoryl groups (P=O) to Lewis acid sites and the condensation reactions of P-OX functions (X could be Et or SiMe₃) with Al-OH surface groups. According to the literature, there are several possible bonding modes for phosphonate coupling molecules on an oxide surface [34]. In the case of phosphoryl imidazolium-based ILs, the possible bonding modes can be mono-, bi- or tri-dentate (Figure 2).




Figure 2. Schematic representation of some possible bonding modes for phosphonate coupling imidazolium-based ionic liquids on a γ -Al₂O₃ surface (X could be Et or SiMe₃).

The FTIR spectra between 1400 and 800 cm⁻¹ of the two organophosphonate functionalized imidazolium bromide-based ILs are presented in Figure 3I. ImPE and ImTMSP showed P=O stretching vibrations at 1230 cm⁻¹ and 1251 cm⁻¹, respectively, and C–H deformation vibrations at 956 cm⁻¹ for ImPE and 1035 cm⁻¹ for ImTMSP. Asymmetric and symmetric P–O–C stretching vibrations are present only for ImPE at 1042 and 958 cm⁻¹ [28,37]. In addition, the spectra of ImTMSP present a P–O–Si deformation vibration at 833 cm⁻¹. Starting from the ionic liquid structure, DFT calculation is useful to estimate the different vibration modes of the coupling agents (Figure S10 in the Supplementary Information) and to identify some of the deformation bands, such as the =C–H imidazolium band and the –CH₂– spacer alkyl chain band present at about 1165 cm⁻¹ for both ILs. In all grafted samples, we can notice the disappearance of the phosphoryl (P=O) stretching bands near 1230 and 1251 cm⁻¹, suggesting that the phosphoryl oxygen is strongly bonded to Lewis acid surface sites by coordination (Figure 3IIa–c). Moreover, the IR spectra are dominated by an absorption band at 1171 cm⁻¹, typical of the =C–H and –CH₂– deformation bands of the imidazolium ring and the spacer alkyl chain. The PO regions of the grafted samples between 950 and 1250 cm⁻¹ differ depending on both the IL and the applied reaction parameters. The IR spectra of samples treated in forcing reaction conditions with ImPE (Figure 3IIb) present a strong absorption band at 1065 cm⁻¹, tentatively ascribed to the P–O–Al stretching vibration [37]. It can be noted that this band became gradually broader when increasing the quantity of grafted species. Therefore, the presence of weak absorption bands at about 1040 and 950 cm⁻¹ (region of P–O–C stretching bands) does not preclude the existence of some P–OEt residual groups.

The FTIR spectrum of the sample modified with ImPE under standard reaction conditions (Figure 3IIa) shows a broader absorption band around 1050 cm⁻¹ corresponding to the P–O group stretching mode. This band could be attributed to P–O surface species in organophosphonate/metal oxide systems according to Quiñones et al. [38]. In addition, the presence of strong residual P–O–C stretching bands at about 1040 cm⁻¹ cannot be excluded. The IR spectra of samples prepared with ImTMSP (Figure 3IIc) in standard conditions are quite similar to the ImPE1 spectrum. The most important difference comes from the presence of residual P–O–Si deformation vibration between ~1000 and 800 cm⁻¹, which suggests that all of the coupling functions have not reacted with the alumina surface [28]. To conclude, IR spectroscopy of samples grafted in standard reaction conditions

clearly reveals the presence of residual P-O-C or P-O-Si vibrations, stating that phosphonate units are preferentially linked to the alumina surface through bidentate (or monodentate) binding modes. In the case of samples prepared in forcing conditions, weak residual P-O-C stretching modes may be present on the infrared spectra, indicating that the dominating bonding mode of the phosphonate groups seems to involve tridentate PO_3 units.




Figure 3. Experimental FTIR spectra of ImPE (Ia,b) and ImTMSP (Ic) and respective grafting on $\gamma\text{-Al}_2\text{O}_3$ prepared under different reaction conditions: (IIa) with ImPE under standard condition (ImPE1), (IIb) with ImPE under forcing conditions (130 °C, 17 h) at different concentration (ImPE2 to ImPE4: two- to 12-fold excess) and (IIc) with ImTMSP under standard conditions (25 °C, six-fold excess).

^{13}C cross polarization magic angle spinning (CP-MAS) liquid NMR spectra of ImPE and ImTMSP display both the specific chemical shifts (Figure 4Ia,b) of the 1-methyl-3-propylimidazolium group, numbered from C_1 to C_7 , and those of the coupling functions, numbered from C_8 to C_9 for $-\text{POCH}_2\text{CH}_3$ and C_8 only for $-\text{OSiMe}_3$. In comparison, the ^{13}C CP-MAS solid state NMR spectra of the grafted samples ImPE4 (Figure 4IIa) and ImTMSP4 (Figure 4IIb) show a slightly upfield shift for all of the atoms, principally due to the spatial proximity and chemical bonds with the $\gamma\text{-Al}_2\text{O}_3$ surface. Whatever the coupling function, the integrity of the organic molecule structure was conserved during the grafting process. In both grafted samples' spectra, we can notice the presence of weak peaks attributed to residual $-\text{POCH}_2\text{CH}_3$ and $-\text{OSiMe}_3$ functions, confirming the conclusions derived from the FTIR spectra (Figure 3) and supporting our hypothesis concerning the presence of multimodal bonding modes (i.e., tridentate, bidentate, monodentate).

Additional information was provided by the ^{31}P MAS NMR spectra of the grafted $\gamma\text{-Al}_2\text{O}_3$. The powder treated under physisorption reaction conditions allows identification of the chemical shift corresponding to physisorbed species, with a sharp resonance at 32.1 ppm (Figure S11). The ^{31}P MAS NMR spectra of all of the grafted samples (Figure 5a,b) did not reveal this peak, indicating that only grafted phosphonate species were present on the alumina surface. Moreover, we did not notice any additional upfield sharp resonance peak resulting from a dissolution/precipitation phenomenon and the formation of aluminum phosphonate bulk phases. This was confirmed by powder X-ray diffraction patterns (XRD) highlighting the amorphous structure of all of the grafted samples (Figure S12).




Figure 4. ^{13}C CP-MAS NMR spectra of pure ionic liquids (I) and the $\gamma\text{-Al}_2\text{O}_3$ grafted samples (II) prepared under the different reaction conditions. Comparison between: (a) pure ImPE and ImPE4 (130 °C, 17 h, 12-fold excess); (b) pure ImTMSP and ImTMSP4 (six-fold excess, 72 h).




Figure 5. ^{31}P MAS NMR spectra of $\gamma\text{-Al}_2\text{O}_3$ grafted samples prepared under different reaction conditions: (a) standard conditions with ImPE (90 °C, 288 h) (ImPE1) and forcing conditions with ImPE (130 °C, 17 h) at different concentrations (ImPE2 to ImPE4: two- to 12-fold excess); (b) standard conditions with ImTMSP (25 °C) at various reaction times and concentrations: twofold excess, ImTMSP1 (17 h); ImTMSP2 (72 h); and six-fold excess, ImTMSP3 (17 h); ImTMSP4 (72 h).

The ^{31}P MAS NMR spectra of the $\gamma\text{-Al}_2\text{O}_3$ powder modified with ImPE under forcing reaction conditions are displayed in Figure 5a (ImPE2, ImPE3 and ImPE4). All three spectra present a broad resonance centered at about 23.6 ppm. The simulation of the spectra indicated the presence of at least three sites (signals at 32.4, 23.6 and 17.9 ppm (Figure 5, Table 3)) revealing the presence of multiple bonding modes (Figure 2) for the phosphonate units as already discussed for the IR spectra. As reported by Brodard-Severac et al. [39], the interaction of the P=O groups with surface Lewis or Brønsted acidic sites should lead to a downfield shift. On this basis, the signal at 32.4 ppm, integrating from 7% to 13%, could be tentatively ascribed to the minor monodentate bonding mode (Figure 2). ^{13}C CP MAS NMR indicated the presence of residual P-OEt functions, and IR spectra showed also weak residual P-O-C stretching modes, stating that the dominating bonding mode of the phosphonate groups seems to involve tridentate PO_3 units. Therefore, we propose to ascribe the major signal at 23.6 ppm, integrating from 55% to 58%, to tridentate phosphonate PO_3 units grafted on the $\gamma\text{-Al}_2\text{O}_3$ surface. The third resonance at 17.9 ppm, integrating from 29% to 38%, was then attributed to grafted phosphonate functions in a bidentate mode. For both ImPE3 and ImPE4, it is interesting to notice that the increase of the proportion of this bonding mode correlates well with the increasing intensity of the IR stretches of residual P-OEt functions. Consequently, by increasing the n-fold excess of coupling agents during the grafting reaction in forcing reaction conditions, both tridentate and bidentate bonding modes of the phosphonate units were favored.

Table 3. Parameters used for the simulation of ^{31}P MAS NMR spectra of $\gamma\text{-Al}_2\text{O}_3$ grafted with ImPE under either standard (ImPE1) or forcing (ImPE2, ImPE3 and ImPE4) reaction conditions.

Sample	ImPE1			ImPE2			ImPE3			ImPE4		
δ (ppm)	31.6	22.1	18.1	32.4	23.6	17.9	32.4	23.6	17.9	32.4	23.6	17.9
Width (ppm)	7.5	7.6	11.5	9.1	6.9	10.0	7.4	7.4	13.0	7.4	8.0	14.4
Integration (%)	18	37	45	13	58	29	7	55	38	7	57	36

The ^{31}P MAS NMR spectrum of the $\gamma\text{-Al}_2\text{O}_3$ powder modified with ImPE under standard reaction conditions is also displayed in Figure 5a (ImPE1). It consists of a broad resonance centered at about 21.6 ppm with an important downfield asymmetrical shape. The simulation of the ImPE1 spectrum using a minimum number of resonances with a Gaussian–Lorentzian shape indicates the presence of at least three sites (Figure 5a, Table 3) at 31.6, 22.1 and 18.1 ppm, evidencing the presence of multiple bonding modes, as for ImPE2 to 4 (Figure 2). On the basis of the IR results, a higher number of residual P-OEt functions was detected when using standard rather than forcing reaction conditions. This implies an increasing proportion of monodentate and/or bidentate bonding modes of the phosphonate units. Thus, by comparison with the ImPE2 to 4 samples, we noticed a raising in the integration of the signals at 31.6 (18%) and 18.1 (45%) ppm, respectively ascribed to monodentate and bidentate bonding modes (Figure 2), which is in a good agreement with FTIR data. The signal corresponding to tridentate bonding mode at 22.1 ppm became minor with 37% integration.

The above results suggest that the grafting of $\gamma\text{-Al}_2\text{O}_3$ with diethyl phosphonate coupling agent strongly depends on the surface modification reaction conditions. Soft standard reaction conditions mainly promote bidentate and monodentate bonding modes on the surface with a minority of tridentate phosphonate units. Conversely, forcing conditions lead rather to tridentate bonding modes on the alumina surface, with a smaller proportion of the other bonding modes.

Figure 5b displays the ^{31}P MAS NMR spectra of $\gamma\text{-Al}_2\text{O}_3$ grafted under standard conditions (25 °C) using ImTMSP at different reaction times and quantities of IL (two- and six-fold excess). The spectra of ImTMSP1 to 4 samples are qualitatively similar and present a broader peak in comparison with the spectra of $\gamma\text{-alumina}$ grafted with ImPE in forcing reaction conditions, centered at 22.1 ppm. In all cases, the NMR signals present an asymmetrical shape. According to the simulated spectra, three chemical shifts at 25.6, 22.1 and 18.1 ppm were identified with a major resonance for the latter (Table 4). As for the ImPE sample in standard condition with the presence of P-OEt groups, the IR

spectra of ImTMSP1 to 4 revealed important residual P-OSiMe₃ functions, implying an increasing proportion of monodentate and/or bidentate bonding modes of the phosphonate units. The liquid state ³¹P NMR spectrum of ImTMSP (Figure S8) indicated an upfield chemical shift at 24.7 ppm (to be compared with 29.8 ppm for pure ImPE (Figure S5)) in good agreement with the P-OEt to P-OSiMe₃ conversion [29]. On this basis, the signal at 25.6 ppm, integrating from 9% to 18%, could be tentatively ascribed to the minor monodentate bonding mode with two P-OSiMe₃ functions (Figure 2). As for the ImPE1 sample in standard reaction conditions, the major resonances attributed to phosphonate units in bidentate bonding mode correspond to the upfield chemical shifts located at 18.2 ppm and integrating from 47% to 67%. The last signal at 22.1 ppm could be ascribed to tridentate phosphonate units. By using ImTMSP as the coupling agent, we cannot correlate unambiguously the influence of the reaction parameters (excess of coupling agent, reaction duration) with the proportion of the different bonding modes.

Table 4. Parameters used for the simulation of ³¹P MAS NMR spectra of γ -Al₂O₃ grafted with ImTMSP.

Sample	ImTMSP1			ImTMSP2			ImTMSP3			ImTMSP4		
δ (ppm)	25.6	22.1	18.2	25.6	22.1	18.2	25.6	22.1	18.2	25.6	22.1	18.2
Width (ppm)	9.6	5.5	12	9	5.8	12.6	9	4.9	11.2	9	4.9	10.8
Integration (%)	18	35	47	9	30	62	10	23	67	13	29	58

The above results suggest that the reaction of γ -Al₂O₃ with either ImPE or ImTMSP in respective standard conditions promotes the grafting of phosphonate units with mainly a bidentate configuration. An increase of the temperature of the grafting reaction with ImPE favors the tridentate bonding mode of the phosphonate units on the γ -Al₂O₃.

3. Materials and Methods

3.1. Starting Materials

Triethyl phosphite (98%), 1-methylimidazole ($\geq 99\%$) and bromotrimethylsilane (BrSiMe₃) (>97%) were purchased from Sigma-Aldrich (Saint-Quentin-Fallavier, France) and were used as received. 1,3-dibromopropane (98%) was provided by Fisher Chemical (Illkirch, France). Boehmite (Pural type) with a high crystallinity and surface area (249 m²/g) was supplied by CTI S.A. (Salindres, France).

A batch of γ -Al₂O₃ powder was prepared by a sol-gel process based on colloid chemistry in aqueous media with a specific surface area of 220 m²·g⁻¹. The γ -alumina powder batch was separated in small samples containing equal amounts of powder (400 mg) into an argon glovebox. This step avoided the presence of water on the alumina surface and yielded comparable conditions for the grafting reactions.

ImPE was obtained as a yellow oil in a high yield by the corresponding nucleophilic substitution of 1-methylimidazole with diethyl(3-bromopropyl)phosphonate in tetrahydrofuran (THF) (δ ³¹P = 29.80 (CDCl₃)).

ImTMSP was synthesized in a round-bottomed flask by the reaction of the ionic liquid ImPE with BrSiMe₃ (3 equiv) in dry methylene chloride (CH₂Cl₂) (δ ³¹P = 24.70 (DMSO *d*₆)).

THF and CH₂Cl₂ were provided by Sigma-Aldrich and dried with the PureSolv, Innovative Technology device.

3.2. Grafting Reactions

Standard Reaction Conditions: The “standard” reaction conditions are summarized in Table 1. Typical experiments are described below.

Grafting solution with ImPE was prepared by dissolving n-fold excess of the IL in the selected solvent. Five milliliters of the grafting solution and 400 mg of the γ -Al₂O₃ powder stored under argon were mixed in a glass bottle closed with a Teflon cap. The suspension was heated at 90 °C for 12 days.

After cooling down to room temperature, the suspension was then centrifuged at 8500 rpm for 5 min using a Sigma 3-16P centrifuge equipped with a Sigma 12150-H rotor. The supernatant was removed, and the remaining powder was re-dispersed in 5 mL of a (1:1) ethanol-water solution to remove the physisorbed species from the surface, and the new suspension was stirred at room temperature for 5 min. The ethanol-water solution supernatant was removed after centrifugation (8500 rpm, 5 min), and this washing step was repeated twice. The resulting paste was then dried under vacuum (5 to 10 mbar) at 70 °C for ~16 h to afford the sample ImPE1 as a powder.

Grafting with ImTMSP was performed directly in the grafting round-bottomed flask in dry CH₂Cl₂. Typically, ImTMSP (1.2 to 3.6 mmol, corresponding to a 2- or 6-fold excess relative to the amount necessary for a full surface coverage on the γ -Al₂O₃ particles) was dissolved in 15 mL of dry CH₂Cl₂ under stirring, and 400 mg of γ -Al₂O₃ powder stored under argon were dispersed in the grafting solution. The suspension was kept under stirring at 25 °C under argon for time periods ranging from 17 h to 3 days. The suspension was then centrifuged at 8500 rpm for 5 min and the supernatant removed. The remaining paste was re-dispersed in 5 mL of CH₂Cl₂, and the new suspension was stirred at room temperature for 5 min. After centrifugation, the CH₂Cl₂ supernatant was removed and the washing step repeated once. Then, the resulting pastes were washed with a (1:1) ethanol-water solution and dried in the same conditions as above, to afford the samples ImTMSP1 to 4 as powders.

Forcing Reaction Conditions: The “forcing” reaction conditions are summarized in Table 1. Typical experiments are described below.

Grafting ImPE solutions was prepared in water by dissolving the pure ImPE at different proportions (2-, 6- or 12-fold excess). Ten milliliters of the grafting solution and 400 mg of the γ -Al₂O₃ powder stored under argon were dispersed in an autoclave, which was closed with a Teflon cap. The autoclave was sealed and the suspension heated at 130 °C for 17 h. The resulting grafted powders were washed and dried as previously described for ImPE samples grafted under standard reaction conditions to afford the samples ImPE2 to 4 as powders.

3.3. Characterization

The BET specific surface areas and the C_{BET} constants of the samples were obtained from nitrogen adsorption experiments at 77 K by using a Tristar instrument (Micromeritics) for the grafted powders and a ASAP 2020 (Micromeritics) for the γ -Al₂O₃ powders. Prior to measurements, samples were degassed under vacuum overnight at 100 °C for the grafted powders and 300 °C for the γ -Al₂O₃ powder. The weight percentage of phosphorus in the samples was determined by EDX using a Zeiss scanning electron microscope (SEM) EVO HD15 at 10 kV equipped for EDX analysis with the AZtecEnergy analysis software (Oxford instruments, Abindong, UK). Samples were prepared as pellets for the analysis and deposited on double-sided carbon tape. FTIR spectra were obtained with a Perkin-Elmer Spectrum 2 spectrophotometer and were recorded in the 4000 to 400 cm⁻¹ range using 32 scans at a nominal resolution of 4 cm⁻¹ in ATR mode (spectrum of γ -Al₂O₃ as a background spectrum).

Solution NMR experiments: ¹³C and ³¹P NMR spectra were recorded using a Bruker 300-MHz NMR spectrometer at frequencies of 150.86 and 242.94 MHz, respectively.

Solid state NMR experiments: Solid state NMR experiments were performed using a Varian VNMRs 600 MHz (14.1 T) NMR spectrometer. A 3.2-mm Varian T3 HX MAS probe was used for ¹H, ¹³C and ³¹P experiments. The operating frequencies for ¹H, ¹³C and ³¹P were 599.95, 150.86 and 242.86 MHz, respectively. All NMR experiments were performed under temperature regulation in order to ensure that the temperature inside the rotor is 20 °C.

¹³C CP-MAS solid state NMR spectra were recorded at a spinning frequency of 12 kHz MAS. Concerning the CP-MAS experiments, a contact time of 1 ms was fixed, the acquisition time to 30 ms, and the ¹H channel was decoupling on this period. A recycle delay of 2 s was used with a number of scans of 11,450, which permit to obtain a signal-to-noise ratio between 30 and 35. ¹³C chemical shifts were referenced to external adamantane at 38.5 ppm.

^{31}P MAS solid state NMR spectra were recorded at a spinning frequency of 20 kHz. The single pulse experiments were performed with a $\sim 90^\circ$ solid pulse of 3 μs and ^1H decoupling during acquisition. A recycle delay of 45 s was employed (corresponding in both cases to full relaxation of ^{31}P) with a number of scans of 56 for obtaining a signal-to-noise ratio between 53 and 79. ^{31}P chemical shifts were referenced to external hydroxyapatite at 2.80 ppm (used as a secondary reference).

4. Conclusions

One important outcome of this study bears on the possibility to perform the grafting with imidazolium bromide-based ILs bearing phosphonate functions (ImPE or ImTMSP) on $\gamma\text{-Al}_2\text{O}_3$ powders, either in dry methylene chloride solvent (for ImTMSP) or in aqueous and alcoholic solvents (for ImPE). Compared to previous studies published in the literature describing the grafting of phenylphosphonic acid or its bis(trimethylsilyl)ester derivative, no bulk aluminum phosphonate phases were evidenced in the present work. Moreover, this study confirmed that the use of the diethyl imidazolium phosphonate coupling molecule allowed the control of the grafting reaction by using either prolonged heating or high temperature. Surprisingly, the same behavior was demonstrated with the bis(trimethylsilyl)imidazolium ester derivative.

FTIR and solid state NMR spectroscopy (^{31}P , ^{13}C) demonstrated that $\gamma\text{-Al}_2\text{O}_3$ surface modification with diethyl phosphonate coupling agent strongly depends on the grafting conditions.

Soft standard reaction conditions mainly promote bidentate and monodentate bonding modes on the surface, with a minority of tridentate phosphonate units. Conversely, the forcing reaction conditions mainly lead to the formation of tridentate bonding modes on the alumina surface, with a smaller proportion of the other ones. In addition, the grafting of ImTMSP in standard conditions seems also to promote the alumina surface modification by phosphonate units in a mostly bidentate configuration.

However, in all cases, the surface coverage does not exceed about 30% of the full monolayer. The results obtained in this study for ImPE and ImTMSP could result from a possible sterically-hindered effect on the $\gamma\text{-Al}_2\text{O}_3$ surface (due to both the alkyl chain and the imidazolium ring) and to the low reactivity of the coupling function. Furthermore, the results obtained with ImTMSP suggest that additional grafting parameters have still to be tested (i.e., grafting duration, concentration, temperature, etc.) in order to optimize the reaction conditions and maximize the $\gamma\text{-Al}_2\text{O}_3$ surface coverage.

This work allowed establishing the optimized synthesis and characterization protocols for the development of imidazolium phosphonate-grafted $\gamma\text{-Al}_2\text{O}_3$ hybrid materials with controlled bonding modes and grafting rates. As a perspective on this fundamental work, the preparation and testing of the corresponding gas separation hybrid membranes will now be investigated.

Supplementary Materials: The synthesis procedures and characterizations of $\gamma\text{-Al}_2\text{O}_3$ powder, the bulk 1-methyl-3-(3-(diethylphosphinyl)propyl)-imidazolium (ImPE), 1-methyl-3-(3-((trimethoxysilyl)phosphinyl)propyl)-imidazolium bromide (ImTMSP), as well as the details on XRD analysis, the synthesis procedure of the physisorbed sample, FTIR and DFT spectra of the ionic liquids, including DFT detailed calculations. The following are available online at Supplementary materials can be found at <http://www.mdpi.com/1422-0067/17/8/1212/s1>.

Acknowledgments: Philippe Gaveau (Ingénieur de Recherche CNRS) and Bertrand Ribière (Assistant ingénieur CNRS) from the Institute Charles Gerhardt in Montpellier are sincerely acknowledged for their useful technical contributions in respectively solid state NMR and EDX analysis.

Author Contributions: Gilles Guerrero and Anne Julbe were the idea source and writers of the manuscript. Marie-Alix Pizzoccaro is the co-writer and responsible for the synthesis and characterizations. Eddy Petit contributed to FTIR spectra attributions and the DFT calculus. Martin Drobek and Peter Hesemann contributed to this article by bringing their scientific expertise, on respectively inorganic (synthesis and characterizations of the $\gamma\text{-Al}_2\text{O}_3$) and organic chemistry (synthesis of ionic liquids).

Conflicts of Interest: The authors declare no conflict of interest.

References

1. Dai, Z.; Noble, R.D.; Gin, D.L.; Zhang, X.; Deng, L. Combination of Ionic Liquids with Membrane Technology: A New Approach for CO_2 Separation. *J. Membr. Sci.* **2016**, *497*, 1–20. [CrossRef]

2. Nair, J.R.; Porcarelli, L.; Bella, F.; Gerbaldi, C. Newly Elaborated Multipurpose Polymer Electrolyte Encompassing RTILs for Smart Energy-Efficient Devices. *ACS Appl. Mater. Interfaces* **2015**, *7*, 12961–12971. [[CrossRef](#)] [[PubMed](#)]
3. Park, H.; Choi, Y.S.; Kim, Y.; Hong, W.H.; Song, H. 1D and 3D Ionic Liquid–Aluminum Hydroxide Hybrids Prepared via an Ionothermal Process. *Adv. Funct. Mater.* **2007**, *17*, 2411–2418. [[CrossRef](#)]
4. Porcarelli, L.; Gerbaldi, C.; Bella, F.; Nair, J.R. Super Soft All-Ethylene Oxide Polymer Electrolyte for Safe All-Solid Lithium Batteries. *Sci. Rep.* **2016**, *6*, 19892. [[CrossRef](#)] [[PubMed](#)]
5. Zehbe, K.; Kolloosche, M.; Lardong, S.; Kelling, A.; Schilde, U.; Taubert, A. Ionogels Based on Poly(methyl methacrylate) and Metal-Containing Ionic Liquids: Correlation between Structure and Mechanical and Electrical Properties. *Int. J. Mol. Sci.* **2016**, *17*, 391. [[CrossRef](#)] [[PubMed](#)]
6. Scovazzo, P.; Kieft, J.; Finan, D.A.; Koval, C.; Dubois, D.; Noble, R. Gas separations using non-hexafluorophosphate [PF₆][−] anion supported ionic liquid membranes. *J. Membr. Sci.* **2004**, *238*, 57–63. [[CrossRef](#)]
7. Albo, J.; Yoshioka, T.; Tsuru, T. Porous Al₂O₃/TiO₂ tubes in combination with 1-ethyl-3-methylimidazolium acetate ionic liquid for CO₂/N₂ separation. *Sep. Purif. Technol.* **2014**, *122*, 440–448. [[CrossRef](#)]
8. Mehnert, C.P. Supported ionic liquid catalysis. *Chem. Eur. J.* **2004**, *11*, 50–56. [[CrossRef](#)] [[PubMed](#)]
9. Van Doorslaer, C.; Wahlen, J.; Mertens, P.; Binnemans, K.; de Vos, D. Immobilization of molecular catalysts in supported ionic liquid phases. *Dalton Trans.* **2010**, *39*, 8377–8390. [[CrossRef](#)] [[PubMed](#)]
10. Qiu, H.; Takafuji, M.; Liu, X.; Jiang, S.; Ihara, H. Investigation of π – π and ion-dipole interactions on 1-allyl-3-butylimidazolium ionic liquid-modified silica stationary phase in reversed-phase liquid chromatography. *J. Chromatogr. A* **2010**, *1217*, 5190–5196. [[CrossRef](#)] [[PubMed](#)]
11. Pino, V.; Afonso, A.M. Surface-bonded ionic liquid stationary phases in high-performance liquid chromatography—A review. *Anal. Chim. Acta* **2012**, *714*, 20–37. [[CrossRef](#)] [[PubMed](#)]
12. Wang, Y.; Tian, M.; Bi, W.; Row, K.H. Application of Ionic Liquids in High Performance Reversed-Phase Chromatography. *Int. J. Mol. Sci.* **2009**, *10*, 2591–2610. [[CrossRef](#)] [[PubMed](#)]
13. Perdikaki, A.V.; Vangeli, O.C.; Karanikolos, G.N.; Stefanopoulos, K.L.; Beltsios, K.G.; Alexandridis, P.; Kanellopoulos, N.K.; Romanos, G.E. Ionic Liquid-Modified Porous Materials for Gas Separation and Heterogeneous Catalysis. *J. Phys. Chem. C* **2012**, *116*, 16398–16411. [[CrossRef](#)]
14. Vangeli, O.C.; Romanos, G.E.; Beltsios, K.G.; Fokas, D.; Kouvelos, E.P.; Stefanopoulos, K.L.; Kanellopoulos, N.K. Grafting of imidazolium based ionic liquid on the pore surface of nanoporous materials—Study of physicochemical and thermodynamic properties. *J. Phys. Chem. B* **2010**, *114*, 6480–6491. [[CrossRef](#)] [[PubMed](#)]
15. Fehrmann, R.; Haumann, M.; Riisager, A. Introduction. In *Supported Ionic Liquids: Fundamentals and Applications*, 1st ed.; Fehrmann, R., Riisager, A., Haumann, M., Eds.; Wiley-VCH Verlag GmbH & Co. KGaA: Weinheim, Germany, 2014; pp. 1–9.
16. Gadenne, B.; Hesemann, P.; Moreau, J.J.E. Supported ionic liquids: Ordered mesoporous silicas containing covalently linked ionic species. *Chem. Commun.* **2004**, 1768–1769. [[CrossRef](#)] [[PubMed](#)]
17. Motos-Pérez, B.; Roeser, J.; Thomas, A.; Hesemann, P. Imidazolium functionalized SBA-15 type silica: Efficient organocatalysts for Henry and cycloaddition reactions. *Appl. Organomet. Chem.* **2013**, *27*, 290–299. [[CrossRef](#)]
18. Nguyen, T.P.; Hesemann, P.; Moreau, J.J.E. I-Silica: Nanostructured silica hybrid materials containing imidazolium groups by hydrolysis-polycondensation of disilylated bis-*N,N'*-alkyl-imidazolium halides. *Microporous Mesoporous Mater.* **2011**, *142*, 292–300. [[CrossRef](#)]
19. Zhang, Q.; Luo, J.; Wei, Y. A silica gel supported dual acidic ionic liquid: An efficient and recyclable heterogeneous catalyst for the one-pot synthesis of amidoalkyl naphthols. *Green Chem.* **2010**, *12*, 2246–2254. [[CrossRef](#)]
20. Kotadia, D.A.; Soni, S.S. Silica gel supported-SO₃H functionalized benzimidazolium based ionic liquid as a mild and effective catalyst for rapid synthesis of 1-amidoalkyl naphthols. *J. Mol. Catal. A Chem.* **2012**, *353–354*, 44–49. [[CrossRef](#)]
21. Zhu, J.M.; Xin, F.; Sun, Y.C.; Dong, X.C. Phosphonium-based ionic liquids grafted onto silica for CO₂ sorption. *Theor. Found. Chem. Eng.* **2014**, *48*, 787–792. [[CrossRef](#)]
22. Julbe, A.; Farrusseng, D.; Guizard, C. Porous ceramic membranes for catalytic and reactors and overview and new ideas. *J. Membr. Sci.* **2001**, *181*, 3–20. [[CrossRef](#)]
23. Xin, B.; Hao, J. Imidazolium-based ionic liquids grafted on solid surfaces. *Chem. Soc. Rev.* **2014**, *43*, 7171–7187. [[CrossRef](#)] [[PubMed](#)]

24. Alami-Younssi, S.; Kiefer, C.; Larbot, A.; Persin, M.; Sarrazin, J. Grafting γ -alumina microporous membranes by organosilanes: Characterisation by pervaporation. *J. Membr. Sci.* **1998**, *143*, 27–36. [[CrossRef](#)]
25. Leger, C.; De Lira, H.L.; Paterson, R. Preparation and properties of surface modified ceramic membranes. Part III. Gas permeation of 5 nm alumina membranes modified by trichloro-octadecylsilane. *J. Membr. Sci.* **1996**, *120*, 187–195. [[CrossRef](#)]
26. Randon, J.; Blanc, P.; Paterson, R. Modification of ceramic membrane surfaces using phosphoric acid and alkyl phosphonic acids and its effects on ultrafiltration of BSA protein. *J. Membr. Sci.* **1995**, *98*, 119–129. [[CrossRef](#)]
27. Caro, J.; Noack, M.; Kölsch, P. Chemically modified ceramic membranes. *Microporous Mesoporous Mater.* **1998**, *22*, 321–332. [[CrossRef](#)]
28. Guerrero, G.; Mutin, P.H.; Vioux, A. Organically modified aluminas by grafting and sol-gel processes involving phosphonate derivatives. *J. Mater. Chem.* **2001**, *11*, 3161–3165. [[CrossRef](#)]
29. Guerrero, G.; Mutin, P.H.; Vioux, A. Anchoring of Phosphonate and Phosphinate Coupling Molecules on Titania Particles. *Chem. Mater.* **2001**, *13*, 4367–4373. [[CrossRef](#)]
30. Mutin, P.H.; Guerrero, G.; Almaric, J. Preparation of An Inorganic Substrate Having Antimicrobial Properties. Patent No. US 8586758 B2, 19 November 2013. CNRS (FR); Université Montpellier II (FR).
31. Mu, Z.; Zhou, F.; Zhang, S.; Liang, Y.; Liu, W. Preparation and Characterization of New Phosphonyl-Substituted Imidazolium ionic Liquids. *Helv. Chim. Acta* **2004**, *87*, 2549–2555. [[CrossRef](#)]
32. McKenna, C.; Schmidhauser, J. Functional Selectivity in Phosphonate Ester Dealkylation with Bromotrimethylsilane. *J. Chem. Soc. Chem. Commun.* **1979**, *17*, 739. [[CrossRef](#)]
33. Leenaars, A.F.M.; Keizer, K.; Bruggraaf, A.J. The reparation and characterization of alumina membrane with ultra-fine pores. *J. Mater. Sci.* **1984**, *19*, 1077–1088. [[CrossRef](#)]
34. Guerrero, G.; Alauzun, J.G.; Granier, M.; Laurencin, D.; Mutin, P.H. Phosphonate coupling molecules for the control of surface/interface properties and the synthesis of nanomaterials. *Dalton Trans.* **2013**, *42*, 12569–12585. [[CrossRef](#)] [[PubMed](#)]
35. Mutin, P.H.; Guerrero, G.; Vioux, A. Hybrid material from organophosphorus Coupling Molecules. *J. Mater. Chem.* **2005**, *15*, 3761–3768. [[CrossRef](#)]
36. Galarnau, A.; Abid, Z.; Said, B.; Didi, Y.; Szymanska, K.; Jarzȳbski, A.; Tancret, F.; Hamaizi, H.; Bengueddach, A.; Di Renzo, F.; et al. Synthesis and Textural Characterization of Mesoporous and Meso-/Macroporous Silica Monoliths Obtained by Spinodal Decomposition. *Inorganics* **2016**, *4*, 9. [[CrossRef](#)]
37. Thissen, P.; Vega, A.; Peixoto, T.; Chabal, J.Y. Environment-Controlled Tethering by Aggregation and Growth of Phosphonic Acid Monolayers on Silicon Oxide. *Langmuir* **2012**, *28*, 8046–8051.
38. Quiñones, R.; mariea, S.; Gawalt, E. Study of the Formation of Self-Assembled Monolayers on Nitinol. *Langmuir* **2007**, *23*, 10123–10130. [[CrossRef](#)] [[PubMed](#)]
39. Brodard-Severac, F.; Guerrero, G.; Maquet, J.; Florian, P.; Gervais, C.; Mutin, P.H. High-Field ^{17}O MAS NMR Investigation of Phosphonic Acid Monolayers on Titania. *Chem. Mater.* **2008**, *20*, 5191–5196. [[CrossRef](#)]
40. Taoufik, M.; Szeto, K.C.; Merle, N.; Del Rosal, I.; Maron, L.; Trébosc, J.; Tricot, G.; Gauvin, R.M.; Delevoye, L. Heteronuclear NMR spectroscopy as a surface-selective technique: A unique look at the hydroxyl groups of γ -alumina. *Chem. Eur. J.* **2014**, *20*, 4038–4046. [[CrossRef](#)] [[PubMed](#)]
41. Hewitt, D.W.; Newland, G.L. Organophosphorus compounds. P-Arylated perhydro-1,2-azaphosphorines. *Aust. J. Chem.* **1977**, *30*, 579. [[CrossRef](#)]

