



**HAL**  
open science

# First Cold Spraying of Carbonated Biomimetic Nanocrystalline Apatite on Ti6Al4V: Physical-Chemical, Microstructural, and Preliminary Mechanical Characterizations

Emmanuelle Kergourlay, David Grossin, Nuria Cinca, Claudie Josse, Sergi Dosta, Ghislaine Bertrand, Irene Garcia, Jose Maria Guilemany, Christian Rey

## ► To cite this version:

Emmanuelle Kergourlay, David Grossin, Nuria Cinca, Claudie Josse, Sergi Dosta, et al.. First Cold Spraying of Carbonated Biomimetic Nanocrystalline Apatite on Ti6Al4V: Physical-Chemical, Microstructural, and Preliminary Mechanical Characterizations. *Advanced Engineering Materials*, 2015, vol. 18 (n° 4), pp. 496-500. 10.1002/adem.201500409 . hal-01456854

**HAL Id: hal-01456854**

**<https://hal.science/hal-01456854>**

Submitted on 6 Feb 2017

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



## Open Archive Toulouse Archive Ouverte (OATAO)

OATAO is an open access repository that collects the work of Toulouse researchers and makes it freely available over the web where possible.

This is an author-deposited version published in: <http://oatao.univ-toulouse.fr/>  
Eprints ID: 16544

**To link to this article :** DOI:10.1002/adem.201500409

URL : <http://dx.doi.org/10.1002/adem.201500409>

**To cite this version:** Kergourlay, Emmanuelle and Grossin, David and Cinca, Nuria and Josse, Claudie and Dosta, Sergi and Bertrand, Ghislaine and Garcia, Irene and Guilemany, Jose Maria and Rey, Christian *First Cold Spraying of Carbonated Biomimetic Nanocrystalline Apatite on Ti6Al4V: Physical-Chemical, Microstructural, and Preliminary Mechanical Characterizations*. (2015) *Advanced Engineering Materials*, vol. 18 (n° 4). pp. 496-500. ISSN 1438-1656

Any correspondence concerning this service should be sent to the repository administrator:  
[staff-oatao@listes-diff.inp-toulouse.fr](mailto:staff-oatao@listes-diff.inp-toulouse.fr)

# First Cold Spraying of Carbonated Biomimetic Nanocrystalline Apatite on Ti6Al4V: Physical–Chemical, Microstructural, and Preliminary Mechanical Characterizations

By Emmanuelle Kergourlay, David Grossin,\* Nuria Cinca, Claudie Josse, Sergi Dosta, Ghislaine Bertrand, Irene Garcia, Jose Maria Guilemany and Christian Rey

*Carbonated Biomimetic Nanocrystalline Apatite (BNAC) coatings are obtained for the first time by Cold Spray. The coatings are characterized by FTIR, Raman, XRD, and SEM and compared to the powders. No significant chemical and structural changes are detected and the nanostructure features of these very reactive BNAC are preserved in the coating. These results and preliminary mechanical assays show that Cold Spray can produce an operational biomimetic coatings offering a high potential for implants functionalization and osseointegration. However, these first results need further studies in order to understand the mechanism of adhesion and the interactions at the coating–substrate interface.*

Hydroxyapatite  $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$  coatings deposited on metallic implants by atmospheric plasma spray (APS) might now be considered the industrial standard.<sup>[1]</sup> These calcium phosphate coatings, which mimic bone mineral, have been found to enhance short and long-term osteointegration.<sup>[2]</sup>

However, two major criticisms with this type of coating need to be addressed:

Plasma spray is a process by which powder is melted and quenched in a few milliseconds. Such a thermal

treatment results in an unavoidable degree of material degradation during processing (deshydroxylation, amorphization, etc),<sup>[3–5]</sup> limiting the long-term patency of coated implants.<sup>[6]</sup> Amorphization at the interface between metal and coating may lead to high rates of dissolution in body fluids at the point of interface, inducing a loss of coating adhesion.

Hydroxyapatite has a chemical composition and crystal characteristics very different from those of bone apatites.<sup>[7]</sup>

Natural bone mineral is a calcium phosphate nanocrystalline apatite which exhibits:<sup>[8]</sup> i) ionic vacancies in calcium and hydroxide crystal sites;<sup>[9]</sup> ii) substitution of calcium ions by a series of elements (present as minor elements like magnesium, or trace elements like strontium, etc.); and most importantly, iii) the replacement of  $\text{PO}_4^{3-}$  by divalent ions,<sup>[10]</sup> such as hydrogenophosphate  $\text{HPO}_4^{2-}$  or carbonate  $\text{CO}_3^{2-}$  ions.<sup>[11–12]</sup> It is estimated that almost a third of all  $\text{PO}_4^{3-}$  ions are replaced by  $\text{HPO}_4^{2-}$  and  $\text{CO}_3^{2-}$  bivalent species. Natural bone mineral is also characterized by platelet-shaped nanosized apatite crystals exhibiting a hydrated surface layer containing bivalent labile ions, offering a basis for functionalization with bioactive mineral ions or active molecules.<sup>[13,14]</sup> Synthesis and processing of biomimetic apatites for bone replacement have been the subject of numerous research activities due to their potent biological properties.<sup>[7]</sup> It is noteworthy that their physico-chemical features are highly dependent on the synthesis protocol and processing conditions.<sup>[15]</sup> Temperature is critical parameter in the processing of biomimetic

[\*] Dr. D. Grossin, Eng. E. Kergourlay, Dr. C. Josse, Prof. G. Bertrand, Prof. C. Rey

Université de Toulouse, CIRIMAT, UMR 5085 INPT-CNRS-UPS, ENSIACET, 4 allée Emile Monso 31030 Toulouse, France  
E-mail: david.grossin@ensiacet.fr

Dr. C. Josse

Centre de Microcaractérisation Raimond Castaing, UMS 3623, Espace Clément Ader, 3 rue Caroline Aigle, 31000 Toulouse, France

Dr. N. Cinca, Dr. S. Dosta, Dr. I. Garcia, Prof. J. M. Guilemany  
Thermal Spray Centre (CPT), Universitat de Barcelona, Martí i Franquès, 1, 08028 Barcelona, Spain

nanocrystalline apatites. Soft processing conditions are required to preserve the hydrated layer the nanocrystalline dimensions, and prevent decomposition.<sup>[10,13,16]</sup> Several processes, using mostly wet-chemical techniques, have been described, such as dip coating, electrodeposition, electrophoretic deposition, and immersion in supersaturated solutions.<sup>[17]</sup> Additionally, physical deposition techniques, such as MAPLE,<sup>[18]</sup> have also been explored.

The above-cited contributions report promising results concerning the use of bone-like apatites in the field of biomaterials and have opened the way for a number of possibility in the coating industry. However, such coatings currently lack the mechanical properties required for biomedical applications.<sup>[1,19–20]</sup> These poor mechanical properties have led to the application of additional thermal treatments which can effectively increase adhesion strength, but may result in a loss of biological activity of the deposited materials.<sup>[21,22]</sup>

In this study, an industrial and relatively low-temperature thermal process, cold spraying (CS),<sup>[23]</sup> was investigated to obtain a coating of carbonated biomimetic nanocrystalline apatite BNAC on Ti6Al4V samples. Using this process, the particles are not melted, consequently, most of the initial characteristics of the particles, such as their chemical composition or the crystal size and habit,<sup>[24]</sup> are expected to be maintained.

Until now, the only published reports concerning the deposition of calcium phosphate apatites by CS involved stoichiometric HA or HA mixed with other compound onto metallic substrates or non-metallic substrates<sup>[25–31]</sup> Other reports have also been published on process modifications (e.g., substrate heating, ultrasonic powder feeding systems, etc.), and at least one modelling study of HA CS.<sup>[32–35]</sup> However, to the best of our knowledge, no reports of biomimetic nanocrystalline apatites cold sprayed onto Ti6Al4V, Co–Cr alloys, or stainless steel 316L have been published for use in medical applications. The present contribution is focused on the i) physical–chemical characterization of the BNAC coatings obtained via CS; ii) microstructure description; and iii) preliminary mechanical evaluation.

## 1. Results and Discussions

Raw BNAC powder and BNAC cold sprayed coatings are described in the experimental part of this paper. These are reproducible samples obtained after optimization of CS parameters.

X-ray diffraction analysis was conducted on the BNAC powder and on the scraped and ground BNAC coating, and compared to those of bone and stoichiometric HA (Figure 1). These diffraction patterns can be indexed in the apatitic structure (hexagonal, P63/m space group, ICDD PDF card 9-432).<sup>[36]</sup> In addition, no trace of impurity or secondary crystalline phases were detected in the coatings.

The poor crystallinity and/or the nanometric dimensions of the coating and the powder's crystals are evidenced by




Fig. 1. XRD pattern of BNAC coating obtained by cold spray, BNAC powder, human bone,<sup>[54]</sup> and stoichiometric HA.

the width of the diffraction peaks in Figure 1. A similar observation was made in regard to the SPS processing of BNA in previous studies.<sup>[37]</sup> This is a specific feature of biological apatites found in bone (Figure 1).<sup>[13]</sup>

Profile fitting analysis allowed for the estimation of the unit cell parameters and crystallite size of the BNAC powder and coating (Table 1). Powder and coating cell parameters almost identical; for the “a” dimension, the difference corresponds to the standard deviation, and for the “c” dimension, the difference is about 0.1%. According to the literature, the widths of the peaks depends on the crystallographic orientation,<sup>[38]</sup> which alludes to the anisotropy of grain size (peaks (002) (004) appear narrower than (hk0) peaks). After CS, a small increase in crystallite size was noted, although the overall nanometer dimensions of the crystals were preserved.

The FTIR spectrum of the powder (Figure 2) shows the characteristic absorption bands of carbonated non-stoichiometric nanocrystalline apatite with:<sup>[36]</sup> i) rather poorly resolved phosphate bands at  $472\text{ cm}^{-1}$  ( $\nu_2\text{ PO}_4^{3-}$ ),  $563\text{--}603\text{ cm}^{-1}$  ( $\nu_4\text{ PO}_4^{3-}$ ),  $961\text{ cm}^{-1}$  ( $\nu_1\text{ PO}_4^{3-}$ ),  $1030$  and  $1081\text{ cm}^{-1}$  ( $\nu_3\text{ PO}_4^{3-}$ ),  $873$ ,  $1140\text{--}1150$ ,  $1250\text{ cm}^{-1}$

Table 1. XRD results after pattern matching analysis.

XRD	Powder <sup>a)</sup>	Coating <sup>a)</sup>
a [Å]	9.449(2)	9.4496(13)
c [Å]	6.8951(17)	6.8883(10)
V[Å <sup>3</sup> ]	533.2(2)	532.68(13)
Rp [%]	2.18	2.47
Rwp [%]	2.83	3.19
GOF	1.06	1.11
FWHM(002)	0.5981	0.4973
FWHM(310)	2.5860	1.4586
L(002) nm <sup>b)</sup>	14(2)	17(2)
L(310) nm <sup>b)</sup>	3.4(3)	6.0(3)

<sup>a)</sup> see experimental part; <sup>b)</sup> using Scherrer approximation<sup>[58]</sup>



hydrated layer was preserved, thereby allowing for greater biological activity as compared to plasma sprayed hydroxyapatite coatings. On top of its ability to maintain the physical-chemical and microstructural characteristics of thermal sensitive apatite, CS permits the production of coatings with sufficient adhesion to be applied to medical implants.

### 3. Experimental Section

#### 3.1. Synthesis of BNAC Powder

A synthesis<sup>[36]</sup> of carbonated biomimetic nanocrystalline apatite (BNAC) was obtained by precipitation in aqueous medium at close-to-physiological pH and room temperature. Precipitation involved separate sources for calcium ions, and phosphate and carbonate ions. The each solution was prepared in advance of precipitation. The calcium solution (solution A, typically 1500 ml) was prepared by dissolving calcium nitrate  $\text{Ca}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$  (Merck Emsure grade, purity  $\geq 99.0\%$ ) in deionized water up to a concentration of 0.3 M. A solution containing phosphate and carbonate (solution B, typically 3000 ml) was prepared by dissolving di-ammonium hydrogenphosphate  $(\text{NH}_4)_2\text{HPO}_4$  (VWR Normapur grade, purity  $\geq 99.0\%$ ) and sodium hydrogencarbonate  $\text{NaHCO}_3$  (Carlo Erba analytical grade, purity  $\geq 99.0\%$ ) up to the respective concentrations of 0.45 and 0.71 M. Solution A was rapidly poured into stirred solution B, then left to mature in the precipitating medium for 1 day (ageing in solution) at room temperature (20–25 °C). During this synthesis, the reaction medium was buffered at a pH value close to physiological pH (pH  $\approx 7.2$ ) by the presence of excess phosphate and carbonate ions. The precipitating medium was then separated into four equal parts, filtered through Büchner funnels, thoroughly washed with deionized water (4 L per funnel), and freeze-dried for 3 days (freeze-dryer set between –60 and –80 °C, residual pressure 10–12 mbar). Unless otherwise stated, the freeze-dried precipitate powder was then collected and stored in a freezer at –18 °C prior to physico-chemical analysis.

#### 3.2. Titanium Alloy Substrate Preparation

Commercial Ti6Al4V ELI (Harald Pihl, Sweden) disks (25 mm  $\times$  2 mm) were used as substrates for this study. The samples were subjected to different surface treatments before deposition: i) degreasing by immersion in acetone followed by rinsing with demineralized water; ii) pickling in a commercial solution (DBP Mayet, France) composed of a mixture of fluorhydric acid ( $0 < \text{wt}\% < 1$ ) and nitric acid ( $2.5 < \text{wt}\% < 10$ ) for 2 min followed by rinsing under tap water then demineralized water; and iii) passivation in a nitric acid solution (46 wt %) for 30 min followed by rinsing in tap water then demineralized water. The three aqueous treatments were prepared at room temperature, without stirring, and the samples were air-dried between treatments. To finish, samples were sandblasted using the CS process with alumina particles before deposition with BNAC.

#### 3.3. Cold Spray Process

The deposition of BNAC was performed at the Thermal Spray Centre (Barcelona, Spain) using a LPCS “low pressure cold spray” system, Dymet 423, equipped with a de Laval nozzle (converging-diverging nozzle). The BNAC powder was injected via a vibrated powder feeder into pure heated air used as accelerating and carrier gas. The gas pressure was set between 0.5 and 0.9 MPa and the temperature was varied from RT to 500 °C. The spray distance and the traversing speed were fixed to produce homogeneous coatings with thickness ranging from 10 to 60  $\mu\text{m}$ .

#### 3.4. X-Ray Diffraction

X-ray diffraction analysis was performed on the coatings using a Bruker D8-2 diffractometer (Cu,  $\text{K}\alpha_1$ , and  $\text{K}\alpha_2$  radiation). The nature and crystallographic features of the crystalline phases were evaluated according to international standards (ISO 13779-3:08). The counting time was 3 s for every 0.02° step, typically in the range  $2\theta$  [20–80°]. JANA2006 software allowed for the evaluation of unit cell parameters and volume using Pseudo-Voigt profile function and anisotropic particle broadening.<sup>[50]</sup> The full-width at half-maximum (FWHM) was extracted after profile fitting. The Scherrer approximation was used to estimate coherence length and to extrapolate crystallite size.<sup>[51–53]</sup> The XRD of human mineral bone comes from the work of Grunenwald et al. (femur, male, 57 years old).<sup>[54]</sup>

#### 3.5. Spectroscopic Analysis

Fourier Transform Infrared (FTIR) spectra of the removed and ground coatings were obtained using a Nicolet 5700 spectrometer in the 400–4000  $\text{cm}^{-1}$  range (64 scans, resolution 4  $\text{cm}^{-1}$ ). Spectral decomposition was performed after subtracting a linear baseline in the 400–800  $\text{cm}^{-1}$  wavenumber range corresponding to the  $\nu_2$ ,  $\nu_4$  ( $\text{PO}_4$ ) and  $\nu$  (OH) vibration modes of phosphate and hydroxide ions using ORIGIN (version 8.6) software.<sup>[40]</sup> The FTIR spectra of bone come from the work of Bohic et al.<sup>[55]</sup>

#### 3.6. SEM

The coatings microstructure was characterized by SEM FEG (Jeol JSM-7100F TTLS LV) at the Centre of Microcharacterization Raimond Castaing (Toulouse, France).

#### 3.7. Mechanical Evaluation by Scratch Test

The scratch test was conducted to evaluate coating adhesion.<sup>[45,46,56,57]</sup> The deposited specimen (thickness  $60 \pm 10 \mu\text{m}$ ) was scratched using “Revetest” (CSM Instrument) with a diamond Rockwell indenter of 200  $\mu\text{m}$  in diameter and a pre-load of 1 N, load speed 15 N  $\text{min}^{-1}$ , scratch speed 1.5 mm  $\text{min}^{-1}$ , and a maximum load of 50 N.

- [1] L. M. Sun, C. C. Berndt, K. A. Gross, A. Kucuk, *J. Biomed. Mater. Res.* **2001**, *58*, 570.
- [2] K. Degroot, R. Geesink, C. Klein, P. Serekian, *J. Biomed. Mater. Res.* **1987**, *21*, 1375.
- [3] R. B. Heimann, *Surf. Coat. Technol.* **2006**, *201*, 2012.
- [4] M. T. Carayon, J. L. Lacout, *J. Solid State Chem.* **2003**, *172*, 339.
- [5] R. B. Heimann, R. Wirth, *Biomaterials* **2006**, *27*, 823.
- [6] I. Demnati, D. Grossin, C. Combes, C. Rey, *J. Med. Biol. Eng.* **2014**, *34*, 1.
- [7] C. Combes, C. Rey, *Actual. Chim.* **2003**, 16.
- [8] C. Rey, C. Combes, C. Drouet, M. J. Glimcher, *Osteoporos. Int.* **2009**, *20*, 1013.
- [9] C. Rey, J. L. Miquel, L. Facchini, A. P. Legrand, M. J. Glimcher, *Bone* **1995**, *16*, 583.
- [10] S. Cazalbou, C. Combes, D. Eichert, C. Rey, *J. Mater. Chem.* **2004**, *14*, 2148.

- [11] L. T. Kuhn, M. D. Grynblas, C. C. Rey, Y. Wu, J. L. Ackerman, M. J. Glimcher, *Calcif. Tissue Int.* **2008**, *83*, 146.
- [12] C. Rey, B. Collins, T. Goehl, I. R. Dickson, M. J. Glimcher, *Calcif. Tissue Int.* **1989**, *45*, 157.
- [13] H. M. Kim, C. Rey, M. J. Glimcher, *Calcif. Tissue Int.* **1996**, *59*, 58.
- [14] C. Rey, E. Strawich, M. J. Glimcher, *Bull. Inst. Oceanogr. Monaco* **1994**, 55.
- [15] C. Drouet, *BioMed Res. Int.* **2013**, *2013*, 490946.
- [16] C. Rey, C. Combes, *BoneKEy Rep.* **2014**, *3*, 586.
- [17] P. Habibovic, F. Barrère, C. A. Van Blitterswijk, K. de Groot, P. Layrolle, *J. Am. Ceram. Soc.* **2002**, *85*, 517.
- [18] A. Visan, D. Grossin, N. Stefan, L. Duta, F. M. Miroiu, G. E. Stan, M. Sopronyi, C. Luculescu, M. Freche, O. Marsan, C. Charvillat, S. Ciuca, I. N. Mihailescu, *Mater. Sci. Eng. B Adv. Funct. Solid State Mater.* **2014**, *181*, 56.
- [19] E. Mohseni, E. Zalnezhad, A. R. Bushroa, *Int. J. Adhes. Adhes.* **2014**, *48*, 238.
- [20] ISO 13779-4:2002(E), **2002**.
- [21] F. Dabbarh, A. Lebugle, A. Taitai, M. Bennani, *Ann. Chim. Sci. Mater.* **2000**, *25*, 339.
- [22] M. Bennani, A. Lebugle, G. Bonel, *Ann. Chim. Sci. Mater.* **1993**, *18*, 245.
- [23] A. Papyrin, *Adv. Mater. Process.* **2001**, *159*, 49.
- [24] F. Gartner, T. Stoltenhoff, T. Schmidt, H. Kreye, *J. Therm. Spray Technol.* **2006**, *15*, 223.
- [25] X. Zhou, P. Mohanty, *Electrochim. Acta* **2012**, *65*, 134.
- [26] Y. Liu, J. Huang, H. Li, *J. Therm. Spray Technol.* **2014**, *23*, 1149.
- [27] Y. Liu, Z. Dang, Y. Wang, J. Huang, H. Li, *Carbon* **2014**, *67*, 250.
- [28] N. Sanpo, M. L. Tan, P. Cheang, K. A. Khor, *J. Therm. Spray Technol.* **2008**, *18*, 10.
- [29] M. Gardon, A. Concustell, S. Dosta, N. Cinca, I. G. Cano, J. M. Guilemany, *Mater. Sci. Eng. C* **2014**, *45*, 117.
- [30] A. C. W. Noorakma, H. Zuhailawati, V. Aishvarya, B. K. Dhindaw, *J. Mater. Eng. Perform.* **2013**, *22*, 2997.
- [31] J. H. Lee, H. L. Jang, K. M. Lee, H.-R. Baek, K. Jin, K. S. Hong, J. H. Noh, H.-K. Lee, *Acta Biomater.* **2013**, *9*, 6177.
- [32] L. Zhang, W. Zhang, Z. Wu, *Appl. Mech. Mater.* **2012**, *130*, 900.
- [33] L. Zhang, W. Zhang, H. Li, W. Geng, Y. Bao, *Appl. Mech. Mater.* **2012**, *151*, 300.
- [34] L. Zhang, W. T. Zhang, *Adv. Mater. Red.* **2011**, *188*, 717.
- [35] R. P. Singh, U. Batra, *J. Appl. Fluid Mech.* **2013**, *6*, 555.
- [36] S. Cazalbou, C. Combes, D. Eichert, C. Rey, M. J. Glimcher, *J. Bone Miner. Metab.* **2004**, *22*, 310.
- [37] D. Grossin, S. Rollin-Martinet, C. Estournes, F. Rossignol, E. Champion, C. Combes, C. Rey, C. Geoffroy, C. Drouet, *Acta Biomater.* **2010**, *6*, 577.
- [38] D. Grossin, M. Banu, S. Sarda, S. Martinet-Rollin, C. Drouet, C. Estournes, E. Champion, F. Rossignol, C. Combes, C. Rey, in *Adv. Bioceram. Porous Ceram. II* (Eds: R. Narayan, P. Colombo), John Wiley & Sons, Inc., Hoboken, USA **2010**, 113.
- [39] D. Eichert, C. Combes, C. Drouet, C. Rey, in *Bioceram. Vol 17* (Eds: P. Li, K. Zhang, C.W. Colwell), Trans Tech Publications, Uetikon-Zuerich, Switzerland **2004**, 3
- [40] C. Rey, C. Combes, C. Drouet, H. Sfihi, A. Barroug, *Mater. Sci. Eng. C Biomim. Supramol. Syst.* **2007**, *27*, 198.
- [41] A. Grunenwald, C. Keyser, A. M. Sautereau, E. Crubézy, B. Ludes, C. Drouet, *J. Archaeol. Sci.* **2014**, *49*, 134.
- [42] D. Eichert, H. Sfihi, C. Combes, C. Rey, in *Bioceram. Vol 16* (Eds: M.A. Barbosa, F.J. Monteiro, R. Correia, B. Leon), Trans Tech Publications, Uetikon-Zuerich, Switzerland **2004**, 927.
- [43] D. Eichert, C. Drouet, H. Sfihi, C. Rey, C. Combes, in *Trends Biomater. Res.* (Ed: P. Pannone), Nova Science Publishers, Inc., New York, USA **2007**, 93.
- [44] B. Ben-Nissan, B. A. Latella, A. Bendavid, in *Compr. Biomater.* (Ed: P. Ducheyne), Elsevier, Oxford **2011**, 63.
- [45] A. Behnamghader, D. Najjar, A. Iost, S. Benayoun, in *Thermec 2009 Pts 1-4* (Eds: T. Chandra, N. Wanderka, W. Reimers, M. Ionescu), Trans Tech Publications Ltd, Stafa- Zurich **2010**, 641.
- [46] A. J. Perry, *Thin Solid Films* **1981**, *78*, 77.
- [47] I. Demnati, M. Parco, D. Grossin, I. Fagoaga, C. Drouet, G. Barykin, C. Combes, I. Braceras, S. Goncalves, C. Rey, *Surf. Coat. Technol.* **2012**, *206*, 2346.
- [48] I. Demnati, D. Grossin, C. Combes, M. Parco, I. Braceras, C. Rey, *Biomed. Mater.* **2012**, *7*, 054101.
- [49] I. Demnati, D. Grossin, O. Marsan, G. Bertrand, G. Collonges, C. Combes, M. Parco, I. Braceras, J. Alexis, Y. Balcaen, C. Rey, *Open Biomed. Eng. J.* **2015**, *9*, 26.
- [50] V. Petricek, M. Dusek, L. Palatinus, *Z. Krist.* **2014**, *229*, 345.
- [51] P. Scherrer, *Nachrichten Von Ges. Wiss. Zu Gött. Math.-Phys. Kl.* **1918**, *1918*, 98.
- [52] A. L. Patterson, *Phys. Rev.* **1939**, *56*, 978.
- [53] J. I. Langford, A. J. C. Wilson, *J. Appl. Crystallogr.* **1978**, *11*, 102.
- [54] A. Grunenwald, C. Keyser, A. M. Sautereau, E. Crubezy, B. Ludes, C. Drouet, *Anal. Bioanal. Chem.* **2014**, *406*, 4691.
- [55] S. Bohic, C. Rey, A. Legrand, H. Sfihi, R. Rohanizadeh, C. Martel, A. Barbier, G. Daculsi, *Bone* **2000**, *26*, 341.
- [56] M. C. Kuo, S. K. Yen, *Mater. Sci. Eng. C* **2002**, *20*, 153.
- [57] K. Cheng, C. Ren, W. Weng, P. Du, G. Shen, G. Han, S. Zhang, *Thin Solid Films* **2009**, *517*, 5361.
- [58] J. I. Langford, A. J. C. Wilson, *J. Appl. Crystallogr.* **1978**, *11*, 102.