



HAL
open science

Electronic properties of hybrid organic and inorganic perovskites

Boubacar Traore, Laurent Pedesseau, Mikael Kepenekian, Jacky Even,
Claudine Katan

► **To cite this version:**

Boubacar Traore, Laurent Pedesseau, Mikael Kepenekian, Jacky Even, Claudine Katan. Electronic properties of hybrid organic and inorganic perovskites. New-comer Oriented School to Ab Initio Nanoscience Simulations (ABINIT SCHOOL 2017), Jan 2017, Bruyères le Châtel, France. . hal-01460705


HAL Id: hal-01460705

<https://hal.science/hal-01460705>

Submitted on 7 Feb 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



ABINIT school : From January 30th, 2017 to February 3rd, 2017

Electronic properties of hybrid organic and inorganic perovskites

B. Traoré¹, L. Pedesseau², M. Kepenekian¹, J. Even², and C. Katan¹

¹ Institut des Sciences Chimiques de Rennes, CNRS, Université de Rennes 1, Rennes, France

² Fonctions Optiques pour les Technologies de l'Information, CNRS, INSA de Rennes, France

In this poster we, first, present ABINIT based DFT results of the optoelectronic properties of $\text{CH}_3\text{NH}_3\text{PbI}_3$ and $\text{CH}_3\text{NH}_3\text{BCl}_3$ (B=Pb, Sn, Ge) hybrid organic-inorganic perovskites (HOP). For $\text{CH}_3\text{NH}_3\text{MCl}_3$ HOP, the pseudocubic high temperature reference HOP structure (Pm-3m) was used to compare spin-orbit coupling (SOC) induced effect due to the metal atom B.^[1-3]


Next, we present 2D layered HOP which received a renewed interest in recent years due to increased stability under lighting conditions and resistance to humidity and moisture. Their electronic properties show their potential in photovoltaic and optoelectronic applications.^[4]

[1] J. Even, L. Pedesseau, J.-M. Jancu, C. Katan, *J. Phys. Chem. Lett.* 4, 2013

[2] C. Katan, L. Pedesseau, M. Kepenekian, A. Rolland, J. Even, *J. Mat. Chem. A*, 3, 2015


[3] J. Even, L. Pedesseau, J.-M. Jancu, C. Katan, *Phys. Status Solidi RRL*, 8, 2014

[4] J. Even, L. Pedesseau, M.A. Dupertuis, J.-M. Jancu, C. Katan, *PRB*, 86, 2012



3D hybrid organic-inorganic perovskites

Formula : ABX_3




A : MA (CH_3NH_3); FA
($\text{HC}(\text{NH}_2)_2$); Cs; Rb

B : Inorganic cation
Pb; Sn; Ge; etc...

X : halogen (I, Br, Cl)


MAPbI_3 Pnma orthorhombic phase^[1]



✧ Band gap at Γ

✧ Importance of spin-orbit coupling effect

MABX_3 Pm-3m cubic phase^[2,3]



✧ Absorption


✧ Band gap at R

✧ selective SOC :

- larger with heavy B
- larger with heavy X
- consistent with atomic tables


2D layered perovskites^[4]

Formula : A_2BX_4



2D structure:


4F-PEPI
($[\text{pFC}_6\text{H}_5\text{C}_2\text{H}_4\text{NH}_3]_2\text{PbI}_4$)



✧ Band gap at Γ

✧ SOC effect important as in 3D

✧ Flat dispersion along Γ -X \rightarrow stacking axis



✧ Reverse band electronic states as compared to III-V conventional semiconductors

✧ Real ψ $|Y\rangle$ and $|Z\rangle$ without SOC are mixed by SOC into real and CBM components