



**HAL**  
open science

## Facile and green reduction of graphene oxide by a reduced polyoxometalate and formation of a nanohybrid

Catherine Debiemme, Benjamin Thomas, Ivan T. Lucas, Mai Tran Tron Long, Jean-Marc Heintz, Amélie Veillere, Jean-François Silvain

### ► To cite this version:

Catherine Debiemme, Benjamin Thomas, Ivan T. Lucas, Mai Tran Tron Long, Jean-Marc Heintz, et al.. Facile and green reduction of graphene oxide by a reduced polyoxometalate and formation of a nanohybrid. ChemPlusChem, 2017, 82 (2), pp.186-189. 10.1002/cplu.201600484 . hal-01463950

**HAL Id: hal-01463950**

**<https://hal.science/hal-01463950>**

Submitted on 3 Feb 2023

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Facile and green reduction of graphene oxide by a reduced polyoxometalate and nanohybrid formation.

Catherine Debiemme-Chouvy<sup>\*a</sup>, Benjamin Thomas<sup>b</sup>, Ivan T. Lucas<sup>a</sup>, T. T. Mai Tran<sup>a</sup>, Jean-Marc Heintz<sup>b</sup>, Amélie Veillère<sup>b</sup>, and Jean-François Silvain<sup>b</sup>


**Abstract:** In this communication, we report an eco-friendly chemical reduction of graphene oxide (GO) in water. The reducing agent is an electrochemically reduced Keggin-type polyoxometalate ( $\text{SiW}_{12}\text{O}_{40}^{5-}$ ). Moreover this process leads to the fabrication of  $\text{SiW}_{12}@r\text{GO}$  nanocomposite. This nanohybrid exhibits an electrochemical response which combines high faradic and capacitive currents due to high coverage of rGO sheets by the polyoxometalates, therefore it has strong potentiality for energy storage.

Graphene is the first two-dimensional atomic crystal available. Its singular structure induces exceptional properties like high mechanical strength and extremely high electrical and thermal conductivities. The potential applications of graphene are multiple ranging from electronics, flexible screen, catalyst to thermal management. However, the difficulties associated its production are a critical drawback for a mass use. Several methods have been developed using chemical and physical exfoliation of graphite such as: electrochemical exfoliation [1], intercalation of element in graphite compounds at elevated temperature [2] and liquid phase exfoliation using agents like N-methylpyrrolidone, iodine chloride or bromide.[3] Nevertheless, the most common method toward a large scale production of graphene is the moderate oxidation of graphite through the modified Hummers method [4], followed by its exfoliation (graphene oxide, GO) and its reduction to obtain graphene (reduced graphene oxide, rGO).[4-6] The last step involves commonly products like hydrazine hydrate or formaldehyde which are known as hazardous to health and the environment. In order to remove this kind of components, an alternative method based on UV-assisted photoreduction of GO in the presence of polyoxometalates (POMs) and of a sacrificial organic reagent has been proposed.[7] POMs are a class of inorganic metal–oxygen cluster anions with redox properties.[8] These clusters (so-called isopoly- and heteropolyanions (HPAs)) contain highly symmetrical core assemblies of  $\text{MO}_x$  units ( $M = \text{V}, \text{Mo}, \text{W}$ ). They can have various structures containing for example 6, 12 or 18 metal atoms in their high oxidation state. For HPAs, the structure with 12 metal atoms is called Keggin structure. In the method just mentioned the POMs act also as anionic stabilizer avoiding the aggregation of rGO and


leading to the formation of  $\text{POM}@r\text{GO}$  nanocomposites. However, only small amount of rGO could be obtained under such conditions due to localized laser irradiation and also an organic reagent has to be used. It has also been shown that the hydrothermal reduction of GO in the presence of  $\text{H}_3\text{PMo}_{12}\text{O}_{40}$  ( $\text{PMo}_{12}$ ) leads to the nanocomposite  $\text{PMo}_{12}@r\text{GO}$ .<sup>[9]</sup> Another route developed recently concerns the electrochemical reduction of GO assisted by POMs <sup>[10]</sup>.

Herein we propose an environmentally friendly two-step process for the preparation of reduced graphene oxide decorated with POMs ( $\text{POM}@r\text{GO}$ ). In this process the first step is the electroreduction of  $\text{SiW}_{12}\text{O}_{40}^{4-}$  ( $\text{SiW}_{12}$ ), a Keggin-type POM which is dissolved in pure water. In its fully oxidized form, all the W atoms are at the oxidation state +VI while in the reduced form a fraction of the W atoms are at the oxidation state +V (blue HPA). Then the catholyte which contains reduced  $\text{SiW}_{12}$  is added to the GO suspension, GO is reduced by the POMs which are reoxidized and a nanocomposite is formed.

First step, reagent preparation (electrochemical step):



Second step, rGO preparation (electroless step):



Reaction (2) is rapid, being completed after one minute, the solution being stirred by Ar bubbling.

In Figure S1, the optical images of the solutions of GO, GO +  $\text{SiW}_{12}$  and GO + reduced  $\text{SiW}_{12}$  show clearly that GO is reduced in the presence of reduced  $\text{SiW}_{12}$ . Black particles are indeed visible in the GO + reduced  $\text{SiW}_{12}$  solution whereas with oxidized  $\text{SiW}_{12}$  no change is observed as compared to the initial GO suspension.

After washing with pure water and isolation by centrifugation, the final products were characterized by XPS, Raman, TEM, thermogravimetry analysis (TGA) and electrochemistry. In order to confirm the proposed mechanism (reaction (2)), we reproduced all the experiments with the fully oxidized POMs (sample named GO- $\text{SiW}_{12}$ ).


The reduction of GO by partially reduced  $\text{SiW}_{12}$  anions and the nanocomposite formation (reaction (2)) were evaluated using X-ray photoelectron spectroscopy (XPS). The XPS survey spectra depicted in Figure 1A evidence that after addition of  $\text{SiW}_{12}$  or reduced  $\text{SiW}_{12}$  in the GO solution, W is detected (see Table S1) with a much higher intensity for the sample prepared with the reduced  $\text{SiW}_{12}$  *i.e.* for the reduced GO.

To estimate the effectiveness of the reduction process of GO, the C/O ratios of the three samples were determined from C1s and O1s high resolution XPS spectra without taking into account the O atoms associated to  $\text{SiW}_{12}\text{O}_{40}^{4-}$ . GO, GO- $\text{SiW}_{12}$  and  $\text{SiW}_{12}@r\text{GO}$  give ratios of 2.5, 2.7 and 6.1, respectively (see Table S1). Moreover the C1s photopeaks were deconvoluted with five contributions corresponding to five types of carbon with

a Dr. C. Debiemme-Chouvy, Dr. I.T. Lucas, Dr. T.T.M. Tran  
Laboratoire Interfaces et Systèmes Electrochimiques, LISE UMR  
8235, Sorbonne Universités, UPMC Univ Paris 06, CNRS, 4 place  
Jussieu, F-75005 Paris, France.  
E-mail: catherine.debiemme-chouvy@upmc.fr

b B. Thomas, Prof. J.M. Heintz, Dr. A. Veillère, Dr. J.F. Silvain  
Institut de Chimie de la Matière Condensée de Bordeaux, ICMCB-  
CNRS, 87 avenue du Docteur Albert Schweitzer, F-33608 Pessac  
Cedex, France

Supporting information for this article is given via a link at the end of the document.




**Figure 1.** XPS spectra. A: Survey spectra from (a) GO, (b) SiW<sub>12</sub> + GO, (c) reduced SiW<sub>12</sub> + GO samples. B, C and D: C1s spectra from GO, SiW<sub>12</sub> + GO and reduced SiW<sub>12</sub> + GO samples, respectively.

different chemical states, C=C, C-C, C-O, C=O, O-C=O (Figures 1B-D). For each sample, the contributions of the different C bonds to the total C1s XPS signal are reported in Table S2. From this table it is clear that rGO is deeply reduced as the C=C bonds increase from 19% in GO to 70% in the nanocomposite ; the carbon-oxygen contributions being drastically lower for the GO treated with reduced SiW<sub>12</sub> in comparison with the pristine GO or with the sample treated with the fully oxidized SiW<sub>12</sub>. The O1s


spectra depicted in Figure S2 confirm the presence of SiW<sub>12</sub>O<sub>40</sub><sup>4-</sup> with a new contribution that is detected at a lower binding energy (530.5 eV). The W4f<sub>7/2</sub> peak located at 35.6 eV is symmetric (see Figure S3) indicating that all the W atoms are at the same oxidation state, *i.e.* +VI, and confirming that the reduced SiW<sub>12</sub> species are oxidized at the graphene oxide surface (reaction (2)). Besides, the integrity of the POMs is confirmed by the detection of a Si2p contribution around 102 eV (Figure S4) and also by the electrochemical studies (see below).

Figure 2 shows the Raman spectra of GO, GO-SiW<sub>12</sub> and SiW<sub>12</sub>@rGO samples collected with a blue excitation laser ( $\lambda_{exc} = 473$  nm). The most prominent features, D (1350 cm<sup>-1</sup>) and G (1580 cm<sup>-1</sup>) bands, are assigned to disorder-induced breathing modes of sp<sup>2</sup> atoms in carbon rings and to stretching modes from the sp<sup>2</sup> carbon pairs respectively.<sup>[11]</sup> The similarity between the GO-SiW<sub>12</sub> and GO spectra attests that no GO reduction took place during contact of GO solution with SiW<sub>12</sub> in its pristine state (oxidized). SiW<sub>12</sub>@rGO spectrum is however considerably altered with a dominant intensity of the D band over the G band. From the ratio of D and G band intensities, I<sub>D</sub>/I<sub>G</sub>, a measure of the inter-defect distance or the average size of the sp<sup>2</sup> domains can be estimated.<sup>[11, 12]</sup> In a large number of papers relative to chemical reduction of GO, this ratio is observed to increase from 0.8-1 to about 1.1-1.2. <sup>[5, 7, 13]</sup> In our experiment, this ratio increases from 0.81 for GO to 1.13 for SiW<sub>12</sub>@rGO which confirms the effectiveness of the reduction process using reduced SiW<sub>12</sub>. It can be interpreted by the creation during the GO reduction process of numerous new graphitic domains (sp<sup>2</sup>) smaller in size as compared to the ones present in the exfoliated GO.<sup>[14]</sup>

Figure 3 shows a HR-TEM micrograph of SiW<sub>12</sub>@rGO. Other TEM or HR-TEM micrographs of typical microstructure of GO, GO with SiW<sub>12</sub>, and reduced GO with SiW<sub>12</sub> are shown in Figures S5, S6, S7, respectively. Typical TEM contrast associated to GO can be observed in Figure S5. For GO materials after contact with fully oxidized SiW<sub>12</sub> (GO-SiW<sub>12</sub>), a few darker contrasts can be observed on the sample surface in the TEM micrograph of Figure S6. These darker dots (sizes ranging from 20 to 40 nm) can be associated with W based clusters. The HR-TEM micrograph taken on the edge of the material shows two typical areas. On the pure edge (black rectangle), the space between two wave lines is closed to 0.34 nm which can be




**Figure 2.** Raman spectra ( $\lambda_{exc} = 473$  nm) of pristine GO (a), GO-SiW<sub>12</sub> (b) and SiW<sub>12</sub>@rGO nanocomposite (c) highlighting the effectiveness of the GO reduction process through the strong D/G ratio increase. All spectra were normalized to the G band intensity.



**Figure 3.** HR-TEM micrograph of the SiW<sub>12</sub>@rGO nano-composite. Scale bar: 5 nm.

associated with the distance between two graphene sheets (3.35 Å). Therefore, this part corresponds approximately to 15 graphene layers. Inside the black circle, on the same micrograph, spot contrasts can be observed. The distance between these spots is close to 0.14 nm which is the distance between 2 carbon atoms in a graphene plane (1.42 Å). For the SiW<sub>12</sub>@rGO composite, TEM and HR-TEM contrasts are quite different from the previous ones (see Figures 3 and S7). The presence of very small clusters can be observed. The size of these clusters is similar to the size of SiW<sub>12</sub> (1.1 nm).<sup>[15]</sup> The interplanar distances, measured on the HR-TEM micrograph (inside the black circles in Figure S7), are close to 0.19 nm, which can be associated to the {611} plane of the SiW<sub>12</sub> compound.


TGA coupled with mass spectrometry were carried out in order to study the stability of the samples for temperatures ranging from 20°C to 1000°C, in air atmosphere. Figure 4 shows the TGA curves recorded for H<sub>4</sub>SiW<sub>12</sub>O<sub>40</sub> (a), GO (b), GO-SiW<sub>12</sub> (c) and SiW<sub>12</sub>@rGO (d) whereas Table S3b reported the mass loss percentage for 4 temperature range areas (TRAs) and the total mass loss at 1000°C. The 4 temperature range areas are called TRA1 (20 °C - 160°C (excepted for H<sub>4</sub>SiW<sub>12</sub>O<sub>40</sub> where final temperature is 108°C)), TRA2 (160°C – 290°C), TRA3 (290°C – 545°C to 610 °C) and TRA4 (545°C to 610°C – 1000°C). For TRA1, mass loss is mostly associated with OH and H<sub>2</sub>O whereas for the 3 other TRAs, mass losses can be associated with the combustion of carbonaceous matter. It has to be mentioned that no weight loss can be attributed to the thermal decomposition of the SiW<sub>12</sub> species for temperature up to 1000°C, as curve (a) in Figure 4 shows that H<sub>4</sub>SiW<sub>12</sub>O<sub>40</sub> is stable until 1000°C. For the GO and the GO-SiW<sub>12</sub> materials, the percentage loss for the 4 TRAs is almost similar. The total loss for GO is 100% and it is close to 98% for GO-SiW<sub>12</sub> (the 2% remaining mass can be related to the presence of W type clusters shown by TEM and XPS). For the SiW<sub>12</sub>@rGO sample the mass loss percentages for the various TRAs are quite different than those determined for the GO and GO-SiW<sub>12</sub> samples. Indeed, it is smaller for the 3 first TRAs leading to a remaining mass closed to 40%. This remaining material can be



**Figure 4.** TGA in air of (a) H<sub>4</sub>SiW<sub>12</sub>O<sub>40</sub>, (b) GO, (c) GO-SiW<sub>12</sub>, (d) SiW<sub>12</sub>@rGO samples.

associated with the POM clusters detected by TEM and XPS. Between 20 and 108°C (TRA1), a mass loss of 7.5% is observed which is mainly due to OH and H<sub>2</sub>O as indicated by the mass spectroscopy analyses (Figure S8 and Table S4). Therefore the real initial mass corresponding only to rGO + SiW<sub>12</sub> is 2.139 mg (see Table S3(a)). After annealing until 1000°C, the remaining sample mass which corresponds to the POMs is 0.914 mg. Thus we can estimate the amount of SiW<sub>12</sub> immobilized onto the rGO sheets that is 0.26 mmol SiW<sub>12</sub>/g GO. This coverage is high, it is higher than the one obtained by hydrothermal reduction of GO in the presence of H<sub>3</sub>PMo<sub>12</sub>O<sub>40</sub> that is 0.18 mmol PMo<sub>12</sub>/g GO.<sup>[9]</sup>

Finally, the SiW<sub>12</sub>@rGO composite was characterized with electrochemical techniques. For this purpose, a drop of the nanocomposite in suspension in ethanol was deposited on a glassy carbon electrode. After solvent evaporation, the electrochemical responses were recorded in an acidic aqueous solution (0.5 M H<sub>2</sub>SO<sub>4</sub>). Faradic current due to reduction/reoxidation of the POMs immobilized on the rGO sheets and capacitive current due to the high surface area of the nanocomposite are detected in the current-potential curves (Figures 5 and S9), confirming the presence of SiW<sub>12</sub> on the rGO surface and the good electronic conductivity of the nanocomposite as no binders nor conductive additives were used. For comparison the response obtained with the pristine GO is also reported in Figure 5 (curve(d)).



**Figure 5.** Cyclic voltammograms in 0.5 M H<sub>2</sub>SO<sub>4</sub> solution of (a-c) SiW<sub>12</sub>@rGO deposited on a GC electrode, at various potential scan rates (v): (a) 100, (b) 200, (c) 300 mV s<sup>-1</sup>; (d) GO deposited on a GC electrode, v=100 mV s<sup>-1</sup>.

In summary, a rapid and easy route for the preparation of an hybrid nanocomposite made of reduced graphene oxide

---

decorated with electroactive inorganic clusters is presented in this work. The partly reduced SiW<sub>12</sub> species prepared by an electrochemical route react with the initial GO leading to a nanocomposite homogeneously decorated with SiW<sub>12</sub> with a final concentration of 0.26 mmol per g of rGO. This materials has many potential applications such as energy storage (supercapacitors)<sup>[9]</sup> or electrocatalysis<sup>[16]</sup>.

## Acknowledgements


The authors would like to thank Dr. M. Chehimi and Dr. P. Dubot for the access to the XPS spectrometer and for their help, as well as D. Denux for TGA experiments. They also acknowledge the Labex Michem (Sorbonne Universités) for the use of nano/microRaman facilities.

**Keywords:** Graphene oxide • Polyoxometalate • Nanocomposite • Electrochemistry • Reduced graphene oxide

- [1] K. Parvez, Z.-S. Wu, R. Li, X. Liu, R. Graf, X. Feng, K. Muellen, *Journal of the American Chemical Society* **2014**, *136*, 6083-6091.
- [2] A. V. Talyzin, T. Szabo, I. Dekany, F. Langenhorst, P. S. Sokolov, V. L. Solozhenko, *Journal of Physical Chemistry C* **2009**, *113*, 11279-11284; O. Akhavan, *Carbon* **2010**, *48*, 509-519.
- [3] T. Lin, J. Chen, H. Bi, D. Wan, F. Huang, X. Xie, M. Jiang, *Journal of Materials Chemistry A* **2013**, *1*, 500-504.
- [4] Y. Xu, K. Sheng, C. Li, G. Shi, *Journal of Materials Chemistry* **2011**, *21*, 7376-7380.
- [5] S. Stankovich, D. A. Dikin, R. D. Piner, K. A. Kohlhaas, A. Kleinhammes, Y. Jia, Y. Wu, S. T. Nguyen, R. S. Ruoff, *Carbon* **2007**, *45*, 1558-1565.
- [6] H. R. Thomas, S. P. Day, W. E. Woodruff, C. Valles, R. J. Young, I. A. Kinloch, G. W. Morley, J. V. Hanna, N. R. Wilson, J. P. Rourke, *Chemistry of Materials* **2013**, *25*, 3580-3588.
- [7] H. Li, S. Pang, X. Feng, K. Muellen, C. Bubeck, *Chemical Communications* **2010**, *46*, 6243-6245.
- [8] M. T. Pope, A. Muller, *Angewandte Chemie-International Edition in English* **1991**, *30*, 34-48; C. Debiemme-Chouvy, H. Cachet, *Journal of Physical Chemistry C* **2008**, *112*, 18183-18188.
- [9] J. Suarez-Guevara, V. Ruiz, P. Gomez-Romero, *Physical Chemistry Chemical Physics* **2014**, *16*, 20411-20414.
- [10] S. Wang, H. Li, S. Li, F. Liu, D. Wu, X. Feng, L. Wu, *Chemistry-a European Journal* **2013**, *19*, 10895-10902.
- [11] A. C. Ferrari, *Solid State Communications* **2007**, *143*, 47-57.
- [12] S. Eigler, C. Dotzer, A. Hirsch, *Carbon* **2012**, *50*, 3666-3673.
- [13] Z. F. Jia, T. D. Chen, J. Wang, J. J. Ni, H. Y. Li, X. Shao, *Tribology International* **2015**, *88*, 17-24; J. L. Zhang, H. J. Yang, G. X. Shen, P. Cheng, J. Y. Zhang, S. W. Guo, *Chemical Communications* **2010**, *46*, 1112-1114; C. Xu, X. Shi, A. Ji, L. Shi, C. Zhou, Y. Cui, *Plos One* **2015**, *10*, e0144842; C. Z. Zhu, S. J. Guo, Y. X. Fang, S. J. Dong, *Acs Nano* **2010**, *4*, 2429-2437; H. J. Shin, K. K. Kim, A. Benayad, S. M. Yoon, H. K. Park, I. S. Jung, M. H. Jin, H. K. Jeong, J. M. Kim, J. Y. Choi, Y. H. Lee, *Advanced Functional Materials* **2009**, *19*, 1987-1992; I. K. Moon, J. Lee, R. S. Ruoff, H. Lee, *Nature Communications* **2010**, *1*, 73-79.
- [14] A. C. Ferrari, J. Robertson, *Physical Review B* **2000**, *61*, 14095-14107.
- [15] L. C. W. Baker, M. T. Pope, *Journal of the American Chemical Society* **1960**, *82*, 4176-4179.
- [16] R. Liu, S. Li, G. Zhang, A. Dolbecq, P. Mialane, B. Keita, *Journal of Cluster Science* **2014**, *25*, 711-740.
-

## Table of Contents

### COMMUNICATION



C. Debiemme-Chouvy<sup>a</sup>, B. Thomas<sup>b</sup>,  
I.T. Lucas<sup>a</sup>, T. T.M. Tran<sup>a</sup>, J.-M. Heintz<sup>b</sup>,  
A. Veillère<sup>b</sup>, and J.-F. Silvain<sup>b</sup>

Page No. – Page No.

**Facile and green reduction of  
graphene oxide by a reduced  
polyoxometalate and nanohybrid  
formation**