

# Structural and Magnetic Properties of Cr Doped SnO2 Nanopowders Prepared by Solid State Reaction

M Kuppan, S Harinath Babu, S Kaleemulla, N Madhusudhanarao, C Krishnamoorthi, G Venugopalrao, I Omkaram, D Sreekantha Reddy, K Venkata Subba Reddy

## ► To cite this version:

M Kuppan, S Harinath Babu, S Kaleemulla, N Madhusudhanarao, C Krishnamoorthi, et al.. Structural and Magnetic Properties of Cr Doped SnO2 Nanopowders Prepared by Solid State Reaction . Mechanics, Materials Science & Engineering Journal, 2017, 9, 10.2412/mmse.9.43.91 . hal-01499372

## HAL Id: hal-01499372 https://hal.science/hal-01499372v1

Submitted on 4 Apr 2017

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution 4.0 International License

## Structural and Magnetic Properties of Cr Doped SnO<sub>2</sub> Nanopowders Prepared by Solid State Reaction

M. Kuppan<sup>1</sup>, S. Harinath Babu<sup>2</sup>, S. Kaleemulla<sup>1,a</sup>, N. MadhusudhanaRao<sup>1</sup>, C. Krishnamoorthi<sup>1</sup>, G. VenugopalRao<sup>3</sup>, I. Omkaram<sup>4</sup>, D. Sreekantha Reddy<sup>5</sup>, K.Venkata Subba Reddy<sup>6</sup>

1 - Thin films Laboratory, Centre for Crystal Growth, VIT University, Vellore, Tamilnadu, India

2 - Department of Physics, Annamacharya Institute of Technology and Sciences, New Boyanapalli, Rajampet, India

3 - Materials Physics Division, Indira Gandhi Centre for Atomic Research, Kalpakkam, Tamilnadu, India

4 – Department of Electronics and Radio Engineering, KyungHee University, Yongin-si, Gyeonggi-do 446-701, Republic of Korea

5 – Department of Physics and Sungkyukwan Advanced Institute of Nanotechnology (SAINT), Sungkyunkwan University, Suwan – 440746, Republic of Korea

6 - Department of Physics, S.B.V.R. Degree college, Badvel-516227 andhra Pradesh, India

a – <u>skaleemulla@gmail.com</u>

DOI 10.2412/mmse.9.43.91 provided by Seo4U.link

Keywords: thin film, nano powder, vacuum annealing, Cr doped SnO<sub>2</sub> nanopowders.

**ABSTRACT.** Chromium-doped tin oxide nano powders ( $Sn_{1-x}Cr_xO_2$ , x = 0.00, 0.03, 0.05 and 0.07) were prepared using simple low cost solid state reaction and followed by vacuum annealing at 900 °C and studied the effects of Cr dopant concentration on structural and magnetic properties. The X-ray diffraction (XRD) studies confirmed that all the diffracted peaks were polycrystalline rutile structure of  $SnO_2$  phase. FT-IR analysis gave additional supports of formation of O-Sn-O and Cr-Sn-O the system. Magnetic studies revealed that all the powder samples were ferromagnetic at room temperature. Further the saturation magnetization increased with increase of doping concentration.

Introduction. Since the discovery of room temperature ferromagnetism in Mn doped GaP and ZnO by Deitl et. al. [1] and the discovery of room temperature ferromagnetism in Co doped TiO<sub>2</sub> by Mastumoto et al [2], intense research work has been carried out on doping og different semiconductors with different impurities. An extensive research work has been carried out on wide band gap oxide semiconductors such titanium oxide, zinc oxide, copper oxide, tin oxide and gallium nitrate systems [3-9]. These semiconductors possess wide band gap of the order of 3.5 eV, high electrical conductivity, high optical transmittance in visible region and high stability. The discovery of high temperature ferromagnetism in Co doped SnO<sub>2</sub> thin films by Ogale et. al. [10] prompted a large number of experimental investigations on pure and transition metal doped tin oxide [11]. Among the other wide band gap oxide, tin oxide is one of the best material due to its wide band gap (3.5 eV), n-type conductivity and high transmittance in visible region of the electromagnetism spectrum and finds many applications such as solar cells, gas sensors, photo detectors etc.[12-14]. Different synthesis methods were adopted for the synthesis of undoped and impurity doped metal oxides. Among the other synthesis methods, solid state reaction method is the one of the best techniques by which one can get nanoparticle with uniform size. The synthesis of nanoparticles such as indium oxide, tin oxide and indium tin oxide were studied and reported the room temperature ferromagnetic

 $<sup>\</sup>odot$  2017 The Authors. Published by Magnolithe GmbH. This is an open access article under the CC BY-NC-ND license http://creativecommons.org/licenses/by-nc-nd/4.0/

properties in these. An effort is made here for the synthesis of Cr doped  $SnO_2$  nanoparticles using simple solid state reaction method and studied their structural and magnetic properties [6, 15, 16]

**Experimental details.** Chromium doped tin oxide  $Sn_{1-x}Cr_xO_2$  (x = 0.00, 0.03, 0.05 and 0.07) concentrations were prepared by a solid state reaction followed by vacuum annealing. Commercially available SnO<sub>2</sub> and Cr<sub>2</sub>O<sub>3</sub> (M/S Sigma-Aldrich 99.99 % pure) were accurately weighed in required proportions and were mixed and ground thoroughly using an Agate mortar and pestle to convert to very fine powders. The grinding of the mixtures was carried out for 16 hours for all the powder samples. The ground powder samples were loaded into a small one end closed quartz tube of diameter 10 mm and length of 10 cm, which was enclosed in a bigger quartz tube of diameter of 2.5 cm and length of 75 cm with provision to allow unwanted vapors to escape from the reaction chamber and evacuated at  $2 \times 10^{-3}$  mbar using a rotary pump was used for the synthesis of the present samples. The complete set up was placed in horizontal tubular microprocessor controlled furnace and fired for several hours at different temperatures. The firing temperature and firing periods were optimized at 900 °C and 10 hours. X-ray diffraction (X-ray diffractometer, D8 Advance, BRUKER) was used to establish structural aspects. Energy dispersive analysis spectroscopy (EDS) (OXFORD instrument inca penta FET X3) was used to carry out elemental analysis. Magnetic measurements were carried out using Vibrating sample magnetometer (Lake Shore-7410)

#### **Results and discussion**

**Structural properties.** Fig.1 shows the XRD pattern of chromium oxide (Cr<sub>2</sub>O<sub>3</sub>). The diffraction peaks such as (0 1 2), (1 0 4), (1 1 0), (1 1 3), (0 2 4), (1 1 6), (2 1 4) and (3 0 0) were observed among with (1 0 4) as the most predominant orientation. All these diffraction peaks were exactly coincided with  $\alpha$ -crystalline Cr<sub>2</sub>O<sub>3</sub> [JCPDS card: 74-0326]. The other stable phases of chromium (Cr) such as CrO, Cr<sub>2</sub>O, CrO<sub>2</sub> and Cr<sub>3</sub>O<sub>4</sub> were not found in the present X-ray diffraction pattern, indicating the absence of other phases of Chromium.



*Fig. 1. XRD profile of bulk Cr<sub>2</sub>O<sub>3</sub>.* 



Fig. 2. XRD profile of bulk SnO<sub>2</sub>.

Fig. 2 shows the XRD profiles of bulk SnO<sub>2</sub>. The diffraction peaks were found at diffraction angles of 26.62° (110), 33.89° (101), 37.98° (200), 39.09° (111), 42.65° (210), 51.80° (211), 54.79° (220), 57.85° (002), 61.92° (310), 64.75° (112), 65.98° (301) 71.39° (202) and 78.73° (321) were exactly coincided with tetragonal structure of SnO<sub>2</sub> [JCPDS No. 411445]. Among the above orientations, (110) was the predominant orientation. No other diffraction peaks related to tin in other phases such as SnO or tin (Sn) metal clusters were identified in XRD within detectable limit of XRD. The same diffraction peaks were observed for the Cr doped SnO<sub>2</sub> nanoparticles and no diffraction peaks related to either Cr or Cr<sub>2</sub>O<sub>3</sub> were observed inXRD. All the diffraction peaks were exactly coincided with tin oxide XRD profiles. The crystallite size (G) was calculated by using the Debye-Scherer formula:

$$G = k \lambda / \beta \cos \theta,$$

where k is particle geometry dependent constant (for spherical shape  $k \sim 1$ ),  $\lambda$  is the wavelength of used ( $\lambda = 1.5406$  Å),  $\beta$  is the full width-at-half maximum (FWHM) and  $\theta$  is the diffracted angle, respectively.

The estimated average crystallite size is found to be 47 nm. The same was confirmed by elemental analysis and spectroscopic studies. It confirms the doping of Cr into the  $SnO_2$  lattice.

**Optical properties.** Fig. 3 shows the optical band gaps of the Cr doped SnO<sub>2</sub> nanopartticles. The optical bang gap was obtained by plotting  $(\alpha hv)^2$  versus the photon energy (hv) and by extrapolating of the linear region of the plots to zero absorption ( $\alpha = 0$ ). The optical band gap of the powder samples decreases from 3.58 eV to 3.63 eV when the Cr doping concentration increased from x = 0.03 to x = 0.07.



Fig. 3. Optical band gaps of Cr doped SnO<sub>2</sub> nanoparticles.

**Magnetic properties.** Fig.4. shows the magnetic measurements, which were carried out for all the samples including pure  $SnO_2$  and  $Cr_2O_3$ . The  $SnO_2$  nanoparticles exhibit the weak ferromagnetism at low magnetic fields and converted to paramagnetic at higher applied magnetic fields. The  $Cr_2O_3$  nanoparticles exhibited antiferromagnetic behaviour. By doping Cr impurity of 3 at.%, 5 at.% and 7 at.%, the nanoparticles exhibited weak ferromagnetism without saturation even at high applied magnetic fields. From this it conclude that the observed ferromagnetism is an intrinsic in nature rather than any impurities as no impurity phase was observed from XRD and other spectroscopic studies.



Fig. 4. M-H loops of Cr doped SnO<sub>2</sub> nanoparticles at different doping concentrations.

**Summary.** Chromium doped  $SnO_2$  nanoparticle were synthesised using simple solid state reaction method and studies their structural, optical and magnetic properties. The structural studies indicated that the synthesised nanopowders were in rutile structure and particle size was of the order of 47 nm. From the optical studies, it was found that the optical band gap of the nanoparticle decreased with the increase of doping concentration. From the magnetic studies it was found that the nanoparticles exhibited ferromagnetism at low external magnetic fields the strength of magnetization increased with the increase of doping concentration. It seems that the observed ferromagnetism is an intrinsic in nature.

### References

[1] T. Dietl, H. Ohno, F. Matsukura, J. Cibert, D. Ferrand, Zener model description of ferromagnetism

in zinc-blende magnetic semiconductors, Science, 287 (2000) 1019-1022, DOI: 10.1126/science.287.5455.1019.

[2] Y. Matsumoto, M. Murakami, T. Shono, T. Hasegawa, T. Fukumura, M. Kawasaki, P. Ahmet, T. Chikyow, S.Y. Koshihara, H. Koinuma, Room-Temperature Ferromagnetism in Transparent Transition Metal-Doped Titanium Dioxide, Science, 291 (2001) 854, DOI: 10.1126/science.1056186.

[3] K.A. Griffin, A.B. Pakhomov, C.M. Wang, S.M. Heald, K.M. Krishnan, Intrinsic Ferromagnetism in Insulating Cobalt Doped Anatase TiO<sub>2</sub>, Physical Review Letters, 94 (2005) 157204, DOI: 10.1103/PhysRevLett.94.157204.

[4] S.R. Shinde, S.B. Ogale, S. Das Sarma, J.R. Simpson, H.D. Drew, S.E. Lofland, C. Lanci, J.P. Buban, N.D. Browning, V.N. Kulkarni, J. Higgins, R.P. Sharma, R.L. Greene, T. Venkatesan, Ferromagnetism in laser deposited anatase  $Ti_{\{1-x\}}Co_xO_{(2-\delta)}$  films, Physical Review B, 67 (2003) 115211, DOI: 10.1103/PhysRevB.67.115211.

[5] S.G. Yang, T. Li, B.X. Gu, Y.W. Du, H.Y. Sung, S.T. Hung, C.Y. Wong, A.B. Pakhomov, Ferromagnetism in Mn-doped CuO, Applied Physics Letters, 83 (2003) 3746-3748, DOI: 10.1063/1.1623944.

[6] M. Kuppan, S. Kaleemulla, N. Madhusudhana Rao, N. Sai Krishna, M. Rigana Begam, D. Sreekantha Reddy, Physical Properties of Sn  $_{(1-x)}$  Fe  $_{(x)}$  O<sub>2</sub> Powders Using Solid State Reaction, Journal of Superconductivity and Novel Magnetism, 27 (2014) 1315-1321, DOI : 10.1007/s10948-013-2457-0.

[7] M. Kuppan, S. Kaleemulla, N.M. Rao, N. Sai Krishna, M.R. Begam, M. Shobana, Structural and Magnetic Properties of Ni Doped, Advances in Condensed Matter Physics, 2014 (2014) 5, DOI: 10.1155/2014/284237.

[8] N. Sai Krishna, S. Kaleemulla, G. Amarendra, N. Madhusudhana Rao, C. Krishnamoorthi, M. Rigana Begam, I. Omkaram, D. Sreekantha Reddy, Magnetic and superconductivity studies on (In  $(1-x)Fe_x)_2O_3$  thin films, Journal of Alloys and Compounds, 637 (2015) 436-442, DOI: 10.1016/j.jallcom.2015.02.167.

[9] C. Xu, J. Chun, K. Rho, D.E. Kim, B.J. Kim, S. Yoon, S.-E. Han, J.-J. Kim, Ferromagnetic GaN:MnAlSi nanowires, Journal of Applied Physics, 99 (2006) 064312, DOI: 10.1063/1.2174125.

[10] S.B. Ogale, R.J. Choudhary, J.P. Buban, S.E. Lofland, S.R. Shinde, S.N. Kale, V.N. Kulkarni, J. Higgins, C. Lanci, J.R. Simpson, N.D. Browning, S. Das Sarma, H.D. Drew, R.L. Greene, T. Venkatesan, High Temperature Ferromagnetism with a Giant Magnetic Moment in Transparent Co-doped SnO<sub>2-\$</sub>, Physical Review Letters, 91 (2003) 077205, DOI: 10.1103/PhysRevLett.91.077205.

[11] C.B. Fitzgerald, M. Venkatesan, L.S. Dorneles, R. Gunning, P. Stamenov, J.M.D. Coey, P.A. Stampe, R.J. Kennedy, E.C. Moreira, U.S. Sias, Magnetism in dilute magnetic oxide thin films based on SnO<sub>2</sub>, Physical Review B, 74 (2006) 115307, DOI: 10.1103/PhysRevB.74.115307.

[12] H.-C. Chiu, C.-S. Yeh, Hydrothermal Synthesis of SnO2 Nanoparticles and Their Gas-Sensing of Alcohol, The Journal of Physical Chemistry C, 111 (2007) 7256-7259, DOI: 10.1021/jp0688355.

[13] Z. Guo-Zhong, W. Jin-Feng, C. Hong-Cun, S. Wen-Bin, W. Chun-Ming, Q. Peng, Effect of Co 2 O 3 on the microstructure and electrical properties of Ta-doped SnO 2 varistors, Journal of Physics D: Applied Physics, 38 (2005) 1072, DOI: 10.1088/0022-3727/38/7/017.

[14] A. Punnoose, J. Hays, V. Gopal, V. Shutthanandan, Room-temperature ferromagnetism in chemically synthesized  $Sn_{(1-x)}Co_xO_2$  powders, Applied Physics Letters, 85 (2004) 1559-1561, DOI: 10.1063/1.1786633.

[15] S.H. Babu, S. Kaleemulla, N.M. Rao, G.V. Rao, C. Krishnamoorthi, Microstructure, ferromagnetic and photoluminescence properties of ITO and Cr doped ITO nanoparticles using solid state reaction, Physica B: Condensed Matter, 500 (2016) 126-132, DOI :

#### 10.1016/j.physb.2016.07.037.

[16] N.S. Krishna, S. Kaleemulla, G. Amarendra, N.M. Rao, C. Krishnamoorthi, M. Kuppan, M.R. Begam, D.S. Reddy, I. Omkaram, Structural, optical and magnetic properties of Fe doped In2O3 powders, Materials Research Bulletin, 61 (2015) 486-491, DOI: 10.1016/j.materresbull.2014.10.065.

Cite the paper

M. Kuppan, S. Harinath Babu, S. Kaleemulla, N. MadhusudhanaRao, C. Krishnamoorthi, G. VenugopalRao, I. Omkaram, D. SreekanthaReddy, K.Venkata Subba Reddy (2017). <u>Structural and Magnetic Properties of Cr</u> <u>Doped SnO<sub>2</sub> Nanopowders Prepared by Solid State Reaction</u>. *Mechanics, Materials Science & Engineering*, Vol 9. doi: <u>10.2412/mmse.9.43.91</u>