

Integrated low drive voltage electro-optic Bragg modulator using a periodically poled lithium niobate

Imed Mhaouech, Virginie Coda, Germano Montemezzani, Mathieu Chauvet,

Laurent Guilbert

► To cite this version:

Imed Mhaouech, Virginie Coda, Germano Montemezzani, Mathieu Chauvet, Laurent Guilbert. Integrated low drive voltage electro-optic Bragg modulator using a periodically poled lithium niobate. Conference on Lasers and Electro-Optics Europe & European Quantum Electronics Conference (CLEO/Europe-EQEC), Jun 2017, Munich, Germany. Paper CE-P29, 10.1109/cleoe-eqec.2017.8086660. hal-01579637

HAL Id: hal-01579637 https://hal.science/hal-01579637

Submitted on 13 May 2020 $\,$

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Integrated low drive voltage electro-optic Bragg modulator using a periodically poled lithium niobate

Imed Mhaouech1,2, Virginie Coda1,2, Germano Montemezzani1,2, Mathieu Chauvet3, Laurent Guilbert1,2

1. University of Lorraine, LMOPS, EA 4423, 2 rue E. Belin, F-57070 Metz, France

2. CentraleSupélec, LMOPS, EA 4423, 2 rue E. Belin, F-57070 Metz, France

3. FEMTO-ST Institute, UMR CNRS 6174, Université de Bourgogne Franche-Comté, 15B Avenue des Montboucons, F-25000 Besançon,

France

Periodically poled lithium niobate (PPLN) is currently used for frequency conversions using quasi-phasematching, thanks to its high nonlinear coefficients and mature poling process. PPLN can also be attractive for electro-optic (EO) applications. Several studies have been conducted on PPLN-based EO deflectors, and recent realizations have lower the required applied voltage under hundred volts [1]. Indeed, for practical EO applications drive voltages as low as 5 V are usually required. For this purpose, we use a recent technique to realize high-quality isolated crystalline film out of LN [2] to implement an EO Bragg deflector with a drive voltage below 10 V. In this work we present an efficient spatial light deflector working for extraordinary or ordinary light polarization using the EO effect in a thinned PPLN planar waveguide confined between two silica layers on a silicon substrate, which allows the deflection of the light under the effect of a low electrical voltage.

To this aim, after the periodic poling of a 500-µm-congruent LN wafer, a thin silica layer is deposited onto one face of the poled wafer, followed by the sputtering of a gold layer. A 500-µm-thick silicon wafer is also coated with a gold layer. The metalized faces of both the PPLN and silicon wafers are then placed into contact and pressed in a wafer-bonding machine. The LN layer is then mechanically ground and polished to get a LN film with a thickness of 5 µm. A second silica layer then is deposited on the top surface of the PPLN. Finally, two gold electrodes are deposited to allows the application of a uniform electric field to activate the EO effect.

As schematically shown in Fig. 1. (a), the PPLN waveguide structure works as a spatial light deflector with two output ports driven by the EO effect. Fig. 1. (b) displays the obtained results. The experimental η_{exp} and theoretical η_{th} diffraction efficiency versus the applied voltage U are represented. More than 97% of diffraction efficiency is obtained with an operating wavelength of 633 nm for the two orthogonal light polarizations with a drive voltage of about 5 V [3]. We also design an EO Bragg filter using a PPLN ridge waveguide. The structure aimed at filtering a wavelength from a broadband spectrum between 1500 nm and 1600 nm delivered by a broadband source for telecommunication applications.



Fig. 1 (a) Configuration of the waveguide electro-optic Bragg deflector tested both with ordinary (*o*) and extraordinary (*e*) light polarizations. (b) Diffraction efficiency versus applied voltage U for (i) e-polarized light and (ii) o-polarized light. Red points are experimental data. Black solid lines are theoretical curves. The blue dash line in (i) is shifted from the latter by an offset $\Delta U_o = -7.5$ V due to the presence of a permanent internal electric field and to a surface grating resulting from the thinning process.

References

[1] M. Okazaki and T. Suhara, "High-performance 1024-pixel EO spatial light modulator using cascaded periodically-poled Raman-Nath gratings ", J. Lightwave Technol. 33, 5195 (2015)

[2] M. Chauvet, F. Bassignot, F. Henrot, F. Devaux, L. Gauthier-Manuel, H. Maillotte, G. Ulliac, and B. Sylvain, "Fast-beam self-trapping in LiNbO3 films by pyroelectric effect", Opt. Lett. **40**, 1258 (2015).

[3] I. Mhaouech, V. Coda, G. Montemezzani, M. Chauvet, L. Guilbert, "Low drive voltage electro-optic Bragg deflector using a periodically poled lithium niobate planar waveguide, Opt. Lett. **41**, 4174 (2016).