



HAL
open science

Experimental characterization of hydrogel swelling under plant cell wall environment

Carole Antoine Assor, Tancrede Alméras, Françoise Quignard, Olivier Arnould

► To cite this version:

Carole Antoine Assor, Tancrede Alméras, Françoise Quignard, Olivier Arnould. Experimental characterization of hydrogel swelling under plant cell wall environment. Plant Biomechanics International Conference PBM8, Nov 2015, Nagoya, Japan. , 2015. hal-01594669

HAL Id: hal-01594669

<https://hal.science/hal-01594669v1>

Submitted on 26 Sep 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - ShareAlike 4.0 International License

Experimental characterization of hydrogel swelling under plant cell wall environment


C. Assor^a, T. Alm ras^b, F. Quignard^c, O. Arnould^b




Context

Characterization of molecular mechanisms responsible of wood maturation growth stress
Biomechanic functions of tension wood: weight increase balance and plant orientation control

Wood tension




[B. Clair]



Cell wall structure: specific gelatinous G-layer


Discrimination of molecular mechanisms producing tissue stress:




— Crystalline cellulose
X Amorphous matrix swelling

consistent with experimental observations: cellulose longitudinal tension and transverse compression


Material and methods



10 mm



-Vertical displacement is locked
-Force due to the "swelling" of the gel is measured continuously



10 mm

-6 mL of water-dissolved alginates (1, 2 or 3%, dw) are enclosed in a 15 mm diameter dialysis membrane and immersed in 35 mL of 0.1 M CaCl₂

-After 24h, hydrogels are cleaned 3x with distilled water and 10 mm disks are sampled from them


Results

In parallel, free swelling of hydrogels in water is characterised:


-linear correlation between volume and mass variations of samples

$$\text{swelling} = (\Delta m/m_0) \times 100$$

Effect of alginate content on hygromechanical properties: free swelling strain and confined swelling stress; elastic shear modulus (rheometer, 0.02-0.1 Hz)



ϵ_{\max}



σ_{\max}

Alginate (% dw)	ϵ_{\max} (%)	σ_{\max} (kPa)	G' (kPa)
1	129	0.71	10
2	103	1.60	41
3	51	1.75	86

Conclusions and perspectives

- The confined swelling stress could more correspond to an osmotic pressure. Additional tests will be established with different alginates structures to characterize the origin of the stress developed.
- The 0.2% deformation of crystalline cellulose estimated within the G-layer require a lateral compressive stress from the matrix closed to 1 MPa, that could not be reached by the osmotic pressure. From these experimental results, it appears that the confined chamber is too stiff as the matrix needs to be less confined to produce a sufficient swelling stress.
- Nano hydrogels could allow to raise a polymer ratio around 20% that would be a more realistic G-layer analog and would allow to study cellulose/matrice interactions.

carole.assor@supagro.inra.fr

^a UMR IATE, INRA, CIRAD, Sup'Agro, Universit  de Montpellier, Montpellier, France

^b Laboratoire de M canique et G nie Civil, Universit  de Montpellier, CNRS, Montpellier, France

^c Institut Charles Gerhardt, Universit  de Montpellier, CNRS, Montpellier, France