



HAL
open science

Highly porous calcium hydroxyapatite-based composites for air pollution control

Mohammed Kemiha, Doan Pham Minh, Nathalie Lyczko, Ange Nzihou,
Patrick Sharrock

► **To cite this version:**

Mohammed Kemiha, Doan Pham Minh, Nathalie Lyczko, Ange Nzihou, Patrick Sharrock. Highly porous calcium hydroxyapatite-based composites for air pollution control. SYMPHOS 2013 - 2ND INTERNATIONAL SYMPOSIUM ON INNOVATION AND TECHNOLOGY IN THE PHOSPHATE INDUSTRY, May 2013, Agadir, Morocco. p. 394-402, 10.1016/j.proeng.2014.09.044 . hal-01611619

HAL Id: hal-01611619

<https://hal.science/hal-01611619>

Submitted on 6 Nov 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



“SYMPHOS 2013”, 2nd International Symposium on Innovation and Technology in the Phosphate Industry

Highly porous calcium hydroxyapatite–based composites for air pollution control

Mohamed Kemiha^a, Doan Pham Minh^{a*}, Nathalie Lyczko^a, Ange Nzihou^a and Patrick Sharrock^{a,b}

^a Université de Toulouse; Mines Albi; CNRS; Centre RAPSODEE, Campus Jarlard, F–81013 Albi cedex 09, France

^b Université de Toulouse, SIMAD, IUT Paul Sabatier, Avenue Georges Pompidou, 81104 Castres, France

Abstract

The control of emission gas from incinerators appears as a key issue for the improvement of the incineration technology. In this paper, we developed new sorbent materials based on calcium hydroxyapatite (Ca–HA) matrix. Using gelatine and bio–glass as porous and structural agents, which are largely available and have reasonable costs, powder of Ca–HA could be easily formulated into desired morphologies. As an example, a Ca–HA based accumulator having good porosity and mechanical stability was obtained by mixing Ca–HA powder with gelatine, bio–glass and water, followed by molding, then calcination steps. This accumulator showed an interesting capacity for the collection and tracing of Cd used as single model heavy metal in gas phase.

© 2014 The Authors. Published by Elsevier Ltd. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/3.0/>).

Peer-review under responsibility of the Scientific Committee of SYMPHOS 2013

Keywords: Calcium hydroxyapatite, composite, porosity, fumes, heavy metals, cadmium.

1. Introduction

Municipal and industrial solid wastes are increasingly produced worldwide [1]. Landfill and incineration are the most used techniques for the management of municipal and industrial wastes. But with the limit in landfill sites and the growing amount of wastes, incineration is becoming more advantageous, because it allows (i) a high reduction of waste volume up to 90% or waste weight up to 70%; (ii) an effective destruction of pathogens and other organic toxic compounds; (iii) the recovery of energy from organic wastes [2, 3]. However, emissions of pollutants from incinerator flue gases are currently of great environmental concern because of their toxicity. The emission of heavy metals takes place during the combustion of wastes, wherein heavy metals are vaporized by the thermal effect of combustion and then emitted with exhaust gases despite filtration of smoke particles [4]. Thus, the control of incinerator gas emission, in particular heavy metal emission, is an important factor for the improvement of the efficiency and acceptability of the incineration technology.

Calcium hydroxyapatite (Ca–HA, chemical formula: $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$) belongs to the family of apatitic compounds [5]. Ca–HA is known as a versatile material for different domains of applications, in particular environmental purposes, thank to its intrinsic physico–chemical properties: high specific surface area, very low solubility in water, high thermal stability, high ionic exchange capacity for several cations and anions [5, 6]. However, most of developments of Ca–HA based materials in environmental field are limited to the liquid phase for the removal of fluoride [7, 8]; organic pollutants [9–12]; metals and heavy metals [13–15] etc.

* Corresponding author. Tel.: +33-563493258; fax: +33-563493243.
E-mail address: doan.phamminh@mines-albi.fr

For such applications, powder Ca–HA is usually used because of its easy production by conventional precipitation or acid–base reaction in an aqueous solution. To our knowledge, no work has been done on the development of porous Ca–HA based composite for the treatment of pollutants in gas phase, in particular the collection and tracing of metals present in incinerator fume.

The objectives of this work are threefold: (i) the formulation of Ca–HA powder composite (accumulator); (ii) the physical, chemical and thermal characterizations of the materials; (iii) and the determination of their reactivity and implantation of the collection and tracing of metal pollutants in gas phase.

The characterization of the composite has been carried out using a combination of various techniques such as SEM-EDS, XRD, BET, adsorption–desorption isotherm, ICP–AES etc). The efficiency and the reactivity of the composite showed that significant amounts of vaporized heavy metals were accumulated at the surface of the solids while a smaller amount of metals diffused in the pores of the solids without destroying the composite. In fact, the composites were obtained in severe experiment conditions (high temperature, high acidity and high humidity) and thus were chemically and thermally stable, and showed good reactivity for the collection of cadmium in gas phase.

2. Materials and methods

All chemical products used in this work were purchased from commercial suppliers (Table 1).

Table 1. Chemical products used in this work.

Name	Principal components	Purity, wt%	Supplier
Calcite	CaCO ₃	98	Fisher Scientific
Ammonium dihydrogen orthophosphate	NH ₄ H ₂ PO ₄	99	Fisher Scientific
Gelatine	Protein	86 (in water)	Weishardt
Bio–glass	SiO ₂ , Na ₂ O, K ₂ O, MgO, CaO, P ₂ O ₅ , B ₂ O ₃	99	Medical Calcium Phosphates
Cadmium chloride	CdCl ₂	99	Fisher Scientific

2.1. Synthesis of calcium hydroxyapatite (Ca–HA)

Ca–HA was synthesized according to the previous studies [16, 17]. Briefly, 66.7 mmol of NH₄H₂PO₄ and 400 mL of permuted water were introduced in a 1.2 litre (L) U-form glass reactor (i.d.: 10 cm, length: 15 cm), equipped with a vertical stirrer. Then, 100 mmol of calcite powder were gradually added in the solution of NH₄H₂PO₄ under stirring (400 rpm). The reaction mixture was kept at 80 °C for 24 h. During the reaction, samples withdrawn from the reactor was filtered, washed several times with permuted water on 0.45 µm filtration paper and dried overnight at 105 °C prior to all analysis. Powder product obtained after 24 h of reaction was finally sieved to eliminate particles larger than 45 µm before the formulation step.

2.2. Formulation of Ca–HA composite

This formulation step was dedicated to the transformation of Ca–HA powder into Ca–HA granulates with controlled porosity and thermal/thermo–mechanical stability. A mixture containing Ca–HA powder, bio–glass (8 wt%), gelatine (10 wt%) and water was prepared. The quantity of water was calculated to obtain a doughy mixture by minimizing water content. Gelatine was used as porous agent, which could be thermally decomposed to create new porosity by release of gas molecules. Bio–glass is used as a structural agent, which is chemically inert and enhances the cohesion of apatitic particles. The moulding was carried out with a plastic cylinder (i.d. of 10 mm, length of 20 mm). This granulate was freely dried under atmospheric conditions until the total removal of water before the calcination at 1000 °C with heating rate of 2 °C min⁻¹ and 15 min of plateau time at 1000 °C. The resulting cylindrical Ca–HA based product is called thereafter accumulator.

2.3. Collection of heavy metals in gas phase

Fig. 1 illustrates the experimental apparatus used for the collection of heavy metal by accumulator at high temperature. The horizontal reactor was composed by a ceramic cylindrical tube (i.d. of 20 mm, length of 100 cm), which can be heated electrically up to 1000 °C by a furnace. The accumulator in cylindrical form (20 mm x 10 mm) was set at one extremity of the furnace where the temperature was well controlled. The reactor was heated to 650 °C which is close to the temperature of incinerator fumes and is above the melting point of CdCl₂ used as source of Cd [18]. After reaching this temperature, a ceramic crucible containing a quantity of approximately 110 mg (exactly weighed) of cadmium under CdCl₂ form was rapidly pushed at the centre of the ceramic tube. An air circulation with controlled flow rate of 1 L h⁻¹ passed through the tube in order to orient the movement of the polluted

gas over the accumulator. A moderate evaporation of CdCl_2 is expected in these conditions. Gas from the outlet of the ceramic tube was washed twice with 5 wt% nitric acid solution. The smaller diameter of the accumulator compared to the internal diameter of the reactor facilitates the metal gas flow. Thus, an accumulation of cadmium on the surface of the accumulator was expected.




Fig. 1. Experimental setup for accumulator testing.

2.4. Analysis and characterization

Elemental analysis was carried out using ICP–AES technique (HORIBA Jobin Yvon Ultima 2). Powder sample was mineralized with mixture of concentrated nitric and hydrochloric acids before analysis. X–ray diffraction (XRD) of the solids was performed using a Phillips Panalytical X'pert Pro MPD diffractometer with a $\text{Cu K}\alpha$ (1.543 \AA) radiation source. Thermogravimetry (TG) was performed in a TA Instruments SDTQ600 analyzer with a heating rate of $5 \text{ }^\circ\text{C min}^{-1}$ under air flux (100 mL min^{-1}). Infrared spectroscopy (IR) was recorded on a Shimadzu FTIR 8400S spectrometer with a direct measure of solid powders. Mercury porosimetry was performed on an Autopore III 9410 Micromeritics. Scanning electron microscopy coupled with energy dispersive X–ray spectroscopy (SEM–EDS) was measured on a Philips XL30 ESEM apparatus (FEI Company). The mechanical resistance was measured using LRX Plus apparatus (Lloyd Instruments).

3. Results

3.1. Synthesis of Ca–HA

The use of calcium carbonate as starting reactant for calcium source has advantages related to its lower cost and availability compared to soluble calcium salt.

Fig. 2 shows an example of TG analysis of the sample withdrawn from the reactor after 30 min of synthesis. Different weight losses were observed and were already discussed in our previous study [16]. Free water was removed below $100 \text{ }^\circ\text{C}$. The second weight loss with the maximum of DTG signal (DTG_{max}) at $108 \text{ }^\circ\text{C}$ could be attributed to the dehydration of mono-calcium phosphate monohydrate (MCPM, $\text{Ca}(\text{H}_2\text{PO}_4)_2 \cdot \text{H}_2\text{O}$). The net DTG signal with DTG_{max} at $185 \text{ }^\circ\text{C}$ was attributed to the dehydration of dicalcium phosphate dihydrate (DCPD, $\text{CaHPO}_4 \cdot 2\text{H}_2\text{O}$) or brushite as the main intermediate. A small weight loss around $430 \text{ }^\circ\text{C}$ could be due to the dehydration of monetite (CaHPO_4) to form calcium pyrophosphate ($\text{Ca}_2\text{P}_2\text{O}_7$). Finally, remaining calcite decomposed in the temperature range of 610 to $730 \text{ }^\circ\text{C}$.




Fig. 2. Example of TG analysis of the solid powder obtained after 30 min of reaction between CaCO₃ and NH₄H₂PO₄ at 80 °C.

From TG curves, the content of calcite remained in the solid powder can be easily calculated, according to the equation of decomposition of calcite (Eq. (1)), where the weight loss corresponds to the formation of CO₂ as exhaust gas.




Fig. 3 present the evolution of the content of calcite remaining in the solid products at different reaction time of synthesis. Most of the calcite was decomposed within the first two hour of reaction, as observed by the violent release of carbonic gas. The decomposition reached up to 99.4 % after 24 h of reaction, indicated the complete decomposition of calcite particles.




Fig. 3. Evolution of the content of remaining calcite in the solid powders obtained from the reaction of CaCO₃ and NH₄H₂PO₄ at 80 °C.

XRD pattern of the final solid powder obtained after 24 h of synthesis at 80 °C is shown in Fig. 4. As expected, there was only a very weak signal of the principal diffraction peak of calcite at 2θ of 29.4 degrees. Ca–HA of low–crystallinity was formed as the main phase. This low–crystallinity must be explained by the moderate temperature of synthesis [15, 16].




Fig. 4. XRD pattern of the solid powders obtained from the reaction of CaCO_3 and $\text{NH}_4\text{H}_2\text{PO}_4$ at 80°C for 24 h; (■) calcite (JCPDS standard N° 01–086–2334); other peaks: Ca–HA (JCPDS standard N° 01–072–1243).

3.2. Characterization of accumulator

The thermal analysis (TG) of the initial Ca–HA and the dried accumulator is shown in Fig. 5. For Ca–HA (Fig. 5 (a)), a continuous weight loss in the studied temperature range was observed which was explained by the removal of lattice molecular water [19, 20]. For the dried accumulator, a removal of surface moisture was observed at the temperatures below 100°C . Then, different weight losses in the temperature range of $114\text{--}670^\circ\text{C}$ were observed which could be all attributed to the complex decomposition of gelatine. This included generally the protein chain breakage and peptide bond rupture [21–23]. No weight loss was observed above 670°C indicating that the calcination at 1000°C allowed the total decomposition of gelatine in the dried accumulator.




Fig. 5. TG analysis of the initial Ca–HA (a) and the dried accumulator (b) in the temperature range of $20\text{--}800^\circ\text{C}$ under air atmosphere.

SEM images of the accumulator calcined at 1000°C for 15 min are showed in Fig. 6. In the left-hand side, Ca–HA particles of sizes varying in a large range from hundreds of nm to hundreds of μm were observed. Big particles of Ca–HA seemed to be formed by agglomeration of small particles as suggested by images at high magnifications [16].




Fig. 6. SEM images of Ca-HA powder dried at 105 °C (A, B, C), and of the accumulator calcined at 1000 °C (D, E, F).

On the right-hand side, the morphology of Ca-HA particles changed completely. Thermal sintering took place with the formation of contacts between adjacent particles. In contrast to the classical thermal sintering of Ca-HA where particles lost their porosity, the accumulator was highly porous and its macropores could be easily observed at different magnifications.

In order to better evaluate the porosity of the calcined accumulator, mercury porosimetry was performed and the result is shown in Fig. 7. Pore distribution extended from about 0.1 μm up to 352 μm could be obtained. Pore sizes around 1 and 150 μm were observed, which confirmed again the observation in Fig. 6. This porosity was probably created by the release of gas molecules during the thermal decomposition of gelatine. The porosity of 62% could also be calculated for this calcined accumulator.




Fig. 7. Pore distribution of the accumulator calcined at 1000 °C obtained from mercury porosimetry; pore diameter is in base 10 logarithmic scale.

The mechanical resistance of the accumulator before and after calcination was also measured and the results obtained are shown in Table 2. The calcination led to the formation of porous material as illustrated above. Thus, the mechanical strength of the accumulator was dramatically reduced from 12.3 to 2.4 MPa. However, the calcined accumulator sustained the mechanical stress well enough for the application considered.

Table 2. Mechanical resistance of the accumulator before and after calcinations.

Accumulator	Height, mm	Diameter, mm	Stress (MPa)
Before calcinations	20	10	12.3
After calcination	20	10	2.4

3.3. Accumulation of heavy metals

The experiment of collection of cadmium was repeated three times in order to check the reproducibility of the procedure. After the collection, the accumulator was carefully recovered and completely mineralized before ICP–AES analysis. Fig. 8 presents the results obtained.




Fig. 8. Cd abatement by the accumulator during the collection test.

For the reactor set-up used (Fig. 1), the stream of polluted gas is expected to pass over the external surface of the accumulator which must not favor the contact of Cd with the surface of the whole accumulator. However, an important abatement of Cd varying in the range of 17–23% was obtained which demonstrated that the accumulator had an interesting reactivity for the collection of Cd.

In order to localize the Cd sequestered in the matrix of the accumulator, SEM–EDS analysis was performed which allows the determination of the elemental distribution within the accumulator. Fig. 9 presents an example of SEM–EDS analysis.




Fig. 9. Example of SEM–EDS analysis of the accumulator after the collection of Cd.

On Fig. 9, the presence of Cd is characterized by bright regions. Cd was clearly observed on the border of the accumulator (dotted arrow). In the middle of the accumulator, some agglomerates of Cd were also observed (continuous arrows). This could be explained by the diffusion and agglomeration of Cd within the pores of Ca–HA composite matrix which may be also considered. Supplementary analysis by the X–ray map of Cd confirmed again the high presence of Cd on the surface of the accumulator (results not shown here).

4. Conclusions

New sorbent materials (accumulator) based on Ca–HA matrix for the treatment of heavy metal in gas phase has been successfully developed using a simple moulding technique. The calcination at 1000 °C allowed the thermal stabilisation of the

accumulator. Thus it can be used in high temperature processes avoiding the classical thermal sintering and loss of reactivity of Ca–HA based materials. The use of gelatine and bio–glass as porous and structural agents allowed the accumulator to have satisfactory porosity and mechanical stability.

In contact with a gas stream containing Cd as model heavy metal at high temperature (650 °C), the prepared accumulator showed an interesting reactivity for the collection of Cd. The Cd abatement reached around 20% in the experimental conditions used. The accumulation of Cd was especially observed at the surface of the accumulator.

Acknowledgements

This work was financially supported by ADEME (contract N° 07-74-C0082). The authors gratefully thank our colleagues at the RAPSODEE center, Christine Roland and Sylvie Del-Confetto, for their technical help.

References

- [1] Rester, R.E., Harrison, R.M., 1994. *Waste Incineration and the Environment*, Royal Society of Chemistry, Thomas Graham House, Science Park, Cambridge.
- [2] Rogaume, T., Auzanneau, M., Jabouille, F., Goudeau, J.C., Torero, J.L., 2002. The effects of different airflows on the formation of pollutants during waste incineration, *Fuel* 81, p. 2277.
- [3] Quina, M.J., Bordado, J.C.M., Quinta-Ferreira, R.M., 2010. Chemical stabilization of air pollution control residues from municipal solid waste incineration, *Journal of Hazardous Materials* 179, p. 382.
- [4] Rio, S., Verwilghen, C., Ramarosan, J., Nzihou, A., Sharrock, P., 2007. Heavy metal vaporization and abatement during thermal treatment of modified wastes. *Journal of Hazardous Materials* 148, p. 521.
- [5] Elliott, J.C., 1994. *Studies in Inorganic Chemistry 18: Structure and Chemistry of the Apatites and Other Calcium Orthophosphates*, Elsevier, Amsterdam/London/New York/Tokyo.
- [6] Nzihou, A., Sharrock, P., 2010. Role of phosphate in the remediation and reuse of heavy metal polluted wastes and sites, *Waste and Biomass Valorization* 1, p. 163.
- [7] Sundaram, C.S., Viswanathan, N., Meenakshi, S., 2009. Fluoride sorption by nano-hydroxyapatite/chitin composite, *Journal of Hazardous Materials* 172, p. 147.
- [8] Jiménez-Reyes, M., Solache-Ríos, M., 2010. Sorption behavior of fluoride ions from aqueous solutions by hydroxyapatite, *Journal of Hazardous Materials* 180, p. 297.
- [9] Tonsuadu, K., Viipsi, K., Trikkel, A., 2008. EDTA impact on Cd²⁺ migration in apatite–water system, *Journal of Hazardous Materials* 154, p. 491.
- [10] Bahdod, A., El Asri, S., Saoiabi, A., Coradin, T., Laghizil, A., 2009. Adsorption of phenol from an aqueous solution by selected apatite adsorbents: Kinetic process and impact of the surface properties, *Water Research* 43, p. 313.
- [11] Lin, K., Pan, J., Chen, Y., Cheng, R., Xu, X., 2009. Study the adsorption of phenol from aqueous solution on hydroxyapatite nanopowders, *Journal of Hazardous Materials* 161, p. 231.
- [12] Wei, W., Sun, R., Cui, J., Wei, Z., 2010. Removal of nitrobenzene from aqueous solution by adsorption on nanocrystalline hydroxyapatite, *Desalination* 263, p. 89.
- [13] Gomez del Rio, J.A., Morando, P.J., Cicerone, D.S., 2004. Natural materials for treatment of industrial effluents: comparative study of the retention of Cd, Zn and Co by calcite and hydroxyapatite. Part I: batch experiments, *Journal of Environmental Management* 71, p. 169.
- [14] Bailleux, S., Nzihou, A., Bernache-Assolant, D., Champion, E., Sharrock, P., 2007. Removal of aqueous lead ions by hydroxyapatites: Equilibria and kinetic processes, *Journal of Hazardous Materials* A139, p. 443.
- [15] Pham Minh, D., Sebei, S., Nzihou, A., Sharrock, P., 2012. Apatitic calcium phosphates: Synthesis, characterization and reactivity in the removal of lead(II) from aqueous solution, *Chemical Engineering Journal* 198-199, p. 180.
- [16] Pham Minh, D., Lyczko, N., Sebei, H., Nzihou, A., Sharrock, P., 2012. Synthesis of calcium hydroxyapatite from calcium carbonate and different orthophosphate sources: A comparative study, *Materials Science and Engineering B* 177, p. 1080.
- [17] Chkir, M., PhD thesis, 2011, Université de Toulouse, France.
- [18] Lide, D.R., 2003. *Handbook of Chemistry and Physics*, CRC Press, Boca Raton, Florida, 84th Ed, p. 447.
- [19] Lazic, S., Zec, S., Miljevic, N., Milonjic, S., 2001. The effect of temperature on the properties of hydroxyapatite precipitated from calcium hydroxide and phosphoric acid, *Thermochim Acta* 374, p. 13.
- [20] Suchanek, W.L., Shuk, P., Byrappa, K., Riman, R.E., Tenhuisen, K.S., Janas, V.F., 2002. Mechanochemical–hydrothermal synthesis of carbonated apatite powders at room temperature, *Biomaterials* 23, p. 699.
- [21] Eid, M., Abdel-Ghaffar, M.A., Dessouki, A.M., 2009. Effect of maleic acid content on the thermal stability, swelling behaviour and network structure of gelatin-based hydrogels prepared by gamma irradiation, *Nuclear Instruments and Methods in Physics Research B* 267, p. 91.
- [22] Peña, C., de la Caba, K., Eceiza, A., Ruseckaitė, R., Mondragon, I., 2010. Enhancing water repellence and mechanical properties of gelatin films by tannin addition, *Bioresource Technology* 101, p. 6836.
- [23] Kacem, M., Salvador, S., Nzihou, A., Flamant, G., 2007. Particle in box: a cell for in-situ measurements of porosity and effective diffusion coefficient during thermo physical transformations. *Industrial & Engineering Chemistry Research* 46, p. 6558.