



**HAL**  
open science

## Creep and moisture interaction on tropical timber structures under outdoor conditions: spatial variability of mechanical parameters

Gustavo Avellaneda-Malagón, Nicaise Manfoumbi, Emilio Bastidas-Arteaga,  
Rostand Moutou Pitti

### ► To cite this version:

Gustavo Avellaneda-Malagón, Nicaise Manfoumbi, Emilio Bastidas-Arteaga, Rostand Moutou Pitti. Creep and moisture interaction on tropical timber structures under outdoor conditions: spatial variability of mechanical parameters. COST ACTION FP1303 Final Conference and MC Meeting Building with bio-based materials: Best practice and performance specification, Sep 2017, Zagreb, Croatia. hal-01616951

**HAL Id: hal-01616951**

**<https://hal.science/hal-01616951>**

Submitted on 15 Oct 2017

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

## Creep and moisture interaction on tropical timber structures under outdoor conditions: spatial variability of mechanical parameters

Gustavo Avellaneda-Malagón<sup>1</sup>, Nicaise Manfoumbi<sup>2</sup>, Emilio Bastidas-Arteaga<sup>1</sup>, Rostand Moutou Pitti<sup>3,4</sup>

<sup>1</sup> UBL, Université de Nantes, CNRS UMP 61B3, France, [gustavo.avellaneda-malagon@etu.univ-nantes.fr](mailto:gustavo.avellaneda-malagon@etu.univ-nantes.fr), [emilio.bastidas@univ-nantes.fr](mailto:emilio.bastidas@univ-nantes.fr)

<sup>2</sup> Université des Sciences et Technique de Masuku, URMM, BP 941, Franceville Gabon, [nicaise.manfoumbi@gmail.com](mailto:nicaise.manfoumbi@gmail.com)


<sup>3</sup> Université Clermont Auvergne, CNRS, 19300 Clermont Ferrand, [rostand.moutou\\_pitti@uca.fr](mailto:rostand.moutou_pitti@uca.fr)

<sup>4</sup> CENARST, IRT, 10794 Libreville, Gabon, [rostand.moutou\\_pitti@uca.fr](mailto:rostand.moutou_pitti@uca.fr)

**Keywords:** Creep, *Baillonella Taxisperma*, reliability, moisture interaction,

### ABSTRACT

The investigation of tropical behaviour woods in their environment is a real challenge for the prediction of the structural responses of tropical timber structures subjected to thermo-hygro-mechanical loadings. The present study is focused on the experimental characterization and modelling of the spatial variability of the physical-mechanical parameters (density, modulus of elasticity, compression and flexion) of a solid wood beam subjected to outdoor conditions in the south of Gabon into equatorial Region.



**Figure 1: (a) Beams in sheltered outside climate; (b) specimens, (c) cross-sections, (d) Spatial specimen modelling; (e) Experimental device modelling.**

The specimens, Figure 1 (b) have been debited from two Moabi specie (*Baillonella Taxisperma*) beams previously subjected to a creep-recovery test in an outdoor tropical

environment during 5 years, Figure 1 (a) (Manfoumbi *et al.*, 2012). The beams were cut into sections 317 mm long. These were also divided into three portions in the height direction, Figure 1 (b-c). From each portion, at least two bending, compression and traction specimens are extracted. Thus, for the two beams the section of specimens are, Figure 1 (d): Compression test: 112 test, 20 x 20 mm<sup>2</sup> for 120 mm long; Tensile test: 104 test, 10 x 10 mm<sup>2</sup> per 100 mm long; Bending test: 106 test, 15 x 15 mm<sup>2</sup> for 300 mm long, Figure 1 (e).

Figure 2 shows an example of the trajectories of bending strength for the first beam, Figure 1 (a). It was observed that different values were measured for a given length. Among the methods available in the literature to represent this spatial variability, we considered the Karhunen-Löve Expansion (Ghanem and Spanos, 1991). As in other materials, the covariance kernel that best fitted modeling mechanical properties was the exponential kernel or the autocorrelation function. We have found values of the parameters for autocorrelation function for each timber property. Further work will focus on the propagation of uncertainty and spatial variability on the mechanical models for reliability assessment of the beams with or without cracks.




Figure 2: Bending Strength Trajectories for Beam 1.

## REFERENCES

N. Manfoumbi, F. Dubois, N. Sauvat, “Behavior in service of beams in flexion: adaptation of the Eurocode 5 to a tropical climate”, World Conference on Timber Engineering (WCTE2012), Session 27, Engineering case studies 1, Auckland, New Zealand, 15-19 July 2012, pp. 455-459.

Ghanem R G, and Spanos P D. (1991). *Stochastic Finite Elements: A Spectral Approach*. New York, USA: Springer. f

## Acknowledgments:

The authors would like to express their appreciation to the National Research Agency (ANR) for its financial support of this work through the CLIMBOIS Project No. ANR-13-JS09-0003-01, as labeled by ViaMeca. The authors thank also the COST Action FP1303 for the financial support to attend this final conference.