

MIXED MODE THREE DIMENSIONAL CONTOUR INTEGRAL: FOR WOOD APPLICATION UNDER CREEP LOADING

S El Kabir, Rostand Moutou Pitti, Frédéric Dubois, N Recho, Y. Lapusta

► To cite this version:

S El Kabir, Rostand Moutou Pitti, Frédéric Dubois, N Recho, Y. Lapusta. MIXED MODE THREE DIMENSIONAL CONTOUR INTEGRAL: FOR WOOD APPLICATION UNDER CREEP LOAD-ING. 14th International Conference on Fracture (ICF 14), Jun 2017, Rhodes, Greece. hal-01616972

HAL Id: hal-01616972 https://hal.science/hal-01616972

Submitted on 15 Oct 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

MIXED MODE THREE DIMENSIONAL CONTOUR INTEGRAL: FOR WOOD APPLICATION UNDER CREEP LOADING

S. El Kabir¹, R. Moutou Pitti, F. Dubois, N. Recho and Y. Lapusta

GEMH Laboratory, Limoges University, Civil Enginering Center, 19300, Egletons, France Université Blaise Pascal, Institut Pascal, PB 10448, 63000, Clermont-Ferrand, France CNRS, UMR 6602, Institut Pascal, 63171, Aubière, France French Institute of Advanced Mechanics, Université Clermont Auvergne, Institut Pascal UMR 6602 /UBP /CNRS /

IFMA, PB 265, 63175, Aubière, France

Abstract: The main goal of this work is to present a new integral for three dimensional crack problems under mixed mode loading. This work is based on a generalization of the M integral proposed initially by Chen and Shield [1] and developed by Moutou Pitti et al. [2] to visco elstic crack growth process. The aim of this generalization is to propose a new parameter integral entitled M_{θ}^{3D} which computes the energy release rate combining real and auxiliary displacement fields in orthotropic material such as wood. The energy release rate distribution along the crack front line is calculated and the non-path dependence is proved with the use of numerical application.

1. Introduction

Two dimensional current approaches studying crack growth problems of a viscoelastic material such as wood, using independent path integrals, do not really include all stresses effects existing in timber structures. By considering a three dimensional orientation of external loading, the crack can be situated in a three dimensional state by considering torsion effects inducing the third crack mode, and which leads to a coupled pure opening mode. Also, we can consider thermal or hydrological effects in timber materials under mixed mode loading. All this cases require the generalization of the J^{3D} -integral formalism for a mixed mode loading problem and the adaptability of the M-theta method for a future finite element implementation.

2. Results

 M^{3D} -integral is a combination between real and virtual strain fields which enables computing fracture parameter. Based on a conservative law, M^{3D} -integral enables to separate fracture mode under creep mixed load. Where σ_{ij}^{u} and σ_{ij}^{v} are real and virtual stresses associated with the real and virtual displacements fields u and v. In order to make easy numerical integration we use the θ method, and by considering Ostrogradski transformation we obtain:

$$M_{\theta} = \frac{1}{2} \int_{V} P_{kj} \cdot \theta_{k,j} \cdot dV + \frac{1}{2} \int_{V_{\Gamma_2}} \left(\left(\sigma_{ij}^{\nu} \cdot \left(\varepsilon_{ij}^{u} \right)_{,k} + \sigma_{ij}^{u} \cdot \left(\varepsilon_{ij}^{\nu} \right)_{,k} \right) - \left(\left(\sigma_{ij}^{\nu} \cdot \varepsilon_{ij}^{u} \right)_{,k} + \left(\sigma_{ij}^{u} \cdot \varepsilon_{ij}^{\nu} \right)_{,k} \right) \right) \cdot \theta_{k} \cdot dV - \frac{1}{2} \int_{S_{CF}} \left(\sigma_{ij}^{\nu} \cdot u_{i,k} + \sigma_{ij}^{u} \cdot v_{i,k} \right) \cdot n_{j} \cdot \theta_{k} \cdot dS$$

$$\tag{1}$$

The finite element implementation is based on a Double Cantilever Beam DCB specimen loaded in mixed mode configuration (Figure 1). In order to validate the non-dependence of

¹ Corresponding author

E-mail address: soliman.el-kabir@unilim.fr (S. El kabir)

the integration domain, the average energy release rate is computed. The second application considers the evaluation of the energy release rate along the crack front line (Figure 2).



Figure 1. Double Cantilever Beam geometry



Figure 2. Average energy release rate vs. R_c (left), Energy release rate distribution along the crack front line (right)

The finite element implementation is proposed by computing a M_{θ}^{3D} -integral based on a numerical definition of the integration domain allowing the computation of the average value of the energy release rate or its distribution along the crack front line.

3. Conclusions

In this work, a new M-integral is developed for three-dimensional problem under mixed mode loading. The evolution of the energy release rate versus crack front line has been determined. The non-dependence of path integral is proved. In future work, it will be necessary to extend the M^{3D} -integral in order to take into account a variable climate case for viscoelastic orthotropic materials. Also, experimental tests will be necessary to validate the numerical results.

Acknowledgements

The authors wish to strongly acknowledge the National Agency of Research (ANR) for its financial support of this work through the project CLIMBOIS N° ANR-13-JS09-0003-01 labeled by ViaMeca.

References

- [1] F.H.K. Chen and R.T. Shield, Conservation laws in elasticity of the J-integral type, *Journal of Applied Mechanics and Physics*, 1977;28:1-22.
- [2] R. Moutou Pitti, F. Dubois, C. Petit, N. Sauvat, and O. Pop, A new integral parameter for mixedmode crack growth in viscoelastic orthotropic media, *Engineering Fracture Mechanics* 2008;75:4450-4465.