

Chemical and structural changes of raw phosphate during heat treatment

A Mgaidi, F Ben Brahim, Driss Oulahna, Ange Nzihou, M El Maaoui

▶ To cite this version:

A Mgaidi, F Ben Brahim, Driss Oulahna, Ange Nzihou, M El Maaoui. Chemical and structural changes of raw phosphate during heat treatment. High-temperature materials and processes, 2004, 23 (3), p.185-194. hal-01626708

HAL Id: hal-01626708 https://hal.science/hal-01626708

Submitted on 8 Mar 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Chemical and Structural Changes of Raw Phosphate during Heat Treatment

A. Mgaidi^{1*}, F. Ben Brahim¹, D. Oulahna², A. Nzihou², M. El Maaoui¹

¹ Industrial Inorganic Chemistry Laboratory, Chemistry Department, Faculty of sciences, Tunis 1060, Tunisia.

² Chemical Engineering Laboratory for Particulate Solids, CNRS UMR 2392, School of Mines of Albi, Campus Jarlards, 81013 Albi, France.

* Corresponding author : Arbi.Mgaidi@fst.rnu.tn

Abstract

In the wet phosphoric acid production using calcined phosphate particles, physical structure and chemical composition of used material have an impact on the reaction speed.

In this study, porous properties of phosphate fraction size 125-200 μ m after heating at different temperature between 240°C to 940°C was investigated.

Fluorapatite, carbonate fluorapatite (Francolite), dolomite and calcite, constitute the major minerals of the phosphate rock used.

TG/DTA, CRTA, IR and ESEM observations results were used to understand the chemical changes observed. The decline of the specific surface area (SSA) from 16.61 m²/g down to 0.81 m^2 /g was interpreted according to the thermal results. The increasing of the linear shrinkage % by sintering process is observed. This process begins near 240°C and reach the maximum near 940°C. These results are in agreement with those in the literature.

Some kinetic tests were understudying at laboratory scale to elucidate the relationship between reactivity and porous properties of phosphate particles.

Keywords: Phosphate ore particles, heat treatment, structural changes, sintering

I. INTRODUCTION

Previous works on the calcination of calcium phosphate compounds may be classified in two categories depending on the field of interest.

The first category deals with the treatment of natural calcium phosphate to be used in the manufacture of phosphoric acid or super phosphate production. It is well known that the composition of phosphate reserves varies from one deposit to another and low-grade phosphate rocks (calcareous, dolomitic, siliceous) are not usually suitable for direct use in acidulation plants. Beneficiation techniques may be applied such as calcination for the carbonate phosphate and flotation for siliceous phosphate rocks.

Calcination of phosphate rocks was proposed and used at the industry scale (1-2). The effect of the different experimental parameters on the beneficiation of phosphate ores by heat treatment has been considered by several authors (3-7).

Previous investigations (8-10) were successful to enrich the low-grade calcareous phosphate using heat treatment. Kaljuvee et al. (6) proposed the calcination-separation method for the separation of carbonaceous phosphates issues from Kazakhastan region. Zafar et al. (7) studied in their experimental investigation, dealing with thermal beneficiation of a low-grade dolomitic phosphate rock, the factors (size, temperature and time) affecting the increase of P_2O_5 weight % upon heat treatment.

Note that phosphate rock with a high level of organic matter can be also processed by thermal route (11). The principal objective of such process is the removal of the organic matter and the increase of the filtration speed of the phosphogypsium.

The second series of studies concerns applications of synthetic calcium phosphate compounds in bioceramic industry. Abadou et al. (12) reported the influence of calcination conditions on the morphological evolution of synthetic hydroxyapatite. The calcination behaviors of pure fluorapatite and its sinterability under oxygen and argon atmosphere were studied by Ben Ayed et al. (13-14). The calcination and sintering of some powders of calcium phosphate apatites with variable (Ca/P) atomic ratio were studied by Raynaud et al. (15).

Recently some synthetic calcium phosphate compounds were tested to trap heavy metals from some industrial wastes. The resulting solid were stabilized by calcination process (16-17). Since, the authors reported some results concerning the heat treatment of pure hydroxyapatite with different (Ca/P) atomic ratio. For the synthetic calcium phosphate compounds used in bioceramic, the X-ray diffraction, thermal analysis and specific surface area determination were used.

According to our knowledge, very few experimental works were devoted to the evolution of physical properties of natural calcium phosphate during heat treatment are available on the literature.

Most of the commercial phosphate rocks are of sedimentary origin and several mineralogical studies indicated that East Mediterranean and North Africa phosphorites were sedimentary deposits with francolite as the main phase. The francolite mineral have the empirical formula $[Ca_{9,51} Na_{0,35} Mg_{0,14} (PO_4)_{4,47} (CO_3)_{1,26} F_{2,50}]$ which generally accompanied by the calcite or dolomite minerals (18). Al though, the choice of a technology for enrichment depends on the origin of phosphorites and on its physical and chemical properties. For Morocco or Tunisian phosphate, the flotation beneficiation results were less satisfactory and thermal methods can be more effective.

The purpose of this work was to investigate the evolution of physical properties according to the temperature of calcination of raw phosphate particles fraction (125-200 μ m). The chemical and structural changes were investigated using experimental techniques such as, Thermal analyzer (DTA-TG and CRTA), I.R spectroscopy, X-ray Diffraction, true density, BET surface area and Environmental Scanning Electron microscopy (ESEM).

II. MATERIAL AND METHODS

The phosphate ore used in the study was provided from the Gafsa area reserves, in Southwest Tunisia. The ore was crushed, ground and sieved to obtain the fraction size (125-200 μ m) using ASTM sieves. The analysis of calcium were performed using Flame Atomic Absorption spectroscopy 'FAAS) from varian. Phosphor as the anion H₂PO₄⁻ and F⁻ were analyzed using a Dionex ion chromatograph with ion Pac AS12A Guard Plus analytical column. The chemical analysis of the sample is reported in Table 1. This chemical composition was given as weight % in dry basis. From this analysis, we observed that the ratio (CaO/P₂O₅ = 1.605) is greater than the one observed for the synthetic fluoraptite (CaO/P₂O₅ = 1.31) and the amount of fluor found in this ore is high (3.16 %). The high fluorine content and the high ratio (CaO/P₂O₅) were attributed to the francolite and fluorapatite the main minerals of phosphate particles.

Component	CaO	P205	F	CO2	MgO	Loss ignition
% Wt	44.8	27.9	3.16	()	()	11,50%
	(47.6)*	(28.8)*	()	(5.62)*	(0.66)*	()

Table 1: Chemical cor	nposition of the	phosphate rock used	(data* from Ben	Brahim (28))
-----------------------	------------------	---------------------	-----------------	-------------	---

Amounts of 10 g of phosphate ore of the investigated fraction size were calcined in a tubular furnace, under airf10w, in isothermal conditions. The treatments were carried out between 240 and 940°C. The heating rate was of 10°C/min. from room temperature to the chosen temperature. Each sample was held for one hour at the chosen temperature and cooled at the same heating rate to room temperature. The results show that the calcination time considered was sufficient to reach thermal equilibrium corresponding to a constant weight loss. At the end of a run, the remaining solid was weighed. In these conditions, we don't observe a sticking at side of the melting pot.

The investigated sample (fraction size 125-200 μ m) and the treated one at 780°C, were examined in X-ray diffractometer using CuK α (PHILIPS apparatus) to identify the mineralogical constituents. The phases present were determined by comparing the patterns with JCPDS standards. The results confirms that the ore contains essentially carbonate apatite, fluorapatite, dolomite and calcite (Figure 1).





The thermogravimetric and the differential thermal analysis were carried out under argon atmosphere on 79 mg of raw material using Setaram® TG-DTA 12 thermal analyzer. The heating rate was 10°C/min. Controlled transformation Rate Thermal Analysis (CRTA) was carried out using sample mass (500-1000 mg), pressure (3.0 kPa) and temperature rise equal to 10°C/min. This analysis was used to identify the chemical change during the heat treatment.

Samples calcined at 240, 600, 780 and 940°C were also submitted to infrared (IR) spectrometry analysis (Perkin Elmer®) at room temperature using KBr Pastilles were prepared from approximately 1 to 1.2 mg of powder mixed with 200 mg of KBr and the mixture was

pressed under vacuum. A scanning of 40 cm⁻¹ per minute was employed.

On the other hand, the true densities of different samples after heating at 240, 400, 550, 600, 780 and 940°C were measured by volume displacement using an Accupyc \mathbb{R} 1330 Helium (Micromeritrics) pycnometer. In addition, the specific surface area was measured by BET method using N₂ at 77 K as an adsorption gas (Micromeritics \mathbb{R} ASAP 2000 Norcross GA).

The shrinkage tests for all raw and calcined samples were carried out by Thermomechanical Analyzer (TMA, Setaram® Setsys 16/20) with 5g constant load using Helium flow and the heating rate of 10°C/min.

The surface characteristics of the sintered phosphate samples agglomerate as well as the unsintered particles-aggregates was studied using Environmental Scanning Electron Microscopy ESEM (XL 30 ESEM-FEG, PHILIPS®).

III. RESULTS AND DISCUSSION

III.1. Chemical changes of phosphate ore

III.1.1. Effect of the temperature on the weight loss

The effect of temperature on the weight loss % of samples heated for one hour is illustrated in figure 2. The weight loss increased continuously indicating that at each temperature, chemical phenomena take place and lead to gas release. Two zones of weight loss are observed, even if the processes generating the weight loses cannot be easily identified, because of the heterogeneity of the phosphate considered. Nevertheless, the weight loss of 2.5% in the first zone below 550°C can be attributed to the evaporation of water and organic matter. In the second zone, the total weight loss of 5.5% is observed from 550 to 600°C and from 600 to around 1000°C.



Fig.2: Weight loss (per cent) of phosphate fractions at various temperatures.

Several methods were used to better understand the chemical changes observed.

DTA and TG studies of the raw material were carried out under Argon atmosphere from room temperature to 900°C. As shown in figure 3, the sample loses weight in two steps. The weight loss which from 120°C to 550°C is due to the removal of water and to the decomposition under argon atmosphere of volatile organic matter (3.7 mass %).

As reported in the literature (11), the content of organic matter of some typical phosphate ores leads between 0.5 to 2.6 %. The second mass loss up to 550° C corresponds to the decomposition of phosphate gangue (dolomite and calcite) and to the decomposition of CO₂ substituted in the apatitic lattice.



Fig.3: TG and DTA curves of phosphate fraction $125-200 \,\mu\text{m}$.

Blazy and Samama (19) reported that the combustion of the remaining of organic matter into calcareous Turkey phosphate occur between 562 and 784°C. For the phosphate sample investigated, the weight loss occurring in this range is about 7.0 %. The high value of CO₂ loss and the content of fuorine of the raw material used mean that the phosphate grains are constituted by carbonato-fluoapatite. This result is in agreement with the X-ray diffraction analysis (figure 1). The final weight loss given by GTA is about 11 mass % is in agreement with the value determined using batch experiment under oxygen atmosphere (figure 2). As it possible to observe, the DTA curve (figure 3) revealed three intensive endothermal effects. The first with a maximum at 400°C corresponds to the physical evaporation of water and volatile organic matter. The second between 700 and 800°C and the third from 820 to 940°C were assigned respectively to the decomposition of dolomite and calcium carbonate (calcite and dolomite). An endothermic peak at 915°C attributed to the decarbonatation of the raw phosphate, also observed by Blazy and Samama (19). However, in this study, this phenomenon is not clearly established.

In addition of DTA-TG, the Controlled Transformation Rate Thermal Analysis (CRTA) were

performed to get the weight loss of phosphate sample (sample mass: 500-1000 mg, heating rate: 10°C/min). In figure 4 we have reported the results obtained for the raw sample and those for the heated one at 780°C.

Theoretically, the sample calcined at 780°C does not present any appreciable weight loss up to this temperature. A straight line with a slope depending on the experimental condition must be obtained which indicating the heat speed of the apparatus. However, a weight loss is observed in the temperature range 500 to about 600°C which probably due to dehydratation of Ca(OH)₂ observed on the sample heated above 780°C.



Fig.4: Controlled transformation Rate Thermal Analysis (CRTA) curves of raw sample and sample heated at 780°C.

For the raw material, the weight loss observed between 200 and 500°C can be attributed to water and the volatile organic matter release. From 550 to 700°C, a linear increase of the weight loss is observed. At 700°C, an important weight loss occur followed by a new slow increase. According to the results of Kaljuvee (6), the decomposition of MgCO₃ occurs between 600 and 780°C and the decomposition of CaCO₃ takes place between 780°C and 900°C. From the forgoing, we attributed the first weight loss occurring at 620°C to the substituted CO₂ in the apatitic network, the CO₂ dolomitic was released at 700°C and the CO₂ of calcite was removed after 900°C.

III.1.3. Infrared spectra

The Infra-red measurements were also performed to describe some of the chemical changes observed. The infrared spectra of the raw material and samples heated at 240, 600, 780 and 940°C were recorded and bands have been assigned. The adsorption peaks at 564, 606, 960 and 1088 cm⁻¹ were assigned to PO₄ ³⁻ group (figure 5). This assignment of adsorption bands is in fair

agreement with the results reported by different authors (20-21). These bands were not affected by heat treatment.

However, for the materials heated above 780°C the additional bands observed at 866, 1426 and 1456 cm⁻¹ disappeared. These peaks assigned to the C-O vibration bands characterizing the carbonate-apatite (named francolite). Studying the infrared spectra of sedimentary phosphate rock, Brassens (22) reported similar results. Moreover, the author noted that the peak adsorption observed at 865 cm⁻¹ was attributed to the CO₂. According to Brassens's study, there are type of CO₂, $CO_{2\alpha}$ and $CO_{2\beta}$, in the francolite network related to the nature of substitution. The $CO_{2\alpha}$ is given off between 500 and 790°C whereas the $CO_{2\beta}$ releases between 800 and 1050°C.



Fig.5: IR spectra of phosphate particles calcined at different temperatures

The absorption band which appears at about 874 cm⁻¹ for the samples heated above 780°C can be attributed to the calcite which results from the action of gaseous CO₂ upon the formed CaO. Organic matter in phosphates shows absorptions in the range 2850-2920 cm⁻¹ which are assigned to C-H vibrations in CH₂ and CH₃. Occluded water gives two bands at 3500 cm⁻¹ and 1630 cm⁻¹ (δ_{OH}).

From the results obtained, it is reasonable to assume that the endothermic elimination of water and of volatile organic matter under argon atmosphere occurs below 500°C whereas the $(CO_{2\alpha})$ released from carbonate apatite appears at 620°C. The endothermic reaction of the dolomite decomposition occurs at 700°C and finally an endothermic peak of decarbonatation was observed up to 900°C.

III.2. Structural changes of phosphate ore

III.2.1. Evolution of the porous properties of phosphate during heat treatment

Absolute density, also called true density was measured for samples after heating at 240, 400, 550, 600, 780 and 940°C. The absolute density is obtained when the volume of Helium measured excludes the pores within the sample material. The percent porosity of solid can be calculated as follow : $Percent \ porosity = [1 - (\rho_b / \rho_a)] * 100$

Where ρ_b and ρ_a were the bulk and absolute density of the sample. These two density values were derivable from a mercury test. Contrary to the true density the bulk one includes the pores within the material. The phosphate ore used in this work presents a true density equal to 2.970 g.cm⁻³ and a percent porosity determined using mercury porosimetry equal to 31%.

Figure 6 shows that helium density pass through a minimum when temperature of calcination reaches 600°C. Our values are less than the data reported by Janikowski (23). The bulk density of different natural phosphate samples reported by the authors is in the range of 2.035 to 2.800 g.cm⁻³ whereas the absolute density is in the range of 3.16 to 4.70 g.cm⁻³. Any correlation was not found between density and surface area.



Fig.6: True density of phosphate fraction 125-200 µm (at various temperatures).

The decrease of the true density of samples after heating at different temperatures below 600°C, can be related to the removal of water and volatile organic compounds. In this region, when mass loss is occurring intensively, the material volume will change slightly involving the decrease of the ratio mass by volume. Up to 600°C, we assist to the densification phenomenon. According to Ben Ayed (14), the Fap densification began at 700°C. The decrease and the increase of the material density can be correlated to the dilatometric behavior.

The nitrogen adsorption and desorption isotherms for the raw material and the products after heating at 600 and 940°C were shown in figure7. All samples exhibit a type H3 isotherm based upon the classification of International Union of Pure Applied Chemistry (IUPAC). This hysteresis loop with a vertical adsorption branch at a medium pressure indicates the presence of pores which have narrow short opening. Moreover, at low relative pressure (p/p_0) less than 0.42 (below this value adsorption and desorption curve were superimposed), the slopes were different. These latter were correlated to the specific surface area which was calculated by the BET method. However pore size was calculated by the BJH method using the desorption isotherm.



Fig.7: Sieved fraction 125-200µm.: Adsorption/ desorption isotherms of phosphate ores before and after heat treatment at 600 and 940°C. (solid lines: adsorption; dotted line: desorption)

The specific surface area, the pore volume and the shrinkage % are most reliable indicators of the sintering event because their evolutions are linked to the mechanism of the sintering and also that these parameters are easily and reliably measured. This paragraph is focused on the effect of calcination temperature and chemical changes observed on the structural behavior of the phosphate ore.

Changes in S_{BET} , pore volume and the linear shrinkage (%) were listed in Table 2. The specific surface area starts to decline at 240°C and reach a minimum at 940 °C (figure 8). Many works are available in the literature on the effect of the calcination in the surface area reduction of hydroxyapatite powders (14-15-16-23). In most cases the reduction of specific surface area is correlated with the reduction of porosity and the densification (increasing of the absolute linear shrinkage %) like it is shown in table 2.

Temperature of	SBET	Pore Volume	Pore diameter	Shrinkage
calcination (°C)	(m ² .g ⁻¹)	(10 ⁻³ ml.g ⁻¹)	D_p (nm)	(%)
As- received	16.61	31.6	7.6	- 4.838
240	13.82	29.6	8.5	- 3.861
550	9.19	27.7	12.1	
600	7.82	25.0	12.7	- 2.648
940	0.81	2.3	6.9	- 0.030

Table 2: Porous properties of calcined samples

Studying the calcination and the sintering of calcium phosphate apatites with variable (Ca/P) atomic ratio, the authors (15-17) noted different domains of surface reduction versus temperature corresponding to different reaction rate. This suggests that the mechanism of loss of specific surface area, pore volume and densification may be changing with the temperature.

In all cases, the low surface decrease, observed below 500°C, corresponds to the removal of the matter according to the gaseous transfer and external diffusion. Above this temperature, a drastic decline of surface area attributed to the diffusion of matter between bounded grains. At higher temperature up to 780°C, the rate of surface area decline slowed down. The kinetic modeling of surface area reduction versus sintering or thermal decomposition temperature of solids was studied by several authors (14-17-24-26). To argue their conclusions about the surface area decrease, Raynaud (15) complete their study by a dilatometric investigation.

In this study, the linear shrinkage % was measured for the raw material and samples after heating at 240, 600, 780 and 940°C. The results are shown in figure 8 and table 2. The raw material expanded in the temperature range up to 1000°C. This phenomenon can be related to the high CO_2 content in phosphate rock. The calcium phosphate apatites have a thermal expansion coefficient ranging between 12.10^{-6} K⁻¹ and 16.10^{-6} K⁻¹. All samples except that heated at 940°C present a thermal expansion in the temperature range up to about 720°C. This is probably due to the removal of volatile organic matter and the dolomite decomposition. However, the shrinkage

began from about 720°C until 900°C. In this domain, similar behavior was already described in other synthetic calcium phosphate compounds. Especially, densification mechanism of synthetic fluorapatite occur in this temperature range. In the other hand, the surface area reduction was attributed to both particle coalescence and sintering. These results were confirmed by scanning electron microscopy observations.



Fig.8: Normalised surface area of phosphate samples after heat treatment (fraction size 125-200 μ m and 1 hour holding time of heat treatment).

III.2.2. The ESEM observations

The morphology of phosphate particles after different calcination treatments are presented in figure 9. It is shown that the shape of phosphate particles is not affected after heating at 600, 740 and 940 °C. The phosphate particles do to not disintegrate during heating.

According to the SEM photographs of raw phosphate rock, given by OSER et al. (27), the Turkey phosphate rock presents two parts, the dark gray one is defined as CaCO3. No distinguish parts were observed in the Tunisian phosphate investigated.

The microstructure observation (enlarged photographs) of calcined materials showed significant differences depending on the temperature of calcinations. Up to 780 °C, the microstructure was close to that of pure Fap (crystallites appear in a rod like form). At 940 °C (seen the enlarged photograph), the calcined particles have a homogeneous microstructure with an average grain size of about 1 μ m. According to Kaljuvee et al. (6) study, the optimum temperature interval for calcination of natural phosphorites is 850-950 °C and the recommended heating time not more than 5-10 minutes. Below 600 °C, samples presented more smooth surfaces with little



cracks and crystallites appear in a flake-like form.

Fig.9: ESEM micrographs of phosphate samples heated for 1 hour at: (a) Raw sample as received, (b) calcined at 600°C, (c) calcined at 740°C, (d) calcined at 940°C

When temperature increases the grains' growth becomes exaggerated according to the thermal expansion of Fap and the decrease of specific surface area can be attributed to the grain growth.

IV. CONCLUSIONS AND RECOMMENDATIONS

Detailed experimental analyses of chemical and physical changes of phosphate ore are presented. On the basis of the present study, the following conclusions can be drawn:

- The main mineral of phosphate particles investigated are Carbonate Fuorapatite, Fluorapatite, Calcite and Dolomite which are dispersed heterogeneously in the grain,
- The water of constitution and volatile matter release below 500°C whereas the CO₂ substituted in the apatitic lattice leaves off up to 620°C. In this temperature range, from room temperature until 600°C, the true density decreases and the grain expanses,
- The dolomite decomposition occurs at about 700°C and the calcite in phosphate decomposes above 900°C. In this domain, the densification occurs and the particles shrank,

- The decreases of the specific surface area and of the pore volume combined with the increasing of the shrinkage percentage confirms the sintering of the ore phosphate during the calcination,
- The ESEM observations reveal the rounding of particles below 600°C and the formation of necks up to this temperature.

More investigation concerning the reactivity of heated phosphate particles is required for better understanding of the influence of chemical and physical properties on the acidic phosphate rate leaching.

V. **R**EFERENCES

- 1. Processing and equipment for Beneficiation of Calcareous Phosphate Ores. Fr. pat., 2, 486, 924 (1982).
- 2. Beneficiation of Phosphate Ores. Fr. pat., 2, 554, 300 (1984).
- 3. A.Z.M. Abouzied, I.S. El Jallad, M.K. Orphy, Min. Sci. Eng. 12, 73-83 (1980).
- 4. D. Kumar, Chem. Eng. Technol., 52 (9), 736-740 (1980).
- 5. P. Becker, *Phosphate and phosphoric acid*, Marcel Dekker Inc, Chapter 2, Process review, 35-140 (1989).
- 6. T.B. Kaljuvee, R.O. Kuusik, M. Viederma, Int. J. Miner. Proc., 43, 113-121 (1995).
- 7. I. Zafar, M.M. Anwar, D.W. Pritchard, 1995, Int. J. Miner. Proc. 43, 123-131 (1995).
- 8. J.R. Lehr, S.S. Hsieh, Beneficiation of High Carbonate Ores, U.S. Pat. 4, 287, 053 (1981).
- 9. J. Fava, A. Lambert, J.P. Tognet, J.M.R. Lafosse, B.J.M. Robet, *Procédé d'enrichissement d'un minerai à gangue carbonatée, notamment d'un minerai de phosphate*, Fr. pat. Appl., 81, 20558 (1981).
- 10. P. Blazy, E.A. Jdid, C.R. Acad. Sci., Paris, (IIa) 321, 287-294 (1995).
- 11. A.V. Slack, *Phosphoric acid part II*, Marcel Dekker, INC, New York (1968).
- 12. A. Ababou, M. Bernache-Assollant, Heughebaert., Ann. Chim. Fr., 19, 165-175 (1994).
- 13. F. Ben Ayed, K. Bouaziz, K. Bouzouita, *Journal of European Ceramic Society*, 20, 1069-1076 (2000).
- 14. F. Ben Ayed, K. Bouaziz, K. Bouzouita, *Journal of Allows and Compounds*, 322, 238-245 (2001).
- 15. S. Raynaud, E. Champion, D. Bernache-Assolant, Biomaterials (23), 1073-1080 (2002).
- 16. A. Nzihou, S. Bailliez, High Temp. Mater. Proc., 21 (5), 281-295 (2002).
- 17. S. Bailliez, A. Nzihou, Chem. Eng. J., 98, 141-152 (2004).
- 18. D.E. Evangelos, T.C. Vaimakis, E.M. Papamicheal, *Journal of colloid and interface Science*, 201, 164-171 (1998).
- 19. P. Blazy, J.C. Samama, C.R. Acad. Sci., Paris, 333, 271-276 (2001).
- 20. C.B. Baddiel, E.E. Berry, Spectrochimica Acta, 22, 1407-1416 (1966).
- 21. V.M. Bhatnagar, Bull. Soc. Chim., Fr., 1771-1773 (1968).

- 22. A. Brassens, C.R. Acad. Sci., Paris., 280 (C), 879-881 (1975).
- 23. M. Janikowski, N. Robinson, W.F. Sheldrick, *Theory and Experimental technique, Fert. Soc.*, 81, 3-51 (1964).
- 24. W.G. Schaffer, C.Z. Morgan, J.N. Wilson, J. Phys. Chem., 61, 714-722 (1975).
- 25. D. Nicholson, Trans. Faraday Soc., 61-509, 990-998 (1965).
- 26. R.M. German, Z.A. Munir, J. Am. Ceram. Soc., 59, 379-84 (1976).
- 27. A.K. Özer, M. Gülabo lu, S. Bayrakçeken, Ind. Eng. Chem. Res. 39, 679-683 (2000).
- 28. F. Ben Brahim, A. Mgaidi, M. El Maoui, Can. J. Chem. Eng. 75, 759-764 (1997).
- 29. F. Peters, K. Schwarz, M. Epple, Thermochimica Acta., 36, 131-138 (2000).