

Role of vapor mass transfer in flow coating of colloidal dispersions in the evaporative regime

Charles Loussert, Frédéric Doumenc, Jean-Baptiste Salmon, Vadim Nikolayev,

Beatrice Guerrier

▶ To cite this version:

Charles Loussert, Frédéric Doumenc, Jean-Baptiste Salmon, Vadim Nikolayev, Beatrice Guerrier. Role of vapor mass transfer in flow coating of colloidal dispersions in the evaporative regime. Langmuir, 2017, 33 (49), pp.14078-14086. 10.1021/acs.langmuir.7b03297. hal-01653411v2

HAL Id: hal-01653411 https://hal.science/hal-01653411v2

Submitted on 27 Jul 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Role of vapor mass transfer in flow coating of colloidal dispersions in the evaporative regime

Charles Loussert,[†] Frédéric Doumenc,^{*,‡,¶} Jean-Baptiste Salmon,[†] Vadim S. Nikolayev,[§] and Béatrice Guerrier[‡]

†CNRS, Solvay, LOF, UMR 5258, Univ. Bordeaux, F-33600 Pessac, France

‡Laboratoire FAST, Univ. Paris-Sud, CNRS, Université Paris-Saclay, F-91405, Orsay,

France

¶Sorbonne Universités, UPMC Univ. Paris 06, UFR 919, 75005, Paris, France

§Service de Physique de l'État Condensé, CNRS, Université Paris-Saclay, CEA Saclay,

91191 Gif-Sur-Yvette, France

E-mail: doumenc@fast.u-psud.fr Phone: +33 1 69 15 37 31. Fax: +33 1 69 15 80 60

Abstract

In flow-coating processes at low substrate velocity, solvent evaporation occurs during the film withdrawal and the coating process yields directly a dry deposit. In this regime, often referred to as the evaporative regime, several works performed on blade-coating-like configurations have reported a deposit thickness h_d proportional to the inverse of the substrate velocity V. Such a scaling can be easily derived from simple mass conservation laws, assuming that evaporation occurs on a constant distance, referred to as the evaporation length, noted L_{ev} in the present paper and of the order of the meniscus size. However the case of colloidal dispersions deserves further attention. Indeed, the coating flow leads to a wet film of densely-packed colloids before the formation of the dry deposit. This specific feature is related to the porous nature of the dry deposit, which can thus remain wet when capillary forces are strong enough to prevent the receding of the solvent through the pores of the film (the so-called pore-emptying). The length of this wet film may be possibly much larger than the meniscus size, therefore modifying the solvent evaporation rate, as well as the scaling $h_d \sim 1/V$.

This result was suggested recently by different groups using basic modeling and assuming for simplicity an uniform evaporation rate over the wet film. In this article, we go a step further and investigate the effect of multi-dimensional vapor mass transfer in the gas phase on L_{ev} and h_d in the specific case of colloidal dispersions. Using simplified models, we first provide analytical expressions in asymptotic cases corresponding to 1D or 2D diffusive vapor transport. These theoretical investigations then led us to show that L_{ev} is independent of the evaporation rate amplitude, and roughly independent of its spatial distribution. Conversely, h_d strongly depends on the characteristics of vapor mass transfer in the gas phase, and different scaling laws are obtained for the 1D or the 2D case. These theoretical findings are finally tested by comparison with experimental results supporting our theoretical simplified approach.

Introduction

Flow coating techniques, such as knife-coating, blade-coating, or doctor-blade, have now become essential processes to coat continuously functional layers on solid substrates starting from dilute inks, and for applications ranging from organic electronics to optical coatings. $^{1\!-\!3}$

Figure 1 shows schematically a typical bladecoating setup for the specific case of a colloidal dispersion. A liquid film is drawn out of a liquid reservoir confined between a fixed blade and a moving substrate at a velocity V. The fine



Figure 1: (a) Perspective view of a blade coating process in the evaporative regime. A dry film is continuously withdrawn from the reservoir by the substrate moving at a velocity V. (b) Side view evidencing the specific case of a colloidal dispersion. A solvent-saturated film is drawn out of a liquid reservoir and maintained by capillary forces between the blade and the moving substrate. Solidification occurs at a distance $x = L_m$, followed by a pore-emptying front at $x = L_{ev}$; arrows show schematically the local evaporative flux v_{ev} (m/s, see text).

description of such flow-coating processes, and particularly the prediction of the final deposit thickness h_d as a function of the process parameters and physico-chemical features of the ink, is still a major issue. Many works previously reported in the literature have clearly identified two regimes for such flow-coating-like processes depending of the coating speed V.^{4–6} At high V, a liquid film is drawn out of the reservoir and dries later on. In this regime, often referred to as the Landau-Levich regime, drying and coating are separated in time, and the height of the liquid film results from a balance between surface tension and viscous friction induced by the substrate motion.^{7,8} At low V, solvent evaporation cannot be neglected during the film with-drawal, and the coating process yields directly a dry deposit: this is the evaporative regime.

In the last few years, many groups performed experimental and theoretical investigations of this evaporative regime for dilute inks ranging from colloidal dispersions^{5,9–14} to solutions of polymers and small molecules.^{4,14–16} Despite the wide complexity of the process and the wide variety of reported phenomena, including streaks or stripes formation,^{17–19} cracks and delamination²⁰ to name a few, many of the above cited works reported the following scaling:

$$h_d \propto \frac{\varphi_0}{V},$$
 (1)

for the dry deposit thickness h_d as a function of the substrate velocity V and the reservoir particle volume fraction φ_0 . Such a robust scaling suggests a common explanation based on mass conservation arguments only. Assuming that coatings are uniform along their width (invariance to translation along the y-direction, see Figure 1), simple mass balances for a binary mixture (volatile solvent + non-volatile solute) provide the following relation for the deposit thickness:⁹

$$h_d = \frac{\varphi_0}{\varphi_c (1 - \varphi_0)} \frac{Q_{ev}}{V},\tag{2}$$

where φ_0 and φ_c are the volume fractions of the non-volatile solute in the bulk and in the dry film, respectively, and Q_{ev} (m²/s) is the solvent volume rate of evaporation per unit of width W. Eq (2) points out the important role played by the solvent mass transfer in the vapor phase to get a quantitative prediction of Q_{ev} and thus h_d .

One recovers the scaling reported experimentally and given by eq (1) in the case of a dilute ink $\varphi_0 \ll \varphi_c$ and assuming that Q_{ev} does not depend on φ_0 , φ_c and V. This behavior was for instance observed in previous experiments performed in dip-coating-like configurations.^{4,5,14} Q_{ev} was shown to depend only on drying air characteristics (temperature, humidity,...) and evaporation occurred over a constant length of the order of the meniscus size L_m .¹⁴

Recently, several groups suggested that the case of colloidal dispersions is expected to be more intricate than the case of molecular solutes, and a significant departure from scaling (1) was even reported by Joshi and Gilchrist.²¹ Indeed, the coating flow first leads to a wet film of densely-packed colloids, which ultimately dries later on at a distance $L_{ev} \geq L_m$ from the static blade, see Figure 1(b). This specific feature is related to the porous nature of the dry deposit, which can thus remain wet when capillary forces are strong enough to prevent the receding of the solvent through the pores of the coating, the so-called *pore*emptying.^{22,23} In the case of colloidal dispersions, the evaporation length L_{ev} now becomes a function of the process parameters, and can modify the solvent volume rate of evaporation Q_{ev} , as, in some cases, L_{ev} can be much larger than the meniscus length L_m .

Jung and Ahn²⁴ along with Joshi and Gilchrist²¹ have considered Darcy's law to model solvent transport in the wet porous film and have assumed the uniformity of evaporation velocity v_{ev} along the film, where v_{ev} (m/s) is the local volume evaporation flux per unit of surface. This results in the expression

$$Q_{ev} \simeq v_{ev} L_{ev}.$$
 (3)

They further derived the following scaling

$$h_d \propto \frac{\varphi_0^2 \, v_{ev}}{V^2},\tag{4}$$

for dilute dispersions $\varphi_0 \ll \varphi_c$, assuming a criterion for estimating the pore-emptying front from the liquid pore pressure. The latter scaling fits correctly the data sets reported by Joshi and Gilchrist.²¹ However it fails to describe the experiments of refs^{5,11,14} which support scaling (1) for colloidal dispersions, as well as measurements of the evaporation length L_{ev} reported by Jung and Ahn.²⁴ However, in the theories^{21,24} evaporation is assumed to be dominated by the wet film only, i.e. $L_{ev} \gg L_m$, and the contribution of the meniscus to the overall evaporation rate Q_{ev} is neglected. In a recent study,²⁵ we included this contribution, still assuming uniform evaporation as above, and we recovered scalings (1) and (4) as two asymptotic limits of the same model, the latter corresponding to $L_{ev} \gg L_m$, the former to $L_{ev} \simeq L_m$. We further showed that this continuous model agrees with the measurements of L_{ev} performed by Jung and Ahn,²⁴ as their experiments were performed in the transition regime between scalings (1) and (4).

It is important to underline that all these models are based on the assumption of a uniform evaporation velocity v_{ev} over the meniscus and the wet film. Indeed, eq (3) implicitly contains the assumption of 1D vapor mass transfer in the gas phase. Real configurations, such as the experimental case described in Figure 1, are expected to yield multi-dimensional mass transfer (2D or even 3D), with spatial variation of v_{ev} all along the evaporation region. Indeed, the function $Q_{ev}(L_{ev})$ should depend on the mechanisms which drive the vapor transport in the gas phase: free or forced convection, laminar or turbulent flow, etc. For instance, eq (3)would be recovered for turbulent free convection, from which proportionality between L_{ev} and Q_{ev} is expected, as derived by estimating mass transfer coefficients from empirical correlations (as available for instance in the book,²⁶ and by using analogy between heat and mass transfer). In case of 3D vapor diffusion in quiescent air from a rectangular solvent puddle, a logarithmic dependence of Q_{ev} on the evaporation length is expected (cf. section Theory for more details).

The main objective of the present article is to investigate the effect of multi-dimensional mass transfer in the gas phase on the evaporation length L_{ev} and the deposit thickness h_d , for blade-coating of colloidal dispersions in the evaporative regime.

Using simplified models, we first provide analytical expressions of L_{ev} and h_d in asymptotic cases corresponding to 1D or 2D vapor transport. These theoretical investigations help us to show that L_{ev} is independent of the evaporation intensity, and nearly independent of the mass transfer geometry, 1D or 2D. Conversely, the deposit thickness strongly depends on vapor mass transfer in the gas phase, and different scaling laws are obtained for the 1D and 2D cases.

We finally compare these theoretical predictions to experimental results obtained with a custom-made blade-coating setup for a wide range of parameters (concentration, colloid diameter, coating speed) and to data previously reported in the literature.

Theory

Building a model yielding an accurate description of a flow-coating-like process for colloidal dispersions in the evaporative regime is a hard Indeed, such a model should include task. a description of vapor mass transfer in the gas phase. Depending on the specific physical mechanism occurring in a given coating device, one should address a 3D diffusion problem if air is motionless, or a problem involving Navier-Stokes equations if the convection is relevant. Then this gas phase model must be coupled to governing equations of the liquid solvent flow within the meniscus and the wet film. Such an approach to our opinion is too complex and its feasibility currently questionable.

Regarding mass transfer in the gas phase, we use a simplified approach, based on analytical solutions of a 2D diffusion problem with a prescribed and constant boundary layer thickness Λ . We show in the next section that this 2D model qualitatively reproduces characteristic behaviour of more complex mass transfer mechanisms, from 3D diffusive transport to turbulent free convection. Therefore our approach, although simplified, is expected to provide physically relevant scaling laws for L_{ev} and h_d .

Mass transfer in the gas phase

The 2D geometry on which our theoretical analysis is based is shown in Figure 1(b). Furthermore, we assume the existence of a boundary layer of constant thickness Λ much larger than the height of the liquid film. We thus neglect the liquid height in the gas phase description and we use a simple rectangular geometry shown in Figure 2, with $0 < x < \infty$ and $0 < z < \Lambda$. To mimic the experimental geometry where a vertical wall blocks the vapor diffusion, we assume impermeability at the boundary x = 0. The wet film extends from x = 0 to $x = L_{ev}$, at z = 0.

The 2D vapor concentration field c(x, z) in the gas domain, shown in Figure 2, satisfies the Laplace equation $\partial_{xx}c + \partial_{zz}c = 0$ with the boundary conditions:

- x = 0 and $0 < z < \Lambda : \partial_x c = 0$; (5)
- z = 0 and $0 < x < L_{ev} : c = c_{sat}$; (6)
- z = 0 and $x > L_{ev} : \partial_z c = 0$; (7)
- $z = \Lambda$ and $x > 0 : c = c_{\infty}$.; (8)

with c_{sat} the saturated vapor concentration at the liquid/gas interface (kg/m³), and c_{∞} the ambient vapor concentration far from the interface (kg/m³).

The evaporation velocity in this wet film region $(0 < x < L_{ev})$ is given by the Fick's law $v_{ev} = -D_v/\rho \partial_z c$, where $D_v (m^2/s)$ is the vapor diffusivity in air and ρ the liquid solvent density (kg/m³). The volume rate of liquid which evaporates between the origin and any abscissa x reads finally $Q_{ev}(x) = \int_0^x v_{ev}(\xi) d\xi$.

This problem is very similar to the one solved by Deegan *et al* for the coffee stain effect.²⁷ These authors considered a 3D axi-symmetric geometry (liquid droplet), while we consider a 2D Cartesian geometry (liquid film). In the latter case, the problem in the upper half-space $(\Lambda \to \infty)$ has no solution in the steady state (see section 2.2 of ref²⁸ for a demonstration). However a solution exists when the boundary condition (8) is prescribed at a finite height Λ .

The analytical solution of the Laplace equation with boundary conditions (5-8) has been obtained with a method of conformal transform. Calculations are detailed in Supporting Information (SI). The resulting evaporation ve-



Figure 2: Gas domain. Solid lines represent isovalues of the concentration field c(x, z) and arrows the diffusive flux.

locity v_{ev} is

$$v_{ev}(x) = \frac{\pi\beta}{2\Lambda K(k)} \left\{ \left[\exp\left(\frac{\pi(L_{ev} + x)}{\Lambda}\right) - 1 \right] \left[\exp\left(-\frac{\pi(L_{ev} + x)}{\Lambda}\right) - \exp\left(-\frac{2\pi L_{ev}}{\Lambda}\right) \right] \right\}^{-1/2},$$
(9)

where $\beta = D_v (c_{sat} - c_{\infty})/\rho$, $k = \exp\left(-\frac{\pi L_{ev}}{\Lambda}\right)$ and K(k) is the complete elliptic integral of the first kind.

 v_{ev} and its integral $Q_{ev}(L_{ev})$ are plotted in Figure 3. Depending on the value of the ratio Λ/L_{ev} , there are two asymptotic limits:

• $\Lambda/L_{ev} \ll 1$. The evaporation velocity is constant, except at the very end of the film, over a distance of the order of Λ . For the inner part of the film, such that $x \lesssim L_{ev} - \Lambda$, the diffusion problem reduces to the 1D case with a uniform evaporation velocity, and $v_{ev} \simeq \beta/\Lambda$, where

$$\beta = D_v c_{sat} \left(1 - H_r \right) / \rho, \qquad (10)$$

with $H_r = c_{\infty}/c_{sat}$ the ambient relative humidity. The evaporation flux corresponding to this part of the film is thus proportional to the ratio $(L_{ev} - \Lambda)/\Lambda \simeq L_{ev}/\Lambda$. It therefore diverges as $\Lambda/L_{ev} \rightarrow 0$.

Using eqs (S16-S17) of the SI, it can be shown that the evaporation flux corresponding to the very small zone at the tip of the film (of the order of $L_{ev} - \Lambda \lesssim x < L_{ev}$) remains finite as $\Lambda/L_{ev} \to 0$ and can be neglected. The total evaporation flux is therefore

$$Q_{ev}(L_{ev}) \simeq \beta \frac{L_{ev}}{\Lambda}.$$
 (11)

• $\Lambda/L_{ev} \gg 1$. The diffusion problem is fully 2D. The total evaporation flux is now much less sensitive to Λ/L_{ev} , since it is inversely proportional to its logarithm:

$$Q_{ev}(L_{ev}) \simeq \frac{\pi\beta}{2\ln[8\Lambda/(\pi L_{ev})]}.$$
 (12)

These two asymptotic regimes thus differ for two main reasons: (1) the local evaporation velocity v_{ev} is nearly uniform in the 1D case, but varies all along the evaporation length in the 2D case; (2) the total evaporation flux is proportional to the evaporation length L_{ev} in the 1D case, while it depends weakly on L_{ev} in the 2D case.

It is worth noting that our simplified model qualitatively reproduces limit cases that would be expected with more detailed descriptions of vapor mass transfer. Indeed, eqs (11) and (3) both exhibit proportionality between L_{ev} and Q_{ev} . This strong dependence of Q_{ev} on L_{ev} may represent turbulent free convection as stated in the introduction.

A weak logarithmic dependence similar to eq (12) may be obtained in 3D diffusion configuration. Indeed 3D vapor diffusion in quiescent air from a rectangular solvent puddle of size $L_{ev} \times W$, a geometry close to the case depicted in Figure 1, would give a volume evaporation rate²⁶

$$Q_{ev} = \frac{\pi\beta}{\ln(4W/L_{ev})},\tag{13}$$

with the assumption $L_{ev} \ll W$ and using equivalence between heat and mass diffusion.

In the following, we investigate the consequences of the two above asymptotic cases (1D and 2D) on the scaling laws for the evaporation length L_{ev} and the deposit thickness h_d .



Figure 3: (a) local evaporation velocity v_{ev} as a function of x/L_{ev} for different values of Λ/L_{ev} [from eq (9)]. (b) total evaporation volume rate Q_{ev} as a function of Λ/L_{ev} ; the general case (black solid line) corresponds to numerical integration of eq (9).

Governing equations in the liquid phase

The global and particle mass balances provide a relation between the deposit thickness h_d and the evaporation flux $Q_{ev}(L_{ev})$:^{4,9,25}

$$h_d = \frac{\varphi_0}{\varphi_c(1-\varphi_0)} \frac{Q_{ev}(L_{ev})}{V}.$$
 (14)

Eq (14) contains an implicit relation between two unknowns, the deposit thickness h_d and the evaporation length L_{ev}^{1} . A second relation can be derived from the Darcy's law and the solvent mass conservation in the wet film region (cf. Figure 1):

$$\partial_x p_{liq} = -\frac{\eta_0}{k(\varphi_c)} (1 - \varphi_c) (u - V), \qquad (15)$$

$$h_d(1-\varphi_c)\partial_x u = -v_{ev}(x), \qquad (16)$$

where p_{liq} , η_0 and u are the solvent pressure, viscosity and velocity, respectively, φ_c is the closepacking particle volume fraction. We used the Koseny-Carman equation²⁹ for estimating the permeability of the densely-packed wet coating

$$k(\varphi_c) = \frac{2a^2 (1 - \varphi_c)^3}{90 \,\varphi_c^2} \,, \tag{17}$$

where a is the particle radius. Eq (17) is empirical for random packings; it also predicts the permeability of periodic arrays of spheres with an error less than 30 % at high volume fraction.³⁰

Since L_{ev} is unknown, the resolution of eqs (15-16) requires three boundary conditions. A first condition is obtained at $x = L_m$ assuming that the capillary pressure in the wet film, fixed by the pore size of the order of the particle radius a, is much larger than the capillary pressure in the meniscus of macroscopic curvature C_0 . We thus make the approximation

$$p_{liq}(L_m) - p_{atm} = 0,$$
 (18)

¹Note that we derived previously in our earlier work a slightly different relation $[h_d V(\varphi_c - \varphi_0)] = \varphi_0 Q_{ev}$ as we developed deliberately a continuous model solvent+colloids. Both relations however are equivalent for dilute dispersions $\varphi_0 \ll \varphi_c$.

where the meniscus length L_m is assumed to be constant, and equal to its value when there is no flow (this last assumption has been validated by numerical simulations, see ref²⁵). Two other conditions are obtained at $x = L_{ev}$. Assuming a negligible flux of water into the dry film yields

$$u(L_{ev}) - V = 0$$
, (19)

and pore-emptying occurs for a critical capillary pressure given by

$$p_{liq}(L_{ev}) - p_{atm} = -\kappa \gamma/a.$$
 (20)

For monodisperse spheres, we use

$$\kappa = 3\varphi_c/(1-\varphi_c),\tag{21}$$

as suggested in ref.³¹

Solving eqs (15-16) with boundary conditions (18-20) yields

$$h_d = \frac{a\eta_0}{\kappa\gamma k} \left[(L_{ev} - L_m)Q_{ev}(L_{ev}) - \int_{L_m}^{L_{ev}} Q_{ev}(x)dx \right].$$
(22)

We introduce now the dimensionless quantities $\tilde{x} = x/L$, $\tilde{L}_m = L_m/L$, $\tilde{L}_{ev} = L_{ev}/L$, $\tilde{\Lambda} = \Lambda/L$, $\tilde{h}_d = h_d/h$ and $\tilde{Q}_{ev} = Q_{ev}/Q$. The scales L, h and Q are defined by taking as a reference the case corresponding to $L_{ev} = L_m$. We thus get $L = L_m$, $h = \varphi_0 Q/[\varphi_c(1 - \varphi_0)V]$, and $Q = \int_0^{L_m} v_{ev}(x) dx$ where L_m has been substituted to L_{ev} in the expression of $v_{ev}(x)$ in eq (9).

Using eqs (14) and (22) to eliminate h_d and turning to dimensionless variables, we get the equation to be solved to get \tilde{L}_{ev} :

$$\tilde{L}_{ev} - \frac{1}{\tilde{Q}_{ev}(\tilde{L}_{ev})} \int_{1}^{\tilde{L}_{ev}} \tilde{Q}_{ev}(\tilde{x}) d\tilde{x} = 1 + \mathcal{M},$$
(23)

where

$$\mathcal{M} = \frac{\varphi_0}{\varphi_c(1-\varphi_0)} \frac{\kappa \gamma k}{V \eta_0 a L_m} \\ = \frac{\varphi_0}{1-\varphi_0} \frac{\gamma/\eta_0}{V} \frac{2a}{L_m} f(\varphi_c) \quad (24)$$

and $f(\varphi_c) = (1 - \varphi_c)^2/(30 \varphi_c^2)$. The dimensionless number \mathcal{M} compares the pore pressure at pore-opening $(\kappa \gamma/a)$ to the scale of the evaporation-induced pressure drop in a wet film of length L_m .²⁵ \mathcal{M} depends on the process geometry, dispersion properties and substrate velocity but not on the vapor mass transfer in the gas phase. Thus it may be easily estimated for a given configuration. As seen in the experimental results, it varies on several orders of magnitude in our experiments.

We see from eq (23) that L_{ev} does not depend on evaporation intensity, but only on the shape of the function $\tilde{Q}_{ev}(x)$ [indeed, multiplying $\tilde{Q}_{ev}(x)$ by a constant has no effect on eq (23)]. The reason is that increasing the overall evaporation rate increases in the same proportion the deposit thickness and the liquid flow rate through the wet film. These two effects compensate each other, and the pressure drop in the wet film is unchanged [see Eqs (15)-(16)].

Eq (23) can be solved numerically to get \tilde{L}_{ev} . Once \tilde{L}_{ev} is known, the deposit thickness \tilde{h}_d is obtained from the dimensionless version of eq (14):

$$\tilde{h}_d = \tilde{Q}_{ev}(\tilde{L}_{ev}). \tag{25}$$

Asymptotic regimes

We first examine simplifications of eq (23) for the 1D and 2D cases.

• $\tilde{\Lambda}/\tilde{L}_{ev} \ll 1$ (1D case). From eq (9), $Q_{ev}(x) \simeq \beta x/\Lambda$. Eq (23) reduces to a second degree algebraic equation whose solution is

$$\tilde{L}_{ev} \simeq (1 + \mathcal{M}) + \sqrt{(1 + \mathcal{M})^2 - 1}.$$
 (26)

This is the solution already found in ref.²⁵

• $\tilde{\Lambda}/\tilde{L}_{ev} \gg 1$ (2D case). The integration of eq (9) yields

$$Q_{ev}(x) \simeq \beta \frac{\arcsin(x/L_{ev})}{\ln\left[8\Lambda/(\pi L_{ev})\right]}.$$
 (27)

Plugging eq (27) into eq (23) provides an

equation for
$$\tilde{L}_{ev}$$
:
 $\sqrt{\tilde{L}_{ev}^2 - 1} + \arcsin\left(1/\tilde{L}_{ev}\right) \simeq \frac{\pi}{2}(1 + \mathcal{M}).$
(28)

Table 1 summarizes the analytical expressions of \tilde{L}_{ev} corresponding to the four asymptotic cases obtained by combining eq (26) and eq (28) with additional assumptions $\mathcal{M} \ll 1$ or $\mathcal{M} \gg 1$. There is no difference between 1D and 2D cases for $\mathcal{M} \ll 1$. For $\mathcal{M} \gg 1$, \tilde{L}_{ev} is proportional to \mathcal{M} in both cases, and numerical prefactors differ only by 20% (for a confirmation, cf. solid and dashed lines in Figure 5(b), in the section dedicated to the comparison with experimental results).

These results lead to the following conclusions about the evaporation length. We already pointed out that evaporation intensity has no effect on \tilde{L}_{ev} ; we see now that \tilde{L}_{ev} is also weakly sensitive to the distribution of evaporation velocity along the wet film. In practice, the simple eq (26), although obtained in 1D, provides a reasonable estimate of \tilde{L}_{ev} when applied to a 2D problem.

Table 1: Analytical expressions of the dimensionless evaporation length $\tilde{L}_{ev} = L_{ev}/L_m$ for all asymptotic cases.

	$\Lambda/L_{ev} \ll 1$	$\Lambda/L_{ev} \gg 1$
	(1D case)	(2D case)
$\mathcal{M}\ll 1$	$\tilde{L}_{ev} = 1$	$\tilde{L}_{ev} = 1$
$\mathcal{M} \gg 1$	$\tilde{L}_{ev} = 2 \mathcal{M}$	$\tilde{L}_{ev} = \frac{\pi}{2} \mathcal{M} \simeq 1.6 \mathcal{M}$

Analytical expressions of h_d deduced from eq (25) are reported in Table 2 for all asymptotic cases. Scaling (4) (deposit thickness varying as $1/V^2$) is recovered for the 1D case $(\Lambda/L_{ev} \ll 1)$ at $\mathcal{M} \gg 1$. It corresponds to the proportionality between L_{ev} and Q_{ev} . In all other situations, a scaling more or less consistent with eq (1) (deposit thickness varying as 1/V) is recovered. Eq (1) is obtained for $\mathcal{M} \ll 1$. For the 2D case $(\Lambda/L_{ev} \gg 1)$ at $\mathcal{M} \gg 1$, h_d weakly depends on the terms under the logarithm, and their effect can hardly be detected experimentally. So for this case too, scaling (1) is expected in experiments. Particle size affects the deposit thickness in the case $\mathcal{M} \gg 1$ only. The dependence is significant in the 1D case (proportionality) but small in the 2D case (logarithmic term).

As a conclusion on the role of vapor mass transfer in the evaporative regime, these asymptotic models show that, unlike L_{ev} , the behavior of h_d depends on the regime occurring in the gas phase.

Experimental results

Experiments

To check the validity of the above theoretical scalings, we developed a blade-coating setup. We measured both L_{ev} and h_d for a wide range of coating speeds (V) and for different model colloidal dispersions, more precisely monodisperse charge-stabilized latex nanoparticles of different sizes and volume fractions (ThermoFisher and Sigma Aldrich Latex beads (PS), dilution with deionised MilliQTM water), see Table 3. All our experiments were performed at room temperature $T = 19.5 \pm 1^{\circ}$ C, and for external relative humidities H_r ranging from 35% to 60%. Eq (10) gives $\beta \simeq$ $(2.3 \pm 0.7) \times 10^{-10} \text{ m}^2.\text{s}^{-1}$, using $D_v = 2.5 \times 10^{-10} \text{ m}^2.\text{s}^{-1}$ $10^{-5} \text{ m}^2.\text{s}^{-1}$ and $\rho = 997 \text{ kg}.\text{m}^{-3}$. c_{sat} is derived from the ideal gas law with the water saturated vapor pressure $P_{vs} = 2300$ Pa at 19.5°C.

Figure 4(a) shows schematically our experimental setup. It consists in a microscope slab (thickness $\simeq 170 \ \mu m$) glued on a thicker glass slab (thickness $\simeq 1 \ mm$) for mechanical stability and fixed to a first translation stage along z-axis (labeled 1 on Figure 4) to control the reservoir height *H*. Indeed, this stage is used to confine a small amount of colloidal dispersions (1 m ℓ) between the blade and a glass substrate holded on another translation motorized stage moving along x-axis at speed *V* (labeled 2 on Figure 4, Märzhäuser Wetzlar). This motorized stage is itself mounted on another motorized translation stage along x-axis supporting the blade setup (labeled 3 on Figure 4) which

Table 2: Analytical expression of deposit thickness h_d for all asymptotic cases.

	$\Lambda/L_{ev}\ll 1~(ext{1D case})$	$\Lambda/L_{ev}\gg 1~(ext{2D case})$
$\mathcal{M}\ll 1$	$h_d = rac{arphi_0}{arphi_c(1-arphi_0)} rac{eta}{V} rac{L_m}{\Lambda}$	$h_d = rac{arphi_0}{arphi_c(1-arphi_0)} rac{eta}{V} rac{\pi}{2\ln\left[rac{8\Lambda}{\pi L_m} ight]}$
$\mathcal{M} \gg 1$	$h_d = 2a \frac{\varphi_0^2}{\varphi_c(1-\varphi_0)^2} \frac{\beta}{V^2} \frac{\gamma f(\varphi_c)}{\eta_0 \Lambda}$	$h_d = \frac{\varphi_0}{\varphi_c(1-\varphi_0)} \frac{\beta}{V} \frac{\pi}{2\ln\left[\frac{8\Lambda}{\pi^2} \left(a \frac{\varphi_0}{1-\varphi_0} \frac{\gamma/\eta_0}{V} f(\varphi_c)\right)^{-1}\right]}$

is fixed on an inverted microscope (Olympus, IX71). This original configuration allows us to monitor the coating process *in-situ* with the accuracy of bright field microscopy, and all along the coating by moving stage 3 over its translation range (50 mm).

For each experiment, we proceed as follows. We first clean the glass substrate (width =50 mm, length = 75 mm and thickness = 1 mm) using a *Piranha* treatment (20 minutes in a 50/50 vol. sulfuric acid/hydrogen peroxide solution, storage in MilliQ water after rinse) to ensure reproducible hydrophilic properties. We then confine a small volume of a colloidal dispersion $(1 \text{ m}\ell)$ as shown schematically in Figure 4, and a static meniscus of typical size $L_m \approx 100 \ \mu \text{m}$ is formed for $H = 500 \ \mu \text{m}$ all along the width W of the substrate. The typical angle that forms the blade with the glass substrate is of a few degrees, the thickness of the coating blade is 170 μ m, and its width is 40 mm. We then apply a constant speed $V = 500 \ \mu m/s$ to deposit a first coating on a distance ≈ 5 mm in order to avoid transient and edge effects (pining of the line for instance), and we then apply a constant V to coat the remaining blade, typically on a length ≈ 35 mm. We then monitor the steady coating process using a 1.25X objective (Olympus) on a sCMOS camera (OrcaFlash, Hamamatsu) with a field of view of $1.3 \times 1.8 \text{ mm}^2$. We finally use stage 3 (synchronised with the image acquisition) to acquire composite images over a wider field of view, typically $5.2 \times 1.8 \text{ mm}^2$.

Figure 4(b) shows a typical example of such an extended image for set # 3 listed in Table 3 $(V = 5 \ \mu m/s)$. The transition from the wet film to the the dry coating occurs at a distance

 $L_{ev} = 2100 \pm 300 \ \mu \text{m}$ in this case, as easily observed using the change of refractive index owing to the invasion of the pores by air. In some conditions, the coatings display regular stripes (with typical wavelength $300 \pm 20 \ \mu m$) which actually correspond to modulations of the deposit thickness of the order of a few μ m, see later. After full coating, the mean final thickness h_d is estimated using a mechanical stylus profilometer (Dektak Veeco). To estimate correctly h_d , we measured the coating thickness in-between two parallel scratches separated by $\approx 1 \text{ mm}$ performed on the coating in the x direction. For undulating conditions, h_d corresponds to the mean thickness, and the typical undulations are of the order of 6 \pm 1.5 μ m, of the order of $15 - 20\% h_d$.

To estimate the evaporation rate Q_{ev} in our configuration for different L_{ev} , we proceed as follows. We glue different glass pieces to form a rectangular tank of width 50 mm, depth 1 mm, and of different lengths L_{ev} ranging from 5 to 10 mm. We then fill the tank to the brim with pure water to mimic the conditions of bladecoating shown in Figure 4(b). The whole setup is then placed on a precision balance, and we record the temporal evolution of its mass over typically 1 hour as well as the external relative humidity and room temperature to further estimate β . Q_{ev} is finally estimated from the temporal derivative of such data, and typical uncertainties are of the order of $\simeq 10\%$.

To estimate the colloid volume fraction φ_c , we acquired top images of the coatings using scanning electron microscopy (SEM, Hitachi TM3030), see Supporting Information for a typical SEM image. We then constructed pair correlation functions g(r) from such images, and extracted the surface fraction occupied by the colloids from the first peak of g(r), see ref³² for details. Assuming the isotropy of the densely-packed colloidal assembly, we finally estimate $\varphi_c = 0.7 \pm 0.02$ for different experimental conditions.



Figure 4: (a) Schematic cross-section of our custom-made blade coating setup mounted on a microscope. The all coating setup is mounted on stage 3 which makes it possible to visualize the film during the coating process at different locations and with the accuracy of optical microscopy. The inset shows schematically a perspective view of the setup. (b) Typical extended image recorded using the setup shown in (a), $L_{ev} = 2100 \pm 300 \ \mu \text{m}$.

In the next section, we include in our analysis measurements of close-packed region length from Jung and Ahn²⁴ and Joshi and Gilchrist.²¹ These data were obtained in the following way. Jung and Ahn used a vertical plate immersed in a dilute dispersion of silica particles in ethanol. The plate is immobile, and the relative motion of the contact line is due to solvent evaporation from the bath (the substrate relative velocity is then equal to the mean evaporation velocity). The meniscus length reads $L_m = \sqrt{2}\ell_c$, where ℓ_c is the solvent capillary length.

Joshi and Gilchrist²¹ used silica particles in DI water, and the same device as that represented in Figure 1, but with a plate angle larger than 90°. They do not provide any estimation of the evaporation rate. We assumed a meniscus length L_m equal to the radius of curvature of the meniscus with zero effective contact angle (see SI of ref³³). L_m ranges from 0.3 mm to 0.9 mm, much lower than L_{ev} in all cases. We disregarded experimental results corresponding to mean deposit thickness lower than particle diameter. Notice that for Jung and Ahn data as well as Gilchrist data, we assumed $\varphi_c = 0.74$ as these authors did so in their models.

Evaporation length

Experimental values of the evaporation length L_{ev} are shown in Figure 5(a). The substrate velocity spreads over three and a half decades, and L_{ev} over two decades. Figure 5(b) shows that our data and that of Jung and Ahn collapse on the same master curve, which coincides with the theoretical prediction. Joshi and Gilchrist data are significantly above the master curve, but still obey the scaling law predicted by theory. This discrepancy may be explained by a shift in the estimation of \mathcal{M} due to (i) the uncertainty on φ_c (Joshi and Gilchrist data collapse on the master curve if we adopt $\varphi_c \simeq 0.61$ instead of 0.74), (ii) the law used to estimate κ , the prefactor of the pore-emptying criterion. We used eq (21) as suggested in ref³¹ for a randompacking of monodisperse spheres, but κ values ranging from 2 to $\simeq 13$ have been used by different groups, depending on the exact packing and particles wetting properties, see e.g. ref.³⁴

Considering that main simplifications in our model lies in the description of vapor mass transfer in the gas phase, these results confirm that the intensity of the overall evaporation rate as well as the shape of the evaporation velocity $v_{ev}(x)$ have only a minor effect on the evaporation length L_{ev} . An important result is that eq (26), although based on a simple 1D model of the gas phase, provides a rather fair estimation of L_{ev} , provided φ_c is known.

Deposit thickness

Experimental data of h_d are reported in Figure 6 for our experiments (Jung and Ahn did

Source	Set $\#$	$2a \ / \ { m nm}$	$V~/~\mu{ m m.s^{-1}}$	$arphi_0$	Symbol
	1	310	[1, 30]	0.048	
771 · 1	2	310	[0.5, 20]	0.0095	
	3	310	[2, 100]	0.096	
	4	170	[2, 100]	0.077	
1 his work	5	170	[1, 50]	0.038	<u> </u>
	6	800	[5, 50]	0.096	♦
	7	800	[1, 20]	0.048	
Leven en d. Alex 24	8	200 ± 14	0.097	[0.001,0.01]	×
Jung and Ann ²¹	9	200 ± 14	[0.036, 0.097]	0.0025	+
Joshi and Gilchrist ²¹	10	1010 ± 20	[27, 74]	0.2	•

Table 3: Experimental data sets (symbols in the last column are used in Figures 5 and 6).

not perform thickness measurements and data in real units were not available in Joshi and Gilchrist work).

Each symbol corresponds to an experimental data set performed with the same particle diameter and the same reservoir particle volume fraction. From Figure 6(a) it appears that, for each data set, h_d is roughly proportional to the inverse of V, following scaling (1). In addition, multiplying h_d by $\varphi_0/[\varphi_c(1-\varphi_0)]$ significantly gathers the data [Figure 6(b)].

The asymptotic models corresponding to scaling (1) predict a negligible (logarithmic) dependence of the deposit thickness on the particle diameter, or no dependence at all. To go further in the comparison between model and data, we define the quantity \bar{C} as the mean value of the expression $h_d V \varphi_c (1 - \varphi_0)/\varphi_0$ for each experimental data set, and we plot it in the inset in Figure 6(b) as a function of the particle diameter 2*a*. Despite the dispersion of the data, a weak dependence of \bar{C} with the particle diameter can be observed. This weak dependence is not captured by the model, likely because mass transfer in the gas phase has been oversimplified.

Nevertheless, h_d is closer to scaling (1) than scaling (4). In addition, large variations of L_{ev} are observed in Figure 5 for the same sets of control parameters. These large variations of L_{ev} for values of $\mathcal{M} \gg 1$, together with scaling (1) for h_d implies that Q_{ev} must depend only weakly on L_{ev} [cf. eq (12)]. To confirm this point, a few measurements of Q_{ev} have been performed (see description above in the Experiment section), in order to investigate its dependence with L_{ev} . While L_{ev} has been varied on two orders of magnitude, Q_{ev} increases only by a factor of about 4 (see Figure 7 and SI for detailed comments). This confirms that our experiments are done in a regime such that the evaporation rate Q_{ev} weakly depends on the evaporation length L_{ev} . Our experimental results are thus consistent with our theoretical findings.

Conclusion

In flow coating processes, the use of colloidal dispersions in the evaporative regime deserves special attention, because the evaporation length can be significantly increased by the water flow in the wet porous deposit. In the present work, the effect of the vapor mass transfer on the evaporation length and deposit thickness has been discussed in-depth. We proposed a 2D model simple enough to derive analytical solutions, yet realistic to predict scaling laws observed in experiments.

We conclude from the theoretical analysis that the evaporation length L_{ev} does not depend on the overall evaporation rate, and weakly depends on the shape of the local evap-



Figure 5: Evaporation length (see Table 3 for symbols). (a) experimental data. (b) master curve (\mathcal{M} has been estimated with $\varphi_c = 0.7$ for our data, and $\varphi_c = 0.74$ for data from refs^{21,24}); the solid and dashed lines correspond to asymptotic cases $\Lambda/L_{ev} \ll 1$ [eq (26)] and $\Lambda/L_{ev} \gg 1$ [eq (28)], respectively.



Figure 6: Experimental deposit height. (a) h_d and (b) $h_d \varphi_c (1 - \varphi_0)/\varphi_0$ as a function of substrate velocity V. Dashed and dotted lines are power laws with -1 and -2 exponents, respectively. See Table 3 for symbols. Inset : parameter \bar{C} defined as the mean value of the expression $h_d V \varphi_c (1 - \varphi_0)/\varphi_0$ for each experimental data set, as a function of particle diameter 2a(errorbars represent the standard deviations).



Figure 7: Normalized experimental evaporation rate Q_{ev}/β as a function of the evaporation length L_{ev} .

oration velocity. For this reason, a model based on 1D vapor mass transfer still provides fair estimates of L_{ev} , when compared to experimental data obtained in a 3D configuration.

On the contrary, an accurate model of vapor mass transfer is required for the prediction of the deposit thickness h_d , in order to describe precisely how the overall evaporation rate Q_{ev} depends on the evaporation length L_{ev} (this is specific to colloidal dispersions, as L_{ev} slightly varies for polymers or small solutes solutions³⁵). The scaling law relating h_d to process control parameters strongly depends on the driving mechanism acting in a given experimental setup. We believe that scalings (4) and (1)are two limiting cases, the latter corresponding to weak variations of Q_{ev} with L_{ev} , as expected for diffusion in semi-infinite quiescent air (essentially a 3D process), the former resulting from proportionality between Q_{ev} and L_{ev} , as would be expected for instance for turbulent free convection. Intermediate scalings should be possible with other vapor mass transfer mechanisms.

Our theoretical work also demonstrates that the comparison between measurements of L_{ev} and the predictions given in Table 1, is a possible way to estimate \mathcal{M} , the dimensionless parameter defined by eq (24). Such estimates are quite robust as our model shows that L_{ev} does not depend on the global evaporation rate, and is nearly insensitive to the distribution of the local evaporation flux. Our measurements are thus an indirect way to estimate precisely the product of the pore pressure at poreopening with the value of the permeability of the densely-packed wet film, see eq (24). This quantity is key to predict the receding of water during horizontal drying of films or sessile drops,^{20,23,34} but also for all unidirectional geometries such as the 1D drying of gels or of dispersions confined within capillaries.^{36–38}

Acknowledgement The authors thank ANR EVAPEC (13-BS09-0010-01) for funding. FD and BG thank Jean-Pierre Hulin, from FAST laboratory, for useful discussions. We thank Jacques Leng for his analysis of the SEM images to estimate φ_c .

Supporting Information Available: Diffusion evaporation flux for an infinite stripe domain - SEM top view of coating - Driving mechanism of the evaporation flux in the experimental device. This material is available free of charge via the Internet at http: //pubs.acs.org/.

References

- Sondergaard, R.; Hösel, M.; Angmo, D.; Larsen-Olsen, T.; Krebs, F. C. Roll-to-roll fabrication of polymer solar cells. *Mater. Today* 2012, 15, 36–49.
- (2) Gu, X.; Yan, H.; Kurosawa, T.; Schroeder, B. C.; Gu, K. L.; Zhou, Y.; to, J. W. F.; Oosterhout, S. D.; Savikhin, V.; Molina-Lopez, F.; Tassone, C. J.; Mannsfeld, S. C. B.; Wang, C.; Toney, M. F.; Bao, Z. Comparison of the Morphology Development of Polymer-Fullerene and Polymer-Polymer Solar Cells during Solution-Shearing Blade Coating. Adv. Energy Mater. 2016, 6, 1601225.
- (3) Prevo, B. G.; Kuncicky, D. M.; Velev, O. D. Engineered deposition of coatings from nano- and micro-particles: A brief review of convective assembly at

high volume fraction. Colloids Surf., A **2007**, 311, 2–10.

- (4) Le Berre, M.; Chen, Y.; Baigl, D. From convective assembly to Landau-Levich deposition of multilayered phospholipid films of controlled thickness. *Langmuir* 2009, 25, 2554–2557.
- (5) Grosso, D. How to exploit the full potential of the dip-coating process to better control film formation. J. Mater. Chem. 2011, 21, 17033–17038.
- (6) Berteloot, G.; Pham, C.-T.; Daerr, A.; Lequeux, F.; Limat, L. Evaporationinduced flow near a contact line: Consequences on coating and contact angle. *Europhys. Lett.* **2008**, *83*, 14003.
- (7) Weinstein, S.; Ruschak, K. Coating Flows. Annu. Rev. Fluid Mech. 2004, 36, 29–53.
- (8) Davis, R.; Jayaraman, S.; Chaikin, P.; Register, R. Creating Controlled Thickness Gradients in Polymer Thin Films via Flowcoating. *Langmuir* **2014**, *30*, 5637– 5644.
- (9) Dimitrov, A. S.; Nagayama, K. Continuous Convective Assembling of Fine Particles into Two-Dimensional Arrays on Solid Surfaces. *Langmuir* **1996**, *12*, 1303–1311.
- (10) Berteloot, G.; Daerr, A.; Lequeux, F.; Limat, L. Dip coating with colloids and evaporation. *Chem. Eng. Proc.* **2013**, *68*, 69–73.
- (11) Prevo, B. G.; Velev, O. D. Controlled, Rapid Deposition of Structured Coatings from Micro- and Nanoparticle Suspensions. *Langmuir* **2004**, *20*, 2099.
- (12) Kuncicky, D.; Naik, R.; Velev, O. Rapid Deposition and Long-Range Alignment of Nanocoatings and Arrays of Electrically Conductive Wires from Tobacco Mosaic Virus. *Small* **2006**, *2*, 1462–1466.
- (13) Brewer, D. D.; Shibuta, T.; Francis, L.; Kumar, S.; Tsapatsis, M. Coating Process

Regimes in Particulate Film Production by Forced-Convection-Assisted Drag-Out. Langmuir **2011**, 27, 11660.

- (14) Jing, G.; Bodiguel, H.; Doumenc, F.; Sultan, E.; Guerrier, B. Drying of Colloidal Suspensions and Polymer Solutions near the Contact Line: Deposit Thickness at Low Capillary Number. Langmuir 2010, 26, 2288–2293.
- (15) Maloy, S. F.; Martin, G. L.; Atanassov, P.; Cooney, M. J. Controlled Deposition of Structured Polymer Films: Chemical and Rheological Factors in Chitosan Film Formation. *Langmuir* **2012**, *28*, 2589–2595.
- (16) Diao, Y.; Tee, B. C.-K.; Giri, G.; Xu, J.; Kim, D. H.; Becerril, H. A.; Stoltenberg, R. M.; Lee, T. H.; Xue, G.; Mannsfeld, S. C. B.; Bao, Z. Solution coating of large-area organic semiconductor thin films with aligned single-crystalline domains. *Nat. Mater.* **2013**, *12*, 665–671.
- (17) Bodiguel, H.; Doumenc, F.; Guerrier, B. Stick- slip patterning at low capillary numbers for an evaporating colloidal suspension. *Langmuir* **2010**, *26*, 10758– 10763.
- (18) Mino, Y.; Watanabe, S.; Miyahara, M. T. In Situ Observation of Meniscus Shape Deformation with Colloidal Stripe Pattern Formation in Convective Self-Assembly. *Langmuir* **2015**, *31*, 4121–4128.
- (19) Boettcher, J. M.; Joy, M.; Joshi, K.; Muangnapoh, T.; Gilchrist, J. F. Spacing of seeded and spontaneous streaks during convective deposition. *Langmuir* **2015**, *31*, 10935.
- (20) Routh, A. F. Drying of thin colloidal films. *Rep. Prog. Phys.* **2013**, *76*, 046603.
- (21) Joshi, K.; Gilchrist, J. Estimation of drying length during particle assembly by convective deposition. J. Colloid Interface Sci. 2017, 496, 222 – 227.

- (22) Routh, A. F.; Russel, W. B. Horizontal Drying Evaporation Fronts During Solvent from Latex Films. *AIChE J.* 1998, 44, 2088–2098.
- (23) Goehring, L.; Clegg, W. J.; Routh, A. F. Solidification and ordering during directional drying of a colloidal dispersion. *Langmuir* 2010, 26, 9269–9275.
- (24) Jung, Y. D.; Ahn, K. H. Prediction of Coating Thickness in the Convective Assembly Process. *Langmuir* 2013, 29, 15762–15769.
- (25) Doumenc, F.; Salmon, J. B.; Guerrier, B. Modeling flow coating of colloidal dispersions in the evaporative regime: prediction of deposit thickness. *Langmuir* 2016, *32*, 13657–13668.
- (26) Rhosenow, W.; Hartnett, J.; Cho, Y. Handbook of Heat Transfer, 3rd ed.; McGraw-Hill: New York, USA, 1998.
- (27) Deegan, R. D.; Bakajin, O.; Dupont, T. F.; Huber, G.; Nagel, S. R.; Witten, T. Contact line deposits in an evaporating drop. *Phys. Rev. E* 2000, *62*, 756.
- (28) Janeček, V.; Doumenc, F.; Guerrier, B.; Nikolayev, V. Can hydrodynamic contact line paradox be solved by evaporationcondensation? J. Colloid Interface Sci. 2015, 460, 329 - 338.
- (29) Guyon, E.; Hulin, J. P.; Petit, L.; Mitescu, C. D. *Physical Hydrodynamics*; Oxford University Press, 2015.
- (30) Zick, A. A.; Homsy, G. M. Stokes flow through periodic arrays of spheres. J. Fluid Mech. 1982, 115, 13–26.
- (31) Brown, L. A.; Zukoski, C. F.; White, L. R. Consolidation During Drying of Aggregated Suspensions. *AIChE J.* 2002, 48, 492–502.
- (32) Angly, J.; Iazzolino, A.; Salmon, J. B.; Leng, J.; Chandran, S.; Ponsinet, V.;

Desert, A.; Beulze, A. L.; Mornet, S.; Treguer-Delapierre, M.; Correa-Duarte, M. Microfluidic-induced growth and shape-up of three-dimensional extended arrays of densely packed nanoparticles. *ACS Nano* **2013**, *7*, 6465.

- (33) Kumnorkaew, P.; Ee, Y.-K.; Tansu, N.; Gilchrist, J. F. Investigation of the Deposition of Microsphere Monolayers for Fabrication of Microlens Arrays. *Langmuir* 2008, 24, 12150–12157.
- (34) Keddie, J. L.; Routh, A. F. Fundamentals of latex film formation. Processes and Properties; Springer, 2010.
- (35) Doumenc, F.; Guerrier, B. Drying of a Solution in a Meniscus: A Model Coupling the Liquid and the Gas Phases. *Langmuir* 2010, 26, 13959–13967.
- (36) Brinker, C. J.; Scherer, G. W. Sol-Gel Science: The Physics and Chemistry of Sol-Gel Processing; Academic Press, 1990.
- (37) Dufresne, E. R.; Corwin, E. I.; Greenblatt, N. A.; Ashmore, J.; Wang, D. Y.; Dinsmore, A. D.; Cheng, J. X.; Xie, X.; Hutchinson, J. W.; Weitz, D. A. Flow and fracture in drying nanoparticle suspensions. *Phys. Rev. Lett.* **2003**, *91*, 224501.
- (38) Lidon, P.; Salmon, J. B. Dynamics of unidirectional drying of colloidal dispersions. *Soft Matter* **2014**, *10*, 4151.

Graphical TOC Entry

