



**HAL**  
open science

## Numerical investigation of the effect of interface conditions in HTM-free and printable WO<sub>x</sub> based perovskite solar cells

Yong Huang, Sigalit Aharon, Alexandre Gheno, Sylvain Vedraïne, Laurent Pedesseau, James P Connolly, Claudine Katan, Mikael Kepenekian, Jean-Philippe Burin, Olivier Durand, et al.

### ► To cite this version:

Yong Huang, Sigalit Aharon, Alexandre Gheno, Sylvain Vedraïne, Laurent Pedesseau, et al.. Numerical investigation of the effect of interface conditions in HTM-free and printable WO<sub>x</sub> based perovskite solar cells. 7<sup>e</sup> Journées Nationales du PhotoVoltaïque (JNPV 2017), Dec 2017, Dourdan, France. . hal-01660167

**HAL Id: hal-01660167**

**<https://hal.science/hal-01660167>**

Submitted on 27 Sep 2022

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Numerical investigation of the effect of interface conditions in HTM-free and standard perovskite solar cells

Y. Huang<sup>1</sup>, S. Aharon<sup>2</sup>, A. Gheno<sup>3</sup>, S. Vedraïne<sup>3</sup>, L. Pedesseau<sup>1</sup>, J. P. Connolly<sup>4</sup>, C. Katan<sup>5</sup>, M. Kepenekian<sup>5</sup>, J. P. Burin<sup>1</sup>, O. Durand<sup>1</sup>, J. Bouclé<sup>3</sup>, L. Etgar<sup>2</sup>, J. Even<sup>1</sup>, A. Rolland<sup>1</sup>

<sup>1</sup>UMR FOTON CNRS 6082, INSA, 35708 Rennes, France

<sup>2</sup>Institute of Chemistry, The Hebrew University of Jerusalem, 91904 Jerusalem, Israel

<sup>3</sup>XLIM UMR 7252, Université de Limoges/CNRS, 87060 Limoges Cedex, France

<sup>4</sup>Institut Photovoltaïque de l'Île de France (IPVF), 92160 Antony, France

<sup>5</sup>Institut des Sciences Chimiques de Rennes, UMR 6226, CNRS - Université de Rennes 1, 35700 Rennes, France

INSA  
RENNES

## Introduction

One of the remaining issues, impeding the commercialization of the low cost and high efficiency perovskite solar cells (PSCs) is the stability of the halide perovskite materials, including the light-induced degradation and the hysteresis effect. The perovskite/TiO<sub>x</sub> and perovskite/Au interfaces are numerically investigated, simulating the current-voltage (J-V) and capacitance-voltage (C-V) characteristics. Furthermore, a new approach is proposed for the modelling of Kelvin Probe Force Microscopy (KPFM). It is applied to hetero-structures in dark and under illumination, aiming at estimating the surface states on the top of the electron transport materials and understanding the charge carrier behavior inside the cells.

## Basic equations used for the numerical simulation[1]

Coupled continuity and Poisson equations

$$\frac{\partial n}{\partial t} = \frac{1}{q} \text{div} \vec{J}_n + G_n - R_n$$

$$\frac{\partial p}{\partial t} = -\frac{1}{q} \text{div} \vec{J}_p + G_p - R_p$$

$$\Delta \Psi = -\frac{\rho}{\epsilon}$$

Drift diffusion currents

$$\vec{J}_n = -qn\mu_n \vec{E}_n + qD_n \nabla n(x)$$

$$\vec{J}_p = -qp\mu_p \vec{E}_p - qD_p \nabla p(x)$$

Recombination rates

$$R_{bi} = k_{bi}(np - n_i^2)$$

$$R_{SRH} = \frac{pn - n_i^2}{\tau_p(n + n_i) + \tau_n(p + n_i)}$$

## HTM-free PSCs

Yong HUANG et al, EPJ Photovoltaics 8, 85501 (2017)

### Materials parameters

	$\chi$ (eV)	$E_g$ (eV)	$N$ (cm <sup>-3</sup> )	$m_e^*$ & $m_h^*$ (m <sub>0</sub> )	$\epsilon_r$ ( $\epsilon_0$ )
CH <sub>3</sub> NH <sub>3</sub> PbI <sub>3</sub>	3.9	1.6	4e16*	0.23&0.26	70
TiO <sub>2</sub>	4.1	3.3	1e19 [2]	5.6&5.6 [3]	31

\* indicates fitting parameters

[1] Silvaco Inc., ATLAS user's manual, Sunnyvale, CA, 2012.


[2] G. Liu, W. Jaegermann, J. He, V. Sundström, and L. Sun, J. Phys. Chem. B **106**, 5814 (2002).

[3] S. Rühle and D. Cahen, J. Phys. Chem. B **108**, 17946 (2004).


[4] W.A. Laban and L. Etgar, Energy Environ. Sci. **6**, 3249 (2013).

[5] A. Gheno et al, Sol. Energy Mater. Sol. Cells. **161**, 347 (2017).

### Static band diagram



Interfacial heavily n-doped layer needed to fit experimental data




$$\frac{1}{C^2} = \frac{2}{qA^2 \epsilon_0 N \epsilon_r} (V_{bi} - V_{bias} + \frac{kT}{q})$$

Equivalent circuit used for capacitance analysis

\* Experimental results from Etgar's group [4], (collaboration with Hebrew University of Jerusalem)

### Capacitance-voltage



V<sub>bi</sub>: built-in potential loss

## Kelvin Probe Force Microscopy

Yong HUANG et al, OQE, submitted






Illustration of the basic measurement setup of Contact Potential Difference (CPD). Tip and sample are a) separated, b) connected at short circuit and c) under bias of V<sub>CPD</sub>.



$$V_{CPD} = \frac{E_{f,tip} - E_{f,sample}}{q}$$

V<sub>CPD</sub> measured by KPFM, E<sub>f,tip</sub> is known.

Spacer	th=10 nm	Tip, WF=4.8 eV
ifTiO <sub>2</sub>	th=10 nm, n=n(TiO <sub>2</sub> ), its(TiO <sub>2</sub> )	Light Tip, WF=4.8 eV
tTiO <sub>2</sub>	th=240 nm, n(TiO <sub>2</sub> )	
bTiO <sub>2</sub>	th=50 nm, n(bTiO <sub>2</sub> )=5E18 cm <sup>-3</sup>	Spacer
FTO	th=200 nm, n(FTO)=1E20 cm <sup>-3</sup>	th=10 nm
		ifMAPbI <sub>3</sub>
		MAPbI <sub>3</sub>
		th(MAPbI <sub>3</sub> ), p=1E15 cm <sup>-3</sup>
		ifTiO <sub>2</sub>
		th=10 nm, n=5E18 cm <sup>-3</sup> , its(TiO <sub>2</sub> )=1E19 cm <sup>-3</sup>
		tTiO <sub>2</sub>
		th(TiO <sub>2</sub> ), n=5E18 cm <sup>-3</sup>



a) Static Contact Potential Difference (CPD.Dark) and work-function as a function of the doping level, n(tTiO<sub>2</sub>) and the surface trap density, its(TiO<sub>2</sub>). b) Schematic representation of the static band alignment with acceptor-like trap density equal to 1E19cm<sup>-3</sup> on the top of a 5E18cm<sup>-3</sup> doped TiO<sub>2</sub>.





a) Experimental and simulated Surface PhotoVoltage (SPV). The simulated light power is 1 W/cm<sup>2</sup>. b) Computed surface work-function and Surface PhotoVoltage (SPV) as a function of the thickness of CH<sub>3</sub>NH<sub>3</sub>PbI<sub>3</sub>. The external light source is one sun.

A new approach to modelling Kelvin Probe Force Microscopy for hetero-structures in the dark and under illumination has been presented. The approach has been tested by examining FTO/TiO<sub>2</sub> and FTO/TiO<sub>2</sub>/MAPbI<sub>3</sub> structures. Unexpected surface states on the top of TiO<sub>2</sub> layer are inferred by the combination of theoretical computation and experimental results. The basic applications of KPFM under illumination are analyzed as well.

## V<sub>oc</sub> Losses in PSCs

Yong HUANG et al, NUSOD international conference (2017)



The V<sub>oc</sub> loss of standard TiO<sub>2</sub>/CH<sub>3</sub>NH<sub>3</sub>PbI<sub>3</sub>/Spiro-OMeTAD PSCs could mainly come from the local trap-assisted recombination in the bulk, besides the interface trap recombination and ion migration.

## Acknowledgements

This work is supported by ANR "Supersansplomb" project, and the CNRS GDR HPERO