



NH 3 treatments of Hf-based layers for application as NVM active dielectrics

Marc Bocquet, G. Molas, E. Martínez, H. Grampeix, F. Martin, J P Colonna, J Buckley, C. Licitra, N. Rochat, T Veyron, et al.

► To cite this version:

Marc Bocquet, G. Molas, E. Martínez, H. Grampeix, F. Martin, et al.. NH 3 treatments of Hf-based layers for application as NVM active dielectrics. IEEE Semiconductor Interface Specialists Conference (SISC), Dec 2007, Arlington, United States. hal-01745607

HAL Id: hal-01745607

<https://hal.science/hal-01745607>

Submitted on 30 Mar 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

NH₃ treatments of Hf-based layers for application as NVM active dielectrics

M. Bocquet^{a,b}, G. Molas^b, E. Martinez^b, H. Grampeix^b, F. Martin^b, J. P. Colonna^b, J. Buckley^b, X. Garros, C. Licitra^b, N. Rochat^b, T. Veyron^b, A. M. Papon^b, F. Aussena^c, V. Delaye^b, M. Gély^b, G. Pananakakis^a, B. De Salvo^b, G. Ghibaudo^a, S. Deleonibus^b.
^a IMEP-CNRS/INPG, MINATEC – INPG – 3, Parvis Louis Néel 38016 Grenoble, France
^b CEA-LETI, 17 rue des Martyrs 38054 Grenoble Cedex 9, France, marc.bocquet@cea.fr

Abstract— The goal of this work is to investigate the effect of NH₃ nitridation on high- κ materials in view of application to non-volatile memories (NVMs). Our study focuses on the trapping properties of thick HfO₂ and HfAlO layers (6-14nm-thick). Through in-depth physical and electrical analyses, we demonstrate that an appropriate nitridation of these layers significantly reduces the charge trapping phenomena. Based on morphological analyses and analytical models, we argue that the lower trapping capability can be related to a smaller ratio of the crystalline phase of the high- κ layers.

Introduction — High- κ materials are currently under strong investigation for non-volatile memory (NVM) applications. They can offer important benefits both when they are used as interpoly (IPD) layer [1, 2], in terms of coupling and insulating properties, and as tunnel stacks [3, 4], due to the improved injection properties. However, the important trap density which characterizes these new materials constitutes a serious roadblock for the large-scale device integration, due to the VT instability and the trap-assisted gate leakage currents [5]. However, it is also possible to benefit from high- κ deep traps when they are used for charge storage in charge-trap memory applications [6]. Hence, today a major challenge is the process control of the high- κ trap properties.

Sample description

Trapping layers capacitor devices :


High- κ were integrated as charge trapping layers in capacitors in order to investigate their trapping properties, depending on the thermal treatments

- ✓ Tunnel oxide: SiO₂ – 2nm
- ✓ Trapping layer : HfO₂ or HfAlO (57% Hf) – 6nm, 10nm or 14nm.
- ✓ Blocking oxide: High Thermal Oxide (HTO) – 10nm

High- κ thermal treatments :

- Post-deposition anneals (PDA):
 - (i) nitridation treatment, under NH₃ at 750°C during 30min. Role: trap passivation
 - (ii) inert treatment, under N₂ at 750°C during 1 min
- High temperature anneals, simulating the dopant activation :
 - (iii) spike anneal under N₂ at 1050°C.
 - (iv) 950°C under N₂ during 15s.

| Thermal treatment | Sample | | | | | |
|-----------------------------------|--------|---|---|---|---|---|
| | A | B | C | D | E | F |
| (i) NH ₃ 750°C 30min | X | | X | | X | |
| (ii) N ₂ 750°C 2min | | X | | X | | X |
| (iii) N ₂ 1050°C spike | | | X | X | | |
| (iv) N ₂ 950°C 15s | | | | | X | X |




Materials study




Based on Auger measurements, the nitrogen incorporation after NH₃ anneal was found localized:

- HfO₂ layer ► At the Si-sub/high- κ interface.
- HfAlO layer ► In the high- κ bulk layer: nitrogen absorption~15%.

Sample B: amorphous structure



Sample C : Polycrystalline structure



→ The NH₃ anneal limited the crystallization of the HfAlO layer.

Results and discussion


Programming characteristics of the capacitors

HfO₂ layer:


- High temperature anneal ► Trapping increasing
- Nitridation treatment ► Trapping reduction

HfAlO layer:

- High temperature anneal ► Trapping increasing
- Nitridation treatment ► Trapping reduction of layers that have undergone a high T° anneal



→ Correlation with the smaller ratio of crystalline phase of nitridated HfAlO layer (see TEM images)



Charge loss rate does not increase after anneals

→ Tunnel oxide is not modified after high temperature anneals or nitridation treatment



Conclusion —

- The trapping capability of the studied high- κ layers increases with the crystalline ratio (electrical results + TEM observations)
- The electron trapping mainly occurs at the bottom oxide/high- κ interface due to faster charging time constants (electrical results + simulations)
- NH₃ anneals can be used to reduce the parasitic trapping in high- κ layers: suitable for interpoly or tunnel applications

Localization of the trapped charge: interface or bulk distribution?


- Interface normalization is consistent with the experimental results
- Bulk normalization do not match with the experimental data

→ Interface rather than bulk distribution




Simulations of trapping in the high- κ layer

- Analytical model based on the SRH statistics presented in [6] and [7]
- Good fit with the experimental data
- The charging time constants increase with the distance between the traps and the cathode



- $\frac{dft}{dt} = (1 - ft) \cdot (cn + ep) - ft \cdot (en + cp)$
- $\Delta V_{fb} = \frac{N_{st} \cdot ft}{C_t}$
- N_{st} : trap density
- E_T : trap depth
- ft : trap occupation probability
- cn/en & cp/ep : electron and hole capture/emission rates



→ Most of the trapped charges are located close to the High- κ /bottom oxide interface (the charging time constants increase with the distance between the traps and the cathode).

- [1] G. Molas et al., ESSDERC, 2006, pp. 242-245.
- [2] D. Wellekens et al., ESSDERC, 2006, pp. 238-241.
- [3] B. Govoreanu et al., in IEEE Electron Device Letters, February 2003.
- [4] R. van Schaik et al., IEEE NVMW, 2006, pp. 50-51.
- [5] M. Bocquet et al., Proc. of ICMTD, 2007, pp. 239-242.
- [6] J. Buckley et al., IEDM Tech. Dig., 2006, pp. 251-254.
- [7] X. Garros et al., IRPS, 2007, pp. 61-66.