



Agglomeration of wet granular materials in rotating drum

Thanh-Trung Vo, Saeid Nezamabadi, Jean-Yves Delenne, Farhang Radjai

► To cite this version:

Thanh-Trung Vo, Saeid Nezamabadi, Jean-Yves Delenne, Farhang Radjai. Agglomeration of wet granular materials in rotating drum. Powders & grains 2017, Jul 2017, Montpellier, France. hal-01772261

HAL Id: hal-01772261

<https://hal.science/hal-01772261>

Submitted on 20 Apr 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

AGGLOMERATION OF WET GRANULAR MATERIAL IN ROTATING DRUM

THANH-TRUNG VO¹, SAEID NEZAMABADI¹, JEAN-YVES DELENNE², FARHANG RADJAI^{1,3}

¹ Laboratoire de Mécanique et Génie Civil (LMGC), Université de Montpellier, CNRS, Montpellier, France

² IATE, UMR1208 INRA - CIRAD - Université de Montpellier - SupAgro, 34060 Montpellier, France


³ < MSE >, UMI 3466 CNRS-MIT, CEE, MIT, 77 Massachusetts Avenue, Cambridge 02139, USA



OBJECTIVES & METHODOLOGY

Simulation the agglomeration process of solid particles in the presence of a viscous liquid. We are mostly interested in application to iron ore granulation in a horizontal rotating drum. In this work, we use Molecular Dynamics (MD) method to simulate the agglomeration process during the dense granular flows in the rotary drum. In which particles are distributed by an uniform distribution of particle volume fractions.


INDUSTRIAL PROCESS



Granulation (balling) Drum

Agglomeration is the process of particles size enlargement and most commonly refers to the upgrading of material fines into larger particles, such as pellets or granules. Iron ore granulation is an important stage in the steel making.

ROLLING - CASCADING MODEL



$$\text{Filling level: } f = \frac{S}{\pi R_c^2} = \frac{\varphi - \sin \varphi}{2\pi}$$

$$\text{Froude number: } Fr = \frac{\omega^2 R_c}{g}$$

$$C = AB = 2R_c \sin \frac{\varphi}{2}$$

$$S = \frac{R_c^2}{2}(\varphi - \sin \varphi)$$

$$LC = \widehat{AB} = \varphi R_c$$

ω Rotational speed (rad/s)
 β Free surface angle
 φ Filling angle (degree)
Packing fraction:
 $\Phi = \frac{V_s}{S * L} = \frac{\Sigma (\frac{4}{3}\pi R_i^3)}{S * L}$

MOLECULAR DYNAMICS METHOD

$$m_i \frac{d^2 s_i}{dt^2} = \sum_{(i)} ((f_n + f_c + f_{vis}) \mathbf{n} + f_t \mathbf{t}) + m_i g$$


s_i position vector of particle i

g vector gravity



n normal unit vector

t tangential unit vector

m_i mass of particle i (kg)



CAPILLARY COHESION & VISCOUS FORCE



$$f_c = \begin{cases} -\kappa R, & \text{for } \delta_n < 0 \\ -\kappa R e^{-\frac{\delta_n}{\lambda}}, & \text{for } 0 \leq \delta_n \leq \delta_n^{max} \\ 0, & \text{for } \delta_n \geq \delta_n^{max} \end{cases}$$

$$f_{vis} = \frac{3}{2} \pi R^2 \eta \frac{1}{\delta_n} \frac{d\delta_n}{dt}$$

$$\kappa = 2\pi\gamma_s \cos\theta$$





$$\delta_n^{max} = (1 + \frac{1}{2}\theta)V_b^{1/3}$$

$$\alpha = \frac{R_{max}}{R_{min}}$$




$$\lambda = c h(\alpha)(\frac{V_b}{R'})^{\frac{1}{2}}$$

$$R = \sqrt{R_i R_j}$$

AGGLOMERATION RESULTS




Exponential increases of wet & contact coordination numbers (a) and decrease of kinetic energy normalized by potential energy of granule (b), as functions of size ratio α .






Conclusions

- The effect of size ratio on the granule growth is more crucial than that of rotational speed.
- Granule growth is an exponential function of size ratio and rotational speed of drum.
- Kinetic energy normalized by potential energy increases proportional to the rotational speed, but inversely proportional to the size ratio.
- The wet and contact coordination numbers of agglomerate grains are proportional to size ratio.

GRANULE COMPRESSION STRENGTH



The snapshots of model and force chains of a granule under diametrical compression.



FURTHER RESEARCHES

- Investigation the agglomeration process of a huge number of particles.
- Comparison between experiment and simulation of agglomeration processes in rotating drum.

8th International Conference on Micromechanics of Granular Media Powders & Grains 2017

