



**HAL**  
open science

## Variational evolution of dislocations in single crystals

Riccardo Scala, Nicolas Van Goethem

► **To cite this version:**

Riccardo Scala, Nicolas Van Goethem. Variational evolution of dislocations in single crystals. 2018.  
hal-01795344

**HAL Id: hal-01795344**

**<https://hal.science/hal-01795344>**

Preprint submitted on 18 May 2018

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Variational evolution of dislocations in single crystals

Riccardo Scala

Universidade de Lisboa, Faculdade de Ciências,  
Departamento de Matemática, CMAF+CIO,  
Alameda da Universidade, C6, 1749-016 Lisboa, Portugal  
rscala@fc.ul.pt

Nicolas Van Goethem

Universidade de Lisboa, Faculdade de Ciências,  
Alameda da Universidade, C6, 1749-016 Lisboa, Portugal  
vangoeth@fc.ul.pt  
ORCID: 0000-0002-5356-8383

May 8, 2018

## Abstract

In this paper we provide an existence result for the energetic evolution of a set of dislocation lines in a three-dimensional single crystal. The variational problem consists of a polyconvex stored-elastic energy plus a dislocation energy and some higher-order terms. The dislocations are modeled by means of integral one-currents and the dissipation distance is chosen to be the flat distance.

## 1 Introduction

### Origin of the model

Dislocations are one-dimensional singularities in a three-dimensional body, whose motion is ultimately responsible for metal plasticity. Their study is of crucial impact in many technological processes such as the industry of semiconductors, as related to bulk crystal growth [27], since metal toughness and conductivity for instance depend on their density. In this process, a crystal is grown from the melt and dislocations are created from the incorporation of point defect at the solid-liquid interface, and can leave the crystal by its solid-gas interface. The particular feature of this process is that the crystal must be considered on a large range of temperatures and hence the motion of dislocations can not be assumed as restricted to some

pre-established glide planes, as for a crystal at ambient temperature. This is the motivation of our series of works [30–33] whose main feature is to consider dislocations in their three-dimensional generality (based on the pioneering contribution [28]). The second specificity of our approach is to consider finite-strain elasticity, since a dislocation does by essence induce large deformations near its singularity. Therefore, our model choice is to consider polyconvex energies [4], together with higher order terms accounting for the energy of the singularities. In turn, dislocation singularities are described as integral 1-currents, which in order to keep track of the associated Burgers vector, are taken with coefficients in a group (see also, e.g., [12]).

So far, our study was dedicated to a variational approach to the static problem, since difficult issues had to be faced, for instance as related to the closedness of the class of admissible fields. As a matter of fact, we consider a limit-case thermodynamics in which the first and second principle are satisfied by minimizing an energy functional, that, quoting Berdichevski [7] ”in crystals with negligible resistance to dislocation motion, like pure copper, [...] can be reached very fast”.

If one restricts to the motion of parallel dislocations, the problem becomes two-dimensional, since the dislocations are modelled as points. In this case, the mathematical analysis of dynamics model already exist in the wake of Ginsburg-Landau vortices dynamics, and can be found for instance in [1, 2, 8, 9]. The dynamics of this kind of dislocations have been studied by several authors, see for instance the important contributions [18] and [25] for a rate-independent evolution. See also the more recent paper [26] and references therein. Let us also mention the interesting analysis contained in [37], and the references therein. Nonlocal evolution models can also be considered as in [29]. At the mesoscale, another route is known as the Discrete Dislocations Dynamics model (DDD), see [11, 36, 38], that considers the dynamics of single dislocations segments and their interactions. Though, this approach is computationally expensive and hence restricted to small samples.

## **Brief exposition of the variational evolution model**

The energetic formulation for quasi-static evolutions, due to Mielke and coauthors (see [22] for a survey) has become very popular in the recent years. One reason is that in this theory, the variational approach and its elegant mathematical techniques meet physical principles among which conservation laws. This approach has proved successful, among other, in fracture dynamics, delamination, damage, as well as Ginsburg-Landau-like models (see, e.g., [13, 21, 23, 24, 34, 35]). To the knowledge of the authors, no such energetic evolution was ever considered for three-dimensional dislocation clusters. It is the first purpose of this paper to recall and expose how the ideas developed in [30–33] meet in a very natural way the lines of Mielke and coauthors well-established existence theory for the quasi-static evolution of rate-independent systems. The basic ingredients are as follows: (i) a variational model at the statics level, and (ii) an appropriate notion of dissipation distance. Whereas the first point has been addressed in previous papers by the authors, the second is presented as a novel contribution in the present work.

We consider a three-dimensional elastic body represented by a bounded and

connected open set  $\Omega$ . In the presence of dislocations, the main variables of the system are the deformation field  $F : \Omega \rightarrow \mathbb{R}^{3 \times 3}$  (which is, locally, the gradient of a displacement  $u : \Omega \rightarrow \mathbb{R}^3$ ), and the associated dislocation density  $\Lambda_{\mathcal{L}}$ , namely a  $\mathbb{R}^{3 \times 3}$ -valued Borel measure on  $\Omega$  defined as

$$\Lambda_{\mathcal{L}} = \tau \otimes b \mathcal{H}^1 \llcorner_L, \quad (1.1)$$

where  $b$  is the Burgers vector,  $L$  is the dislocation curve with unit tangent vector  $\tau$ , and  $\mathcal{H}^1$  is the one-dimensional Hausdorff measure. The deformation  $F$  and the dislocation density  $\Lambda_{\mathcal{L}}$  are related by the identity

$$-\text{Curl } F = \Lambda_{\mathcal{L}}^T, \quad (1.2)$$

where symbol  $T$  stands for the transpose. We denote  $\mathcal{L} := \tau \mathcal{H}^1 \llcorner_L$  and in the language of currents we write  $\Lambda_{\mathcal{L}}^T = b \otimes \mathcal{L}$ , since in our approach the measure  $\mathcal{L}$  is identified with a one-dimensional integral current and is called dislocation current.

We consider a quasi-static evolution in the presence of a nonlinear stored-elastic energy following the framework proposed in [31–33], which relies on a polyconvex elastic energy, plus two higher order terms depending on the first derivatives of  $F$ , and in particular on the dislocations density. We supplement the system with a time-dependent external bulk force  $f$  and a traction  $g$  acting on the Neumann part of the boundary, which drives the evolution. For the dissipation functional  $\mathcal{D}$ , we make the choice of a the flat distance on the spaces of dislocations currents. Its physical meaning is discussed below. Lastly, we choose a fixed Dirichlet boundary datum  $w$  independent of time. The more involved problem of imposing a time-dependent Dirichlet boundary condition is a challenging issue that we are not able to address at the present stage (see the Open problems section). This is due to additional difficulties deriving from the fact that fixing time-dependent dislocations at the boundary yields a poor regularity in the boundary datum for the displacement field, and this prevents to have control on the time derivative of the energy.

## Mathematical modeling of the dissipation

Let us now spend some words on the model. In the spirit of Gurtin [17], we will consider the work expended by a dislocation to change position. This so-called configurational work represents the dissipation produced by this configurational motion. Moreover, any other source of dissipation is assumed negligible with respect to micro-structure dissipation. Let  $\mathcal{L} \subset \Omega$  be a dislocation loop with tangent vector  $\tau$  and Burgers vector  $b = |b|B$  where  $B \in S^2$ . In a first step, we assume that the time-dependent dislocation  $t \mapsto \mathcal{L}(t)$  lies and moves on a glide plane  $\Pi$  with unit normal  $n$ . We will consider the case when the dislocation moves by a displacement  $\vec{\delta q} \in \mathbb{R}^3$  during the time interval  $\delta t$ , i.e.,  $\vec{q}(t + \delta t) = \vec{q}(t) + \vec{\delta q} \in \Omega$ . Accordingly, let  $\mathcal{L}' := \mathcal{L}(t + \delta t)$ . Let us write  $\vec{\delta q}$  in the local base  $(\tau, B)$ , i.e.,

$$\vec{\delta q} = \delta q_{\tau} \vec{\tau} + \delta q_B \vec{B}$$

where  $\vec{\delta q}_\tau$  and  $\vec{\delta q}_B$  are the components of  $\vec{\delta q}$  respectively along  $\tau$  and  $B$ . We write  $\vec{\delta q}_B := (\delta\ell)B$  for  $\delta\ell \in \mathbb{R}$  to mean the configurational displacement. If the dislocation changes location, the micro-structure configuration has changed, and configurational work has been expended (in the form of a dissipated energy). Hence, to compute the configurational work, we will consider the force over a displacement  $\vec{\delta q}_B$  purely along  $B$ , since the component along  $\tau$  does not change the defect configuration, hence its associated work is assumed negligible. Define the surface element  $\vec{\delta S} := \vec{\delta q} \times \tau$  (vanishing if the displacement has no configurational component).

Now, denoting the (symmetric) Cauchy stress tensor  $\sigma$ , the force per unit surface exerted by the crystal on any facet of the glide plane  $\Pi$  is  $\vec{t} = \sigma\vec{n}$ . In particular  $\vec{t}(\delta S) = \sigma_{jl}(\delta S)_l$  represents the configurational force exerted on the planar strip  $\delta S$  with normal  $n_l$ . The associated variation of configurational work, or micro-structure dissipation, is defined as

$$\delta W_c := \vec{t} \cdot \vec{\delta q}_B.$$

Indicewise, we define the normalized configurational work of a dislocation as  $\delta\bar{W}_c := (|b|/\delta\ell)\delta W_c = \sigma_{jl}(\delta S)_l b_j$ , representing the work expended for a displacement of  $\mathcal{L}$  by  $b$  caused by the configurational force  $\vec{t}(\delta S)$ . By  $(\delta S)_l = \epsilon_{lmi}(\delta q)_m \tau_i$ , we have  $\delta\bar{W}_c := \sigma_{jl} b_j \epsilon_{lmi}(\delta q)_m \tau_i$ . Owing to the symmetry of  $\sigma$ , the configurational force  $F^{\text{PK}}$  is defined componentwise as follows:  $F_m^{\text{PK}} := \frac{\partial \delta\bar{W}_c}{\partial (\delta q)_m} = \epsilon_{mil} \sigma_{lj} b_j \tau_i$ , known as the Peach-Koehler force on  $\mathcal{L}$ . In compact form, for the motion on the glide plane,

$$\delta\bar{W}_c = \sigma b \cdot n |\delta S|, \quad (1.3)$$

where

$$\begin{aligned} |\delta S| &= \text{the area of the planar strip between } \mathcal{L} \text{ and } \mathcal{L}' \\ &= d_F(\mathcal{L}, \mathcal{L}') \\ &:= \text{the minimum area of the surfaces enclosed by } \mathcal{L} - \mathcal{L}'. \end{aligned} \quad (1.4)$$

Consider now that the motion is free of any predefined glide plane. The configurational work is again defined by (1.3), with  $n$  the unit normal to the strip  $\delta S$ . However, being the motion no more planar,  $\delta S$  is not univoquely defined, since it can be any two-dimensional manifold enclosed by the closed loop  $\mathcal{L} - \mathcal{L}'$ . Taking such strip of minimal area, we take by definition the configurational dissipation as given by (1.3) and (1.4). By this means, we introduce precisely the notion of flat distance between  $\mathcal{L}$  and  $\mathcal{L}'$  (see for instane [20]). The key point to observe is that the configurational work, that indeed represents the dissipation produced by the configurational motion [17], is proportional to  $d_F(\mathcal{L}, \mathcal{L}')$  for dislocation movements in the glide plane. Therefore we extend this property to be a definition of configurational dissipation for a general motion, i.e.,

$$\text{Dislocation dissipation} = W_c = \gamma d_F(\mathcal{L}, \mathcal{L}'),$$

where  $|\delta S| = d_F(\mathcal{L}, \mathcal{L}')$  is indeed the minimal area between  $\mathcal{L}$  and  $\mathcal{L}'$ , and  $\gamma > 0$  is a material parameter. It is crucial to have in mind that  $\mathcal{L}$  and  $\mathcal{L}'$  have an

orientation and hence the flat norm between to geometrically closed loops with opposite orientation will not tend to zero. This corresponds to the highly dissipative process required to invert the orientation of a dislocation. Summarizing, our total energy will be

$$\mathcal{E} + \mathcal{D} := \mathcal{W} + \mathcal{P} + W_c,$$

with  $\mathcal{W}$  the stored-elastic energy,  $\mathcal{P}$  the potential energy equals to minus the work of the external loads, and  $W_c$  the configurational work. The problem that we address is to indeed find an evolution  $t \mapsto \mathcal{L}(t)$  such that at each time the minimum of  $\mathcal{E} + \mathcal{D}$  is achieved (such a minimization is for instance attained for certain crystals such as copper, cf. [7]). This dynamics indeed is a variational evolution in the sense of Mielke and coauthors [22] together with the existence results established by the authors for the statics problem [31–33].

## 2 Preliminaries and model description

The crystal is represented by a bounded, connected open set  $\Omega \subset \mathbb{R}^3$ . We assume that  $\Omega$  has a Lipschitz boundary  $\partial\Omega$  that writes as the union of a Dirichlet and Neumann part, the first one with positive Hausdorff measure, namely

$$\partial\Omega := \Gamma_D \cup \Gamma_N, \quad \text{with } \mathcal{H}^2(\Gamma_D) > 0. \quad (2.1)$$

It is convenient to assume that there is a Lipschitz bounded and connected open set  $U$  such that  $\partial\Omega \cap U = \Gamma_D$ . We set  $\hat{\Omega} := U \cup \Omega$ .

**Setting and kinematical variables.** Referring to the classical nonlinear model for crystals in the presence of dislocations, the main variables of the system are the deformation field  $F$  and its induced dislocation current  $\mathcal{L}$ . The deformation field satisfies  $F \in L^p(\Omega; \mathbb{R}^{3 \times 3})$  for some  $p \in (1, 2)$ , while  $\mathcal{L} \in \mathcal{D}_1(\Omega)$  is a integer-multiplicity boundaryless 1-current (here  $\mathcal{D}_k(\Omega)$  denotes the space of  $k$ -currents in  $\Omega$ ). These two variables are related by the equation

$$-\text{Curl } F = b \otimes \mathcal{L}, \quad (2.2)$$

where  $b \in 2\pi\mathbb{Z}$  is the Burgers vector associated to the cluster  $\mathcal{L}$ . Here  $\mathcal{L}$  is identified with the Radon measure  $\mathcal{L} = \tau \mathcal{H}^1 \llcorner_L$ , where  $\mathcal{H}^1$  is the one-dimensional Hausdorff measure restricted to  $L$ , the support of  $\mathcal{L}$ , which is a rectifiable 1-set with unit tangent vector  $\tau$ . For the detailed description and the general properties of these objects we refer to [31, 32].

Following [32, 33], the deformation tensor can be always decomposed as the sum of two gradients, namely

$$F = \nabla \bar{u} + \nabla v = \nabla u, \quad (2.3)$$

where  $\bar{u} \in W^{1,p}(\Omega; \mathbb{T}^3)$  (with  $\mathbb{T}^3$  being the three dimensional flat torus),  $v \in$

$W^{1,p}(\Omega; \mathbb{R}^3)$ , satisfy

$$\begin{cases} \Delta \bar{u} & = 0, \\ -\text{Curl } \nabla \bar{u} & = b \otimes \mathcal{L}, \end{cases}, \quad \begin{cases} \Delta v & = \text{Div } F \\ -\text{Curl } \nabla v & = 0, \end{cases},$$

together with suitable boundary conditions. The maps  $\bar{u}$  and  $v$  are referred to as incompatible and compatible displacements, respectively. It is always possible to consider  $v$  with values in the flat torus as well, in such a way that it is licit to define  $u := \bar{u} + v \in W^{1,p}(\Omega; \mathbb{T}^3)$  to be the total displacement field as in (2.3). If the divergence of the deformation  $F$  belongs to  $L^r(\Omega; \mathbb{R}^3)$  for some  $r \geq 1$ , then from the last equation in (2.4), it is possible to prove (see [32]) that

$$v \in W^{2,r}(\Omega; \mathbb{R}^3). \quad (2.4)$$

Moreover, as admissible deformation fields always satisfy this regularity condition, the compatible displacement  $v$  shows some higher regularity properties than  $\bar{u}$ .

**Set of admissible variables.** We introduce the space of admissible deformation fields  $\mathcal{F}_b$  for the domain  $\Omega$  as follows

$$\mathcal{F}_b(\Omega) := \{F \in L^p(\Omega; \mathbb{R}^{3 \times 3}) : \text{cof } F \in L^{p_2}(\Omega; \mathbb{R}^{3 \times 3}), \det F \in L^{p_3}(\Omega), \text{Div } F \in L^r(\Omega; \mathbb{R}^3), \text{ and } -\text{Curl } F = b \otimes \mathcal{L} \text{ for some dislocation current } \mathcal{L}\}, \quad (2.5)$$

where the exponents  $p, p_2, p_3, r \geq 1$  will be specified later. The variables of the model being the deformation field  $F : \Omega \rightarrow \mathbb{R}^{3 \times 3}$  and its dislocation density, suitable boundary conditions must be prescribed. The Dirichlet boundary datum, in the spirit of the minimum problem in [31–33], can be given by introducing an admissible deformation field  $\hat{F} \in L^p(\hat{\Omega}; \mathbb{R}^{3 \times 3})$  and saying that  $F \in \mathcal{F}_b$  satisfies the Dirichlet boundary condition if  $F|_{\hat{\Omega} \setminus \Omega} = \hat{F}$ . However, since by (2.3), to any admissible field  $F \in \mathcal{F}_b$  there exists a displacement  $u \in W^{1,p}(\Omega; \mathbb{T}^3)$  such that  $\nabla u = F$ , we formulate our problem in terms of  $u$  and correspondingly we will impose Dirichlet boundary conditions on  $u$ . We therefore introduce the class of admissible displacement fields as follows: fix a displacement  $w \in W^{1,p}(\hat{\Omega}; \mathbb{T}^3)$  satisfying the condition

$$\nabla w \in \mathcal{F}_b(\hat{\Omega}),$$

and say that  $u \in W^{1,p}(\Omega; \mathbb{T}^3)$  is an admissible displacement if  $u \in \mathcal{U}(w)$ , where

$$\mathcal{U}(w) := \{u \in W^{1,p}(\Omega; \mathbb{T}^3) : \nabla u \in \mathcal{F}_b(\Omega) \text{ and } u = w \text{ on } \Gamma_D\}. \quad (2.6)$$

The equality  $u = w$  on  $\Gamma_D$  must be understood in the sense of trace, as elements of  $W^{1-1/p,p}(\Gamma_D; \mathbb{T}^3)$ . Further we introduce the class of admissible dislocation currents as

$$\mathcal{R} := \{\mathcal{L} \in \mathcal{D}_1(\hat{\Omega}) : \mathcal{L} \text{ has integer multiplicity, } \partial \mathcal{L} = 0, |\mathcal{L}| < \infty, \text{supp } \mathcal{L} \subset \hat{\Omega}\}. \quad (2.7)$$

Furthermore, for any constant  $C > 0$  we denote by  $\mathcal{R}_C$  the subset of  $\mathcal{R}$  defined as

$$\mathcal{R}_C := \{\mathcal{L} \in \mathcal{R} : |\mathcal{L}| \leq C\}. \quad (2.8)$$

Lastly, a couple  $(u, \mathcal{L}) \in \mathcal{U}(w) \times \mathcal{R}$  is said admissible,  $(u, \mathcal{L}) \in \mathcal{A}(w)$ , if

$$-\text{Curl } \nabla u = b \otimes \mathcal{L}. \quad (2.9)$$

## 2.1 Properties of the energy

The energy of the body depends on the tensor field  $F$  and on its derivatives. The stored-elastic energy density is given by the functional  $W_e(M(F))$ , where  $M(F)$  is the vector of minors of  $F$ , and hence the stored-elastic energy by

$$\mathcal{W}_e(M(F)) = \int_{\Omega} W_e(M(F)) dx. \quad (2.10)$$

We assume that

(E1)  $\mathcal{W}_e$  is polyconvex, i.e.  $W_e$  is convex in  $M(F)$ .

We suppose that  $W_e$  fulfills the following growth condition: there are constants  $c_1, c_2 > 0$ , and  $\delta \geq 0$  such that

(E2)  $W_e(M(F)) \geq c_1(|F|^p + |\text{cof } F|^{p_2} + \delta|\det F|^{p_3}) - c_2$ ,

for some coefficients  $p, p_2, p_3 > 1$  to be specified later. Notice that polyconvexity together with condition (E2) implies lower semi-continuity with respect to the weak convergences of  $F$ ,  $\text{cof } F$ , and  $\det F$  in  $L^p(\Omega; \mathbb{R}^{3 \times 3})$ ,  $L^{p_2}(\Omega; \mathbb{R}^{3 \times 3})$ , and  $L^{p_3}(\Omega)$ , respectively (see, e.g., [4, 14]). It is also assumed that  $W(M(F)) \geq h(\det F)$  for a continuous and positive function  $h$  satisfying  $h(t) \rightarrow \infty$  as  $t \rightarrow 0$  and  $h(t) = +\infty$  for  $t \leq 0$ . The total energy of the system also depends on the derivatives of  $F$ . The microstructure part of the energy related to the presence of dislocations is denoted by  $\mathcal{W}_{\text{dislo}}$  and is taken as a function of the dislocation density  $\Lambda_{\mathcal{L}} := (\mathcal{L} \otimes b)^T$  that we recall is related to the curl of deformation tensor,  $\text{Curl } F$ . We make the following assumption:

(E3)  $\mathcal{W}_{\text{dislo}}$  is l.s.c. with respect to the weak star convergence of measures,

and assume the following growth condition:

(E4)  $\mathcal{W}_{\text{dislo}}(\Lambda_{\mathcal{L}}) \geq c_3|\Lambda_{\mathcal{L}}|(\Omega) - c_4$ ,

for some positive constants  $c_3$  and  $c_4$ . Eventually, we assume that the total energy of the system depends on  $\text{Div } F$  via the higher order term  $\mathcal{W}_d$  in the form

$$\mathcal{W}_d(\text{Div } F) = \int_{\Omega} W_d(\text{Div } F) dx,$$

where

(E5)  $\mathcal{W}_d$  is l.s.c. with respect to the weak topology of  $L^r(\Omega; \mathbb{R}^3)$ ,

(E6)  $\mathcal{W}_d(\text{Div } F) \geq c_5 |\text{Div } F|^r - c_6$ ,

for some positive constants  $c_5$  and  $c_6$ . Summarizing, the total energy of a deformation field  $F$  reads

$$\mathcal{W}(F, DF) = \mathcal{W}_e(M(F)) + \mathcal{W}_{\text{dislo}}(\text{Curl } F) + \mathcal{W}_d(\text{Div } F), \quad (2.11)$$

and satisfies the coercivity condition

$$\begin{aligned} \mathcal{W}(F, DF) &\geq \\ &\geq C (\|F\|_{L^p}^p + \|\text{cof } F\|_{L^{p_2}}^{p_2} + \delta \|\det F\|_{L^{p_3}}^{p_3} + \|\text{Div } F\|_{L^r}^r) + c|\Lambda_{\mathcal{L}}|(\Omega) - \gamma, \end{aligned} \quad (2.12)$$

for suitable positive constant  $C, c, \gamma$ , and  $\delta \geq 0$ , depending on the material properties. We refer to [33] for more detail on the model, and in particular for explicit examples of energies satisfying these properties.

### Time-dependent external load

Let  $T > 0$  and let us consider the time interval  $[0, T]$ . The volume and surface forces are  $f \in C^1([0, T]; L^{p'}(\Omega, \mathbb{R}^3))$  and  $g \in C^1([0, T]; W^{1-1/p', p'}(\Gamma_N, \mathbb{R}^3))$ , satisfying

$$\int_{\Omega} f(t) \, dx + \int_{\Gamma_N} g(t) \, d\mathcal{H}^2 = 0, \quad (2.13)$$

for any  $t \in [0, T]$ . Following the approach introduced in [3], we consider the tensor of external load  $\mathbb{K}(t) \in C^1([0, T]; W^{1, p'}(\Omega; \mathbb{R}^{3 \times 3}))$ , satisfying at each  $t \in [0, T]$ ,

$$\begin{cases} -\text{Div } \mathbb{K}(t) = f(t) & \text{in } \Omega \\ \mathbb{K}N = g(t) & \text{on } \Gamma_N, \\ \mathbb{K}N = 0 & \text{on } \Gamma_D, \end{cases} \quad (2.14)$$

(for the existence of  $\mathbb{K}$  we refer to [3]). The justification for this approach is that in the absence of dislocations, one has  $u \in W^{1, p}(\Omega, \mathbb{R}^3)$  and one recovers by integration by parts the classical expression of the work of the external forces, namely

$$\langle \mathbb{K}(t), \nabla u \rangle = \langle f(t), u \rangle + \langle g(t), u \rangle_{\Gamma_N}. \quad (2.15)$$

However, in the presence of dislocations, such integration by parts cannot be made in a classical manner. Thus, we define the work of the external forces by the term  $\langle \mathbb{K}(t), \nabla u \rangle_{L^{p'}, L^p}$ . Therefore, the total energy at a given time  $t \in [0, T]$  is given by

$$\mathcal{E}(t, u) = \mathcal{W}(\nabla u, D\nabla u) - \langle \mathbb{K}(t), \nabla u \rangle_{L^{p'}, L^p}. \quad (2.16)$$

By Young inequality  $\langle \mathbb{K}(t), F \rangle_{L^{p'}, L^p} \leq \frac{\lambda^{p'}}{p'} \|\mathbb{K}(t)\|_{L^{p'}}^{p'} + \frac{1}{p\lambda^p} \|F\|_{L^p}^p$  for any  $\lambda > 0$  and hence one also has, from (2.12),

$$\begin{aligned} \mathcal{E}(t, u) &\geq \\ &\geq C (\|F\|_{L^p}^p + \|\text{cof } F\|_{L^{p_2}}^{p_2} + \delta \|\det F\|_{L^{p_3}}^{p_3} + \|\text{Div } F\|_{L^r}^r) + c|\Lambda_{\mathcal{L}}|(\Omega) - \gamma, \end{aligned} \quad (2.17)$$

for suitable positive constant  $C, c, \gamma$ , and  $\delta \geq 0$ , depending on the material properties. Note that

$$\partial_t \mathcal{E}(t, u) = \langle \dot{\mathbb{K}}(t), \nabla u \rangle_{L^{p'}, L^p}, \quad (2.18)$$

and thus again by Young inequality, one obtains

$$|\partial_t \mathcal{E}(t, u)| \leq \frac{1}{p'} \|\dot{\mathbb{K}}(t)\|_{L^{p'}}^{p'} + \frac{1}{p} \|\nabla u\|_{L^p}^p. \quad (2.19)$$

In particular, due to estimate (2.17) and the regularity of  $\mathbb{K}$ , one recovers the following important bound:

$$|\partial_t \mathcal{E}(t, u)| \leq C_1(\mathcal{E}(t, u) + C_2), \quad (2.20)$$

for suitable constants  $C_1, C_2 > 0$ .

## 2.2 Static problem

Let us discuss several possible hypotheses according to the results contained in [31–33]:

**(D1) Continuum dislocations as in [31].** In this setting we assume (E1), (E2), and (E3). Moreover, the regularizing term  $W_d = 0$ , whereas the dislocation singularities energy  $\mathcal{W}_{\text{dislo}}$  satisfies the following condition, replacing (E4):

(E4)'  $\mathcal{W}_{\text{dislo}}(\Lambda_{\mathcal{L}}) \geq \kappa \inf_{\mathcal{K}} (\mathcal{H}^1(\mathcal{K}) + \sharp \mathcal{K}) - C$ , where the infimum is computed on all rectifiable and closed 1-sets containing the support of  $\Lambda_{\mathcal{L}}$ ; here  $\sharp \mathcal{K}$  represents the number of connected components of  $\mathcal{K}$ ,  $C > 0$  and  $\kappa > 0$  are material parameters.

The infimum in this condition is assumed to attain the value  $+\infty$  if the family of continuum sets  $\mathcal{K}$  is empty. Notice that the energy is finite only if the dislocation density  $\Lambda_{\mathcal{L}}$  is a continuum dislocation, according to [31]. A physical interpretation of this assumption is also proposed in [31]. Moreover we assume the following conditions on the coefficients in (E2):  $\delta > 0$ ,  $p_2, p_3 > 1$ , and  $1 < p < 2$ . Finally we replace the class of admissible displacement  $\mathcal{U}(w)$  by

$$\mathcal{U}'(w) := \{u \in \mathcal{U}(w) : \text{if } B \subset \Omega \text{ is a ball not intersecting the support of } \Lambda_{\mathcal{L}}, \\ u \in \text{Cart}(B; \mathbb{T}^3) \text{ is a Cartesian map on } B\}. \quad (2.21)$$

The fact that  $u$  restricted to any ball is Cartesian means that its graph, seen as a integral current, is boundaryless (see [31] and [16] for general treatment of Cartesian currents). We emphasize that this hypothesis was first introduced in [28].

**(D2) Regular compatible displacement  $v$ , as in [32].** We assume (E1)–(E6). In this scenario, the compatible deformational part  $v$  of the displacement is smooth enough, i.e.,  $v \in \mathcal{C}^1(\Omega, \mathbb{R}^3)$ , due to the assumption  $r > 3$  in (E6). Moreover we set  $\delta > 0$ ,  $p_2, p_3 > 1$ , and  $1 < p < 2$ .

**(D3) Singular compatible displacement  $v$ , as in [33].** We assume (E1)-(E6).

We suppose that the coefficients in (E2) satisfy  $1 < p < 2$ ,  $p_2 \geq 2$ ,  $p_3 > 1$ ,  $r > \frac{12}{7}$ . Moreover, one of the following two technical conditions are required

$$(E7) \quad \delta > 0;$$

$$(E7)' \quad \delta = 0 \text{ and either } r > \frac{6p}{5p-3} \text{ or } \frac{1}{p} + \frac{1}{p_2} > 1.$$

**Remark 2.1.** Notice that by [33, Lemma 1.1 and Lemma 1.2] (see also the discussion in Section 4 of [33]) in the case (E7)' then the energy satisfies, even if  $\delta = 0$  in hypothesis (E2), the following coercivity condition:

$$\mathcal{W}(F, DF) \geq c_7 \|\det F\|_{L^t}^t - c_8, \quad (2.22)$$

for some positive constants  $c_7$  and  $c_8$  and for  $\frac{1}{t} = \frac{6-2r}{3r} + \frac{1}{p}$ .

Let us discuss the conditions in (D2) and (D3). In the first case, thanks to the results in [32], the fact that  $r > 3$  allows us to characterize the graph of the displacement field  $u$ , seen as an integer multiplicity 3-current in  $\Omega \times \mathbb{T}^3$ . In particular, it turns out that its boundary is an integer multiplicity 2-current in  $\Omega \times \mathbb{T}^3$ , given by

$$\begin{aligned} \partial \mathcal{G}_u(\omega) &= \mathcal{L} \wedge \vec{b}(\omega) + \mathcal{C}_v(\omega) := \\ &= -\frac{1}{2\pi} \int_L \int_0^{2\pi} \langle \omega(x, \frac{b\theta}{2\pi}), \bar{\tau} \wedge \bar{b} \rangle d\theta d\mathcal{H}^1(x) \\ &\quad + \frac{1}{2\pi} \int_L \int_0^{2\pi} \langle \omega(x, \frac{b\theta}{2\pi} + v(x)), \frac{\partial \bar{v}}{\partial \tau} \wedge \bar{b} \rangle d\theta d\mathcal{H}^1(x), \end{aligned} \quad (2.23)$$

for any 2-form  $\omega \in \mathcal{D}^2(\Omega \times \mathbb{R}^3)$  being  $2\pi$ -periodic in the second variable. In the formula above  $\tau$  is the oriented tangent vector to the dislocation line  $L$ , and  $\bar{\tau} = (\tau, 0) \in \mathbb{R}^6$ ,  $\bar{b} = (b, 0) \in \mathbb{R}^6$ ,  $\frac{\partial \bar{v}}{\partial \tau} = (0, \frac{\partial v}{\partial \tau}) \in \mathbb{R}^6$ , and  $v \in \mathcal{C}^1(\Omega, \mathbb{R}^3)$  is the compatible displacement associated to  $u$ . In particular, it is proven in [32, Theorem 4.6] that

$$M(\partial \mathcal{G}_{u+v}) \leq C(1 + \|Dv\|_{L^\infty(\Omega)}) |\mathcal{L} \otimes b|(\Omega),$$

in such a way that a bound on the dislocation density provides a bound on the mass of the boundary, as required to have compactness (see next theorem). The condition  $\text{Div } F \in L^r$  with  $r > 3$  together with  $F \in L^p$  with  $p < 2$  might appear as a strong assumption. In the setting (D3) the requirement  $r > 3$  is relaxed (and indeed  $r < 2$  is admissible), but we add the hypothesis that  $p_2 \geq 2$  in order to control the part of the current  $\partial \mathcal{G}_u$  given by  $\mathcal{C}_v$ . Indeed, if  $p_2 \geq 2$  it is proved that  $\mathcal{C}_v$  vanishes, and again it is possible to control the mass of  $\partial \mathcal{G}_u$  (see [33]). It is also discussed in [33] why the hypothesis  $p_2 \geq 2$  is rather natural from a modeling viewpoint. It is now possible to prove that the energy has compact sublevels.

**Theorem 2.2.** *Assume that one of the working hypotheses (D1), (D2) or (D3) holds. For all  $t \in [0, T]$  the energy  $\mathcal{E}(t, \cdot) : \mathcal{U}(w) \rightarrow \mathbb{R} \cup \{+\infty\}$  has compact sublevels. Namely, let  $(u_k, \mathcal{L}_k)_k \in \mathcal{A}(w)$  be a sequence such that*

$$\mathcal{E}(t, u_k) < C < +\infty,$$

for all  $k > 0$ , then there exists a (not relabelled) subsequence such that  $(u_k, \mathcal{L}_k) \rightharpoonup (u, \mathcal{L}) \in \mathcal{A}(w)$ , and  $\mathcal{E}(t, u) \leq \liminf_{k \rightarrow \infty} \mathcal{E}(t, u_k)$ .

*Proof.* Assume  $\mathcal{E}(t, u_k) < C$  for all  $k > 0$ . Then by the equi-coercivity (2.17), which actually holds in the scenarios (D2) and (D3), there exist  $u \in W^{1,p}(\Omega; \mathbb{T}^3)$ ,  $A \in L^{p_2}(\Omega; \mathbb{R}^{3 \times 3})$ ,  $D \in L^{p_3}(\Omega)$ ,  $G \in L^r(\Omega; \mathbb{R}^3)$ , and  $\mathcal{L} \in \mathcal{D}_1(\Omega)$ , such that

$$u_k \rightharpoonup u \quad \text{weakly in } W^{1,p}(\Omega; \mathbb{T}^3), \quad (2.24)$$

$$\text{cof } F_k \rightharpoonup A \quad \text{weakly in } L^{p_2}(\Omega; \mathbb{R}^{3 \times 3}), \quad (2.25)$$

$$\det F_k \rightharpoonup D \quad \text{weakly in } L^{p_3}(\Omega), \quad (2.26)$$

$$\text{Div } F_k \rightharpoonup G \quad \text{weakly in } L^r(\Omega; \mathbb{R}^3), \quad (2.27)$$

$$\mathcal{L}_k \rightharpoonup \mathcal{L} \quad \text{weakly in } \mathcal{D}_1(\Omega). \quad (2.28)$$

Moreover, by the identities  $-\text{Curl } \nabla u_k = b \otimes \mathcal{L}_k$  and (2.27)-(2.28), it is easy to see that  $-\text{Curl } \nabla u = b \otimes \mathcal{L}$  and  $\text{Div } \nabla u = G$ . Denote  $F := \nabla u$ . Notice that in the case (D1) the convergence of the divergence is missing. In order to prove the statement we have to show that  $\text{cof } F = A$ , and  $\det F = D$ . Let us discuss the three cases (D1), (D2) or (D3) separately. For (D3), we apply [33, Theorem 3.3] (this actually is the Federer-Flemming closure theorem for integral currents, see also [16, Theorem 3.2.2] for cartesian maps), so that we have to check that the maps  $u_k$  have the properties that their graphs  $\mathcal{G}_{u_k}$  are integral currents in  $\mathcal{D}_3(\Omega; \mathbb{T}^3)$  with equibounded boundary. But this is guaranteed by [33, Theorem 4.9] which in turn characterizes the boundary of  $\mathcal{G}_{u_k}$  thanks to the fact that  $p_2 \geq 2$ , and that the dislocation currents  $\mathcal{L}_k$  are equibounded. Eventually, the lower-semicontinuity of the energy follows from (E1), (E3), and (E5).

In the case (D2) the required closeness of admissible states is ensured again by Theorem [33, Theorem 3.3], but in order to control the boundaries of the graphs of  $u_k$  we have to employ [32, Theorem 4.6]. Let us stress that in this case the hypothesis  $r > 3$  compensates the lack of integrability of the cofactor (namely we only have  $p_2 > 1$ ). Again the lower-semicontinuity of the energy derives from (E1), (E3), and (E5).

In the case (D1) we have to argue differently. Actually, the proof relies on suitable application of Golab Theorem, as in [31, Theorem 5.6]. We refer to this for the complete discussion.  $\square$

## 2.3 Dissipation

We introduce the concept of dissipation distance between to internal admissible states. Let  $u_1, u_2 \in \mathcal{U}(w)$  for a Dirichlet datum  $w \in W^{1,p}(\hat{\Omega}; \mathbb{T}^3)$  with  $\nabla w \in \mathcal{F}_b(\hat{\Omega})$ . Being admissible,  $u_1$  and  $u_2$  satisfy

$$-\text{Curl } \nabla u_i = b \otimes \mathcal{L}_i, \quad i = 1, 2, \quad (2.29)$$

for some integral 1-currents  $\mathcal{L}_i \in \mathcal{D}_1(\Omega)$ . Then the dissipation distance between the two states  $(u_1, \mathcal{L}_1)$  and  $(u_2, \mathcal{L}_2)$  is given by

$$\hat{\mathcal{D}}((u_1, \mathcal{L}_1), (u_2, \mathcal{L}_2)) = \mathcal{D}(\mathcal{L}_1, \mathcal{L}_2) = \gamma d_F(\mathcal{L}_1, \mathcal{L}_2), \quad (2.30)$$

where  $\gamma > 0$  is a constant and  $d_F$  is the flat distance in  $\mathcal{D}_1(\Omega)$  (see [20]). Keeping into account that  $\mathcal{L}_i$  are closed 1-currents, this is defined in the following equivalent way:

$$d_F(\mathcal{L}_1, \mathcal{L}_2) := \inf\{|\mathcal{S}| : \mathcal{S} \in \mathcal{D}_2(\Omega) \text{ with } \partial\mathcal{S} = \mathcal{L}_1 - \mathcal{L}_2\}. \quad (2.31)$$

The flat distance satisfies, by definition,

$$d_F(\mathcal{L}_1, \mathcal{L}_2) = d_F(\mathcal{L}_1 - \mathcal{L}_2, 0). \quad (2.32)$$

The following well-known result (see, e.g., [20]) will be crucial for our subsequent discussion.

**Theorem 2.3.** *Let  $\mathbb{L} = \{\mathcal{L}_i\}_i \subset \mathcal{D}_1(\Omega)$  be a family of boundary-less integral 1-currents such that*

$$\sup_i |\mathcal{L}_i| \leq C < \infty. \quad (2.33)$$

*Then the family  $\mathbb{L}$  is relatively compact with respect to the weak topology of  $\mathcal{D}_1(\Omega)$ ; namely, for any sequence  $(\mathcal{L}_k)_k \subset \mathbb{L}$  there is an integral 1-current  $\mathcal{L}$  such that, up to a further subsequence,  $\mathcal{L}_k \rightharpoonup \mathcal{L}$  weakly in  $\mathcal{D}_1(\Omega)$ .*

*Moreover, for any sequence  $(\mathcal{L}_k)_k \subset \mathbb{L}$  and  $\mathcal{L} \in \mathbb{L}$  satisfying (2.33), the following equivalence holds true*

$$d_F(\mathcal{L}_k, \mathcal{L}) \rightarrow 0 \text{ iff } \mathcal{L}_k \rightharpoonup \mathcal{L} \text{ weakly in } \mathcal{D}_1(\Omega). \quad (2.34)$$

The last assertion can be found in [20, Theorem 8.2.1]. As a consequence of Theorem 2.3, the set  $\mathcal{R}_C$  introduced in (2.8) is a sequentially weakly compact subset of  $\mathcal{D}_1(\Omega)$ .

**Definition 1** (Total dissipation). *The total dissipation of a process  $u : [t_1, t_2] \rightarrow W^{1,p}(\Omega; \mathbb{T}^3)$  such that  $(u(t), \mathcal{L}(t)) \in \mathcal{A}(w)$  for any  $t \in [t_1, t_2]$ , is defined as follows:*

$$\text{Diss}_{\mathcal{D}}(\mathcal{L}; [t_1, t_2]) := \sup \sum_{i=1}^{n-1} \mathcal{D}(\mathcal{L}(r_{i+1}), \mathcal{L}(r_i)), \quad (2.35)$$

*where the supremum is computed over all partitions  $t_1 = r_1 < r_2 < \dots < r_n = t_2$  and all  $n > 1$ .*

**Theorem 2.4.** *Set  $(\bar{u}, \bar{\mathcal{L}}) \in \mathcal{A}(w)$ . Under the assumptions of Theorem 2.2, there exists a minimum  $(u, \mathcal{L}) \in \mathcal{A}(w)$  of the energy*

$$(u, \mathcal{L}) \mapsto \mathcal{E}(t, u) + \mathcal{D}(\mathcal{L}, \bar{\mathcal{L}}).$$

*Proof.* By the direct method of the calculus of variation, this is an immediate corollary of Theorems 2.2, once it is proven that the flat distance is lower semi-continuous (see also the discussion in Section 3.2 of [22]). Let us verify that  $d_F : \mathcal{R}_C \times \mathcal{R}_C \rightarrow [0, \infty)$  is lower-semicontinuous. Let  $\mathcal{L}_k$  and  $\hat{\mathcal{L}}_k$  be two sequences in

$\mathcal{R}_C$  converging weakly to  $\mathcal{L}$  and  $\hat{\mathcal{L}}$  respectively. Let  $\mathcal{S}_k \in \mathcal{D}_2(\Omega)$  be a quasi-minimizer for the distance  $d_F(\mathcal{L}_k, \hat{\mathcal{L}}_k)$ , that is, it holds

$$\partial\mathcal{S}_k = \mathcal{L}_k - \hat{\mathcal{L}}_k, \quad |\mathcal{S}_k| < d_F(\mathcal{L}_k, \hat{\mathcal{L}}_k) + \frac{1}{k}, \quad (2.36)$$

It is easy to see that the sequence  $\{\mathcal{S}_k\}_k$  admits a (not relabeled) subsequence such that  $\mathcal{S}_k \rightharpoonup \mathcal{S}$ , and it is clear that  $\partial\mathcal{S} = \mathcal{L} - \hat{\mathcal{L}}$ , so that we infer  $d_F(\mathcal{L}, \hat{\mathcal{L}}) \leq |\mathcal{S}|$ . Moreover, from (2.36) and the lower-semicontinuity of the mass, it follows that

$$|\mathcal{S}| \leq \liminf_{k \rightarrow \infty} |\mathcal{S}_k| \leq \liminf_{k \rightarrow \infty} d_F(\mathcal{L}_k, \hat{\mathcal{L}}_k). \quad (2.37)$$

Hence, we conclude  $d_F(\mathcal{L}, \hat{\mathcal{L}}) \leq \liminf_{k \rightarrow \infty} d_F(\mathcal{L}_k, \hat{\mathcal{L}}_k)$ , that is the claim.  $\square$

### 3 Quasi-static evolution

In this section we study the problem of existence of a quasi-static evolution related to the energy  $\mathcal{E}$  with dissipation distance  $\mathcal{D}$ . Let us introduce the concept of stable states: fix  $t \in [0, T]$  we define

$$\mathcal{S}(t) := \{(u, \mathcal{L}) \in \mathcal{A}(w) : \text{for all } (\hat{u}, \hat{\mathcal{L}}) \in \mathcal{A}(w), \mathcal{E}(t, u) \leq \mathcal{E}(t, \hat{u}) + \mathcal{D}(\mathcal{L}, \hat{\mathcal{L}})\}. \quad (3.1)$$

Moreover, set

$$\mathcal{S}_{[0, T]} := \cup_{t \in [0, T]} (t, \mathcal{S}(t)) \subset [0, T] \times \mathcal{A}(w). \quad (3.2)$$

Following the classical theory of energetic formulation for quasi-static rate-independent processes [23], we introduce the definition of solution as follows:

**Definition 2** (Energetic solution). *Given a Dirichlet condition  $w \in W^{1,p}(\hat{\Omega}; \mathbb{T}^3)$  such that  $\nabla w \in \mathcal{F}_b(\hat{\Omega})$  and an external force  $\mathbb{K} \in C^1([0, T]; W^{1,p'}(\Omega; \mathbb{R}^{3 \times 3}))$  we say that a function  $(u, \mathcal{L}) : [0, T] \rightarrow \mathcal{A}(w)$  is an energetic solution with initial datum  $(u_0, \mathcal{L}_0) \in \mathcal{S}(0)$  if  $u(0) = u_0$ ,  $\mathcal{L}(0) = \mathcal{L}_0$ , and the two following conditions are satisfied*

(S) *Stability condition: for all  $t \in [0, T]$  and any  $(\hat{u}, \hat{\mathcal{L}}) \in \mathcal{A}(w)$  it holds*

$$\mathcal{E}(t, u(t)) \leq \mathcal{E}(t, \hat{u}) + \mathcal{D}(\mathcal{L}(t), \hat{\mathcal{L}}). \quad (3.3)$$

(E) *Energy balance: for all  $t \in [0, T]$  it holds*

$$\mathcal{E}(t, u(t)) + \text{Diss}_{\mathcal{D}}(u; [0, t]) = \mathcal{E}(0, u_0) + \int_0^t \partial_s \mathcal{E}(s, u(s)) ds. \quad (3.4)$$

In terms of stable states, condition (S) is equivalent to say that, for all  $t \in [0, T]$ , we have  $(u(t), \mathcal{L}(t)) \in \mathcal{S}(t)$ .

### 3.1 Helly's selection principle

In order to prove existence of an energetic solution, we rely on the general results provided by Mielke and coauthors (see, e.g., [22, 23]). In particular, we need a suitable version of the Helly's selection principle. To this aim we must check that our chosen framework is compatible with the hypotheses of the theory of rate-independent systems [21]. First, let us recall that the dissipation distance, namely the flat distance, is defined on the topological Hausdorff space of closed 1-dimensional integral currents. We recall that the lower semicontinuity of the flat distance was proved in Theorem 2.4. Moreover, by [20, Theorem 8.2.1], the continuity of the flat norm for a fixed  $\mathcal{L}$  holds, namely (2.34). Thus the following continuity property holds true:

**Lemma 1** (Continuity of the flat distance). *Let  $\mathcal{L}_k$  and  $\hat{\mathcal{L}}_k$  be two sequences in  $\mathcal{R}_C$  converging in the sense of currents to  $\mathcal{L}, \hat{\mathcal{L}} \in \mathcal{R}_C$ , respectively. Then*

$$\lim_{k \rightarrow \infty} d_F(\mathcal{L}_k, \hat{\mathcal{L}}_k) = d_F(\mathcal{L}, \hat{\mathcal{L}}).$$

*Proof.* We have that  $\mathcal{L}_k - \hat{\mathcal{L}}_k$  weakly converges to  $\mathcal{L} - \hat{\mathcal{L}}$ , and

$$\begin{aligned} \limsup_{k \rightarrow \infty} d_F(\mathcal{L}_k, \hat{\mathcal{L}}_k) &= \limsup_{k \rightarrow \infty} d_F(\mathcal{L}_k - \hat{\mathcal{L}}_k, 0) \leq \\ \limsup_{k \rightarrow \infty} d_F(\mathcal{L}_k - \hat{\mathcal{L}}_k, \mathcal{L} - \hat{\mathcal{L}}) + d_F(\mathcal{L} - \hat{\mathcal{L}}, 0) &= d_F(\mathcal{L}, \hat{\mathcal{L}}), \end{aligned}$$

the first inequality deriving from the triangle inequality, and the last equality being in force by (2.34). Hence we get upper-semicontinuity, which together with the lower-semicontinuity established in Theorem 2.4 provides the desired continuity.  $\square$

After this check, we observe that we are under the hypotheses of [22, Theorem 5.1] with  $\mathcal{V}(t) = \mathcal{R}_C$ , and thus infer the following statement:

**Proposition 3.1.** *Let  $\mathcal{L}_n : [0, T] \rightarrow \mathcal{R}_C$  for some constant  $C > 0$ , and assume that*

$$Diss_{\mathcal{D}}(\mathcal{L}_n; [0, T]) \leq C', \tag{3.5}$$

*for all  $n > 0$  and for a constant  $C' > 0$ . Then there exist a function  $\varphi \in BV([0, T]; \mathbb{R})$  and  $Y \in BV_{\mathcal{D}}([0, T]; \mathcal{R}_C)$  such that, up to a subsequence,*

- (a)  $\varphi_n(t) := Diss_{\mathcal{D}}(\mathcal{L}_n; [0, t]) \rightarrow \varphi(t)$  for all  $t \in [0, T]$ ,
- (b)  $\mathcal{L}_n(t) \rightarrow \mathcal{L}(t)$  for all  $t \in [0, T]$ ,
- (c)  $Diss_{\mathcal{D}}(\mathcal{L}_n : [t_1, t_2]) \leq \varphi(t_2) - \varphi(t_1)$  for all  $0 \leq t_1 < t_2 \leq T$ .

### 3.2 Quasi-statics existence result

The proof of existence of a quasi-static evolution relies on the fact that our model [31–33] indeed applies to the framework of energetic evolution for nonconvex problem. Specifically, in order to prove our main result Theorem 3.2, stating the existence

of an energetic solution to the quasi-static evolution of dislocation clusters in single crystals, we consider the standard scheme introduced in [22, Theorem 5.2]. To this aim, we collect here some useful properties of the dissipation and the energy functional.

(A1) The dissipation distance satisfies

$$\begin{aligned} (i) \quad & \forall \mathcal{L}_1, \mathcal{L}_2 \in \mathcal{D}_1(\Omega) : \quad d_F(\mathcal{L}_1, \mathcal{L}_2) = 0 \Leftrightarrow \mathcal{L}_1 = \mathcal{L}_2, \\ (ii) \quad & \forall \mathcal{L}_1, \mathcal{L}_2, \mathcal{L}_3 : \quad d_F(\mathcal{L}_1, \mathcal{L}_2) \leq d_F(\mathcal{L}_1, \mathcal{L}_3) + d_F(\mathcal{L}_3, \mathcal{L}_2). \end{aligned}$$

(A2) There exist constants  $C_1, C_2 > 0$  such that for all  $u^* \in \mathcal{A}(w)$  : if for all  $t \in [0, T]$  we have  $\mathcal{E}(t, u^*) < \infty$ , then

$$\begin{aligned} \partial_t \mathcal{E}(\cdot, u^*) : [0, T] &\rightarrow \mathbb{R} \text{ is measurable and} \\ |\partial_t \mathcal{E}(t, u^*)| &\leq C_1(\mathcal{E}(t, u^*) + C_2). \end{aligned} \tag{3.6}$$

(A3) For all  $t \in [0, T]$  the energy  $\mathcal{E}(t, \cdot) : \mathcal{U}(w) \rightarrow \mathbb{R} \cup \{+\infty\}$  has compact sublevels and  $\mathcal{D} : \mathcal{R}_C \times \mathcal{R}_C$  is lower semicontinuous for any  $C > 0$ .

(A4) Let  $C > 0$  be a constant. Whenever  $\mathcal{L}_k$  is a sequence in  $\mathcal{R}_C$  and  $\mathcal{L} \in \mathcal{R}_C$ , then property (2.34) holds true.

(A5) The following uniform continuity of the power holds true:  $\forall C > 0, \forall \epsilon > 0, \exists \delta > 0$ :

$$\mathcal{E}(t, u) < C, \quad |t - s| < \delta \quad \Rightarrow \quad |\partial_t \mathcal{E}(t, u) - \partial_t \mathcal{E}(s, u)| \leq \epsilon. \tag{3.7}$$

(A6) The dissipation distance  $d_F$  is continuous on  $\mathcal{R}_C \times \mathcal{R}_C$ .

Let us check the validity of such hypotheses in our setting: property (A1) is immediate from the properties of the distance. Fixing a boundary Dirichlet datum, property (A2) is (2.20). Similarly (A5) follows from (2.18) and the regularity of the external load  $\mathbb{K}$  which belongs to  $C^0([0, T]; W^{1,p'}(\Omega; \mathbb{R}^{3 \times 3}))$ . Property (A3) has been proved in Theorem 2.4, whereas property (A4) is the content of Theorem 2.3. Finally property (A6) is guaranteed by Lemma 1. The abstract existence result for energetic solution is given by the following theorem:

**Theorem 3.2** (Existence result; Theorem 5.2 in [22]). *Fix  $w \in W^{1,p}(\hat{\Omega}; \mathbb{T}^3)$  with  $\nabla w \in \mathcal{F}_b$ . Assume that the energy and dissipation  $\mathcal{E}$  and  $\mathcal{D}$  satisfy conditions (A1)-(A6). Then, for each  $(u_0, \mathcal{L}_0) \in \mathcal{S}(0)$  there exists an energetic solution  $(u, \mathcal{L}) : [0, T] \rightarrow \mathcal{A}(w) \times \mathcal{R}$  as in Definition 2.*

The proof follows the lines of [22, Theorem 5.2] For completeness, we sketch it with our notations.

*Proof.* Let us choose a sequence of partitions  $0 = t_0 < t_1 < \dots < t_n = T$  whose fineness  $\eta_n := \max_i |t_i - t_{i-1}|$  tends to 0 as  $n \rightarrow \infty$ . Recursively we solve the time-incremental minimization problem  $(u_i, \mathcal{L}_i) \in \operatorname{argmin} \mathcal{E}(t_i, \cdot) + \mathcal{D}(\cdot, \mathcal{L}_{i-1})$ , which is solvable thanks to Theorem 2.4 (consequence of (A3)). The piecewise constant interpolation function  $(U_n, \mathcal{L}_n)$  defined via

$$u_n(t) := u_i \text{ if } t \in [t_i, t_{i+1}), \quad \mathcal{L}_n(t) := \mathcal{L}_i \text{ if } t \in [t_i, t_{i+1}), \quad (3.8)$$

satisfies the a-priori estimates

$$\forall t \in [0, T] \quad \mathcal{E}(t, u_n(t)) < C, \quad \text{and} \quad \operatorname{Diss}_{\mathcal{D}}(\mathcal{L}_n; [0, T]) < C, \quad (3.9)$$

for a constant  $C > 0$  independent of  $n$ . These are consequence of (A2) and (A5), see [22, Section 3.2]. We set  $\theta_n(t) := \partial_t \mathcal{E}(t, u_n(t))$ . Now, we apply the generalized Helly's selection principle and passing to a subsequence we get the existence of functions  $\delta$ ,  $\mathcal{L}$ , and  $\theta$ , such that

$$\delta_n(t) := \operatorname{Diss}_{\mathcal{D}}(\mathcal{L}_n; [0, t]) \rightarrow \delta(t) \quad \forall t \in [0, T], \quad (3.10)$$

$$\mathcal{L}_n(t) \rightharpoonup \mathcal{L}(t) \quad \forall t \in [0, T], \quad (3.11)$$

$$\theta_n \rightharpoonup \theta \text{ weakly star in } L^\infty([0, T]). \quad (3.12)$$

The function  $\theta_{\sup}(t) := \limsup_{n \rightarrow \infty} \theta(t)$  for any  $t \in [0, T]$  belongs to  $L^\infty([0, T])$  and satisfies  $\theta \leq \theta_{\sup}$  by Fatou's Lemma. For any fixed  $t \in [0, T]$  it holds  $\mathcal{E}(t, u_n(t)) < C$  so that by compactness of the sublevels of the energy there are a subsequence of  $n$  denoted by  $k_n^t$  (dependent on  $t$ ) and a function  $u(t) \in \mathcal{A}(w)$  such that

$$\theta_{k_n^t}(t) \rightarrow \theta_{\sup}(t) \quad \text{and} \quad u_{k_n^t}(t) \rightharpoonup u(t) \text{ in } \mathcal{A}(w). \quad (3.13)$$

We will now see that the defined function  $t \mapsto (u(t), \mathcal{L}(t))$  satisfies (S) and (E). First we observe that condition (A6) implies that the equibounded (in energy) stable states are weakly closed, and this is sufficient to conclude that the couple  $(u(t), \mathcal{L}(t))$  is stable. Again, as in [22, Theorem 5.2], we infer that  $\theta_{\sup}(t) = \partial_t \mathcal{E}(t, u(t))$  and the upper energy estimate

$$\mathcal{E}(t, u(t)) + \operatorname{Diss}_{\mathcal{D}}(\mathcal{L}; [0, t]) \leq \mathcal{E}(0, u_0) + \int_0^t \partial_t \mathcal{E}(s, u(s)) ds. \quad (3.14)$$

Since  $\theta_{\sup} = \partial_t \mathcal{E}(\cdot, u(\cdot)) \in L^\infty([0, T])$  we are in position to apply [22, Proposition 5.7] to infer the opposite inequality, concluding the proof of (E).  $\square$

Eventually, as in [22, Theorem 5.2], we infer the following auxiliary result:

**Theorem 3.3.** *For any sequence of partitions  $\{\Pi_l\}_l$ ,  $\Pi_l := \{0 = t_0^l < t_1^l < \dots < t_{n_l}^l = T\}$  whose fineness  $\eta_l$  tends to 0 as  $l \rightarrow \infty$ , the corresponding interpolant solutions  $(u_l(t), \mathcal{L}_l(t))$ , up to a subsequence, converges to an energetic solution  $(u(t), \mathcal{L}(t))$ , in the following sense*

- (i)  $\forall t \in [0, T] \quad \mathcal{L}_l(t) \rightharpoonup \mathcal{L}(t)$ ,
- (ii)  $\forall t \in [0, T] \quad \operatorname{Diss}_{\mathcal{D}}(\mathcal{L}_l; [0, t]) \rightarrow \operatorname{Diss}_{\mathcal{D}}(\mathcal{L}; [0, t])$ ,
- (iii)  $\forall t \in [0, T] \quad \mathcal{E}(t, u_l(t)) \rightarrow \mathcal{E}(t, u(t))$ ,
- (iv)  $\partial_t \mathcal{E}(\cdot, u_l(\cdot)) \rightarrow \partial_t \mathcal{E}(\cdot, u(\cdot))$  in  $L^1([0, T])$ .

## 4 Open problems

We list here some interesting generalization we are not able to cover at the present stage.

### 4.1 Time-dependent Dirichlet boundary condition

The validity of (3.9) relies on the fact that  $u_j$  and  $u_{j-1}$  have the same boundary conditions, since it is crucial that the following inequality can be written

$$\mathcal{E}(t_j, u_j) + \mathcal{D}(\mathcal{L}_j, \mathcal{L}_{j-1}) \leq \mathcal{E}(t_j, u_{j-1}),$$

by minimality of  $u_j$  at time  $t = t_j$  in the time incremental problem. If we consider a non-constant boundary condition  $t \mapsto w(t)$ , we must first correct  $u_{j-1}$  by adding  $\delta w_{j-1} = w_j - w_{j-1}$  in such a way that  $u_{j-1} + \delta w_{j-1}$  has the same boundary condition as  $u_j$ . Therefore we are led to estimate

$$\delta W := |\mathcal{W}(\nabla u_{j-1}) - \mathcal{W}(\nabla u_{j-1} + \nabla \delta w_{j-1})|. \quad (4.1)$$

We see two ways for proceeding. Letting  $W(F) := W_e(M(F))$ , the first consists in making a standard assumption of the type  $F^T DW(F) \leq C(W(F)+1)$ , as in [5,6] (see also [19]), where  $DW$  stands for the Fréchet differential of  $W$ . Then, following [5,6], one has (see [19, Eq. (14)])

$$\begin{aligned} \delta W &:= |\mathcal{W}(\nabla u_{j-1}) - \mathcal{W}(\nabla u_{j-1}(\mathbb{I} + (\nabla u_{j-1})^{-1} \nabla \delta w_{j-1}))| \\ &\leq C(W(\nabla u_{j-1}) + 1) |(\nabla u_{j-1})^{-1} \nabla \delta w_{j-1}|. \end{aligned} \quad (4.2)$$

Due to the integrability of  $(\nabla u_{j-1})^{-1} = \text{cof}^T \nabla u_{j-1} (\det \nabla u_{j-1})^{-1}$  (at best  $L^{p_2}$  with  $p_2 \geq 2$ ) and  $\nabla \delta w_{j-1} \in L^p$  with  $p < 2$ , we were not able to bound the right-hand side of (4.2) by Hölder's-like inequalities. Note that in [19,21], in the absence of dislocations, this estimate was possible in view of the better regularity of the strains.

The second way consists in writing  $DW(F)[\nabla \delta w_{j-1}]$  as  $\partial_F W_e(M(F))[\nabla \delta w_{j-1}] + \partial_C W_e(M(F))DC(F)[\nabla \delta w_{j-1}] + \partial_J W_e(M(F))DJ(F)[\nabla \delta w_{j-1}]$ , where we have noted  $C := \text{cof } F$ ,  $J = \det F$ . For simplicity take the last term zero (see Remark 2.1). Then the first term is bounded, since  $\partial_F W_e \sim |F|^{p-1} \in L^{p'}$ . As for the second, let us first compute the differential of the cofactor. According to [10] one has

$$C := \text{cof } F = \frac{1}{2} F \times F, \quad \text{with } (A \times B)_{il} = \epsilon_{ijk} \epsilon_{lmn} A_{jm} B_{kn}.$$

and hence

$$D \text{cof } F[H] = F \times H. \quad (4.3)$$

Thus

$$\partial_C W_e(M(F))DC(F)[\nabla \delta w_{j-1}] := \partial_C W_e(M(F))F \times \nabla \delta w_{j-1}. \quad (4.4)$$

Again one has  $\partial_C W_e(M(F)) \sim |C|^{p_2-1} \in L^{p'_2}$  but  $F \times \nabla \delta w_{j-1}$  does not belong to  $L^{p_2}$ ,  $p_2 \geq 2$ , since  $F, \nabla w_{j-1} \in L^p$ ,  $1 \leq p < 2$ .

It is also remarkable that a multiplicative decomposition of the displacement  $u(t) = w(t) \circ v$  as suggested in [15], here  $v$  satisfying  $v = Id$  on  $\Gamma_D$ , does not help in our setting. At the present stage we see that the main difficulty relies in the fact that, if we want to impose the presence of dislocation at the boundary  $\Gamma_D$  (which is essential to guarantee that the dislocation cluster in  $\Omega$  is not null), one has to assume that  $\nabla w(t)$  is singular on  $\Gamma_D$ , and in particular is not square-integrable.

## 4.2 Generalization to linearly independent Burgers vectors

In all the scenarios (D1), (D2), and (D3), the admissible deformation fields  $F$  are assumed to satisfy the condition

$$-\text{Curl } F = b \otimes \mathcal{L}. \quad (4.5)$$

Since  $b$  is fixed we see that all the Burgers vector of the related cluster have the same direction. The generalization of this setting would include all the possible directions, and hence we would obtain a formula like

$$-\text{Curl } F = e_1 \otimes \mathcal{L}_1 + e_2 \otimes \mathcal{L}_2 + e_3 \otimes \mathcal{L}_3, \quad (4.6)$$

for three integral currents  $\mathcal{L}_1$ ,  $\mathcal{L}_2$ , and  $\mathcal{L}_3$ . The main problem in this case arises from the closedness of the sublevels of the energy, which in the cases discussed here is ensured by the characterization of the graphs of the involved displacement field  $u$ , where  $F = \nabla u$ . Such characterization under the general condition (4.6) is currently missing. Some partial results are available in [33], but only in some constrained geometric setting on the dislocation locations. Hence, also the statics case in the setting (4.6) is yet an open problem.

In [33] we conjecture that for a general  $F = \nabla u$ , with  $u \in W^{1,p}(\Omega; \mathbb{T}^3)$ , satisfying (4.6), the graph of  $u$  is an integer multiplicity current in  $\Omega \times \mathbb{T}^3$  with integral boundary as soon as the cofactor of  $F$  turns out to be square integrable. More specifically, if  $\text{cof } F \in L^2(\Omega; \mathbb{R}^{3 \times 3})$ , then we expect that the graph  $\mathcal{G}_u$  of  $u$  has boundary  $\partial \mathcal{G}_u$  satisfying

$$\begin{aligned} \partial \mathcal{G}_u(\omega) &= \sum_{i=1}^3 \mathcal{L}_i \wedge e_i(\omega) \\ &= \sum_{i=1}^3 \int_0^{2\pi} \int_{S^i} \langle d\omega(x, e_i \theta + \hat{u}_i(x)), (s_1, 0) \wedge (s_2, 0) \wedge \vec{e}_i \rangle d\mathcal{H}^2(x) d\theta, \end{aligned}$$

for all 3-forms  $\omega \in \mathcal{D}^3(\Omega \times \mathbb{R}^3)$  that are  $2\pi$ -periodic in the second variable. In this formula the functions  $\hat{u}_i$  are specific harmonic maps defined via

$$\hat{u}_i(x) = -e_i \int_{S^i} \nabla \Phi(x' - x) \cdot N(x') d\mathcal{H}^2(x'), \quad (4.7)$$

where  $\Phi$  is the the fundamental solution of the Laplacian in  $\mathbb{R}^3$ , with  $\Delta\Phi = \delta_0$ , and  $S^i$  is any closed surface with boundary  $\mathcal{L}_i$  and unit normal  $N$ . In the formula above the vectors  $s_1$  and  $s_2$  form an orthonormal basis of the tangent plane to  $S^i$ .

## Acknowledgements

We acknowledge the support of the FCT Starting Grant “ Mathematical theory of dislocations: geometry, analysis, and modeling” (IF/00734/2013).

## References

- [1] R. Alicandro, L. De Luca, A. Garroni, and M. Ponsiglione. Minimising movements for the motion of discrete screw dislocations along glide directions. *Calc. Var. Partial Differ. Equ.*, 56(5):19, 2017.
- [2] R. Alicandro, L. De Luca, A. Garroni, and M. Ponsiglione. Metastability and dynamics of discrete topological singularities in two dimensions: a  $\Gamma$ -convergence approach. *Arch. Ration. Mech. Anal.*, 214(1):269–330, 2014.
- [3] S. Amstutz and N. Van Goethem. Incompatibility-governed elasto-plasticity for continua with dislocations. *Proc. R. Soc. A*, 473(2199), 2017.
- [4] J. M. Ball. Convexity conditions and existence theorems in nonlinear elasticity. *Arch. Ration. Mech. Anal.*, 63:337–403, 1977.
- [5] J. M. Ball. Some open problems in elasticity. In *Geometry, mechanics, and dynamics. Volume in honor of the 60th birthday of J. E. Marsden*, pages 3–59. New York, NY: Springer, 2002.
- [6] P. Bauman, D. Phillips, and N. C. Owen. Maximal smoothness of solutions to certain Euler-Lagrange equations from nonlinear elasticity. *Proc. R. Soc. Edinb., Sect. A, Math.*, 119(3-4):241–263, 1991.
- [7] V. Berdichevsky. Continuum theory of dislocations revisited. *Cont. Mech. Therm.*, 18(9):195–222, 2006.
- [8] T. Blass, I. Fonseca, G. Leoni, and M. Morandotti. Dynamics for systems of screw dislocations. *SIAM J. Appl. Math.*, 75(2):393–419, 2015.
- [9] G. A. Bonaschi, P. Van Meurs, and M. Morandotti. Dynamics of screw dislocations: a generalised minimising-movements scheme approach. *Eur. J. Appl. Math.*, 28(4):636–655, 2017.
- [10] J. Bonet, A. J. Gil, and R. Ortigosa. A computational framework for polyconvex large strain elasticity. *Computer Methods in Applied Mechanics and Engineering*, 283:1061 – 1094, 2015.

- [11] H. H. M. Cleveringa, E. van der Giessen, and A. Needleman. A discrete dislocation analysis of bending. *International Journal of Plasticity*, 15(8):837–868, 1999.
- [12] S. Conti, A. Garroni, and A. Massaccesi. Modeling of dislocations and relaxation of functionals on 1-currents with discrete multiplicity. *Calc. Var. Partial Differential Equations*, 54(2):1847–1874, 2015.
- [13] R. Scala D. Melching and J. Zeman. Damage model for plastic materials at finite strains. *Preprint*, 2017.
- [14] B. Dacorogna. *Direct methods in the calculus of variations*. Applied Mathematical Sciences. Springer, 2008.
- [15] G. Francfort and A. Mielke. Existence results for a class of rate-independent material models with nonconvex elastic energies. *J. reine angew. Math.*, 595:55–91, 2006.
- [16] M. Giaquinta, G. Modica, and J. Souček. *Cartesian currents in the calculus of variations I. Cartesian currents*. Ergebnisse der Mathematik und ihrer Grenzgebiete. 3. Folge. 37. Berlin: Springer, 1998.
- [17] M. E. Gurtin. *Configurational Forces as Basic Concepts of Continuum Physics*. Applied Mathematical Sciences, 137. Springer, 2000.
- [18] V. V. Bulatov J. Chang, W. Cai and S. Yip. Molecular dynamics simulations of motion of edge and screw dislocations in a metal. *Computational materials science*, 23(1):111–115, 2002.
- [19] D. Knees and A. Mielke. Energy release rate for cracks in finite-strain elasticity. *Math. Methods Appl. Sci.*, 31(5):501–528, 2008.
- [20] S.G. Krantz and H.R. Parks. *Geometric Integration Theory*. Cornerstones. Birkhäuser, 2008.
- [21] A. Mainik and A. Mielke. Global existence for rate-independent gradient plasticity at finite strain. *J. Nonlinear Sci.*, 19(3):221–248, 2009.
- [22] A. Mielke. Evolution of rate-independent systems. In *Handbook of differential equations: Evolutionary equations. Vol. II*, pages 461–559. Amsterdam: Elsevier/North-Holland, 2005.
- [23] A. Mielke and T. Roubicek. *Rate-Independent systems: Theory and Applications*. Springer, 2005.
- [24] A. Mielke and T. Roubicek. Rate-independent damage processes in nonlinear elasticity. *Math. Models Methods Appl. Sci.*, 16:81–123, 2006.

- [25] G. Monnet and D. Terentyev. Structure and mobility of the edge dislocation in bcc iron studied by molecular dynamics. *Acta Materialia*, 57(5):1416–1426, 2009.
- [26] M. G. Mora, M. Peletier, and L. Scardia. Convergence of interaction-driven evolutions of dislocations with wasserstein dissipation and slip-plane confinement. *SIAM J. Math. Anal.*, 49, 2017.
- [27] G. Müller and J. Friedrich. Challenges in modeling of bulk crystal growth. *J. Cryst. Growth*, 266(1-3):1–19, 2004.
- [28] S. Müller and M. Palombaro. Existence of minimizers for a polyconvex energy in a crystal with dislocations. *Calc. Var. Partial Differential Equations*, 31(4):473–482, 2008.
- [29] S. Patrizi and E. Valdinoci. Long-time behavior for crystal dislocation dynamics. *Math. Models Methods Appl. Sci.*, 27(12):2185–2228, 2017.
- [30] R. Scala and N. Van Goethem. Constraint reaction and the Peach-Koehler force for dislocation networks. *Mathematics and Mechanics of Complex Systems*, 4(2):105–138, 2016.
- [31] R. Scala and N. Van Goethem. Currents and dislocations at the continuum scale. *Methods Appl. Anal.*, 23(1):1–34, 2016.
- [32] R. Scala and N. Van Goethem. Geometric and analytic properties of dislocation singularities. *Proc. Roy. Soc. Edinburgh Sect. A*, 2017.
- [33] R. Scala and N. Van Goethem. A variational approach to single crystals with dislocations. *Preprint*, 2018.
- [34] M. Thomas. Quasistatic damage evolution with spatial bv-regularization. *Discrete and Continuous Dynamical Systems-S*, 6(1):235–255, 2013.
- [35] M. Thomas and A. Mielke. Damage of nonlinearly elastic materials at small strain: existence and regularity results. *ZAMM Z. angew. Math. Mech.*, 90(2):88–112, 2010.
- [36] E. van der Giessen and A. Needleman. Discrete dislocation plasticity: a simple planar model. *Modelling and Simulation in Materials Science and Engineering*, 3:689–735, 1995.
- [37] P. J. P. van Meurs. *Discrete-to-Continuum Limits of Interacting Dislocations*. Phd thesis, Technische Universiteit, Eindhoven, Netherland, 2015.
- [38] H. M. Zbib. *Introduction to discrete dislocation dynamics*. In Sansour C. and S. Skatulla, editors. Springer, 2012.